This is a digital copy of a book that was preserved for generations on library shelves before it was carefully scanned by Google as part of a project to make the world's books discoverable online.

It has survived long enough for the copyright to expire and the book to enter the public domain. A public domain book is one that was never subject to copyright or whose legal copyright term has expired. Whether a book is in the public domain may vary country to country. Public domain books are our gateways to the past, representing a wealth of history, culture and knowledge that's often difficult to discover.

Marks, notations and other marginalia present in the original volume will appear in this file - a reminder of this book's long journey from the publisher to a library and finally to you.

Usage guidelines

Google is proud to partner with libraries to digitize public domain materials and make them widely accessible. Public domain books belong to the public and we are merely their custodians. Nevertheless, this work is expensive, so in order to keep providing this resource, we have taken steps to prevent abuse by commercial parties, including placing technical restrictions on automated querying.

We also ask that you:

+ *Make non-commercial use of the files* We designed Google Book Search for use by individuals, and we request that you use these files for personal, non-commercial purposes.

+ *Refrain from automated querying* Do not send automated queries of any sort to Google's system: If you are conducting research on machine translation, optical character recognition or other areas where access to a large amount of text is helpful, please contact us. We encourage the use of public domain materials for these purposes and may be able to help.

+ *Maintain attribution* The Google "watermark" you see on each file is essential for informing people about this project and helping them find additional materials through Google Book Search. Please do not remove it.

+ *Keep it legal* Whatever your use, remember that you are responsible for ensuring that what you are doing is legal. Do not assume that just because we believe a book is in the public domain for users in the United States, that the work is also in the public domain for users in other countries. Whether a book is still in copyright varies from country to country, and we can't offer guidance on whether any specific use of any specific book is allowed. Please do not assume that a book's appearance in Google Book Search means it can be used in any manner anywhere in the world. Copyright infringement liability can be quite severe.

About Google Book Search

Google's mission is to organize the world's information and to make it universally accessible and useful. Google Book Search helps readers discover the world's books while helping authors and publishers reach new audiences. You can search through the full text of this book on the web at `http://books.google.com/`





BRANNER
EARTH SCIENCES LIBRARY

STANFORD UNIVERSITY LIBRARIES

NEW PLANT UNDER CONSTRUCTION.

EXISTING SMELTING PLANT.

J C Brunner

NEW SOUTH WALES.

DEPARTMENT OF MINES.

GEOLOGICAL SURVEY.

E. F. PITTMAN, A.R.S.M., Government Geologist.

MINERAL RESOURCES.

No. 6.

THE COPPER-MINING INDUSTRY

AND THE

Distribution of Copper Ores in New South Wales.

BY

J. E. CARNE, F.G.S.,

ASSISTANT GOVERNMENT GEOLOGIST.

SECOND EDITION.

1908.

SYDNEY: WILLIAM APPLEGATE GULLICK, GOVERNMENT PRINTER.

1908.

2423

209739

TABLE OF CONTENTS.

	PAGE.
Introduction and Acknowledgment	1
Historical	6
Chronological Order of Opening of New South Wales Mines	10
Copper—probably the first Metal used by Man	12
Surface Indications of Copper Lodes	12
Natural Leaching of Copper Ores	13
Commercial Ores of Copper—their occurrence in New South Wales	17
Abandoned Mines and Re-opening	19
Development	21
Low-grade Deposits	24
Furnaces—	
Reverberatory Smelting ... / Cupola or Blast Smelting... / Pyritic Smelting	27
Treatment of Copper Ores, by W. H. Corbould	30
Smelting	33
Smelting Deductions	34
Great Cobar Electrolytic Plant, and Process of Refining, by G. H. Blakemore	36
Mineral Associates of Copper Ores injuriously affecting Smelting Operation or the quality of the Metal	41
Concentration	44
Concentration and Smelting Plants at the Washoe Plant, Anaconda, U.S., by L. S. Austin	48
Permanence of Copper Lodes	57
Depths of American Mines	59
Copper Mines of the World, by W. H. Weed	59
The Mineral Industry during 1906, by W. R. Ingalls	60
Depths of New South Wales Mines	61
Bedded Deposits	61
Brief Descriptive Notes of famous Copper Mines (for comparison)—	
In South Australia (Moonta, Wallaroo, and Burra Burra)	63
In Queensland (Peak Downs, Chillagoe, and Mount Morgan)	66
In Tasmania (Mount Lyell)	70
In Germany (Mansfeld)	74
In Spain (Rio Tinto and Tharsis)	75
Wet Methods of Extracting Copper at Rio Tinto, Spain, by C. H. Jones	75
In United States (Lake Superior and Montana)	79
Copper Mines of Japan, by W. H. Weed	84
Statistical Return of Copper Output of—	
Australasia	86
The World	88
Descriptive Register of New South Wales Copper Mines and Occurrences	90

P.

Refractory Materials locally used in the Manufacture of Fire-bricks, with Analyses of other Fire-clays of New South Wales suitable for Fire-bricks, &c. 3

Limestone 4

Appendix I—Local Customs Smelting Works, and their Tariffs 4

Appendix II—Additional Notes on Ettrema and Talwong Mines..... 4

Appendix III—Methods of Acquiring Titles to Prospect or Mine for Copper on Crown Lands 4

Map of New South Wales, showing Mining Districts and Divisions to illustrate the Distribution of Copper Ores ....End of volun

GENERAL BOOKBINDING CO.
QUALITY CONTROL MARK

LIST OF PLATES.

	PAGE.
Great Cobar Copper mine—General View	Frontispiece
Broken Hill—Outcrop of Lode	16
Great Cobar, Limited, Roasting and Electrolytic Plant, Lithgow	34
,, ,, Depositing Tanks	38
Mt. Morgan, Open Cut	66
,, Steam Shovel	67
,, Blast Furnaces	68
,, Converters	69
Table showing Australian Copper Production	87
Comparative Table, Production and Consumption of Copper, 1906	88
Blayney Copper Mines—Works	111
,, ,, Winch converted into Shell of Copper	113
,, ,, Converter Plant	114
Lloyd Copper Mine—General View	117
,, ,, Section	120
,, ,, Plan of Workings	121
,, ,, Concentrating Mill	122
,, ,, Roasters	123
,, ,, Smelting Works	124
,, ,, Refining Plant	125
,, ,, Reservoir	126
Calla Copper Mine	127
,, ,, Iron Duke Outcrop	128
,, ,, Smelting Works	132
,, ,, Iron Duke Workings	132
Cargai Copper Lode	181
,, Smelting Works	182
,, Plan and Section	186
Cobar Chesney Main Shaft	198
,, ,, Mine Section	199
Crowl Creek, Shuttleton, Plan and Sections	212
Girilambone Copper Mine	218
,, Main Drive	220
,, Refinery	223
Great Cobar Company Main Stack	228
,, ,, 90-fathom Level	233
,, ,, ,,	240
,, ,, Interior of Smelter Building	242
,, ,, No. 1 Blast Furnace	243
,, ,, Nos. 1 and 2 Converter Vessels	244
Mt. Hope Copper Mine	250

PAGE.

Mt. Hope Copper Mine Smelting Works 252
Nymagee Copper Mine 255
,, ,, Plan and Section 258
Belara Copper Mine 286
,, ,, Plan 287
Mount Stewart Mine, Leadville, Plan 296
Gulf Creek Copper Mine 322
,, ,, Smelting Works 324
Frogmore Copper Mine 346
Lake George Copper Mines 355
Talwong Copper Mine 366
,, ,, Shoalhaven River Gorge 367
Lobb's Hole Copper Mine, Yarrangobilly 384
,, ,, ,, Plan 386
Snowball Copper Mine, Plan 392
English and Australian Copper Smelting Works, Waratah 409

AT END OF VOLUME.

Lloyd Copper Mine—Plan of Reverberatory Furnace.
,, ,, Plan of W. Thomas' Hearth Reverberatory Furnace.
Great Cobar, Limited—Details of Construction of Electrolytic Copper-refining Plant.
Map of New South Wales, showing Mining Districts and Divisions and principal Copper Lodes.

LETTER OF TRANSMITTAL.

Department of Mines,
12th August, 1908.

Sir,

Mr. J. E. Carne's Monograph on "The Copper Mining Industry, published in 1899, proved so useful to the mining community that there has been a continuous demand for it, and in view of the marked advance which took place in copper production in 1907, consequent upon the increased price of the metal, it was felt that a second edition was almost a necessity. This has now been prepared by Mr. Carne, and it will be found to contain a large amount of new and valuable information, which will doubtless be appreciated by mining men. The book is practically a record of the work done upon copper deposits in this State, and, as such, it must always be of use to persons contemplating the reopening of old mines, when improved conditions in regard to price of metals, methods of treatment, &c., appear to give promise of success.

I think that Mr. Carne is to be congratulated upon the manner in which he has completed his work.

I have the honor to be,
Sir,
Your obedient servant,
E. F. PITTMAN,
Government Geologist.

The Hon. W. H. Wood, Esq.,
Minister for Mines.

The Copper-mining Industry and the Distribution of Copper Ores in New South Wales.

Introduction and Acknowledgment.

The copper-mining industry of New South Wales, after languishing for several years owing to the low price of copper and the consequent closing of some of the principal mines, entered upon a new era of prosperity about 1894, when the Great Cobar Mine was reopened under the advantages of improved and accelerated methods of ore reduction, and of rapid and constant transport afforded by railway communication with the sea-board.

The success of the undertaking was, moreover, influenced to no small extent by realisation of the intrinsic worth of the valuable associated metals previously ignored, and augmented and confirmed by the steadily increasing value of copper—from £39 in 1893 to £75 in February, 1899.

This substantial advance stimulated interest in copper properties both old and new, and awakened a desire to look further into mines long since closed under less favourable conditions. The interest awakened, however, was slight compared with that following the phenomenal rise to over £100 per ton in 1907. Many of the early mines were reopened to ascertain whether under advanced metallurgical methods and reduced costs they could be profitably worked. Such early mines as Currowong, Snowball, Frogmore, Ophir, Belmore, Britannia, Copper Hill, Apsley, Wertago, Green Swamp, Cadia, and Goodrich being among the number. Unfortunately for the majority, the boom was too brief; by the time the old workings were unwatered and secured, the fall had begun and capital was scared.

The time being opportune, an attempt is herein made to supply useful information for the benefit alike of the prospector, miner, and investor, by collecting and bringing up to date all the available information the Writer has been able to glean concerning the inception and progress of the copper-mining industry, and of the distribution of copper ores in New South Wales. Its object is threefold—concentrating the substance of early references and reports, recording present conditions, and registering known copper occurrences and localities. To this end public and private documents have been carefully noted, whilst the experience of many prominently connected with the industry, and the personal knowledge of the Writer and his colleagues of the Department of Mines, have been placed under tribute.

It is believed that a useful purpose is served in thus presenting in convenient form the sum-total of our knowledge of the subject, and in con-

centrating information previously scattered through numerous documents and publications, the earlier portions of which at least are hardly available to the general public.

Each of the States of Australasia has become noted for abundance of one or more essential elements of mineral wealth and prosperity; thus New South Wales for coal, silver, tin, and lead; Victoria, New Zealand, Queensland, and now the youngest State—West Australia—for gold; South Australia for copper; and Tasmania for tin and copper.

In copper New South Wales ranks second to South Australia as regards the total value of production to date, whilst Queensland, thanks to Mount Morgan, assumed the premier position in the annual output in 1906, Tasmania, which held that position from 1897, taking second place, New South Wales third, and South Australia fourth. The relative figures for each of the States are as follows :—

State.	Total Production to end of 1906.*	Production for 1907.	Total Production to end of 1907.
	£	£	£
South Australia	25,575,846	691,888	26,267,734
New South Wales	8,472,629	727,774	9,200,403
Tasmania	6,753,561	869,666	7,623,227
Queensland	4,402,003	1,028,179	5,430,182
Western Australia	478,129	180,387	658,516
Victoria	123,454	2,356	125,810
Total	45,805,622	3,500,250	49,305,872

* Supplied by Commonwealth Statistician.

In bringing the chequered history of the local copper-mining industry up to date, advantage has been taken of the opportunities afforded by consideration of individual enterprises, to contrast past and present difficulties besetting them, and the methods and processes experience and altering conditions have suggested and enforced.

Copper mining, no less than that of the nobler metals, has had its "boom" times and its reactionary depressions, the causes of which in some instances were not far to seek—notably the fictitious advance in value in 1888 consequent on the futile attempt of a French Société des Metaux to "corner" the market, which entailed loss and disappointment through speculative investment and attempted exploitation of unworkable deposits. Slowly, but surely, the industry recovered from the inevitable fall in values following the Society's failure. The steadily-maintained advance in the market value of copper, notwithstanding the rather disconcerting jump to £75 per ton in February, 1899, attributed to a similar attempt to control the market, continued as the natural outcome of increased and healthy demand, culminating in 1900 in an average of £73 2s. 5d. and £78 9s. 1d. for "standard" and "best selected" copper. "Towards the end of 1901 the reaction in European trade became very pronounced."[1] As a result of reduced consumption, aggravated by heavy stock-selling, the average prices for the above grades fell to £52 8s. 3d. and £56 12s. 7d. in 1902, rising again in June, 1907, to £103 4s. 4d. and £111 8s. 4d. (according to the Commonwealth Statistician), when a fluctuating fall began, until £62 10s. was reached in October and December.

[1] A Century of Copper, 2nd ed., 1906, p. 17.

The following interesting table of fluctuations in the value of copper from 1896 to June, 1907, has been prepared by Mr. G. H. Knibbs, Commonwealth Statistician,[1] who also kindly supplied the earlier returns from 1893 from the files of the *Economist*:—

Year.	Average Price of Copper per Ton.		
	Standard.	Best selected.	
	£ s. d.	£ s. d.	
1893	42 16 5	48 0 0	
1894	40 13 8	43 7 6	
1895	42 18 2	46 18 4	
1896	46 18 2	50 13 5	
1897	49 2 6	52 5 6	
1898	51 16 7	55 8 3	
1899	73 13 9	78 2 3	
1900	73 2 5	78 9 1	
1901	66 19 1	73 8 2	
1902	52 8 3	56 12 7	
1903	58 3 2	62 13 1	
1904	59 0 7	62 13 0	
1905	67 2 1	71 3 9	January to June.
1905	72 1 11	77 7 11	July to December.
1906	82 2 8	86 18 11	January to June.
1906	92 15 1	97 11 1	July to December.
1907	103 4 4	111 8 4	January to June.

Comparative Statement of Yearly Average Prices compiled by the Metallgesellschaft and the Metallurgische Gesellschaft A-G. (14th Ann. Issue 1898 1907, March, 1908, p. 5 :—

	Standard (London).	Best Selected (London).	Lake (New York).	Electrolytic (New York).
	£ s. d.	£ s. d.	£ s. d.	£ s. d.
1906	87 8 6	92 5 0	90 10 0	88 18 1
	87 1 8	93 14 6	95 5 0	92 5 2

The following notes from Aron Hirsch and Son's "Copper Outlook," to the end of February, 1907, are of special interest in view of the recent phenomenal rise and subsequent recession of values :—

Page 6. "In recent issues we have been able to describe the period under review as a record year of the copper-mining industry; 1906 may more aptly be described as a record year of *consumption*. Mining industry received its greatest impetus from higher values ruling in 1904 and 1905 (£60-£70). Increase of production in 1906, proportionately appreciably smaller, notwithstanding higher values, £90-£100."

Page 7. "Germany, France, United Kingdom, and United States consume about 80-90 per cent. of the world's production. Of the total consumption of these countries—670,543 tons—the United States consumed 316,964 tons."

Page 6. "Whilst in 1891, with a world's production of 279,309 tons, the North American countries (in which class we include Mexico and Canada, the product of these being for the most part refined in North America) produced 136,874 tons—less than half the total production—in 1906 North America's share formed 70 per cent. of the entire world's production."

[1] Official Year-book of the Commonwealth of Australia, No. 1, 1908, p. 412.

Pages 10 and 11. "In conclusion, we repeat that in 1906 the world's consumption of copper exceeded its production by 51,297 tons (in the years 1902, 1903, 1904, and 1905 consumption was respectively 51,799, 26,899, 32,856, and 54,772 tons greater than the production). It is quite impossible to state in figures what portion of these 51,297 tons should be considered as an actual deficit. A most important point is that the invisible, or rather indeterminable, stocks in the hands of manufacturers are reduced to the very utmost possible level, or we may rather say they are nearly exhausted. As a large part of the production until well into the summer of this year (1907) has already been sold to consumers, and the latter, in spite of this, are still insufficiently covered with supplies, the situation is most serious, the more so because there is lack of any stocks, apart from the small stocks of standard copper in England—5,600 tons at the end of February, 1907. One can therefore understand the considerable advance in price, and it is clear that this advance has not been artificial. But such conditions are not healthy in the interests of the industry, and it is much to be hoped that the tension, and with it the exceptionally high prices, may give way somewhat. For this, an increase in production would primarily be needed; but there are as yet no indications of any appreciable increase. The price of copper will much depend upon the development of economic conditions in general. The whole world, but Germany and the United States in particular, now enjoys an industrial prosperity which has never been equalled. The world's demand for raw and industrial products of every description is phenomenal. But this state necessitates supplies of money in such abundance that one is not certain whether the scarcity of money does not actually signify that the boundaries of present conditions have been reached."

In view of subsequent financial troubles in the countries specifically mentioned, the concluding part of the latter paragraph was prophetic.

As all authorities are agreed upon the excess of consumption over production during the period mentioned, it seems tolerably certain that the fall in values during the latter part of 1907 (which continues) was due to lessened consumption, and not to market manipulation principally.

The magnitude of the United States consumption (47·2 per cent. of the world's consumption in 1906—Hirsch and Son) and its influence on the copper market is forcibly realised when financial panic and industrial stagnation temporarily supervene in that country.

"Booms" are unhealthy stimulants of mining industry. Financial exhaustion and distrust inevitably follow feverish speculative excitement and over-confidence.

Abnormal increases of metal values likewise dislocate trade and create fictitious market standards, from which even moderate recession is regarded as depression, notwithstanding superior averages maintained over preceding years.

Established mines benefit during the period of inflation, but those inaugurated because of it suffer proportionately to failure of the high margins on which they were floated.

"Booms," moreover, stimulate injudicious enterprises which would be impossible under normal conditions. Unscrupulous market manipulation is an inevitable consequence of a "boom." On the strength of legitimate discovery "wild cat" offshoots are sprung on the public, usually under misleading nomenclature, implying lode connection.

Frequently, without the slightest stratigraphic evidence of extension or parallelism, the familiar "Norths," "Souths," Easts," or Wests," and their inevitable "Extendeds," "Blocks," and "Underlays," are set as traps for the public, baited with the magic names of successful or promising mines, and not always with too slavish regard for the implied connection.

Doubtless the spirit of gambling underlies a good deal of "wild cat" speculation. Hope of sudden enrichment—beyond the scope of prosaic business—lures ordinarily shrewd men to reckless mining investment. Rumoured discovery, whispered secrecy—another Mount Morgan! a second Broken Hill! or a mysterious "Big Hole" with gold and diamonds!—secure victims as gullible as those who trust the disinterestedness of the casual acquaintance with the rich uncle in Fiji.

Alluring hope of unearned increment, large and immediate, claims its dupes in professional and business ranks as easily as in bucolic. Native caution, professional and business instinct, yield before the mining syren.

From the wiles of smaller fry—the "Monte man" and "thimble-rigger"—beneficent legislation protects the unwary or vicious. From "mining shark" and "market rigger" is there no protection? The former victimises in shillings; the latter in fortunes. The former is anathema; the latter tolerated, if not envied.

Discovery is the harvest time of the illegitimate mine (?) floater and boomer, who garners his gains before independent report protects and guides investment. The longer the delay in reporting, the greater the harvest gleaned. Instant publication of facts of occurrence, and proving, without comment, protects public interests, without "booming" legitimate enterprise.

Each important productive deposit has herein received independent historic notice, embracing all available particulars of discovery, size, nature of the ores, extent of development and output,[1] and the methods of treatment adopted. In each case where the mine is still working, these data have been brought up to the present chiefly from personal inspection by the Writer. The individual descriptions may in some instances appear prolix; but experience has proved that even apparently trivial details have a value, and are eagerly sought by those desirous of information on which to base a decision.

In noting the occurrence of copper, no restriction has been adopted in the register; but with a desire of imparting knowledge of the distribution of the ores of this metal throughout the State, its scope has been widened to embrace all cupriferous localities irrespective of abundance or richness. The individual references, however, contain all that is known of each deposit.

The presence of copper in a locality may be a guide to prospectors, and a record of proved unworkable deposits may prevent useless expenditure or misrepresentation.

Brief descriptive notices of some of the principal copper lodes of the world, and the metallurgical and other processes connected therewith, have also been introduced for comparison and instruction.

Here the Writer desires to acknowledge the obligation he is under to Mr. W. H. Corbould, Managing Director of the Lloyd and other copper mines, who, with a view to assisting in the early issue of this work, generously volunteered to extract items of interest from recent literature on the subject, and in other ways rendered valuable aid.

[1] In some instances the outputs may be only approximate as they are dependent entirely upon the courtesy or willingness of the owners, returns not being compulsory under the New South Wales Mining Act.

"The success which has attended the opening of these mines has as yet only been partial; but experiment has not yet proceeded far enough to test with any certainty their ultimate productiveness. It is also contemplated, I understand, to open mines in the neighbourhood of Carcoar [Coombing?—J.E.C.], in the county of Bathurst, and at Summerhill, in the same county, where strong indications of the existence of lodes of sufficient richness to justify their being worked have for some time been known to exist.

"A lead mine was opened during last year in the neighbourhood of Yass [Woolgarlo?—J.E.C.], but has been abandoned in consequence of its not being proved sufficiently productive to defray expenses of working it.

"An iron mine was also recently opened in the neighbourhood of Berrima [the Fitzroy Mine, Nattai.—J.E.C.]. It may not be superfluous to add that all the mines which have as yet been opened are on lands which have been alienated from the Crown without any reservation of the mineral rights."

The Governor concluded by recommending that a competent geologist be sent out. The position was subsequently offered to Mr. Beete Jukes, who declined it. Afterwards Mr. Bristowe was selected, but did not take up the work for family reasons. Later, Mr. S. Stutchbury was appointed to the position of the first Government Geological Surveyor, which he occupied until 1855, when he resigned on account of failing health.

In 1803, Mr. A. W. H. Humphrey was appointed as Mineralogist to the Territories of New South Wales. His arrival in March was noted; but there is no record of any reports having been furnished by him.[1]

In 1851, Mr. J. R. Hardy, Commissioner for Crown Lands for the gold district, writing to the Governor, on 12th June, from Summerhill Creek, near Orange, reported that several Cornish miners had applied to him to be allowed to work copper ore on the same terms as gold, namely, on payment of 30s. per man monthly.[2] Mr. Hardy recommended that the request be granted if within the province of the Government, as it was very desirable that every valuable article of export should be developed, and that it would give back loading to teams bringing supplies to the gold-fields, thereby lessening cost of transit.

On the 24th June the Governor invited the attention of the Executive Council to the application. The latter, however, was of opinion that "there was no such analogy between digging for gold and working copper mines as to render practicable the application of the same code of regulations to both." It, however, recommended "that until proper regulations were established for the working of metals other than gold, that any Crown lands containing such should be surveyed and offered for sale as mineral lands at an upset price sufficient to cover their proper value."

The difficulty of ascertaining the latter doubtless caused the abandonment of this idea of dealing with metalliferous lands, for no provision was made in the first Mining Act, issued in 1852, which was confined to gold-mining only. Nor did that of 1855, which repealed the previous Act and substituted the "miner's right" for the license to mine, and also provided for the issue of gold-mining and business leases, make any provision for minerals other than gold. Neither did the Act of 1857 remedy this defect.

---

[1] Lord Hobart to Governor King, 24th February, 1803, Hist. Records N. S. Wales, 1803-1805, p. 47.

[2] Probably at Carangara, near Byng, afterwards known as the Cornish Settlement.

In the Crown Lands Act of 1861 provision was first made for mineral leases; prior to this it would appear that copper-mining was entirely confined to private lands or was unprotected by specific title.

The first copper lease registered in the Departmental records, so far as can be ascertained, was in 1864, being portion 448, parish Baring, county Westmoreland, taken up by H. Donnelly.

In 1851 the first geological examination of the then known copper lodes of the Colony was begun, for in the official records of that year are embodied reports by Mr. S. Stutchbury, Government Geological Surveyor, and the Rev. W. B. Clarke, who was also engaged by the Executive Council to make geological examinations, chiefly, however, in connection with gold; but, as was characteristic with Mr. Clarke's work, little escaped his keen observation, hence references to copper localities are frequent in his reports.

Apparently Mr. Stutchbury's first duty on arrival in the State was the systematic examination of the copper mines in operation, and of all known cupriferous localities. Under the names of the mines in the descriptive record of this paper will be found details of his report on them at that early date. In these introductory notes brief references will be given.

It is significant that as early as the 12th April, 1851, inspired doubtless by phenomena observed in his travels, he took the opportunity of chronicling his opinion "that the large masses of iron ore found in veins and on mountain tops will, in some way or other, be found to be connected with copper or other metallic lodes." Probably the allusion was to gossany outcrops destitute of any surface traces of copper ores which might naturally be expected to mark the decomposition of cupriferous pyrites. In another portion of this work this interesting subject will receive further attention.

In 1851 Mr. Stutchbury reported on the Summerhill, Coombing, Cornish Settlement (Carangara), and other mines, and on deposits then unopened.[1]

In the same year Mr. (afterwards Sir Thomas) Mitchell, Surveyor-General, in a report on the gold-fields of the Bathurst District, mentioned copper mines at Kyong (probably Guyong, near Carangara) and at Copper Hill, near Molong, but gave no particulars.

In September, 1851, the Rev. W. B. Clarke recorded the presence of copper ores in "more or less abundance" a few miles to the westward of Inverary Quarry, in the Marulan District; also their occurrence in the neighbourhood of Boro, where the Mulloon Copper Mine was afterwards opened, about 1872.

In February, 1852, he noted the presence of copper and lead ores at Quidong, near the Snowy River, close to the Victorian border, and anticipated a profitable mining field. In 1868 the prospectus of the "Belmore Freehold Silver and Lead Mining Company," Quidong, was announced in the Press. Subsequently, prospecting operations were begun both for the silver-lead and the copper ores, and a furnace and battery erected; but apparently little ore was obtained, as the furnace betrays slight evidence of use.

[1] Mr. Stutchbury's reports are published in Votes and Proceedings of the Legislative Council under the years mentioned, and may be seen at the Public Library.

The approximate chronological order of opening of the best-known copper mines in the State is as follows :—

Year.	Mine.	Mining District.	Division.
†1845 ...	Copper Hill	Bathurst	Molong.
1845 ...	Little Copper Hill	,,	,,
1845 ...	Belubula	,,	Canowindra.
†1846 ...	Summerhill	,,	Rockley.
1847 ...	,,	,,	,,
1848 ...	Good Hope	Southern	Yass.
†1849 ...	,,	,,	,,
†1850 ...	Coombing Park	Bathurst	Carcoar.
†1850 ...	Carangera	,,	Orange.
†	Cadia	,,	,,
	Cadia Extended	,,	,,
†	Icely	,,	,,
†1851	Ophir (1852)	,,	,,
to	Britannia	,,	,,
1865	Belmore	,,	,,
	Moonta	,,	,,
	Nelson	,,	,,
	Geurophian	,,	,,
†1872 ...	Essington	Bathurst	Rockley.
†1874 ..	Frogmore	Southern	Frogmore.
†1874 ...	Pride of Frogmore		
1874 ...	Lobb's Hole	Tumut and Adelong	Kiandra.
†1874 ...	Snowball	,,	Gundagai.
†1874 ...	Belara	Mudgee	Wellington.
†1875 ...	Apsley	Bathurst	Bathurst.
†1875 ...	Belmore	,,	,,
1875 ...	Glamorgan	Clarence and Richmond	Copmanhurst.
1875 ...	Bobby Whitlow	Peel and Uralla	Bingara.
†1876 ...	Burraga	Bathurst	Burraga.
†1876 ...	Wertago	Albert	White Cliffs.
1877 ...	Burley Jacky	Bathurst	Cowra.
1877	Esmeralda	,,	Bathurst.
†1877 ...	Bundarra	Peel and Uralla	Bundarra.
†1878 ..	Mount Hope	Cobar	Mount Hope.
†1878 ...	Great Central	,,	,,
1878 ...	Cyclops	Tambaroora and Turon	Stuart Town.
1878 ...	Mount Ragan	Bathurst	Orange.
1878 ...	Green Swamp	,,	Bathurst.
†1879 ...	Nymagee	Cobar	Nymagee.
†1880 ...	Girilambone	,,	Nyngan.
†1881 ...	Blayney	Bathurst	Blayney.
†1881 ...	Eurow and Vychan	Lachlan	Forbes (?)
†1881 ...	Trough Gully	Peel and Uralla	Nundle.
†1882 ...	Lake George (Captain's Flat)	Southern	Bungendore (?)
1883 ...	Pluck	Clarence and Richmond	Copmanhurst.
†1886 ...	Mount Boppy Copper	Cobar	Canbelego.
1887 ...	Mount Jasper	Hunter and Macleay	Port Macquarie.
1888 ...	Sydney-Wallaroo	Mudgee	Dandaloo.
1890 ...	Mount Laut	,,	Denison Town.
1891 ...	Will Will	Hunter and Macleay	Kempsey.
†1894 ...	Mount Everest	Peel and Uralla	Bingara.
†1895 ...	Gulf Creek	,,	Barraba.
1895 ...	Mayfield	Southern	Burrowa.
†1895 ...	Mountain Run	Bathurst	Rockley.
†1895 ...	Phœnix	,,	Oberon (?).
1897 ...	Tuglow	,,	Oberon.
1897 ..	Christmas Gift	Mudgee	Dandaloo.
1898 ...	Elizabeth	,,	,,

† Furnaces established in connection therewith.

Year.	Mine.	Mining District.	Division.
1898 ..	Mount Pleasant	Mudgee	Dandaloo.
1898 ...	Bob's Mount	Bathurst	Orange.
1898 ...	Monaro	Tumut and Adelong	Cooma.
1899 ..	Kangiara	Southern	Yass.
†1899 ...	Sugarloaf	Bathurst	Rockley.
†1900 ...	Crowl Creek	Cobar	Nymagee.
1900 ...	Lobb's Hole Central	Tumut and Adelong	Kiandra.
†1901 ...	Cangai	Clarence and Richmond	Copmanhurst.
1901 ...	King of England	Lachlan	Cowra.
1901 ...	Canbelego	Cobar	Canbelego.
†1902 ...	Queen Bee	,,	Cobar.
1902 ...	Attunga	Peel and Uralla	Tamworth.
†1903 ...	Mount Royal	Mudgee	Dandaloo.
1903 ..	Underlay	,,	,,
1903 ...	Namoi	Peel and Uralla	Tamworth.
1903 ..	Al Tinby	Tambaroora and Turon	Stuart Town.
†1905 ..	Bogan River	Mudgee	Dandaloo.
1905 ..	Cowfell	Lachlan	Cowra.
1905 ...	Cash (Essington)	Bathurst	Rockley.
1905 ...	Lucky Hit	Southern	Goulburn.
1906 ...	Badgery	Cobar	Canbelego.
1906 ...	Native Bee	Mudgee	Wellington.
1906 ...	Orange Plains	,,	Dandaloo.
1906 ...	Ace	,,	,,

† Furnaces established in connection therewith.

Copper.

Atomic weight 63·4; specific gravity, 8·94; melting point, 1080·5° C. (H. M. Howe); boiling point, about 3000° C.; volatile at highest obtainable temperature in electric arc, &c. Just before melting becomes very brittle, and may be pulverised.

Molten metal has a greenish colour, also imparts green colour to oxidising flame. Absorbs certain gases when molten, which it sets free on solidifying, requiring special precautions in copper casting to prevent porosity.

Electrical conductivity, 931—silver being 1,000 (Peters); capacity for conducting heat, 898—gold being 1,000 (*ibid*).

The necessity for careful selection of ores for roasting with matte, especially if electrolysis is not to follow (and this process is also effected), is emphasised by Dr. W. Borchers and W. G. McMillan,[1] "because copper readily dissolves (when melted) aluminium, nickel, cobalt, zinc, cadmium, tin, lead, bismuth, gold, silver, manganese, chromium, tungsten, molybdenum, and iron; also various metallic compounds (cuprous oxide, sulphide, and phosphide, and the arsenides, arseniates, antimonides, and antimonates of lead, bismuth, &c.)."

In combining with sulphur copper exhibits far greater chemical energy than any other of the heavy metals. The first process of chemical concentration is dependent upon high chemical stability of copper when combined with sulphur in the melted condition.[2]

Principal solvents of copper are nitric, concentrated sulphuric acids, and aqua-regia (a mixture of nitric and hydrochloric acids). Hydrochloric and dilute sulphuric acids only dissolve the metal when air or some other oxidising substance is present.[3]

[1] Electric Smelting and Refining, 1897, p. 171. [2] *Ibid.*, p. 173. [3] *Ibid.*, p. 172.

Copper was probably the earliest of the metals converted to human use; certainly it is the first of which relics have been discovered amongst the primitive implements of prehistoric man, and has, indeed, furnished evidence of his intellectual progression by the advance it marks in material adaptation to his needs. With the abundant celts or stone implements of North America —where native copper abounded at Lake Superior—occur similar forms in metallic copper. Probably first by hammering, and subsequently by melting, the native metal was shaped according to the knowledge of our ancestors. Later, by the addition of lead, zinc, or tin, which may first have been naturally associated with copper ores, was the harder bronze alloy obtained. The far more infusible and valuable iron—which in its native state is a rarity in nature—was still later smelted from its ores. The intellectual and industrial progress of prehistoric man has, by means of his weapons and implements, been divided by archæologists into—

(*a*) Palæolithic or Ancient Stone Age—Roughly chipped and unpolished flints and chips.
(*b*) Neolithic or Newer Stone Age—Smooth and polished flints and chips.
(*c*) Copper and Bronze Age.
(*d*) Iron Age.

The composition of a prehistoric bronze from Ireland is given by Professor Roberts-Austen[1] as copper, 83·5; tin, 5·15; lead, 8·3; iron, 3·0.

Copper, of all metals, most readily betrays its presence in Nature by the remarkably attractive colouring assumed by some of the ores resulting from its decomposition, such as the carbonates, silicates, and oxychlorides. The beautiful sapphire-blue azurite, the bright and dark-green malachite, the turquoise-blue chrysocolla, the dark-green atacamite, and the pellucid blue sulphate from solution, are specially distinctive. Mere traces of some of these minerals characteristically colour large outcrops of rock, or the dry beds and sides of channels through which cupriferous waters have intermittent flow. These superficial colourings may frequently be delusive, and entail endless labour and disappointment on the uninitiated, especially in those instances resulting from decomposition or alteration of small particles of native copper, or one of its sulphide compounds, occurring probably, as idiogenetic, or original constituents, of some intrusive rock, as in the Wellington and Carcoar Districts.

Usually one of the most favourable surface indications of an extensive copper lode is abundant gossany or cellular iron oxide and quartz, stained with carbonate of copper, commonly described by old copper-miners as a "good iron hat" or "an iron saddle riding a good horse." Such an outcrop affords presumptive evidence of extensive deposits of sulphides below the zone of oxidation or water-level. But surface indications cannot be relied on as infallible guides to conditions below. The Great Cobar, Nymagee, New Mount Hope, and Burraga Mines were instances of the unreliability of any one set of conditions for all occurrences; Cobar, in particular, afforded little surface evidence of the immense bodies of payable ore beneath. The reverse also frequently holds good, large and promising outcrops capping lean and unprofitable deposits. Copper Hill, near Molong, and possibly Cow Flat Mines, may be cited as instances of failure to realise the fair promise of the outcrops so far as tested.

Though the presence of copper is usually recognisable in a gossany outcrop forming the back of a copper-bearing lode, yet its absence must not be

[1] An Introduction to the Study of Metallurgy, 3rd ed., 1894, p. 105.

inferred from lack of the usual indications, for notable instances are not wanting of such a deficiency. According to Dr. Peters,[1] the famous Montana lode, which at the present day, perhaps, is furnishing the largest amount of copper from any single deposit in the world, down to levels averaging about 250 feet from the surface carried comparatively no copper, and was worked solely for the silver it contained;[2] it had, in fact, become a low-grade silver deposit. At the level mentioned, a rich zone of copper ore was struck between the argentiferous, yellow, quartzose cap and the leaner copper ores below. The Anaconda Mine, was, perhaps, the only exception, the rich zone being met under 200 feet from the surface. The cause of the enrichment was, doubtless, the leaching and removal of the copper from the higher levels, and reprecipitation and concentration below; the line of demarcation between the impoverished and enriched zones being sudden and distinct.

The experience gained at C.S.A., Budgery, and other mines proves the necessity of reaching water-level before abandoning prospecting. In the arid western country, where the water-level lies deep, whilst porous gossan continues in the ore channel—even with little or no other metallic association than the iron oxide—prospecting should be continued. But there is no justification for the wild idea of sinking deep simply for the purpose of cross-cutting, where there is entire absence of gossan, or channel rock, or other evidence of a metalliferous deposit.

During the C.S.A. and Budgery "booms" the popular local idea of getting down deep and cross-cutting, irrespective of the slightest indication, entailed extensive expenditure sinking holes in the ground.

Ferruginous outcrops usually make into pyritic masses or impregnated country, but do not necessarily make into copper lodes. Copper is more easily decomposed and leached than its usual associates, but generally leaves traces (stains of carbonate) to represent the transferred proportion concentrated about water-level. Where an outcrop has been leached, the resultant gossan usually becomes porous or cellular, by removal of the minerals rendered soluble by oxidation. Lead is sometimes similarly redeposited—as at C.S.A.—but generally leaves scattered crystals and bunches of carbonate in the leached zone.

Where a concentrated mass of ore immediately overlies the water-level, its thickness is proportional to the original richness and thickness of the impoverished mass from which it has been derived. Likewise the metallic values of the primitive or unaltered extension of the lode below water-level may be gauged by the vertical extent of leaching necessary to produce the thickness of enrichment.

Where pyritic and solid below water-level, the great desideratum is, sufficient copper to form a copper matte and concentrate gold and silver values.

A feature of the West Bogan (Orange Plains and Albert Water Holes) copper lodes is the very slight surface development or outcrop—a feature probably due to the flatness and aridity of the country, and consequent slight degradation and dissection. At most a few nodules, or a small patch of ironstone, form the only superficial indication. Ferruginous quartzites are occasionally moderately conspicuous, but rarely prove of any value at lower levels.

[1] Modern Copper Smelting, 5th ed., 1892, p. 16. [2] In the 7th edition the figures are 40 to 300 feet.

The white clays and bleached rock, frequent in the leached upper levels of lodes, result from the action of soluble sulphates derived from oxidation of pyrites.

The famous Burra and Moonta Mines of South Australia also furnish evidence which counsels caution in condemning a ferruginous deposit betraying little surface indication of permanent deposits beneath.

At the Burra Mine, according to Mr. H. Y. L. Brown, Government Geologist,[1] there was no appearance of defined ore-bodies above the 180-foot level, the carbonates occurring very irregularly as nodules and investing cavities and fissures; but below the 180-foot level regular lodes were met containing very rich ores—malachite, cuprite, and grey ore.

In the Moonta Mine, according to the same authority, between a very thin superficial coating of malachite and atacamite only a few inches thick, and the 50 or 60 foot level, no further ore was met, and, as a rule, not even a stain indicated the rich oxides and malleable copper just beneath, which were succeeded by black and grey sulphides.

In the Blayney or Annandale Mine of this State, beyond a mere trace in a thin quartz vein, no copper ore was met with above the 90-foot level, though some 2,000 tons of iron ore were removed from the back of the lode for iron-smelting at Lithgow.

At the celebrated Mount Morgan Gold Mine, Queensland, practically no trace of the copper ore which is now converting it into a large smelting proposition, was visible above the 300-foot level.

Going further afield for examples, according to R. Hunt, F.R.S.,[2] in Cornwall no copper ore of any value was raised until the 180-foot or 240-foot levels were reached, and that the great mine of Przibram, in Bohemia, had to be sunk 120 to 180 feet before it became productive.

The instances quoted are sufficient to demonstrate the wisdom of continuing sinking in the cap of a copper lode until the water-level and the yellow sulphide zone are reached. The rich secondary ores, such as copper glance (grey ore) and bornite, resulting from the leaching of the higher levels and redeposition, are usually found concentrated just about water-level, and above the ordinary chalcopyrite (yellow ore). When the latter is reached little permanent alteration for the better can be anticipated, but rather the reverse; the general experience being that depreciation waits on depth.

As most copper ores occur in more or less disconnected masses along the strike or channel of a lode, it follows that levels extending beyond the productive masses should not be too readily abandoned in blanks whilst channel conditions—defined walls with crushed filling between—continue. The same applies to shafts and winzes, for blanks occur vertically as well as horizontally.

Frequently the intervening spaces are not wholly blanks; thin seams and kernels of ore occur in the crushed filling, which may be hand-picked or concentrated to a degree suitable for fluxing more basic ores.

Main shafts for haulage must be sunk vertically, or in a straight line on the underlay, preferably in the country; but prospecting shafts and winzes should be sunk in the ore-bodies, to avoid dead or unproductive work. As levels are driven, shafts and winzes should be consistently deepened, or fresh

[1] Record of South Australian Mines. [2] British Mining, 1884, p. 506.

ones started following the ore-lenses. The aim should be to continually have "in sight" a considerable body of "reserves" ahead of main stopes; though stoping, for judicious furnace blending, should proceed at all levels as opened up.

If this systematic development be followed there will be no danger of the bottom suddenly "dropping out" of a mine.

The cause of the occasional enrichment of the lower levels and the poverty of the cap is the greater solubility of the copper salts resulting from the decomposition of cupriferous pyrites, than those of the associated iron sulphide, which meanwhile are converted chiefly into insoluble oxides. The copper salts are thus removed by percolating waters, and carried to lower levels where precipitation in more concentrated form ensues.

An interesting instance of the relative solubility of copper, zinc, and iron is afforded in the accompanying analyses of samples of mine water from the Currowong Mine, near Lake George; the proportions of the several metallic salts manifest their differing solubility:—

	[1] Water from Working Shaft.	Water from Old Shaft.	Water from Currowong Creek.
	Grains per gallon.	Grains per gallon.	Grains per gallon.
Sulphate of Copper	1·12	17·67	6·42
,, of Zinc.....	16·98	53·54	7·20
,, of Iron.....	0·43	1·42	0·98

The sulphur compounds of copper being less stable under the chemical reactions set up by ordinary atmospheric conditions in an outcrop than those of the commonly associated metals, such as iron, lead, silver, and free gold, are frequently almost entirely removed, and redeposited at lower levels comparatively freed from the latter, which remain to enrich the leached gossan.

In the artificially-stimulated reactions of the roasting furnace, however, the reverse holds good as regards the commonest associate—iron sulphide. It is possible to remove the latter as a loose pulverulent oxide, whilst the intimately mixed copper sulphide not only remains scarcely altered, but melts and retreats to the centre of the ore lump through the porous iron oxide, a movement taken advantage of in "kernel roasting."

As Dr. Peters points out,[2] the metallurgical processes for obtaining copper from its ores are based upon its strong affinity for sulphur, wherein it exceeds every other metal. Silver frequently accompanies the leached and redeposited copper from the upper levels of lodes. Dr. Peters gives two very interesting instances of this.[3] Just below the oxidised cap of a portion of the Rio Tinto deposits (Spain) was a soft, greyish, earthy deposit from 1 to 6 inches thick, resting on the scarcely altered pyrites, which contained from 50 to 150 oz. of silver per ton, whilst the original pyrites contained about 1 oz. or less per ton.

At one portion of the Mount Lyell (Tasmania) deposit of pyrites, which averaged about 4½ to 5 per cent. of copper, with 3 dwt. of gold and 3 oz. of silver per ton, a remarkable chute of gossan descended on the footwall to the 200-foot level. It contained nearly the same amount of gold as the

[1] Ann. Rept. Dept. Mines for 1880, p. 59. [2] Modern Copper Smelting, 9th ed., 1908, p. 5.
[3] *Op. cit.*, p. 11.

original pyrites from which it was derived, but neither copper nor silver, the latter having been leached out and redeposited on the footwall under the lower border of the gossan in a series of extensive and irregular pockets. The first 50 tons extracted averaged close to 2,000 oz. of silver per ton, and 21 per cent. of copper.

In arid tracts where denudation has not been extensive, and where climatic conditions have assisted decomposition, as at Cobar and Broken Hill, oxidation extends to considerable depths, from 250 to 400 feet in the instances mentioned; though the vertical level of alteration is never uniform, being determined by the nature of the different portions of the lodes, and the occurrence of open fissures and caverns.

One of the most striking examples of a large outcrop, and of the effects of oxidation, leaching, and partial removal, was furnished by the famous Broken Hill silver-lead lode. Its bold, rugged outcrop of manganiferous iron oxide, upwards of 300 feet wide in places, formed a conspicuous feature in the landscape prior to the introduction of the open-cut system of extraction. From the oxidised cap of this giant lode the zinc sulphide, which caused such metallurgical trouble at lower levels, was almost completely removed, leaving a kindly ferruginous carbonate of lead under the iron cover.

The potential action of circulating waters above and below permanent water-level is distinctly opposite; in the former it oxidises and dissolves, in the latter protects from oxidation, and tends to deposit rather than dissolve.

Uses of Copper.

The qualities and uses of copper are so well known that repetition is unnecessary. Reference might, however, be made to the large part it is destined to take in the increasing application of electricity to the industrial arts and sciences, owing to its great conductivity (931, silver being 1,000). The practical potentialities of electrical energy appear almost boundless, and all things point to its rapid conversion to wider and ever-augmenting demands of industrial progress. Herein lies one of the most hopeful auguries of the copper industry. At the same time, it must be borne in mind that aluminium is likely to prove a rival for electrical purposes, especially if a high price be maintained for copper. The cost of aluminium has been rapidly reduced during the past few years, whilst, bulk for bulk, copper is 3·3 times heavier than aluminium. Pure aluminium[1] has a conductivity of 63 to 64 per cent., or 630 to 640 compared with the silver standard. Aluminium wire is in use for movable telephone and telegraphic work. Its extreme lightness renders it most suitable for field military telephones and telegraphs.[2] A contract was let to supply 150,000 lb. of aluminium wire to convey power from the Shoqualme Falls to Tecoma, Washington; the metal to be alloyed with 1½ per cent. of pure copper. In connection with this subject, it is interesting to note the discovery of the most important commercial ore of aluminium—bauxite—in New South Wales. For electrical purposes copper must be practically free from impurities, as such tend to diminish its conductivity. Lake Superior copper—prepared from the native metal—enjoys the distinction of being equal, or almost so, to copper prepared by electrolysis, owing to its purity.

[1] Mineral Industry, VI, 1898, p. 39. [2] *Aust. Mining Standard*, 13th April, 1899.

Broken Hill.

Original outcrop of lode at south end of Block 11.)

Commercial Copper Ores.

Copper occurs in Nature in a variety of combinations with other elements, but those of commercial importance are comparatively few, and only such will be considered here.

Native Copper—Specific gravity, 8 to 8·9, when pure and solid.—Native copper is common in New South Wales wherever copper ores occur, but in no instance has it been discovered in appreciable quantities. In the oxidised zone of the Great Cobar, Girilambone, Blayney, Peelwood, Cadia, and other mines, it occurred in small irregular masses, crystalline, arborescent, and leafy forms. In the Broken Hill lode very beautifully crystallised aggregates of native copper and cuprite occurred above water-level, where also a new combination—iodide of copper—was discovered by Mr. C. W. Marsh, after whom Professor Liversidge proposed to name it "Marshite."[1]

At Reedy Spring, near Molong, on the Gamboola Estate, one of the largest blocks of native copper (1 cwt.) found in the State was discovered, and exhibited in the London Exhibition of 1851. A similar block from the same locality, weighing three-quarters of a hundredweight, is now at the station homestead. Mr. Stutchbury recorded the presence of native copper in porphyry in this locality in 1852.

It is interesting to note that at Lake Superior, U.S., masses of native copper, weighing several hundred tons, were found, the largest, according to C. Le Neve Foster,[2] weighing nearly 600 tons. These immense masses proved anything but profitable discoveries, owing to the difficulty of extraction, having literally to be sawn into blocks for removal.

In the andesitic and epidotic rocks of Wellington, Cowra, and Carcoar Districts, small, possibly idiogenetic grains, and thin secondary veinlets of native copper are present, which, owing to decomposition at the outcrops, frequently very deceptively stain large areas of rock superficially.

The presence of minute particles of native copper in the tuffaceous shales of the Narrabeen Series (Triassic) overlying the Sydney Permo-Carboniferous Coal Basin, will be found fully described in another section of this work. Is also found in a basalt at Kiama, which is regarded by Professor David as one of the probable sources of the volcanic particles in the cupriferous shales.[3]

Cuprite (Red Oxide of Copper) Cu_2O. Specific gravity, 5·8-6·1. (Composition—copper, 88·8; oxygen, 11·2 = 100).—This is the richest ore of copper, and is found in the upper portions of lodes, frequently forming a coating of native copper as a result of decomposition. Though rarely persistent in lodes, and comparatively scarce when compared with lower-grade combinations, it is yet frequently of considerable commercial importance. In the Great Cobar lode it occurred in massive bunches of great purity near the surface. At Girilambone it formed an important source of the metal in the South lode, where it occurred as "carbonas" or isolated nodules, which probably represent altered masses of native copper. In most of the copper-mines of the State it was present, but rarely, if ever, in quantity approaching the Cobar occurrence.

Melaconite (Black Oxide of Copper) CuO. (Composition—copper 79·8; oxygen, 20·2 = 100). Specific gravity, 6·2 (when solid).—This, the second richest ore of copper, though of common occurrence, has not yet

[1] Journ. R. Soc. N. S. Wales, 1892, XXVI, p. 328. [2] Text-book of Ore and Stone Mining, 1894, p. 36.
[3] Rept. Austr. Assoc. Adv. Sci., 1881, I, p. 289.

been found in extensive deposits in New South Wales. It is frequently mistaken for the black partially altered and enriched sulphide of the transitional zone, between the thoroughly oxidised ores and the yellow sulphide below water-level, unfortunately in this state forming an incoherent powder very difficult to save in mining and dressing, hence a good deal of actual loss occurs.

Malachite (Green Carbonate of Copper) $CuCO_3 + Cu(OH_2)$ (Peters). Specific gravity, 3·7 to 4. (Composition—cuprous oxide, 71·9; carbonic acid, 19·9; water, 8·2 = 100).—Malachite is a valuable ore of copper, and one of the most common in the oxidised zone; hence it is familiar to miners, and necessitates brief notice only. In all the principal mines of the State, with the sister carbonate—azurite—it furnished considerable supplies of direct smelting ore. At Cobar it occasionally occurred fairly massive; but not sufficiently so for ornamental purposes. At New Mount Hope it occurred in rather earthy form, and as a "stockwork" of minute interlacing veins, an interesting feature of which is the secondary origin of some of the malachite veins which cross and intrude the azurite. Beautiful velvet and moss-like crystalline aggregates (sometimes stellate) frequently lined fissures and cavities in both mines. The Cobar carbonate ores are practically exhausted in the present workings; but at Girilambone, New Mount Hope, and the Central, considerable quantities of low-grade carbonates and oxides still await an economic and efficient treatment, probably other than smelting, in consequence of the excess of silica and the absence of solid sulphides.

Azurite (Blue Carbonate of Copper) $2CuCO_3 + Cu(OH_2)$. Specific gravity, 3·7 to 3·8. (Composition—cuprous oxide, 69·2; carbonic acid, 25·6; water, 5·2 = 100).—Azurite occurs almost invariably associated with malachite, but in lesser quantities, and is, therefore, common in the upper levels of copper lodes. Very beautiful radiate crystalline aggregates were obtained in the New Mount Hope and Girilambone lodes, and almost equally as fine crystals from the Peelwood and Broken Hill lodes.

Chalcocite (Copper Glance, Grey Sulphide of Copper) Cu_2S, locally known as "grey ore" amongst miners. Specific gravity, 5·8. (Composition—copper, 79·7; sulphur, 20·3 = 100).—One of the most important ores of copper, usually resulting from redeposition of copper-salts leached from the upper levels. It occurs in most of the local copper lodes. At Cobar it formed massive bunches. At the Bingara mines and at the Bumbery, some of the most characteristic examples of this ore have been obtained; usually, however, it is massive and destitute of typical structure and lustre.

Bornite or *Erubescite* (Variegated Copper Ore) $3Cu_2S, Fe_2S_3$. Specific gravity, 4·5 to 5·5. (Composition—copper, 55·58; iron, 16·36; sulphur, 28·6 = 100).—A rich ore of copper, also probably derived from the redeposition of ores leached from higher levels. It is remarkable for rich colouring (to quote Dr. Peters), from "golden yellow to deepest indigo, and from brilliant green to royal purple," which the freshly-broken purplish-brown mineral assumes on exposure to the air. It occurs sparingly in a number of localities in the State. In the Burley Jacky Mine, near Woodstock, the only important deposit was mined, upwards of £10,000 worth of bornite being raised from one chute, averaging 30 per cent. of copper. At the Hampden Mine, between Mount Victoria and Jenolan Caves, bornite also occurs; but the quantity is doubtful.

yrite (Yellow Sulphide of Copper, Copper Pyrites) Cu_2S, Fe_2S_3. ravity, 4·1 to 4·5; hardness, 3·5 to 4. (Composition—copper, on, 30·5; sulphur, 35·1=100).—Copper pyrites is the most istributed, and in view of its persistence in depth, the most ore of copper. The lower extensions of all copper lodes almost y owe their value to chalcopyrite; and conversely nearly all the ie surface zone have originally resulted from its decomposition. t occurs associated with iron sulphide (pyrite) as a mechanical

In the most important deposits the iron pyrite constitutes the mineral, and generally carries small proportions of gold and hich are recoverable under metallurgical treatment. In the re notes on Working Mines, particularly in connection with and concentration, where it occurs sparingly and independently ated through the gangue, this important ore will be fully dis-

Abandoned Mines.

leavour was made in the first edition of this work to give the ssible information obtainable under the circumstances of the the ores and the extent of development of the early-opened ines of the State, the sites of many of which were marked only illock heaps, slag dumps, and ruins of furnaces. The value of rds of the dead past may not at first glance be apparent; but the light of the successful reopening and working of mines at nt day which in the past had a fluctuating existence, neither nor the effort was in vain.

early days of copper mining and smelting in New South Wales were either disregarded in mining or discarded in sorting, only would pay to smelt direct at the mines, or cover the higher l cost of carriage and smelting at some central works, being

The early miners had further to contend with enormous initial nsequent upon long carriage by teams over bad roads (over 300 the case of Cobar, for which as high as £42 per ton was paid) arest railway; conservation of water, in some instances in arid lestitute of natural drainage channels; in fact, in almost every for development an outlay was incurred altogether disproportion the cost of similar requirements in these latter days of extended and cheaper freights and fuel.

ccessful working of the far Western mines under these abnormal s for a number of years is eloquent testimony to the richness of ear the surface, as well as to those of mines nearer the seaboard, n earlier days under rather more favourable conditions as istance of carriage and of water supply.

stion of these richer oxidised supplies, and encountering with e more permanent but greatly poorer sulphides below the water- many cases compelled abandonment, in some instances abruptly position was aggravated by a sudden drop in the market value r.

y be approximately stated that, even under existing local con- a return of less than £55 per ton to the producer will not margin for profitable working, except, perhaps, in the case of able of treatment on a large scale.

ew of the modern advantages of cheaper freights (which are a *non*) and improved processes and machinery, which tend to balance depreciating yields by larger and more rapid output, it

is reasonable to anticipate that mines closed owing to adverse circumstances, rather than exhaustion, will yet yield profit for capital invested. It must, however, be strongly emphasised that successful reopening is dependent not only on the size of the low-grade ore-body, but to a larger extent perhaps on its composition, which determines the possibility of direct furnace treatment or mechanical concentration. Direct or partial pyritic smelting affords the most economic and rapid reduction of quantity, which is an indispensable factor in low-grade problems.

Not only in working the present active mines, but also in reopening old ones from which the richer surface ores have been removed, every advantage offered by cheapened freights and fuels, more efficient processes and machinery, combined with strictest economy in mining and supervision, must be utilised to offset gradually depreciating ore tenor, increasing haulage, and augmenting water, which assuredly wait on depth.

Nor should the value of the accumulated mine water be overlooked when reopening after years of enforced idleness, for it becomes saturated more or less with soluble salts of copper, which can be readily and cheaply extracted by means of metallic iron. The affinity of the sulphuric acid in the solution for iron being stronger than for copper, the latter is expelled in the metallic state, whilst the former enters into combination with the acid. Therefore, before unwatering, provision should be made for testing the quantity of copper in solution, and for preparation of vats lined with old scrap-iron for precipitating the metal, if the proportion is sufficient for profitable extraction.

The recent experience of the Blayney Copper Company is an instance in point, 67½ tons of cement copper were obtained by precipitation whilst unwatering the workings, the percentage of copper in the accumulated water amounting to 32·9 lb. per 1,000 gallons.

As little free acid as possible should be present in the solution, otherwise a larger quantity of iron is dissolved without increasing the precipitation of the copper. Theoretically, according to Dr. Schnabel, 88·8 parts of iron are required to precipitate 100 parts of copper; in practice, however, the consumption of iron is considerably greater, owing to the presence of free acids.

The precipitating tanks at Rio Tinto are of brick, lined with plaster of Paris, and inside this with asphalt or Portland cement. Size, 6 ft. 6 in. x 6 ft. 6 in. x 2 ft. 6 in. The solutions traverse a series of these tanks. The consumption of iron is 1·12 parts to 1 part of copper.[1] Mount Morgan employs cemented tanks.

At the Gulf Creek Mine, near Barraba, coke, in contact with iron, was found to be an effective precipitating agent.

An analysis by Mr. W. A. Dixon, F.C.S., F.I.C.,[2] of the Milburn Creek drainage water yielded copper at the rate of 328·9 grains per gallon, equal to 4·698 lb. per 100 gallons. The iron and steel tools left in the mine during suspension owing to litigation were converted into hollow shells of metallic copper. A winch was similarly converted in the Blayney Mine.

Many old mines are on land acquired by mineral conditional purchase. There is little doubt that few of the mines so situated would remain unexplored if provision were made in the Consolidated Mining Act for ascertaining, as far as possible, by prospecting, the necessary valuation before resumption.

---

[1] Handbook of Metallurgy, by C. Schnabel; English translation by H. Louis, 1898, I, p. 242.

[2] Ann. Rept. Dept. Mines for 1879, p. 37.

›s the most noticeable and regrettable feature in the early work-
he majority of New South Wales mines, and, unfortunately, of
the present also, is the almost, if not complete, absence of any-
proaching system. Sufficient unto the day has been, and is, the
eof. Where rich ores occur the paramount object appears to be
, as speedily and cheaply as possible, without regard to the future.
› a payable mine opened systematically by extending prospecting
ıs beyond actual stoping; in fact, proving almost invariably
: the very time it should be most vigorously prosecuted, viz.,
vidends are being paid; and perhaps still more rarely is any
le portion of the latter set aside as a reserve against contingen-
ɛnce, when the richer ores are exhausted, or the known pay-chute
lls are necessary for improvement of plant, or the search which
ave been synchronous with payable working.

eters states[1] that the rich ores of Butte, U.S., furnished the
hat was needed to design and construct the improved plants, and
ɛxperience necessary for treating the lower-grade ores at a profit;
ıately, this has not been the case with certain well-known copper-
this State.

ecessity for timely proving is peculiarly essential in copper-
if any enlightened and progressive system is to be adopted in
he hand-to-mouth policy which robs the mine of its richer ores,
:he poorer to bear alone the steadily increasing cost of extraction
ıibly of treatment. A more reasonable method would appear to
vhich speedily opens up the sulphide resources beneath the richer
and secondary ores of the surface zone, and not alone in depth,
itudinally and laterally, proves the deposits and the barren inter-
›lanks.

f the first requisites is proof of the vertical extent of the richer
he oxidised and redeposition zones, and the nature and quality
›orer but more permanent sulphides beneath.

ɛidised and sulphuret ores are natural fluxes one for the other;
would appear more profitable to open up the latter and work
:h the former, as far as these are available, instead of procuring
luxes, often at considerable cost, and thus introducing into the
unproductive material, and thereby proportionally lessening
›ful capacity.

, the necessity for timely proof of the nature of the sulphides, or
f their matrix, is clearly an urgent matter, for frequently, as at
pe, Great Central, Girilambone, &c., concentration, with its
ıt costs, has to be faced. Few mines offer the exceptional advan-
a Great Cobar or a Nymagee, where the solid pyritic matrix
ı kindly fluxing base in blast-furnace treatment; and, moreover,
ready and efficient means of treating gold and silver ores as fluxes
›ocess. This important advantage will be more fully discussed when
e mines are under description.

from the metallurgical advantage derivable from proper blend-
he different grades of ore in a mine, another equally desirable end
›d, viz., regularity and equality of output, which alone render
a sound and secure investment. Command of rich and poor ores

[1] Modern Copper Smelting, 9th edition, 1898, p. 19.

in a deposit may, unfortunately, be also used for the ignoble ends of market riggers and share gamblers; but fluctuating yields, either through lack of system or through design, must always react at the expense of legitimate mining and security.

Shortness of initial capital and the natural desire to make a mine "pay from the start" are frequent sources of after trouble and avoidable expenditure, leading to depletion of the richer and kindlier ores of the surface zone, and saddling the lesser and predominating with entire cost of suitable reducing plant.

It cannot be too strongly emphasised that it is the less, and not the rich, which should determine the character of the plant; also that the often extremely narrow margin between profit and loss is dependent on the scale on which the low grades can be handled.

From these premises it is clear that the first duty is to pierce the enriched zone, and ascertain qualities and probable quantities of primitive ores below the protecting water-level. In this way only can an intelligent insight into the smelting problem be obtained, and the fullest advantage of natural fluxing secured.

Determination of these important questions should be followed by installation of plant commensurate with nature and quantity of reserves disclosed.

Establishing a smelting plant prior to adequate proving, unfortunately, is still not uncommon, leading to a hand-to-mouth existence wherein smelting is dependent on the daily mining output, and the latter on the exigencies of blind stoping.

The Crowl Creek-Shuttleton Mine is a case in point, where the daily requirements of the established furnaces overtaxed the output of the proved ore lens, preventing prospecting ahead of actual stoping. Difficulties, moreover, become accentuated when, as frequently happens, the primitive ores are not amenable to direct furnacing.

Trafficking in shares during the "boom" period of a mine's history frequently imparts an entirely false idea of its financial strength. The inflated value of its stock on the market is no criterion of the capital available for development, which only too often is absurdly inadequate for placing it on a proper working basis.

The sudden shock of a call for necessary developmental expenditure is like a "bolt from the blue" to uninquiring investors who bought at the top of the market. It should be a *sine quâ non* that a sufficient sum for the purpose should be secured against promoters' interests in the paid-up capital, and no better time for this than when confidence is strong. Again, in all legitimately-worked mines a reserve fund against contingencies should be established out of profits.

Brown and Turnbull, writing on this subject, state: "It must, however, be always remembered that much time and generally much more money than is at first anticipated have to be expended in the initial stages of development before any results are obtained that make for permanence or a reasonable prospect of such. To neglect the patient application of those scientific principles by which a new field can be laid out so as to ensure such a regular output as may be commensurate with the importance of the undertaking, the creation of reserves of ore, and the deciding on erection of a suitable plant, is but to court disaster."[1]

[1] A Century of Copper, 1900, Pt. II, p. iv.

Dr. Peters states: "It is impossible to make any calculation about the probable behaviour of an ore in the blast furnace, or indeed any other, until we know its exact chemical composition." Hence the necessity for securing qualified metallurgical knowledge and skill when smelting is determined upon. Ordinary furnace experience may be sufficient where only the simplest and richest ores are to be dealt with, but as these should form the vehicle for inferior and refractory associates, correct blending is dependent on exact knowledge of chemical affinity and equivalence.

Where, for instance, rich basic (sulphide) ores occur in the enriched zone, these should afford the means for furnace concentration of leaner ores mixed with country or gangue. Mechanical concentration should be the last resort in such cases. Likewise, where oxidised ores are available, it is preferable to use them with raw sulphides instead of roasted sulphides.

Peters says: "Fluxes need hardly ever be used if the analyses of ores are studied metallurgically. Sometimes, however, silicious fluxes containing gold and silver can be used with great profit." Silicious ores require ferruginous flux, and *vice versâ*.

Every ton of barren flux increases cost of smelting. Recent turning to account of grades, previously unthinkable of as profitable smelting propositions, is owing to the great advance in economic mining and reduction, notably, in this State, the Burraga silicious ore of 2¾ per cent., and Great Cobar (basic) of 2·7 per cent.

Falls in copper value are not altogether unmixed evils, for they have been the spurs to greater efforts to reduce costs, compelling increased efficiency and economy, which ensured greater profit in periods of enhanced value.

It is worth considering whether advantage should not be taken of "boom" times to work the lowest grades, leaving the richer for exploitation when values are lower, thus lengthening the life of the mine.

Brown and Turnbull, in their review of the copper-mining industry during the past century, state: "The most remarkable feature next reviewed is the great reduction which has taken place in costs.

"The average 'copper contents' of the various classes of ore are shown, and while it is to be observed that they are on a declining scale throughout, the adaptation of improved methods of treatment of a necessarily increased bulk more than compensates for the falling off in percentage. It will be seen that, approximately, the cost of making copper has been reduced during the century (in the case of sulphide mines using the smelting processes) from £80 per ton to £40 per ton of metal." [The great scale of operations at Mount Lyell (Tasmania) enables blister copper to be produced at about £39 per ton from 2 per cent. ore.—J.E.C.]

"It has been to an increase from the older sources of supply, such as Lake Superior, Montana, and Arizona, that the constantly increasing consumption has had mainly to depend upon for several years past.

"To the older smelting methods have been added blast furnace, water-jacket furnace, Bessemer converters, pyritic smelting, and enlarged reverberatory furnaces; while an entirely new type of refining has been introduced by the electrolytic method, which not only refines the copper, but recovers the gold and silver contents in the same operation."[1]

[1] A Century of Copper, 1900, Pt. II, p. iii.

Low-Grade Deposits.

Until the Cobar Mining Syndicate began operations in 1893-4, when local copper was realising but £39 per ton, the successful treatment of low-grade copper ores was solely dependent upon the value of the copper contents, no allowance being made by purchasers for the associated gold and silver in certain brands of copper, which must have been an important source of profit to them. This serious defect was soon remedied, the full market values of the associated metals, less cost of extraction, being obtained. Still the additional advantages enjoyed by European smelters of realising the values of by-products is not yet possible to those of Australia. The Tharsis Copper and Sulphur Company, of Glasgow, affords, perhaps, the most signal example in this respect. Working the low-grade cupriferous pyrites of the Spanish Peninsula, containing barely 3 per cent. of copper, and traces only of gold and silver, it was enabled, through realisation of the by-products, to pay dividends of 750½ per cent. on a capital of £1,250,000 between 1868 and the end of 1905. Theoretically, the only loss in its operations is the scrap-iron used in precipitating the copper from solution, each of the component minerals in the ore being turned to commercial account. A short description of the interesting Tharsis process, from notes made by the Writer during a visit to the Company's Glasgow works in 1890,[1] may prove of interest:—

"During my stay in Glasgow, through the courtesy of the proprietary, I was enabled to visit the Tharsis Copper Reduction Works. The Spanish ore treated at these works consists chiefly of iron pyrites with a percentage of copper pyrites equal to about 3 per cent. of metallic copper; the sulphur being equal to from 46 to 48 per cent.; very small quantities of gold and silver are also present. The ore is first roasted at the Sulphuric Acid Works, in the immediate vicinity, to obtain the sulphur, about 4 per cent., however, being purposely left in the calcined ore; it is then mixed with 16 per cent. of salt, and charged into roasting furnaces in charges of about 3½ tons, exclusive of the salt. The furnaces are known as blind muffles, the ore being within a central brick oven out of contact with the flames. The roasting continues for about ten and a-half hours. The fumes are led from the muffles into towers containing coke, over which water is constantly trickling, which absorbs the gases given off. A small proportion of gold is carried down in the acid solution, and is precipitated along with the other metals present by a small quantity of sulphide of calcium, which is allowed to trickle into the solution at the points where it issues from the base of the towers into the settling vats. The clear acid solution, which contains about 30 grains of copper per gallon, is in part used for washing the roasted ore, the balance being treated with scrap-iron to precipitate the copper.

"The roasted ore is thrown into vats, and hot water pumped on to the top; as it percolates through the mass it dissolves the soluble copper salts formed by roasting; the copper solution passes through the filter bottom into the adjoining compartment. The ore is then discharged into another vat and rewashed, the weak solutions being constantly charged into the ore vats until they attain a certain strength. The gangue is washed until no appreciable quantity of copper is left; the completely decopperised gangue, after exposure and oxidation, is known as "blue-billy," and is sold to the iron foundries for fettling purposes. The strong copper solution is pumped into vats and treated with iodide of zinc to precipitate

[1] Ann. Rept. Dept. Mines N. S. Wales for 1890, p. 278.

r; the solution is after a time drawn off and treated with iron precipitate the copper in the metallic state; the resulting copper rashed and then smelted into ingots.

precipitates obtained with the sulphide of calcium and iodide of sent to Birmingham for treatment. In the above interesting nomic process there is, therefore, no waste, save the unavoidable manipulation, all the commercial constituents of the ore being d."

y at Cobar or Lithgow is forcibly convincing of the great, yet y unavoidable, loss of valuable material, viz., sulphur, that is ontinually volatilised into the atmosphere. Unfortunately, local ons prevent its utilisation in the manufacture of sulphuric acid, as is nes the practice of European countries, where protection of vegeta- art from commercial advantage, compels preventive measures against astrous effects of sulphuric acid gas, more particularly in humid s. Fortunately, or unfortunately, little loss is likely to accrue he latter cause at Cobar.

re smelting operations are carried on in centres of population, the nuisance is capable of abatement by erection of tall chimney-stacks, ans of which the noxious gases become largely diluted with air reaching the ground. Experiment has proved that the other e substances discharged into the atmosphere in copper-smelting actically inert, or too diffused to be objectionable.

monosulphide—pyrrhotite or magnetic iron pyrites—which is n in copper lodes, and in considerable proportions in some of those Blayney District, and is also present in the Cobar lode, is of little for sulphuric acid manufacture, as it contains but one atom of r against two in the ordinary pyrite, and requires greater heat expulsion. It is, however, of equal calorific power to the bisulphide tic smelting, owing to the volatilisation of one atom of sulphur from er in the native state.

ecent years, large bodies of low-grade cupriferous sulphides have nch sought for, the most important ventures in this direction being nt Lyell, of Tasmania, and the Great Cobar, of New South Wales. low a grade may be profitably exploited depends upon local con- and the nature of the ores. If gold and silver be present, even paratively insignificant proportions, an ore capable of pyritic treat- n a large scale, containing even 2 per cent. of copper, will yield a nder favourable circumstances (especially of transport). It is, indeed, ible upon how little depends the profitable or unprofitable operation of posits on a scale of great magnitude; the almost infinitesimal gold ver contents may represent the difference between profit and loss. t the famous Butte Mines, of Montana, U.S. (according to Dr.), it may be assumed that the net profits are mainly derived from er contents, which amount to about 5 oz. per ton of 2,000 lb., in ore then averaging about 6½ per cent. Deducting the losses in ration and smelting, the net yield of the Butte ores was 5 per cent. of and 4 oz. (0·014) per cent. silver,[2] the present yield being about 3¼ t.

melting yield of the Great Cobar ore is estimated at the present average about 2·7 per cent. of copper and 2½ dwt. of gold per ton.

[1] Modern Copper Smelting, 9th ed., 1898, p. 20. [2] *Ibid.*, p. 19.

The actual returns of gold and silver are, however, difficult of estimati owing to complication arising from admixture of gold and silver f from the neighbouring Great Peak Mine as fluxes.

In one respect, auriferous, low-grade copper deposits possess a distin advantage over richer, viz., the extreme smelting concentration necess to produce a profitable matte from poor copper ores brings their co gold and silver contents within the range of profitable extraction, wh is an impossibility in low concentration, owing to the cost of electrol separation. The ratio of concentration during the two campaigns Lake George Mines (Ltd.), Captain's Flat, averaged 27 tons of ore 1 ton of 30 per cent. matte.

The proximity of siliceous flux, having of itself considerable value, an important factor in the determination of the profitableness of a low-grade pyritic lode.

The regrettable failure of the operations of the Lake George Mi turned on 1 per cent. of copper. The pyritic smelting adopted, after initial difficulties had been overcome, reached so high a pitch of econo efficiency that a smelting yield (according to the Company's certi returns) of a shade over 1 per cent. of copper, and proportionately co yields of gold and silver, amounting in aggregate value from 22s. to 2 only failed by about 5s. 6d. per ton to pay cost of mining and smelti An additional percentage of copper at the market rate would have turn the balance between profit and loss.

The failure of the Company's first operations resulted in the achie ment of further reductions in cost of production, under the skilful tre ment of Mr. A. W. Hudson, which, combined with strictest economy mining and supervision, established a record.[1] This result is best app ciated after a study of the refractory composition of the ore in questi which is fairly represented in the following analysis by Mr. H. P. Wil F.C.S., Assistant Analyst to the Department of Mines and Agricultu of an average sample selected by Messrs. Jaquet and Watt, Geologi Surveyors, from the various exposed faces at the 400-foot level:—

Analysis.	
Moisture at 100° C.	0·10
Combined water	0·65
Insoluble in acids (gangue)	23·70*
Metallic iron	17·75
,, zinc	14·50
,, lead	8·04
,, copper	1·11
Sulphate of lead ($PbSO_4$)	0·32
Alumina (Al_2O_3)	1·38
Lime (CaO)	0·40
Magnesia (MgO)	0·65
Sulphur trioxide (SO_3)	0·25
Carbonic acid (CO_2)	2·08
Phosphoric acid (P_2O_5)	0·57
Sulphur (S)	27·97
Oxygen, and undetermined	0·53
	100·00

* Note.—91·35 per cent. of the gangue consists of silica, the remainder containing alumina, magn and alkalies. The gold contents averaged 1 dwt. 12 grs., and the silver 2 oz. 8 dwt. 14 grs. per ton.

The actual smelting returns from over 90,000 tons of ore, subsequen furnaced by the Company, verified the accuracy and thoroughness of sampling represented by this analysis.

[1] Which, according to the Company's State representative, was 14s. 9d. per ton of ore for mining reducing to matte and general expenses.
[2] Ann. Rept. Dept. Mines and Agric. for 1897, p. 21.

r comparison it is interesting to note the cost of mining, smelting, levelopment at Mount Lyell, Tasmania, about the same date. For alf-year ending 31st March, 1897,[1] the following costs are quoted :—

	£	s.	d.
Mining operations	0	2	4·64
Removal of overburden	0	2	0
Smelting operations	0	17	9·87
Converter	0	2	9·18
	£1	4	11·69[2]

ducting the converter charge, the cost of producing a 50 per cent. e amounts to £1 2s. 2·51d. per ton of ore treated. The Mount Lyell i, however, favourably distinguished from that of Lake George Mines, 'eater richness and freedom from refractory associates.

undance and a kindly matrix are indispensable conditions in low- e deposits; the dimensions should be such as to allow of continuous mic winning without excessive deadwork.

e composition of the matrix and the proportion of sulphur are the rtant factors, for upon these depend the nature of the treatment. rgely pyritic, smelting is greatly simplified, the partial pyritic ss being most suitable and economic.

silicious (quartz) matrix, from its great infusibility and consequent fluxing requirements (2 lb. of basic flux to 1 lb. of silica), is, aps, the most intractable. The silica, however, should be kept above r cent. A deficiency of silica or excess of iron in the slag interferes the separation of the matte, as it increases the specific gravity of ormer.

ith pyritic ores a considerable amount of silica—from 30 to 40 per —can be safely included in the blast-furnace charge, to form a fluid te of iron slag. The range of silica in an ideal slag lies between t 30 and 38 per cent., but it is unquestionable that a considerably r limit is possible. This interesting and important question receives extended consideration in the second part of this work, under the of Great Cobar.

es containing an excess of silica and deficient in iron and sulphur are r suited for reverberatory furnaces, as a large proportion of unfused tz can be floated off in the slag of a reverberatory furnace without iring the separation of the matte. Lean silicious sulphide ores, ver, require concentration before effective independent smelting is ble. Oxide of iron, or, better still, ferruginous slag from matte ing, is the best flux for silica.

e following *résumé* from a paper on Copper Smelting, by Mr. H. M. , A.M., S.B.,[3] on the advantages of the two forms of furnaces— la (blast) and reverberatory—is extracted from "Modern Copper ting," Fifth Edition, 1892, p. 258 :—

FURNACES.

r smelting ore the cupola is specially advantageous—

"1. With highly ferruginous ores.

"2. Where the cost of anthracite, coke, or charcoal is not excessively greater than that of bituminous coal, wood, and other fuels fitted for the reverberatory only.

"3. For oxidised ores.

"4. For low-grade native copper.

"5. Where, as in the case of lean ores, clean slags are a necessity."

---

asmania and its Mineral Wealth ; special edition of *Austr. Mining Standard*, 1st July, 1898.
t. Lyell has now reduced cost of mining, smelting, and bessemerizing to 15s. 4d. per ton of ore. arly Report, 31st March, 1908.
ull. U.S. Geol. Survey, 1885, No. 26.

The reverberatory is especially advantageous—

"6. With highly refractory silicious, aluminous, calcareous, or ma nesian ores.
"7. Where the composition of the ore changes suddenly and greatly.
"8. Where bituminous coal, wood, or other reverberatory fuel is ve much cheaper than anthracite, coke, or charcoal.
"9. For smelting and immediately refining rich native copper.
"10. Its disadvantages in yielding richer slags than the cupola weig less heavily in case of rich ores."

The application of the principle of pyritic, or partial pyritic, smelti is of very recent date, and in Australasia but five instances are kno to the Writer, viz., at Mount Lyell, Captain's Flat, Great Cobar, a Nymagee. As, therefore, pyritic smelting is comparatively little kno rather full extracts have been made from the writings of Dr. Pete junior, and Mr. Robert Sticht, of Montana, illustrating its princip scope, and results.

Pyritic Smelting.—"Pyritic Smelting—Its History, Principles, Sco Apparatus, and Practical Results," is the title of a very interesting a instructive article by Mr. Robert Sticht,[1] from which extracts have b made, as well as from the chapter on the same subject by Dr. Pete To quote the latter: "Mr. W. Lawrence Austin, of Denver, Colora is fully entitled to the credit of carrying out to a commercial suc the principles that John Hollway, of London, proved to be practicab (in 1878, according to Sticht.—J.E.C.).

Pyritic smelting is defined by Dr. Peters as "the fusion of sulphi ores by the heat generated by their own oxidation, and without the a of extraneous heat, such as carbonaceous fuel, the electric arc, &c."

Its object, according to Mr. Sticht, is "to make the pyritic, or oth sulphuretted materials of the ores, act in a unique and threefold capacit viz.:—

"1. As a fuel.
"2. As a collector of the precious metals, as also of the copp nickel, &c., present.
"3. As a flux, or slag-making factor."

From Dr. Peters' summary of pyritic smelting the following abstrac are taken:—

"1. Genuine pyritic smelting (without the aid of any carbonaceo fuel) demands exceptionally favourable ores.
"2. Partial pyritic smelting, with the aid of a hot blast, and t addition of from 1·5 to 5 per cent. of coke to the charge, is a assured success, and may, under proper conditions, be the mo economical method that can be employed.
"3. Both pyrrhotite (magnetic pyrites) and matte make excelle materials for this process, pyrrhotite affording practically abo as much heat as does iron pyrites, owing to the loss of the fi atom of sulphur in the latter mineral, by volatilisation metallic sulphur. The oxidation of the iron probably furnish as much effective heat as the burning of the remaining atom sulphur.

[1] Peters—Mod. Copper Smelting, 8th ed., 1898, pp. 396–401. [2] *Ibid.*, pp. 372–395.

"4. Arsenic and antimony are more thoroughly removed, and cause less trouble than in ordinary smelting. Zinc and lead sulphides are about equally deleterious in the new, as in the old, method of smelting. Heavy spar works particularly well in a pyritic furnace, the baryta being slagged and the sulphuric acid decomposed and escaping as gas, instead of augmenting the quantity of matte, as in ordinary blast-furnace work.

"5. The recovery of the precious metals is as good in pyritic as in ordinary smelting, and the slags are equally clean.

"6. The rate of concentration is very satisfactory under proper conditions, and can, in the main, be regulated at will, according to shape of furnace, volume and pressure of blast, fusibility of charge and rapidity of driving, and amount of carbonaceous fuel added.

"7. A plant for pyritic smelting can be erected at least as cheaply as one to produce similar results by the ordinary methods."

The advantages of pyritic smelting are (*a*) the enormous saving effected cost of fuel as compared with ordinary blast and reverberatory thods; (*b*) saving the initial cost of roasting or calcining plant, with labour attaching thereto, and the additional handling of the ore; (*c*) production of cleaner and more silicious slags, the latter an object of at importance in many localities (Cobar, for instance) where gold and er ores can be worked with the copper, for by keeping the slags cious these metals may be concentrated to any reasonable extent.

n rare instances, where the ores are very suitable, carbonaceous fuel almost entirely be dispensed with; usually, however, from 3 to 5 per t. (coke) is used. In ordinary smelting in the United States, Dr. ers estimates the proportion of coke in the blast furnace as fully equal ne-sixth of the weight of ore; and the combined cost of fuel in roasting l smelting as about equal to 60 per cent. of the total cost, the difference cost of fuel between pyritic and ordinary blast furnace smelting being al to 40 per cent. in favour of the former.

At Mount Lyell almost pure pyritic smelting is in progress, 1¼ per t. of coke only being used.

The Writer tenders appreciative thanks to the Directors of the Great ar and Lloyd Copper-mining Companies for generously permitting ir General Managers, Messrs. G. H. Blakemore and W. H. Corbould, ing the mining public the benefit of local experience—the former for s article on electrolytic copper-refining, and the latter on treatment copper ores.

In commending such a policy to the Institute of Mining and Metallurgy, London, Professor James Douglas, an American copper authority, ted: "The ridiculous secrecy maintained at so many of the metallurical works, especially in Europe, benefits no one, least of all those who sdulously close their works against inspection, and at the same time ipotedly close their own minds against all reasonable expansion. It ands to reason that there must be in art, as well as in science, a give-nd-take rule; and people who will contribute nothing to the information f the world or their co-workers in any given art are not those who are nerally most progressive in their own practice."[1]

[1] A Century of Copper, Pt. II, p. iv.

Brown and Turnbull state that "these economic advances being so great, and the displacement of old processes so rapid, it is of the utmost importance that all facts connected therewith should be fully disclosed."[1]

To the Lloyd Copper Company the Writer is also indebted for working plans of the large reverberatory at the Lloyd Copper-mine (the largest wood-fuel furnace in the State), and of the "W. Thomas" small reverberatory, suitable for small mines. The working details of construction are of special value to those contemplating smelting, who will doubtless appreciate the generosity of the designers.

The symmetry of the Lloyd furnaces is most noticeable, even after long smelting campaigns—a fact due, according to the designers, to the solid foundation and thorough under-bracing.

Treatment of Copper Ores.

(By W. H. Corbould, Managing Director, The Lloyd Copper Company, Ltd., New South Wales.)

"In considering the best method of treatment for copper ores, one must be guided by the value and character of the ore, the facility for securing fluxes, the cheapest class of fuel obtainable, and the nature of the water supply.

"*Blast Furnace Treatment on Oxidised or Part Oxidised Ore or Calcined Sulphide Ores.*

"The slag from such ores should have a composition of, say, 30-35 per cent. silica, 30-40 per cent. ferrous oxide, 8-20 per cent. lime, or fluxes must be obtainable to produce same.

"Coke and delivery of same must be at a rate in keeping with the value of the ore.

"Water, suitable and in quantity for boilers and cooling water-jackets, must be obtainable.

"If the furnace is to run on oxidised ores, and the grade of the ore will not stand a high loss of copper in the slag, sulphide ore must be obtainable.

"*Blast Furnace Treatment on Pyrite Ores.*

"The slag from such ores will, to a great extent, form its own composition of slag.

"For direct pyrite (sulphide ore) smelting, the height of the furnace column should be increased over previous method, and the air capacity of the blower must be much greater.

"The ore must carry sufficient free silica, or free silica must be added to the charge, as it is the free silica available with sufficient blast that produces the necessary grade of matte, without which one would be simply melting the ore without deriving any concentrating of the copper in the matte.

"*Reverberatory Furnace Treatment on Oxidised or Part Oxidised or Calcined Sulphide Ores.*

"Should the ores be sulphides, they should be calcined to drive off excess sulphurs, leaving about 8 per cent. of sulphur in the ore. If smelting oxidised ores, and if necessary commercially to produce a clean slag, a certain quantity of sulphide ore must be available. There must

[1] A Century of Copper, 1900, Pt. II, p. iv.

be ample fireclay in the district, or inferior clay and sufficient quartz to produce an artificial fireclay for brick-making. For fuel there must be abundance of firewood or coal at a reasonable rate.

"The advantage of this method of treatment over blast furnace is when the ore is very silicious and fluxes are unobtainable, as a slag high in silica and alumina can be worked. Very often reverberatory slag will go 48-55 per cent. silica and 10-13 per cent. alumina, and still carry more silica and silicate of alumina as float, *i.e.*, the iron and lime in the ore has taken up as much silica and alumina as it possibly can, still is fluid enough to carry in suspension more free particles of silica and silicate of alumina.

"In the construction of reverberatory furnace, one must take into account the class of slag that will be produced and the grade of the matte. If the grade of the matte will be, say, 50-55 per cent. copper, and the silica in the slag, say, 48-55 per cent., a narrow hearth, say, 13 feet wide, is the best; but if the grade of matte is not to be over 40-45 per cent., and the silica in the slag, say, about 35 per cent., and low in alumina, a hearth up to 20 feet wide would result in economy in treatment. The length of the hearth, with wood for fuel, will do good smelting up to 50-55 feet long, and I consider safely up to 70 feet if the grade of the matte is not over 45 per cent., and the silica 33-35 per cent., and alumina not over 7 per cent. With coal for fuel and suitable slag, there is no reason why the hearth should not be in the vicinity of 100 feet long. (At the Anaconda Copper Company, U.S.A., they have reverberatory hearths up to 115 feet long and 19 feet wide, smelting 300 tons of ore per day.)

"*Wet Concentrating.*

"The gangue must liberate itself from the ore previous to or at 400 holes to the square inch.

"The ore must be in a state of metallic, oxide or sulphide ore of copper (sulphide of copper that is part decomposed or been leached from upper level and redeposited as a sulphide, is often next to impossible to concentrate).

"*Oil Concentrating.*

"The ore must be in a state of sulphide, and which, on crushing, can be liberated from the gangue.

"*Magnetic Concentrating.*

"Ores that are magnetic, or that on heating at a low temperature become magnetic, and show a different degree of magnetic attraction from their gangue.

"*Leaching.*

"Ores that on exposure to the atmosphere and moisture decompose within a limited time, or where the ores are oxidised and sulphuric acid cheaply obtained, or ores amenable to roasting with common salt to form a soluble copper salt.

"The foregoing give a rough sketch of the different methods, and in installing new methods one must be guided by the commercial aspect; it is not a plant one requires, but profits. It is no use erecting a blast furnace if there is cheap and ample firewood available, coke expensive, and water scarce; or if the ore decomposes readily, there is no use in going in for an expensive smelting plant. Again, if there is not sufficient sulphur in the ore for direct pyrite smelting, there is no use expending money on high-pressure blowers.

"It is often brought against wet concentrating of silicious sulphide copper ores that it is impossible to make a good extraction. A good mill will lose ·8 to 1 per cent. of copper in the tailings. It does not matter if the ore to be concentrated goes 5 per cent. or 3 per cent., the loss will be about the same, as the extraction is not in ratio to the grade of the ore; in fact, often on the higher grade ore the tailings are cleaner.

"The concentrates and picked ore from above, after calcining and smelting, will produce, say, a 45 per cent. matte.

"Instead of concentrating the above ore, it is smelted direct, and to smelt same it requires for each ton of ore, say, 2 tons of flux, and the grade of the matte produced is the same as the former method, viz., 45 per cent. The slag from such a grade of matte would go ·5 per cent. copper; but to flux the ore it is necessary to use 2 tons of flux with each ton of ore, which combines with the gangue in the ore to form a slag, and as each ton of slag carries ·5 per cent. copper, the loss of copper per ton of ore would probably be greater than the former method of concentrating and smelting the concentrates obtains, to say nothing of the extra cost.

"The question of costs per ton of ore does not count in copper-mining. The question is: what does it cost to produce per ton of marketable copper? and this depends on the size of the ore-body, the percentage and class of copper in the ore, management, and plant.

"A low-grade mine of sulphide ore may be worked to just meet expenditure on 100 tons per day; but if the size and length of the ore-chutes will warrant a large plant to treat 500 tons per day, it is then a question of the necessary capital to place the mine in the dividend stage.

"A concentrating proposition, yielding metallic copper even if of low grade, say, 1·5 per cent., with a good-size lode and large plant, may yield larger profits than, say, a 2½ per cent. sulphide ore with, say, same size lode, as in the former case the concentrates produced will go about 80 per cent. copper, and in the latter 8 to 15 per cent. copper. The costs to place the sulphide concentrates into refined copper will be much greater than in the case of the metallic concentrates.

"A sulphide ore, low in copper and high in sulphide of iron, and carrying a sufficient percentage of free silica (in sulphide smelting, analysis may show that there is a certain percentage of silica; but it is necessary to determine if the silica is free or combined; if combined, it is no use for pyrite smelting), with a reasonable freight rate for coke, can be worked at a very low cost; but if the ore is deficient in free silica, and free silica has to be added in, say, the form of quartz, it means an increased cost to smelt the ore, also reducing the capacity of the furnace, with the result that working costs are higher.

"On low grade propositions, unless there is a body of sufficient size, or of small size and great length, so that a number of machine drills can be kept going to keep a large treatment plant running constantly, it is madness to attempt to work the property. The cost of management and staff over a small plant is about the same as over a large one. Take a concentrating mill that treats, say, 100 tons in twenty-four hours. Now, if that mill is enlarged to treat 300 tons per twenty-four hours, the number of men employed about the plant will be very slightly increased, and the only other increase will be the extra cost for fuel and renewals, which is a small item over the whole. The same applies to furnace treatment.

"Taking, say, the same district and about the same conditions, the higher the grade of the ore the less it must cost to produce a ton of copper. To mine 12 per cent. ore would cost no more than to mine 3 per cent. ore; but the mine with the 3 per cent. ore has to mine 4 tons to obtain the same tonnage of copper—in fact, would have to mine 4½ tons, as the loss in treatment would in the latter case be proportionately greater. So, to produce a ton of copper from a low-grade property, there must be increased cost.

"One may have a large lode of low-grade ore; but there is a limit to the grade that can be worked at a profit, and one of the great factors is the cost to mine same. No matter how wide the lode may be, once the ore is won the lode must be made secure by filling with mullock or timbering; and in undertaking to make a profit on low-grade ore one must consider what it is going to cost to mine, also to know in what state the copper in the ore is in, and what grade of copper it will produce in the first treatment operation, as the higher the grade produced the less after-cost to place it into refined copper.

"Where suitable fluxes carrying gold and silver can be purchased, such fluxes may perhaps make a low-grade non-paying copper property a financial success, as buyers of marketable copper will pay a high price for gold and silver contents, as the process to extract the gold and silver increases the quality of the copper, resulting in a higher price per ton of copper being obtained.

"If possible, never produce a matte for sale. Go a step further, and make marketable copper. There is always a market for the latter; but there are few buyers for an unfinished product, with the result, if you produce a matte, you are in the hands of a few.

"Capital is found to part-open up a mine and erect treatment works; but the two most important items for copper-mining are fuel and stores, and unless extra capital in the first instance had been allowed for to instal a system of transport, it may make all the difference between profit and loss on a low-grade property.

"In the erection of copper-treatment works, it is a good maxim not to erect until the sulphide zone is reached and opened up (in the case of a bedded deposit in limestone there may not be sulphide ore). To treat only oxidised ores there is bound to be high losses of copper in slag, and once the oxide ore is worked out, and it comes to working up the sulphide ore, the oxidised ores, which in smelting would have most valuable in bringing up quickly and cheaply the grade of the copper in the matte, are no longer available. Again, by knowing the character of sulphide ores obtainable, one is in a better position to judge as to the most suitable plant, and to a great extent as to the permanency of the mine, and if the property will warrant an outlay on a large plant."

Smelting.

Nothing racks to pieces a furnace of this description (reverberatory) as cooling it down occasionally, owing to shortage of ore or fuel, or other similar causes, which are usually the want of foresight.[1]

Hence the wisdom of accumulating ore and fuel stocks before commencing smelting. Frequently this policy is neglected, the furnace being

[1] Peters' Principles of Copper Smelting, 1907, p. 508.

started before adequate proving and accumulation; and wo pecting of lower levels as frequently ceases whilst the furnac erected.

Furnace Temperatures, judged by appearance of fire and by fusion metals.—(H. M. Howe.)

Red—just visible	475 deg. Cent.,	887 deg. Fah
,, dull	550 ,,	1,022 ,,
,, cherry—dull	625 ,,	1,157 ,,
,, ,, full	1,165 ,,	2,129 ,,
,, light	850 ,,	1,562 ,,
Yellow—full	1,000 ,,	1,832 ,,
,, light	1,050 ,,	1,922 ,,
White	1,150 ,,	2,102 ,,

Melting Points of Metals.

Tin	232 deg. Cent.,	449·6 deg. Fal
Bismuth	260 ,,	500 ,,
Lead	326 ,,	618·8 ,,
Zinc	420 ,,	788 ,,
Antimony	632 ,,	1,169·6 ,,
Aluminium	655 ,,	1,211 ,,
Silver	960 ,,	1,760 ,,
Gold	1,065 ,,	1,949 ,,
Copper	1,080·5 ,,	1,976 ,,
Nickel	1,500 ,,	2,732 ,,
Platinum	1,780 ,,	3,236 ,,

Furnace Products.

"Blue metal"	Matte containing 60 to 70 per cent. of c
"White metal"	,, ,, 70 to 75 ,,
"Pimple metal"	,, ,, 80 to 85 ,,
"Black Copper"	Impure metallic copper; name derived tion of surface to dull black.
"Blister Copper"	Highest grade of unrefined metal, 96 cent. copper; name derived from ble ters," in which gases are retained as

Market Brands.

English	"Best Selected."
	"Tough Copper."
	"Tile" (brittle for castings).
	"G.M.B." (good merchantable brand).
	"Chili Bars"—blister, refined before use.
	"Electrolytic."
American	"Lake," from Lake Superior native copper
	"Electrolytic," by electrolysis of blister.
	"Standard" (not very good or bad).
	"Casting."

Smelting Deductions.

The old Swansea smelters' practice of demanding 21 cwt. to copper ore, perpetuated in some local Customs smelting plant gether inequitable in regard to the producer. So far as the aware, it is applied only to copper ores.

The unreasonableness of the exaction is more apparent w quantities are dealt with, especially when contingent costs are miner being mulct, not only in the product of his mine, but cash for mining and transport.

The following statement, based on actual facts, should make this clear:—

100 tons, less 109 cwt. = 95 tons.

	£	s.	d.	£	s.	d.
Value of deduction—5 tons—28 per cent. ore at £97 per ton of copper[1]				135	16	0
Cost of mining and dressing, at 10s. per ton				2	10	0
Carriage from mine to smelter				17.	11	3
				£155	17	3
Less smelting charge 5 tons of ore at £2 6s. 6d. per ton	11	12	6			
„ 1½ units deducted from 5 tons of 28 per cent. ore	7	5	5			
„ 1s. 9d. per unit „ „ „ „	12	5	0			
				31	2	11
				£124	14	4
Add 14s. allowance due on first-class ore				0	14	0
Net value of deduction against miner				£125	8	4

This deduction is over and above all legitimate treatment charges and all reasonable smelting-loss margins, 1½ per cent. being deducted from the metallic contents, as well as 1s. 9d. per unit from market value.

The margin for smelting loss is sufficiently high; indeed, slags approaching 1½ per cent. in copper would certainly be regarded as slovenly work, and inexcusable. This fact is thrown into strong relief by contemplation of what such a loss would mean to enterprises like the Great Cobar (Limited) and Lloyd Copper Company (Limited), with their 2 to 3 per cent. propositions.

"Unfortunately, it is the small producer, who has not sufficient ore in sight or capital to establish reduction works, who is thus penalised.

"How the deduction is viewed in England and America may be judged from the following extracts:—

"Nichol Brown and C. C. Turnbull write: 'For some reason or other the custom of delivering a baker's dozen in really thirteen, or the long hundred, really 120, which prevailed in many trades during mediæval times, but since in most cases been discontinued, lingered on and is still very common in the delivery of ore. In the case of copper ore, the recognised addition was at the rate of 1 in 20; so that for every ton bought, 21 cwt. were delivered, an advantage to the smelter of 5 per cent. in weight. Over and above this, an allowance for draftage was made of 3½ lb. in every 3 cwt. bought, which meant that 24½ lb. were allowed from a ton of 21 cwt. This was an advantage of another 1 per cent. to the smelter; so that, in all, he was allowed 6 per cent. increase in weight on every ton of ore delivered at his works.'[2]

"America has a simpler and more equitable method. Ore weighed and delivered in the usual way, no allowance being made on the actual beam and scale weight, a first allowance, 1·3 per cent. being made for loss in smelting, whether high or low grade ore."[3]

"Peters writes: 'The smelters' ton of 2,352 lb. is a local and, I believe, nearly obsolete measure of weight.'

"It may be found in some of the older mining and metallurgical literature of England, and is said to have originated from a very natural desire on the part of the smelters to protect themselves against losses when purchasing ore, by insisting that they should receive an extra hundredweight (112 lb.) for good measure with each ton (2,240 lb.) of ore.

[1] Value of copper at the time (1907). The proportions remain constant whatever the price of the metal.
[2] A Century of Copper, 1900, p. 70. [3] *Ibid.*, p. 72.

"This precaution, taken in conjunction with the 'dry assay' of copper (to be described later), would seem admirably adapted to safeguard them against metallurgical losses. The system has never flourished in the United States."[1]

"*Wet assay* of an ore, or product, means the actual amount of copper which it contains, as determined by accurate chemical methods, and expressed in percentage.

"The '*dry assay*' means (in the United States) the wet assay minus some agreed arbitrary deduction. This arbitrary deduction is a quantity established by local custom, and is often the number 1·3." (1·3 deduction from wet assay of ore; thus 13·6 — 1·3 = 12·3 per cent. of copper.)

"This arbitrary deduction from the true assay of copper ores is derived from the former practice at Swansea of making the copper assay of the parcels of ore offered for sale by means of a fire method, by which the ore was melted, and the resulting matte was refined, in a manner analogous to that pursued in the actual smelting process.

"This Cornish fire assay was supposed to yield results approximating those which were obtained in the actual smelting of the ore on a large scale, and thus to cover the actual metallurgical losses.

"It answered very well when executed by assayers thoroughly versed in this peculiar and difficult operation, and when the ores were tolerably uniform in composition; but is not suited to the broader commercial conditions, and is too susceptible to the personal equation.

"It would, no doubt, have been better in the United States to drop all attempts to provide for metallurgical losses in the original assay of the ore, and to add merely a sufficient sum to the smelting price to cover this point. But it is difficult to overthrow established customs, and a compromise was made by which the content in copper is determined by accurate chemical methods, and a deduction of 1·3 (or some understood amount) is made therefrom, the resulting figure being called the *dry assay*, and representing the amount of copper for which the miner is paid."[2]

Brief Description of the Great Cobar (Limited) Electrolytic Plant at Lithgow, and the Process of Refining.

(By G. H. Blakemore, General Manager.)

"The electrolytic plant consists of seven depositing dynamos, six of which are four-pole dynamos of 72 k.w., voltage being 60, and the amperage 1,200; the other dynamo being 15 k.w. capacity, voltage 25, and amperage 600. The six large dynamos are driven by six compound tandem steam engines, and one single-cylinder engine drives the small dynamo. In the engine-room are three Knowles' air-pumps, for forcing air through the electrolyte in the depositing tanks, and for providing air to the air-lifts, which elevate the electrolyte to the distributing tanks above the depositing tanks. The depositing tanks are at present arranged so that five of the large dynamos do the work of deposition, leaving one standing idle.

"Two dynamos are working 144 tanks each, whilst the other three dynamos each have 128 depositing tanks.

[1] Principles of Copper Smelting, 1907, p. 556. [2] *Ibid.*, pp. 558–559.

"The small dynamo of 15 k.w. capacity is used for removing excess copper in the electrolyte and for providing electricity for the Doré parting plant.

"The plan herewith fully explains the system of the arrangement of the tanks:—

"The tanks are made from Oregon pine. The boards are 2 inches thick, and dressed on both sides; they are lined with 6 lb. lead, the lead being carried over the top edges of the tanks, so as to protect the wood from the acid liquor. To protect the lead lining from injury, a lining of 1 inch redwood is fitted. All woodwork about the tanks is boiled in paraffine wax of a melting point of 140° F. for half an hour. No pitch or bitumen is used in the construction of the tanks. The electrolyte flows from one tank to the next below it through leaden pipes, which are burnt on to the lead lining, and pass through the wooden end wall of the tank. On this lead pipe is fitted a short piece of rubber pipe carrying a glass pipe, 5 or 6 inches long, which is long enough to convey the electrolyte into the next tank. The tanks of each dynamo are arranged in four long rows. Each row has three terraces, and each terrace a separate feed of electrolyte; and the tanks in each terrace are stepped 3 inches below one another, so as to ensure a proper circulation of the electrolyte from tank to tank. At the end of a terrace of tanks the electrolyte escapes to the collecting sump, from where it is elevated by an air-jet into the storage tanks, and thence into circulation again.

"By providing three separate supplies of electrolyte to every row, in the manner described, a fairly even temperature is maintained in the electrolyte.

"The electrolyte is warmed to 120° to 125° F. by means of steam passing through hard lead coils. The effect of temperature on the electrolyte is to make the cathodes grow smoothly, and it also obviates a risk of short-circuiting to which rough cathodes are liable, and it further reduces the resistance of the electrolyte, enabling more copper to be produced for the same horse-power.

"The average composition of the electrolyte is about 13 per cent. of bluestone, 13 per cent. free H_2SO_4; specific gravity, 1·16 to 1·18 at the inlet. In the course of the passage of the electrolyte through a series of tanks, it increases in bluestone.

"For instance, the analysis of the inlet liquor will be, say, 12·8 per cent. free acid, 13·8 per cent. bluestone; and the outlet liquor from this will assay 12·5 per cent. free acid, 14 per cent. bluestone.

"The electrolyte which passes through the tanks of the small dynamo by which copper is being removed from the electrolyte, and where insoluble anodes are used, will assay as follows:—

"Inlet, 12·4 per cent. free acid, 13·6 per cent. bluestone; outlet, 15 per cent. free acid, 8·4 per cent. bluestone. These figures are not at all fixed. There are constant variations from day to day in the composition of the electrolyte; but the analyses given are an index to the character of the electrolyte from the depositing tank and from the insoluble anode tank. If the excess copper were not removed by electrolysis, then it would have to be taken out by crystallisation, otherwise the amount of bluestone would reach such a point in the electrolyte that it would commence to crystallise out in the tanks, and at once bring about short-circuit of a dangerous character. Each tank is separately aerated by a small jet of air working at the bottom of a leaden pipe, which hangs in the liquor;

the air-jet forces up electrolyte from the bottom of the tank, and aerates the liquor, while at the same time it brings up from the bottom of the tank the denser liquor which is constantly being formed by the process of electrolysis. This creates a circulation of the electrolyte apart from the flow of the electrolyte from one tank to the other. If there were no air-jet working in each tank, the tendency of the liquor is to divide itself into two layers, the lower layer rich in bluestone, the top one in free H_2SO_4. The consequences of this are: first, crystallisation of bluestone at the bottom of the tank, and second, cutting through of the anodes and cathodes at the junction line of the two layers of liquor. Air agitation tends also to oxidise some of the impurities which otherwise accumulate in the electrolyte.

"If the temperature of the electrolyte is 120° F. on entering the first tank of a terrace of tanks, it will probably have fallen to 90° by the time it leaves the tenth tank of the terrace, owing to the cooling effect of the atmosphere. If the liquor could be maintained at 120° in every tank better working results would be obtained. With an electrolyte containing 12 to 14 per cent. of free acid, a temperature of 90° to 120° is imperative—preferably 120° if it can be obtained—because with a lower temperature an electrolyte so high in acid as 12 per cent. or 14 per cent. causes the copper to be deposited on the cathodes in fine wires instead of a level growth; and as these wires grow fast, they cause in an hour or two numberless short-circuits in every tank. It is advisable to work with a high acid percentage, first, to reduce the resistance of the electrolyte, and secondly, because the quality of the copper is superior to that deposited in an electrolyte low in acid.

"The amperage per square foot of cathode surface is about 14; the voltage per tank is about 0·3 volts. There are nine anodes and nine cathodes per tank; the square feet of area on a cathode is about 10 feet, and the amperage of the dynamo is from 1,200 to 1,300 ampères. In cold weather the dynamos can be run up to 1,300—perhaps 1,400—ampères without danger, if the resistance or voltage is low enough to allow of it being done.

"The copper treated in the electrolytic plant is first refined before it is cast into anodes. The anodes assay about 99·4 per cent. copper before being electrolytically treated; the silver contents are from 16 to 20 oz., and the gold from 2 to 4 oz. Each anode weighs approximately 200 lb. These are put into the depositing tanks as required. The whole of the anodes are not removed in one lot, as is done in many American refineries. An anode generally cuts out in three weeks' time. The remains of it is then taken out, washed from gold and silver mud, and sent to the furnace to be remelted up into anodes; but as this copper has once been charged to the electrolytic plant (as a book-keeping point), these anodes are now described as 'scrap anodes,' to distinguish them from the anodes made direct from the matte. The weight of scrap anodes made is about 8 per cent. of the weight of the original anodes put into the electrolytic tanks.

"The cathodes are removed in regular numbers every day from each set of tanks on a dynamo, but not in regular numbers from every tank. They are only removed when they have grown to such a size as to render short-circuiting possible. The removal of the cathodes is so arranged that all the cathodes are taken out of every dynamo every fourteen days. By working the tanks on this system—that is, leaving in the anodes twenty-one days and the cathodes fourteen days—the short-circuits in the tanks are very materially reduced.

Depositing Tanks, Great Cobar (Limited) Electrolytic Plant, Lithgow.

'The cathodes are melted up in weights of 10 to 16 tons into ingots, ring the brand 'E.L.C., Aust.' The conductivity of this electrolytic per, measured by Dr. Matthiessen's standard, very often runs over per cent., and never lower than 99½ per cent. The gold contents of 'E.L.C.' copper rarely exceeds 12 grains, and the silver about 9 dwt. ton, and the copper contents 99·98 per cent. Each day's charge is rately tested for its conductivity and the gold and silver contents.

The starting-sheets on which the cathode copper is deposited are grown the works. First of all, some copper is rolled into sheets about one-th of an inch thick; these are cut to the size required, which is about ch wider and 3 inches longer than the starting-sheet will be when wn. These rolled-copper sheets are dipped in boiling tallow, allowed rain and cool, and are then dusted with ground graphite. The om edge and two side edges are then dipped in molten tallow once e, to form an insulated rim on the rolled plate. These prepared ts are then hung in the depositing tanks, and copper is deposited on graphite surface from the ordinary auriferous anode; but where the es have been dipped in tallow no copper deposits. The rolled sheets left in the depositing tanks from two to four days. They are then hdrawn, and the two thin sheets of copper which have deposited, one h side of the rolled plate, are then stripped off by boys. The rolled ets are once more dipped in boiling tallow, dusted with graphite, &c., d put back into the depositing tanks to grow more starting-sheets, ilst the very thin starting-sheets are hung in other depositing tanks as athode, and in two weeks' time are heavy enough to send to the cathode rnace to melt up into 'E.L.C.' copper ingots.

"The dynamo which is removing the excess copper from the electrolyte s but twelve tanks on it. While the resistance on the depositing tanks rking with soluble copper anodes is but 0·30 volts, in these tanks, using insoluble lead anode made from 8 lb. lead, the resistance sometimes aches 2 volts per tank. The copper removed in this way is about 60 ns per annum, being deposited very much more slowly than is the case the tanks using soluble copper anodes, and the face of the cathode roduced is quite polished. This copper is very tough, and is particularly od copper.

"The mud which accumulates in the ordinary depositing tanks, where e anodes are being treated, contains copper, selenium, tellurium, iron, old, silver, &c. It is taken out of the depositing tanks at regular ervals and sieved through copper sieves, to remove the large pieces of pper that have fallen off the anodes. It is then dried, afterwards heated redness, to burn off any grease and to alter the graphite. This simple int of heating the mud redhot enables all the copper to be dissolved t by the sulphuric acid of 1·830 with which it is next boiled. The iled mud is then fused with a little sand and carbonate of soda to a ré bullion, which is cast into 7 or 8 lb. anodes, and refined in a all Moebius plant for the separation of gold and silver. The gold wder, which is black, is warmed with nitric acid to take out as much lver as possible, and then melted into bars, which are about 980 fine, d sold to the Mint. The silver is melted into 500-oz. bars of 996 to 999 e, and shipped.

"The composition of the electrolyte in the Moebius tank is as follows:—

"1·7 per cent. copper; 6 to 9 oz. silver per gallon; free nitric, 0·11 per nt. to 3 per cent.; specific gravity, 1·120 to 1·135.

"The flow of the electrolyte through the depositing tanks is about 1½ gallon per minute.

"The starting-sheets were at one time grown in non-circulating tanks—that is, each tank was separately supplied with electrolyte. The trouble with this arrangement was that each tank was a separate electrolytic refinery, and the quality of the skins or starting-sheets was very irregular and uncertain. A starting-sheet needs to be tough; but in the old system it was not at all uncommon, out of thirty-six tanks growing skins or starting-sheets on the still-liquid principle, to not get more than 5 per cent. of the total skins produced fit for use as cathodes. As some hundreds of skins are required daily, this brought about a serious shortage of the necessary starting-sheets or skins, and had to be remedied, or else a dynamo or more would have to stop for want of them. Using some colloidal substance like gum was the usual remedy; it acted sometimes, and at others failed. A great deal of labour was entailed by the system, and a considerable amount of dissatisfaction always resulted from it. Now the skins are grown in the ordinary circulating liquor, and the usable skins or starting-skins represent 95 per cent. of the total produced.

"The depositing tanks rest on six glass blocks. The copper bars carrying the current are made on the works, and give about 2¼ square inches in section for a current up to 1,400 ampères. The copper leads are insulated from the tanks, and the tanks are insulated from the earth and from each other. The anodes are made with one arm long enough to rest on the positive lead; the other arm is shorter, and rests on a glass block standing on the wall of the tank.

"The efficiency of the depositing tank is now over 90 per cent. of the power indicated on the volt and ammeters. The capacity of the five sets of tanks is about 140 tons of electrolytic copper per week.

"Scrap-holders were at one time used in the depositing tanks to work up the scrap anodes in the course of electrolysis. They were made of lead in basket form, pierced with holes, and rested by means of copper pipes on the positive lead. The electrolyte circulated through them. Experiment showed it took two or three times as long to redeposit the copper from the scrap holders, and, counting interest and the cost of cutting up the scrap and resistance losses, it was cheaper and more expeditious to remelt the scrap and recast the copper into anodes.

"The conductivity apparatus used is that made by Elliott Brothers, of the Century Works, Lewisham, London.

"It consists of a Wheatstone bridge, with fixed ratio arms and a copper coil standard equivalent to a pure annealed copper wire 100 inches long and weighing 100 grains of 100 per cent. conductivity according to Matthiessen's standard—that is, ·1516 British Association ohms at 60° F. The conductivity is arrived at by the formula—

$$\frac{L^2}{W}$$

where "L" is length in inches, and "W" is weight of the wire in grains; or,

$$\frac{0{\cdot}1516 \times L^2}{W{\cdot}R}$$

0·1516 = Resistance of 100 inches of pure annealed copper wire at 60° F.
L = Length of test in inches.
W = Weight in grains.
R = Resistance in B.A. ohms at 60° F.

"R. is adjusted until it is equal to standard of pure annealed copper wire by altering its length until the galvonometer in the apparatus shows no deflection.

"The annealing of the sample of wire is done by covering it with sawdust on an iron plate, which is put over a fire until the sawdust takes fire, when it is allowed to smoulder away. When cool, the wire is cleaned. It is drawn through about a 23 B.W.G.-size hole."

Mineral Associates of Copper Ores injuriously affecting Smelting Operations or the Quality of Copper.

The presence of sulphides of zinc and lead, especially the former, add greatly to the troubles of the smelter, owing to their tendency to choke the furnace by forming a crust in the throat, necessitating frequent "barring-down." The effect of zinc sulphide (blende) in copper-smelting is stated by Sticht, in "Peters' Modern Copper Smelting,"[1] to be that part only is oxidised, and enters the slag to that extent; it is also deposited in the furnace throat. "A greater portion of it in its unaltered chemical state is held in solution in the slag chemically or merely mechanically. Another portion enters the matte, and the balance escapes as fumes, part of which is sublimated and regenerated in the upper and cooler regions of the furnace-shaft. Its immediate action is to vitiate the separation of the matte and slag by decreasing the specific gravity of the former."

Another authority quoted—Herbert Lang—in the same work[2] refers to the influence of zinc-blende on smelting operations, as follows:—"Zinc enters the slag as oxide and the matte as sulphide, rendering the former viscid, the latter light, and by injuring the separation diminishes very seriously the saving of the precious metals. By volatilisation as metal or oxide it causes heavy loss of silver."

At Lake George Mines, Captain's Flat, zinc entered the slag to the extent of 14 or 15 per cent., and into the matte from 9 to 10 per cent.

Dr. Schnabel states that large quantities of zinc form with the slag and a portion of the matte—a porous mass, called *skumnas* (scum or foam) in Sweden—from which the copper can only be extracted with great difficulty. He advises the conversion of zinc sulphide as far as possible into oxide during roasting, carbonaceous matter being mixed with the ore during calcination to decompose any basic sulphate formed during the operation.[3]

The principal copper mines of the State, so far, have been fortunately free from serious zinc troubles. A thin skin of zinc-blende occasionally coats either wall of the Cobar lode; but the quantity is so slight compared with the mass of the ore that it can be disregarded. At Peelwood it was unpleasantly prominent in the lowest workings; at Apsley, Wiseman's Creek, and Captain's Flat mines it is intimately associated with the copper sulphide.

The recently-discovered Ettrema lodes in the Nowra division, and the Just-in-Time in the Casino, consist principally of zinc sulphide, associated in parts with chalcopyrite, and in the first-mentioned with mispickel also.

In both the admixture of the chalcopyrite with the zinc-blende is so intimate as to defy classification by hand, whilst equal densities prevent gravity separation, though the latter would, to a certain extent, be effective in the case of the heavier mispickel.

---

[1] 7th edition, p. 424. [2] *Op. cit.*, 1896, p. 79.
[3] Handbook of Metallurgy. Trans. by H. Louis. Vol. I, p. 89.

To render the chalcopyrite marketable or smeltable, magnetic separation would be necessary.

The amount of zinc that may be introduced into the furnaces depends largely upon surrounding conditions; but it is noteworthy that in Customs Smelting Works any excess of zinc over 10 per cent. (in some instances 5 per cent,) carries a deduction of 1s. per unit. To quote the tariff of the Walleroo Smelting Company of South Australia: "In no case will any zinc be paid for, and for all zinc over 10 per cent a deduction will be made at the rate of 1s. per unit." The rates quoted for copper ores in the tariff issued by the Great Cobar, Limited, in connection with its Lithgow Refining Works, are stated to be for copper ores free from impurities. The smelting charges for ores containing arsenic, antimony, tin, zinc, bismuth, &c., are higher than the ordinary, and vary proportionately with the nature and quantity of the impurities present. Whilst smelting companies reserve the right of rejection altogether.

The effect of zinc entering the matte as sulphide, in copper-smelting, must be to seriously diminish realisation values of such material, as its deleterious effects manifest themselves in refining.

The effect of metallic zinc on copper is variously stated by the following authorities:—

Bruno Kerl states[1] that "0·6 per cent. of zinc produces red-shortness, to a degree cold-shortness, whilst many alloys of copper with zinc (malleable brass) are malleable between certain limits of temperature."

C. Schnabel[2] states "that zinc alloys itself with copper and diminishes the malleability of the metal when hot. A copper zinc alloy, with more than 20 per cent. of zinc, is at all temperatures less malleable than copper."[3]

C. Stölzel[4] states that copper containing 0·6 per cent. of zinc and 0·25 per cent. of tin causes the metal when beaten out under the hammer to show fractured (rugged) edges.

E. D. Peters states that zinc forms an alloy with copper in every proportion, and slightly lowers its ductility at high temperatures, but until it reaches at least 18 per cent., the tenacity of the alloy at ordinary temperatures does not seem to be lessened.[5]

Bismuth, however, is the most injurious impurity in copper, as very small quantities render the copper unworkable. Dr. Peters states that "it clings to copper with much tenacity, and affects its properties in a most surprising manner."[6] Hampe, quoted by both Dr. Peters and Dr. C. Schnabel, of Clausthal,[7] states that copper containing as little as 0·02 per cent. of bismuth is red-short, and 0·05 cold-short, the term "red-short" signifying brittleness when red-hot, and "cold-short" brittleness when cold. The same authority also states that with 0·1 per cent. of bismuth copper crumbles under the hammer at red heat, and that the tendency to cold-shortness is somewhat counteracted by the presence of a certain proportion of antimony. Schnabel and Louis state[8] that oxide of bismuth, which is mechanically taken up by copper, affects it like the metal, but in a less degree as far as cold-shortness is concerned, its effect being further diminished if the bismuth oxide is combined with cuprous oxide.

Bismuth is present in the Great Cobar lode to a small extent. In a series of analyses by Mr. W. A. Dixon, F.C.S., F.I.C., of the oxidised ores worked in 1878, bismuth was found to be present in proportions ranging from 0·21

[1] Grundriss der Metallhüttenkunde, 1881, p. 220. [2] Handbuch der Metallhüttenkunde, 1894. Vol. I, p. 3.
[3] *Op. cit.* Trans. by H. Louis, 1898, I, p. 3. [4] Die Metallurgie, Vol. I, 618, 1886.
[5] Mod. Copper Smelting, 9th ed., 1898, p. 2. [6] *Ibid.*, p. 2.
[7] *Op. cit.* Trans. by H. Louis, 1898, I, p. 3. [8] *Ibid.*, p. 4.

to 2·58 per cent.[1] The same authority analysed the copper from these ores in 1879,[2] which he described as somewhat difficult to refine, and not coming to the proper "tough pitch," owing to the presence of bismuth. Following are the results obtained :—

Copper	99·346	
Bismuth	·419	
Iron	·083	
Lead	·086	
Silver	·026	= 8 oz. per ton.
Antimony	·029	
Traces of arsenic, nickel, cobalt, gold, and loss	·011	
	100·000	

As the Cobar copper is now electrolytically refined, all impurities are practically eliminated, as will be seen in the analysis of the metal under the heading of Great Cobar.

Arsenic, usually in the form of mispickel, is one of the commonest and most objectionable associates of copper ores. Arsenic, and also antimony, though volatile, readily combine with the metallic bases, forming combinations difficult to split up. This affinity necessitates keeping the metal in the copper refinery at a high temperature for an excessive period to allow for volatilisation, a process involving great destruction to the furnace linings. The removal of arsenic is assisted by the addition of pyrites during calcination, which volatilises a portion as sulphide of arsenic.[3] At Sunny Corner realgar and orpiment (sulphides of arsenic), by their bright red and yellow colours, sometimes characterised the roasted ore.

Dr. Peters states that arsenic has a greater affinity for metallic copper than for matte; hence, if the smelting charge be so regulated that there shall be an insufficiency of sulphur to combine with the copper, the product of a quick fusion will be a considerable quantity of rich matte comparatively free from arsenic and a much smaller quantity of very impure metallic copper known as "metallic bottoms."[4]

The effect of arsenic on copper was formerly regarded as highly injurious, even $\frac{1}{10}$ of arsenic producing both red and cold shortness, but Schnabel[5] quotes Hampe[6] to the effect that 0·5 per cent. of arsenic produces no bad effects; only when the proportion rose to 1 per cent. could a slight degree of red-shortness, but no cold-shortness, be detected. According to the same authority, copper with 0·8 per cent. of arsenic could be drawn into the very finest wire, and small percentages of arsenic (0·216 per cent.) even increase the tenacity of copper.[7] According to Stahl, a small amount of arsenic prevents copper from becoming porous.

Professor W. C. Roberts-Austen[8] states that arsenic materially increases the electrical resistance of copper; on the other hand, it increases its durability when used in locomotive fire-boxes.

Tin, according to Dr. Peters, alloys with copper in all proportions and begins to injure its ductility when present in quantities of 1 per cent.

Nickel, frequent in commercial copper, up to 0·3 per cent. seems to produce no injurious results.

Dr. Peters states that iron when present in the usual minute proportion probably has no appreciable effect on the useful qualities of copper—except possibly its electrical conductivity.

---

[1] Ann. Rept. Dept. Mines for 1878, pp. 38–41. [2] *Ibid.*, 1879, p. 20.
[3] Handbook of Metallurgy, I, p. 25, 1894. [4] Mod. Copper Smelting, 5th ed., 1892, p. 339.
[5] *Op. cit.*, 1898, I. p. 4.
[6] Chemiker-Ztg., 1892, 16, No. 42. [7] Inaugural Dissertation. Turbingen, 1886.
[8] An Introduction to the Study of Metallurgy, 1894, p. 11.

The action of lead on copper is stated by Schnabel, on the authority of Hampe's recent experiments, to be that 0·15 per cent. does not affect the malleability of copper in any way; with 0·3 per cent. of lead it becomes slightly red-short, and with 0·4 per cent. slightly cold-short. With 1 per cent. of lead copper is unworkable.

Dr. Peters states while lead is a useful addition to copper to be employed for certain mechanical purposes, and assisting in procuring solid castings, it has a decidedly injurious effect if present in too large quantities. One-third of 1 per cent. is sufficient to make the metal both red-short and cold-short; while 0·75 per cent. will ruin copper for any ordinary purpose.[1]

Antimony in small quantity, according to the same authority, does not affect the good qualities of copper. With 0·529 per cent. copper can be drawn into the finest wire equally as well as pure copper. One per cent. of antimony, however, renders copper extremely red-short. It likewise impairs its electrical conductivity.

Hampe's latest experiments[2] show that silicon (the metallic base of quartz) hardens copper without impairing its toughness or its malleability when less than 3 per cent. is present. With 6 per cent. of silicon copper becomes brittle; with 8 per cent. it is readily pulverised, and with 11·7 per cent. it is as brittle as glass. The electrical conductivity of copper is impaired by small proportions (0·52 per cent.) of silicon.

Sulphur in quantities of 0·25 per cent. lowers the malleability of copper. 0·5 per cent. produces cold-shortness, though such copper is not red short.[3]

Phosphorus in small quantities seems to produce no injurious effect. At 0·4 per cent. red-shortness is developed (Peters).[4]

The process of copper-refining depends upon the rapid oxidation of the impurities usually associated with copper, and their greater affinity for oxygen; the less oxidisable impurities, however, by the protracted "roast' required for their elimination cause great destruction to the furnace hearths. According to Dr. Peters[5] a considerable part of the injurious substances can be extracted by exposing the pigs of matte to a slow oxidising fusion, the operation being interrupted as soon as a certain amount of metallic copper is formed when the furnace is tapped; the small quantity of copper thus produced contains not only the greater part of such impurities as arsenic, antimony, tellurium, tin, &c., but also the gold-contents. The great affinity of gold for metallic copper and its unoxidisability renders it possible to concentrate it, and, owing to the latter quality it would be theoretically possible to oxidise and slag off the copper, leaving the precious metal behind.

Concentration.

In connection with the lower levels of copper mines in which copper and iron sulphides are leanly distributed through the lodestuff, a prevalent hope is indulged by prospectors that increasing depth will reveal increasing solidity or concentration of these minerals. Certainly instances are not wanting of such a desideratum, but their rarity and transiency but emphasise the necessity for resolutely facing the problem of concentration, for the hope of richer ore-bodies with depth vanishes in the light of experience. Below the water-level gradual depreciation is invariably associated with depth.

[1] Mod. Copper Smelting, 9th ed. 1898, p. 2. (Schnabel and Louis, I, 1898, p. 5.)
[2] Chemiker-Ztg., 1892, 16, No. 42.
[3] Peters, *ibid.*
[4] *Ibid.*
[5] Mod. Copper Smelting, 5th ed., 1892, p. 378.

Concentration of lean ores is a question looming large in the future of copper-mining in New South Wales, as the grade of the available ores in the principal producers is low and falling, necessitating increasing outputs to maintain returns. In fact, an optimistic view of the industry is not possible, though discovery may at any time change its aspect. The rich ores of the important mines have been exhausted, and no later discoveries of equal magnitude and richness stand ready for development. Great Cobar and Nymagee, thanks to the kindly nature of their ore, are amenable to furnace concentration. The absence of permanent water supply in the far western copper-fields increases the difficulties to be overcome, which in themselves are sufficient to tax the ingenuity and skill of the most experienced manipulators.

Concentration on a primitive scale was adopted at a few western mines. The "seconds" from the jigs consist chiefly of fragments of earthy and silicious carbonates in slate and fine-grained sandstone, the difference between the gravity of this class of ore and of the waste being so slight as to defy mechanical separation beyond a certain unsatisfactory point. In connection with the "seconds" at Girilambone, the Writer, in 1898, gave some attention to the possibility of mechanically separating the particles after careful sizing, but the difference between the specific gravities of even the richest ore-particles (azurite) and the waste was so slight—0·73—as to render mechanical separation impossible. The green carbonate particles, which are also conspicuous in the "seconds," need only a glance to reveal the fact that their copper contents are more apparent than real; the green particles are mostly quartz stained with malachite, the specific gravity of which is about 2·74, and that of the waste 2·72. Even the translucent crystals of azurite (blue carbonate) contain but 31 per cent. of copper instead of the 53·2 per cent. of the pure mineral.

Though no tests were made with the earthy carbonates of the New Mount Hope and Great Central mines, it is probable that to a large extent the same difficulties will be encountered. At Burraga, since the advent of the Lloyd Company, the great bulk of the ore is concentrated. (See under Burraga.)

These considerations open up the question of the possibility of a leaching process with sulphuric acid being adopted, the acid being manufactured in chambers on the spot from the roasting of lump sulphides from lower levels. Unfortunately, in some of the mines mentioned, so far as the pyritic zone has been pierced, the sulphides of both iron and copper are leanly distributed through the matrix, and therefore unsuitable for the purpose without previous concentration. Given sufficient sulphides suitable for producing sulphuric acid, the process is worthy of serious consideration, as a similar means of extraction has been adopted for lean oxidised ores by the Arizona Copper Company, at Clifton, Arizona, U.S.[1] The Girilambone tailings were subsequently profitably leached. (See Girilambone.)

Carbonates and oxides of copper can be dissolved by hydrochloric and sulphuric acids, ferrous chloride, ammoniacal compounds, hyposulphate of soda, and ferrous sulphate; but only the first three have been practically employed. The two first act very energetically.

At the World's Columbian Exhibition, Chicago, 1893, the Writer had the "Douglas Central Flue Revolving Cylinder Furnace" explained by means of a model by the inventor, Mr. James Douglas, President of the Copper Queen Mine, Arizona. In this furnace, which is used in connection with

[1] Mineral Industry, 1898, VI, p. 230, *per* J. Douglas.

above-mentioned process, instead of the heated gases from the fireplace coming in contact with the ore charge, they are conveyed through the furnace by means of a central flue, and the charge is heated therefrom by radiation. The cylinder is of iron, lined internally with firebrick; the central flue is constructed of tiles kept in position by four tiles locked into the lining, these tiles extending the whole length of the cylinder, dividing the ore-chamber into four compartments. The fire required to ignite the charge is contained in a movable furnace on wheels, which can be connected or disconnected at will from the cylinder. The air-draft into the ore compartments is regulated by means of an adjustable register, which closes the front or discharge end of the cylinder.

The internal flue is the main difference between the Douglas and Brückner revolving cylindrical furnace, and perhaps the only one so far as practical working is concerned.

For sulphuric acid manufacture the Douglas furnace offers exceptional advantages, inasmuch as it delivers the gases from the ore uncontaminated with any impurities from the fuel used in firing.

The divisions of the compartments are pierced at intervals with slots or openings, so that the ore can fall from one to the other, and thus increase the agitation.

The capacity of the furnace is about 6 tons per diem, when the ore is liable to sinter, owing to presence of lead or high percentage of copper; and up to 12 tons of pure pyrites. Owing to the inaccessible nature of the ore-chambers, ore liable to sinter at a low heat is unsuitable for treatment.

The speed of revolution varies from one revolution in three minutes to one in ten minutes.

A dust-chamber is a necessary adjunct of this furnace.

The vital question in concentration, however, refers almost solely to the sulphides which constitute the permanent sources of supplies, the oxidised ores at best being but superficial. The estimated copper contents of the sulphides under consideration range from 2 to 4 per cent. in gangues of slate, quartzite, and quartz; in the descriptive records of the individual mines concerned full particulars are given of the methods of concentration adopted. It is noticeable in the slate and sandstone or quartzite country, wherein the lodes are mostly segregations or replacements, that where the ore is more concentrated quartz is a more or less abundant associate. Usually, however, the sulphides are sparingly distributed through the matrix. The most advantageous method of dealing with the ore as it comes to the surface is to carefully select all lumps capable of being dressed by hand to smelting grade, and to deal with these separately by breaking and picking. In siliceous lodes, such as Girilambone, Mount Hope, and Burraga, too much care cannot be given to this section, for, to quote a high authority,[1] "When ores are siliceous a mere rejection of such pieces of barren quartz or wall rock as have accidentally got among the ore, or first become visible on breaking up the large masses, may have a most beneficial influence on the subsequent fusion. Where the expense of treatment is high, and work is conducted on a large scale, the profits resulting from raising the average contents of the ore even a single per cent. is hardly credible, even aside from the increased fusibility due to the decreased proportion of the silica."

[1] Dr. E. Peters, junr.—Modern Copper Smelting, 5th ed., 1892, p. 54.

The second step in the process is the rejection of the waste mixed with the ore from the working stopes; after screening, the larger fragments could be broken and sorted by cheap boy or elderly labour; by these means a good proportion of actual waste could be at once discarded. In some instances it is unquestionable that a good deal of such material goes direct to the jigs and adversely affects the results proportionately with the quantity added, both as regards efficiency and capacity. There can be little doubt that the benefits of sorting will outweigh the cost, both directly and indirectly.

The sorted lodestuff, with the screenings and fines from the dressing of the "firsts," should then pass through the breakers to the rolls; the mesh of the trommel screens between the latter and the jigs should be regulated by the character of the ore, a second crushing being preferable to fine crushing in the first instance. Attempting to free all the scattered ore particles at the first crushing would, in the absence of an abundant water supply, increase, instead of reduce, the present loss, owing to the great tendency of some of the gangues to slime. If the seconds from the jigs offer sufficient inducement, then finer crushing and further jigging could follow, though better results would be obtained with buddles and vanners. Both the latter are in extensive use in Montana, United States, where fine crushing and concentration are carried out on a large scale. The Anaconda Company are understood to have adopted buddles wholly for the fines to the exclusion of vanners.

At the point of treatment indicated, it will be a matter for consideration, depending on the assay values of the seconds, whether it will not be more advantageous to waste a proportion of the ore than attempt to save it. This question has considerable weight where low-grade ore is abundant and fluxes scarce.

Theoretically, clean extraction, either mechanical or metallurgical, indicates good work, but the term "good work" is purely relative when commercially considered. However desirable it may appear to obtain clean tailings or slags, the cost of securing them may easily outweigh the advantage.

The form of jig most suitable for any class of ore must be decided entirely by practical test and observation. The Cornish, Handcock, and May Bros. machines are each represented in the State.

Concentration is naturally productive of an accumulation of "fines," which is unsuitable for furnace charging; metallurgists suggest several remedial methods of dealing with it, apart from covering or blinding roast heaps and stalls, if such be in operation, viz., mixing into balls with milk of lime and hydraulic cement, or with clay, or moulding into bricks in an ordinary pug-mill, as the finest material possesses inherent cohesiveness. The use of clay as a binding medium should be avoided, if possible, on account of the introduction of useless and refractory material into the furnace. Silicate of soda (water-glass) has also been tried, but its cost precludes extensive use.

The specific gravities and hardnesses of frequently-associated sulphides are as follow :—

	Specific gravity.	Hardness.
Chalcopyrite	4·1–4·3	3·5–4
Pyrite	4·8–5·2	6–6·5
Pyrrhotite	4·4–4·7	3·5–4·5
Blende	3·9–4·2	3·5–4
Mispickel	6·0–6·4	5·5–6

The Washoe Plant of the Anaconda Copper-Mining Company.

Extracts from description by L. S. Austin, Houghton, Mich.

Concentration.

"The concentrating plant has a side-hill or terrace location, and adjoins the high-level track and storage bins, from which it draws its supply of ore. It consists of two mills, with a power-house between. Each mill has four sections, so there are eight in all. The capacity of a section may be given at 1,000 tons per day of 24 hours, and it may be estimated that 7·5 sections are constantly running, or that one section is down half of the time for repairs or adjustments. This would give a daily capacity, when the ore supply is sufficient, of 7,500 tons. A maximum output of 8,250 tons, however, has been attained. There is a large power and boiler plant between the two halves of the concentrator building, but much of this installation will be thrown out of use when the company obtains its power by electric installation from the plant of Montana Water E. P. Company, 22 miles distant, and the Missouri River Power Company, near Helena, 75 miles away.

"To supply the eight units, already specified, there are eight storage bins, each of 1,200 tons capacity. These bins have flat bottoms, the ore forming its own slope in them, so that the wear of the bin is slight.

"The following outline describes the flow of the ore through one section of the mill:—

(1.) Hopper-bottomed cars of 50 tons capacity to (2).
(2.) Storage or supply bin of 1,200 tons to (3).
(3.) Shaking feed-trough, having a screen-bottom of 1·25-inch round holes, oversize to (4), undersize to (7).
(4.) Coarse crusher, 12 inches by 24 inches, to (5).
(5.) Two trommels, each 36 inches in diameter by 5 feet long, and having 1·25-inch round holes, oversize to (6), undersize to (7).
(6.) Two crushers, each 5 by 15 inches, to (7).
(7.) Two elevators, having 15-inch belt, buckets 7 by 14 inches, speed per minute, 450 inches, to (8).
(8.) Two trommels, 36 inches in diameter by 6 feet long and having $\frac{7}{8}$-inch round holes, oversize to (9), undersize to (13).
(9.) Two two-compartment Harz jigs on 1·25-inch feed, concentrates to (12), middlings to (16), through (15), (8), and (13), hutch product to (14).
(10.) Four Harz jigs.
(11.) One coarse roll, 42 by 15 inches, 1,147 feet peripheral speed, to (13), through (8).
(12.) Coarse concentrates bin; concentrates to blast-furnace in hopper-bottom cars.
(13.) Two 7-mm. trommels, 36 inches in diameter by 8 feet long, oversize to (10), undersize to (16).
(14.) Twelve two-compartment Evans' jigs on 7-mm. feed, size of screen 24 by 41 inches, concentrates to (32), middlings to (35), hutch product to (32).
(15.) One fine roll, 42 by 15 inches, 1,147 feet peripheral speed, to (16), through (8) and (13).
(16.) Four 5-mm. trommels, 36 inches in diameter by 6 feet long, making twenty revolutions per minute, oversize to (14), undersize to (18).

[1] Transactions Am. Institute Mining Engineers, 1907, XXXVII, pp. 431–485.

(17.) Twelve two-compartment Evans' jigs, 5-mm. feed, concentrates to (32), middlings to (35).
(18.) Four 2·5-mm. trommels, 36 inches in diameter by 7·5 feet long, oversize to (17), undersize to (19).
(19.) Twelve 2·5-mm. Evans' jigs, concentrates to (32), middlings to (35).
(20.) One middlings-roll, 42 by 15 inches, to (21).
(21.) Four 1·5 by 12-mm. diagonal-slot trommels, 36 inches in diameter by 6 feet long, oversize to (20), undersize to (22).
(22.) Four three-spigot separators, spigot-product to (23), overflow to (26).
(23.) Eighteen three-compartment middling jigs, 1·5-mm. feed, concentrates to (32), middlings to (24), tailings to dump.
(24.) Three 6-feet Huntington mills, fifty-three revolutions per minute, 62 tons capacity, grinding to pass a 1-by 12-mm. slot-screen, to (25).
(25.) Eighteen three-compartment Huntington mill finishing jigs, 1mm. feed, concentrates to (32), middlings to (24), tailings to dump.
(26.) Sixteen settling-tanks, 5 feet wide by 4 feet deep by 18 feet long, spigot-product to (27), overflow to (28).
(27.) Eighteen Wilfley tables, concentrates to (32), tailings to dump, slime to (29), middlings to (34).
(28.) Slime ponds situated below the reduction works.
(29.) One large tank, spigot-product to one Wilfley table (30), overflow to (28).
(30.) One Wilfley table, concentrates to (32), tailings to dump.
(31.) Elevator to (32).
(32.) Settling-tanks, concentrates to roasting furnaces, overflow to (28).
(33.) Eighteen Wilfley tables, concentrates to (32), tailings to dump, slime to (28).
(34.) Eight tanks, spigot-product to (33), slime to (28).

"It will be noticed, in this scheme of separation, that no product of the coarse jigs is allowed to go to waste, but that all the portion going over the tail-boards of these jigs is recrushed and sized for further jigging. No tailings go to waste larger than 1·5 mm. Screening by trommels is carried as far as practicable, after which the spigot-products of classifiers are used on the fine jigs. Settling-tanks are used for unwatering, and for classifying the unwatered product. All fine concentrates from the fine jigs and from the Wilfley tables pass to an extended series of boxes in which the concentrates settle out, while the supernatant water slowly passes through the boxes, dropping most of its load, the settled product being drawn off at the bottom of the boxes through water-tight gates or valves. The final muddy water, however, is carried half a mile by launders to the slime-ponds, elsewhere described. The coarse concentrates go to a set of hopper-bottom bins, from which they are drawn off to cars, and carried to the storage bins at the blast furnaces.

"The concentrating ore is practically chalcocite, enargite, and pyrite in a quartz and aluminous gangue.

"*Blast Furnace Plant.*

"*Construction.*—At present there are three large-sized furnaces, each 51 feet long, and one furnace 180 in., or 15 feet long. At the slag floor level are seven fore-hearths or settlers, as arranged for the original furnaces, which serve equally well for the enlarged furnaces, there being two fore-hearths for each. A matte-track, at a lower level, serves to bring in the matte-ladles, into which the matte of the fore-hearths is tapped.

The large blast-furnaces, 56 by 612 in. tuyere-dimensions, have side-bushes of 8 inches, making the width at the throat 6 feet. There is no end-bush. There are two tiers of jackets, each 7 ft. 5 in. high. In either row, and on either side, the three central jackets are 7 feet wide each, and the four remaining ones are 7 ft. 6 in. each, making thus the total length of 54 feet. The concrete foundation is surmounted by the two original crucibles, to which was added the connecting bridge, the latter formed of water-cooled plates supported by short jack-screws. The crucibles, or sumps, as they may be aptly called, slope to the tap-hole. The bridge portion has a hearth sloping either way from the centre to the crucibles. Thus the total charge gravitates to either tap-hole. It may happen that the hearth becomes obstructed, so as to throw more of the flow to one of the crucibles and less to the other. Such a result, however, need not interfere with the effective operation of the fore-hearths. Both crucible and hearth are made of silica brick, which has been found to be very enduring with the 40 per cent. silica slag here produced.

"Above the upper tier of jackets comes the heavy mantel-plate, 2 ft. 3 in. high, having a sloping front, and surmounted by the apron or receiving-plates, 21 inches high, with a slope of 45 degrees, both together making a hopper, upon which the charge slides down, tending to keep the finer portion closer to the walls, and the coarser material at the centre of the furnace, all of which helps to promote regular working.

"The furnace has a closed top, the fumes being carried off by three down-takes to the large dust-chamber adjoining the blast-furnace building. There are forty-six tuyeres at the back, and forty-two at the front side of the furnace, or eighty-eight in all, set at 14-inch centres. The space supplementing the lesser number of tuyeres at the front is utilised to make room for the two slag-spouts. It is customary to plug, or leave off, the four tuyeres nearest the ends of the furnace, as this is found somewhat to prevent accretions, so that practically only eighty-four tuyeres are used. The omission of the two tuyeres over the spouts does not appear to interfere with the proper operation of the furnace at this point, all of which indicates irregular working of tuyeres. Where it has been undertaken to cut out every alternate tuyere the furnace has not worked so well. This, indeed, may be due to the fact that some of the tuyeres cut out were in good working position, or, rather, that the more frequent tuyeres mean more chances of getting air into the furnace. The tuyeres are punched several times on a shift, and it can hardly be supposed that all the air enters the furnace by the small 1-inch hole thus formed. No doubt a good deal gets in between the jacket and the crust, eventually finding its way by devious passages (those of the least resistance) to the interior of the furnace.

"The bustle-pipe extends completely around the furnace, with two branches from the blast-main, each with its own shut-off gate, so that, to shut down the furnace, two valves must be closed. The tuyere-pipes are 5 inches in diameter; the tuyeres being bolted to the jacket for easy removal in case of necessity. The connection to the blast-pipe is made by a galvanized-iron sleeve, with a ring-clamp to make the joint tight. The fore-hearths, or settlers, of the former smaller furnaces, serve equally well for the large ones. They are 16 feet in diameter and 5 feet high, the matte-tap being 3 feet below the top of the fore-hearth. The slag enters on the side adjoining the furnace, and flows out on the opposite or front side. Experiments at Great Falls show the best point of outflow to be opposite the point of entrance. The discharging slag flows down a steeply-inclined spout, which delivers it

opposite a 6-inch flattened water-jet situated just below the floor. This is supplied by jacket and other water. Besides this, there is a flow of water from the encircling cooling-pipe of the fore-hearth, which contributes to the stream that sweeps away the granulated slag through a semicircular cast-iron lined launder, and conveys it to the dumping-point on the flats below the works.

"The exterior of the furnace, having so long a side-wall, is braced and prevented from bulging by ties, carried around the furnace both at the level of the top of the lower jacket, and also under the floor. The horizontal pull of this bracing at the corner posts of the furnace is resisted by inclined ties attached to the floor above at adjoining corner posts. It will be noticed that between the three panels forming the length of the furnace, the jackets are supported by I-beams of the length of the panel (22 feet). Two sets of the I-beams are to resist outward pressure of the jackets, the upper and heavier set to hold up the upper jackets when the lower ones have, for any reason, been removed. Two of the outlet, or down-take, flues (soon to be changed to resemble the central one) are of steel, lined with brick, and have hopper-bottoms for the removal of the flue-dust. The third, or central down-take, has an upward and then a downward slope, having a pitch so steep that no flue-dust can rest upon it. Flue-dust, on the upward-sloping flue, slides back to the furnace; on the downward-sloping side it goes to the dust-chamber.

"The dust-chamber, 40 feet wide and 280 feet long, is provided with sheet-steel pyramidal hoppers, by which the flue-dust is conveniently drawn off to the charge-cars when they are run in below. This chamber, 20 feet high, affords a liberal space for the settling of the flue-dust. It is connected to the stack by means of a flue of 20 feet by 15 feet, or 300 square feet area of cross-section.

"*Operation.*—The furnace is charged through seven doors on each of the long sides, giving access to the entire length. It also has end doors for barring-out. The charge is brought in by a train of eighteen cars at a time, each car holding 2·5 tons. Eight of these cars constitute a charge, amounting to from 18 to 20 tons. The coke is charged separately in two-wheeled buggies, each of 30 cubic feet capacity, and capable of holding 1,000 lb. The amount used is 10 per cent. of the charge.

"The weighing of charges to an eighteen-car train is thus performed: The cars are spotted to the coarse concentrates bins, where the specified quantity is weighed in (to two at a time), the flow being controlled by a slide-gate operated by hand. A swinging chute, operated by a compressed-air cylinder, also assists in controlling the discharge. After the concentrates, the eighteen cars are simultaneously charged with the briquettes, as more fully mentioned in the description of the briquetting-plant. The train is then taken to the first-class ore bins, for the next item of the charge, then to the slag bins and the limestone bins. It will be seen that, in this way of putting in the materials, the finer portion is at the bottom of the car, and it is so charged into the furnace that it falls to the near side, while the coarser material goes to the centre portion of the furnace.

"The temperature of the gases from all the furnaces, in the flue beyond the dust-chamber, drops as much as 62 degrees C., and the draft-pressure drops ·2 inches of water when six of the forty-six doors are open. The air with a draught-pressure of 1·7 inches in the flue has a velocity of 1·5 feet per second through the doors (each of 20 square feet area), and with six doors open, an

admission of 10,800 cubic feet per minute, or one-fifth of the total outgoing gases. The quantity entering is proportional directly to the number of doors opened. Of the total heat developed by the burning of the coke and sulphur, 18·6 per cent. escapes in the outgoing gases, which, at the entrance to the down-take, have a temperature of 380 degrees C. Not more than these six doors need be opened at any one time, either for charging or for cutting accretions or crusts from the furnace.

"With regard to the influence of limestone, comprising approximately one-third of the charge, whose decomposition into CaO and CO_2, completed at 800 degrees C., abstracts heat at the surface of the charge, and thus lessens overfire; such decomposition takes 425 pound-calories per pound of limestone, or, as 3·5 lb. limestone is used per pound of coke consumed, it absorbs 1,487 calories out of the total of 6,680 calories developed by the combustion of this pound of coke and the 1 lb. of sulphur which is disposed of at the same time.

"On the other hand, at the zone of fusion, the CaO, in forming a silicate, evolves 297 calories, where such an evolution is most to be desired, resulting in an outflowing slag which reaches a temperature of 1,150 degrees C.

"The temperature of the escaping gases varies from 100 degrees C., in a freshly-charged furnace, to 560 degrees, just before a new charge is put in, especially when there has been a longer interval than usual before again charging. These variations become greater as the jackets become more crusted over, such accretions forming to the thickness of several inches.

"The addition of a fresh charge results in a drop of temperature of 200 degrees C., while the opening of the doors on one side cools the gases 80 degrees C., the difference, 120 degrees, being due to the putting in of the cold charge. There results a gradual rise of temperature of 25 degrees C. per minute, the rise being retarded because of the endothermic action of the limestone, the evaporation of the water, and the heat absorbed in heating up the charge.

"It would be well to note here, that with a fusible self-fluxing charge containing but little limestone, and with so high a percentage of coke, this rise of temperature would be more rapid, and overfire would increase to such a degree, indeed, as to promote the greater formation of accretions which tend to crust over the top of the charge and to delay, if not stop, smelting.

"With regard to the charging operation, I am not at liberty to give the proportions or analyses of the constituents of the charge at the Washoe plant, but, in Table I, I present a typical Montana blast-furnace charge made up from data in Professor Hofman's paper, 'Notes on the Metallurgy of Copper of Montana.' The analyses of matte and slag are from the same source, and from Peters' book on 'Copper smelting' (7th ed., p. 552). Compared with the charge calculation given by him on p. 367, there is but little flue-dust made. To-day, all fine concentrates are sent to the roasters, and then to the reverberatory furnaces. The fine ore is also screened out from the first-class ore, and is worked into briquettes. Thus the flue-dust loss has been cut from 18·75 per cent. (which he mentions) down to 3 per cent. in present practice. The grade of the matte has also been reduced from 50 per cent., the practice at the time the book was written, to 40 per cent., as now made. It is now possible to work 40 per cent. copper matte successfully in the converter, because of the firmer quality of the lining due to the power-rammers used. The loss by volatilisation, 80 per cent. of sulphur, has, in spite of the large amount present, resulted in giving a 40 per cent. matte.

This has been brought about, in part, by the use of a high-pressure blast of 40 oz. per square inch, which shows itself in much overfire and by the violent agitation of the materials at the surface of the charge.

"The high pressure of 40 oz. is necessary because of the small openings by which the air enters the surface, consisting of holes no more than 1 inch in diameter, where the slag has been pierced by the punching-bar, and of accidental seams between the jacket and its adherent crust, as well as by cracks and seams in this crust. The estimate allows for no leakages about the tuyeres, and the sound of escaping air indicates there is some loss from this source—a defect due to faults of construction, since, with the much higher pressures carried by the iron blast-furnace, the furnace-room is comparatively quiet. It may also be concluded that, with a more unrestrained entrance for the air, the pressure might well drop to half its present value, and that, moreover, with twice the volume of air now entering the furnace twice the tonnage could be put through. It is true, in the case of these large furnaces, that improvement has been incompletely met in other details. The same feeble methods are used to day in punching the tuyeres, and in barring-down the large furnaces, that have been used for many years. Improvement in the delivery of air at the tuyeres is the direction in which improvement will best be repaid. It would result in a furnace needing a low smelting column, in the dropping of pressure and, with it, the saving of power, as well as the ability of the furnace to increase its tonnage with the increase of the air admitted.

"Crusts or accretions are to-day removed by attack from feed-floor level by a gang of three or four men, who, exposed to the high radiant heat and fumes at that point, feebly work a heavy bar to break down these accretions. I believe, however, that metallurgists are well aware of these defects, and at this particular plant they will endeavour to remove them as soon as they can get to it. It must be remembered that the first of those 51-feet furnaces has been in operation only since March, 1904, less than a year before the present writing. There seems now, however, but little chance of the solution of the problem of improved air-supply into the furnace when one takes into consideration its difficulties.

"As indicated, there is a track at a level 10 feet below the slag-floor. The matte-ladles are run in and spotted to the desired furnace, and the fore-hearth tapped to the ladle. A dolly, having a 6-inch button-head, carries the conical clay stopper, made of a local clay. A full ladle of matte of 10 tons is drawn off. The flow is stopped with the dolly, the tapper pressing it in with all his force, while an assistant strikes the head of the dolly. The opening having been stopped, the tapping-bar is gently driven through the fresh clay, remaining there until the next tapping. The launder, leading the matte to the ladle, is 12 inches wide, with a semicircular bottom lined with clay. There is an independent launder to the other settler also, so that it is possible to tap from both fore-hearths to the same ladle. The ladle, when spotted, is ventilated by a hood suspended above it, which, terminating in a straight stack through the roof above, carries off the fumes.

"It has sometimes, though seldom, happened, as after a shut-down, that the contents of the fore-hearth have become cooled. Directly after tapping the matte, and before the settler has again filled with slag, it has been warmed by blowing compressed air into the settler, so as to bessemerize the molten matte still remaining in the settler. The reaction, being exothermic, serves to raise the temperature of the molten contents."

TABLE I.—Charge-sheet.

Name of Ore.	Moisture.	Weight.		Cu.		SiO_2.		Fe and Mn.		CaO and MgO.		S.	
		Wet.	Dry.	Per Cent.	Wt.	Per Cent	Wt.	Per Cent.	Wt.	Per Cent.	Wt.	Per Cent.	W
Coarse concentrates ..	3·0	1,550	1,500	8·7	130	22·0	330	27·0	405	..	....	35·7	
Briquettes.....	8·0	1,630	1,500	6·9	104	45·0	675	11·0	165	..	....	17·0	
First-class ore	3·0	2,060	2,000	8·0	160	50·0	1,000	12·1	242	0·5	10	15·4	
Converter-slag.....	..	1,500	1,500	2·0	30	30·0	450	42·9	643	1·0	15	0·7	
Limestone.....	..	3,500	3,500	..	..	5·0	175	1·0	35	51·0	1,785	..	
Coke	..	....	1,020	..	..	6·9	70	1·2	12	0·8	8	0·7	
	..	10,230	....	..	424	..	2,700	..	1,502	..	1,818	..	1,

Weight of slag. $\frac{2,700}{40 \text{ per cent.}}$ = 6,750 lb., or 66 per cent. of charge.

Cu in slag, 6,750 by 0·33 per cent. = 22 lb., or Cu_2O = 25 lb.

Cu in matte, 424 — 22 = 402 lb., and the matte weighs, $\frac{402}{40 \text{ per cent.}}$ = 1,005.

Fe in matte, 1,005 by 30 per cent. = 301 lb., leaving for the slag 1,502 — 301 = 1,201 lb., or of 1,544 lb.

S. in matte, 1,005 by 23 per cent. = 231 lb., and in slag 26 lb., or in both 257 lb.

S. volatilised 1,115 - 257 = 859 lb., or 77 per cent. of the total sulphur.

From these data we have in the slag SiO_2 2,700 lb. (40 per cent.); Fe 1,526 lb. (22·5 per cent.); CaO, 1,818 lb. (26·9 per cent.); Cu_2O, 25 lb. (0 per cent.); S., 26 lb. (0·4 per cent.); other bases, by difference, 9·8 per cent.

From Peters[1] we have taken a matte and used it in our calculation; the composition, S, 23 per cent. (231 lb.); Cu, 40 per cent. (402 lb.); Fe 30 per cent. (301 lb.); other bases, 7 per cent. (71 lb.).

The matte fall, based upon the entire charge of 10,230 lb., is 10 per cent and the concentration 5 tons of ore into 1 of 40 per cent. matte.

"ROASTING PLANT.

"*Reverberatory furnaces.*—There are seven reverberatories, the largest of kind in the world, placed in two buildings. Each furnace supplies waste h enough for two 300 h.p. Stirling water-tube boilers. The gases, after pass through the boilers, are conveyed by the reverberatory flue to the main fl Whenever it is desired to clean the boilers, a by-pass flue conveys escaping gases direct to the reverberatory flue, the connection through boiler being meanwhile shut off.

"Length of hearth, No. 1, 115·8 feet; of Nos. 2, 4, and 5, 102·5 fe and of Nos. 3, 6, and 7, 112·5 feet; all hearths are 19 feet wide, and h fire-boxes 16 feet by 7 feet, or 112 square feet area. Referring to furn No. 1, the outlet-flue at the neck is 60 by 38 inches, or of 16 square f area. The skimming-door, 12 inches by 15 inches wide, has its skim-pl 4 inches above the hearth at that point. The hearth, however, has a slop 8 inches towards the matte tap-holes. At 24 feet from its front end, furnace begins to draw into the jamb, where it is 7 feet wide and 4 feet h to the crown of the arch. The rise of the arch is 1 inch to the foot, o the middle section is 19 inches. In the roof there were ten transv

[1] Modern American Methods of Copper Smelting, by E. D. Peters, jr., 7th ed., p. 552 (1895).

ansion-joints, 3 inches wide, or 30 inches in all left in the furnace when lt. These, however, are now each a little more than 1 inch when the nace is cold. In the bridge itself there are three transverse expansion-nts, each of 4 or 5 inches, which close up when the furnace is fully heated. e bridge is 4 feet across, and is 27 inches above the hearth and 24 inches ve the grate. It has a hollow conker-plate, through which air passes by a ntilating passage to the draft-flue, thus keeping the bridge cool. At this d of the furnace the height from the hearth to the crown of the arch is feet. Twenty checker holes, each 3 by 3 inches, provided for the mission of air, are located transversely to the furnace over the fire-bridge.

"In some of the furnaces additional checker-holes have been made at the nt of the fire-box for additional air, but for other furnaces this extra pply is not needed. In order to determine the height of the coal in the e-box, two circular stoke-holes, 12 inches in diameter, are placed in the nt wall of the fire-box, and these openings are closed by wheel-doors. er the middle line of the fire-box are four charge openings, 12 inches uare, through which the four coal-hoppers discharge into the fire-box. There e ten side doors, each 8 by 15 inches, with sills 18 inches above the level the skim-plate at the front. The sides of the furnace and the fire-bridge e stepped off for several courses on the inside, thus strengthening the wer portion of the walls and the bridge. There are four charge openings the roof, having circular covers. Through these openings the charge from e two hoppers above drops into the furnace.

"The operation of these furnaces is as follows :—In the fire-box of a rnace, which has been shut down for repairs, a fire of wood is put, followed an increasing firing of coal, until, in forty-eight hours, the first charge ay be dropped in. As fast as charges are melted, others are added until e furnace has been filled. The furnace takes from ten to fifteen days to t up to its full heat. The charges of 15 tons are put in, on the average, ery eighty minutes, 10 tons being dropped from the first hopper and 5 tons the second one, 90 feet from the front of the furnace. It must be noted at the charge drops upon a bath of a minimum depth of from 3 to 4 inches matte with 8 inches of slag above it, so that there is little chance of the w charge sticking to the hearth. The hot calcines, of which the charge is incipally composed, spread out less than commonly represented. There is, owever, a movement of the entering charge towards the front of the furnace, consequence of which the ore may be observed floating down in two ridges wards that end, and gradually spreading out. Heat is taken up not only om the flame, but also from the highly-heated molten bath of the furnace, consequence of which fusion proceeds rapidly.

"Before dropping the next charge, the side-door near the hoppers is opened, nd a rabble inserted to determine that no unfused material remains. It metimes happens that some of the charge becomes agglomerated, and, oving down towards the front end, escapes fusion. These 'floaters,' as they e termed, are moved up toward the fire-bridge by inserting a rabble at the roper doors, so that they are brought to the hottest part of the furnace and en fused; or, better, a pipe is inserted under them by which the matte st under the floater is bessemerised, and the mass melted at the increased mperature resulting. Skimming is performed every four hours, care being ken, however, to do it not less than forty-five minutes after a charge has en dropped. It takes about fifteen minutes, the amount run out being om 45 to 50 tons. The slag is granulated in water, and is run to aste by a launder to the dump. This operation, called skimming, is rather tapping, the rabble being used to hold back and control the speed of the

outflowing stream of slag. A rabble with a 5-inch by 9-inch blade and a 12-foot handle is used, and sometimes a larger one, having a 6-inch by 16-inch blade. The slag runs through a settling-pot, or trough, 7 feet long, 24 inches wide, and 18 inches deep, intended as a safeguard against a possible escape of matte. The slag adhering to this pot is called pot-slag, and is sent to the blast-furnaces, since it may contain drops of matte. When as much as 200 tons of matte has accumulated in the furnace, it is tapped off, according to the amount of matte needed at the converters. The matte flows into a 10-ton ladle from two reverberatory furnaces, 80 feet distant. A compressed-air locomotive is coupled to the ladle-car, ready to move it when full. Quite commonly the matte is tapped from two furnaces simultaneously, the runner or launder, 80 feet long, branching to the adjacent tap-holes of the two furnaces. These tap-holes, two to each furnace, are at the hearth level. The plugging of a tap-hole is done with a stopper-rod, or dolly, having a button of 4 inches diameter, on which is stuck a conical clay plug. This is inserted by one man, whose efforts are seconded by another, who strikes the end of the dolly with a heavy hammer, to enter the plug effectually into the tap-hole.

"Coal is charged into the fire-box about once in forty minutes, dropping in 3,000 lb. of coal at the four charge-openings. The level of the coal is found by feeling it with a rod introduced through the stoke-openings at the front of the fire-box. A mica-covered hole, located in the outlet flue of the furnace, can be observed by the fireman 125 feet away, who regulates the firing of the fuel by observing the appearance of the flame at this hole. The coal is carried on the grate to the height of the bridge, or about 24 inches, and a clinker-bed is permitted to form on the grate-bars. These bars, 2 inches square and 6-inch centres, permit a good deal of ash and unburned coal to fall through. The dropping of these materials is constant, the coke amounting to 10 per cent. of the total coal used.

"About monthly it is necessary to patch or fettle the furnace near the fire-box end, where it is subjected to the greatest action of the fire. This is known by looking in at the slot of the fire-bridge, where the conker-plates are observed becoming red-hot. Repairs having been determined on, the matte is allowed to accumulate in the furnace to near the level of the sill of the skimming-door. Slag is tapped and skimmed close to the matte, and then the latter is tapped dry from the furnace. Such a large amount of matte will fill a train of sixteen ladles. To take care of it, preparations have been made by having withdrawn matte just before from the blast-furnace settlers or fore-hearths. Thus full attention can be given to this supply at the converters. At the reverberatory half the matte is tapped off into ladles and covered; the remainder is then treated in the same way. The first three side-doors of the empty furnace are opened and about 20 tons of sand, used for fettling, thrown in against the corroded sides, as well as placed there by means of paddles. To tap the matte and to repair the furnace requires more than eight hours after which the doors are put up, the fires urged, and new charges added until 250 tons of ore has been put in. About once in eight months it becomes necessary to repair the furnace fully, when it is tapped dry and allowed to cool off until it is possible for the masons to enter. This waiting may be lessened by admitting a blast of air from a fan to ventilate the portions of the furnace where the repairing has chiefly to be done, viz., the 25 or 30 feet at the fire-box.

"These reverberatory furnaces can smelt from 250 to 325 tons daily, and may be termed 300-ton furnaces. They burn from 55 to 60 tons of coal in twenty-four hours, or 21 per cent. of the charge. It must be remembered

about 10 per cent. of this, however, is recovered in the cinders as coke. $4·50 per ton for coal this would make $1 per ton of charge treated, to nothing of the 600 h.p. of steam obtained from the waste gases. On unt of the large body of matte and slag carried in the furnaces, the ations of temperature are less than in smaller ones. Skimming or tapping l done at the front door, where the entering air will not cool off the ace. Care is taken to lute up all openings, and upon the cooler front-half he furnace-arch, to carry a layer of 3 inches of sand to retain the heat and top every crack. When the sand is removed at any spot upon the arch, hot brick shows itself. The charge being dropped near the fire-box end, dust has a chance to settle in going the long distance of 100 feet through furnace, so that the loss by flue-dust is small. With a furnace-width of eet distant from the centre-line of the furnace and hence far from the , the corrosive action is less than in a narrower furnace.

A type charge of these reverberatories consists of calcines, limestone (put the charge at the McDougall roasters), and flue-dust, containing—SiO_2, ; FeO, 31·3; CaO, 2·9; S, 8·1; and Cu, 9 per cent. The slag contains , 37·8; FeO, 38·6; CaO, 4·6; Al_2O_3, 6; and Cu, 0·37 per cent.; and the of sulphur by volatilization is 33 per cent. Corresponding reverberatory- s at Great Falls, Mont., show Cu, 0·69 per cent.; the higher copper- tent, as compared with that of the Anaconda slag, being due—(1) to the er temperature and hence less fluid slags, (2) to the better settling in the ger furnace, and (3) to the greater amount of lime contained in the aconda slag. The matte is tapped, through plates 24 by 24 by 2·5 inches, he matte launders, which convey it 80 feet to discharge it to the ladles. o ladlesful of matte are generally drawn at a time without stopping the r. It is found that but little matte is spilled in moving the empty ladle o the place of the full one. The best point to which to roast the calcines good reverberatory work is from 7 to 8 per cent. of sulphur."

The blast furnace, as well as the reverberatory and calcining furnaces in smelting works of the Washoe Copper Company at Anaconda, have been arged, and now upwards of 10,000 tons of ore are treated daily.[1]

Permanence of Copper Lodes.

The permanence of copper lodes may be gauged by two factors—duration perations, and actual depths of workings combined with extent of out- . The first is applicable to deposits whose early history is obscured in haze of intervening centuries; the latter, to mines in operation. In ichever light regarded, the prospect is cheering. Copper lodes, judging history, are among the most persistent metalliferous repositories in ture; it seems almost superfluous to add that this statement applies only important occurrences.

Japan furnishes remarkable instances of the longevity of copper mines, ich rank first in the mineral wealth of the country. In the "Mining lustry of Japan during the twenty-five years—1867 to 1892"—Wada Tsunashiro, Director of the Mining Bureau, Department of riculture and Commerce, it is stated that "Yoshioka and Osaruzawa per Mines, with several silver and gold mines, started in the the 9th century, still working and prosperous." At the World's Fair, Chicago, the iter was informed by Mr. Rejii Kanda, Mining Commissioner for Japan, t vertical shafts sunk under his engineering supervision to depths

[1] Report of the Amalgamated Copper Company, 30th April, 1907.

of over 1,000 feet had revealed early workings extending even below that level. From these great depths the ore was carried to the surface in baskets on men's backs, through galleries or levels connected by short ladders. This primitive system of mining was admirably illustrated by models in the Japanese Mining Court at the World's Fair.

In England[1] the Cornish tin lodes were worked in the time of the Phœnicians. With depth, copper ores replaced those of tin, and still deeper, the latter reappeared. Copper-mining in England began about 1700; previously the metal was obtained chiefly in connection with tin-mining.

The famous Tharsis and Rio Tinto Mines of the Spanish Peninsula were worked by the Romans, and are still in operation on a scale of great magnitude (2,157,470 tons of cupriferous pyrites were extracted by the Rio Tinto Company alone in 1905), with an estimated reserve proved by drill borings equal to 130,000,000 tons.[2] The timbers in the old Roman workings have been so preserved by the copper salts in solution as to retain markings and letters cut by Roman miners eighteen centuries ago.

A local instance of the preservative qualities of certain mineral solutions may be cited; the time test, though comparatively extremely limited, is none the less effective. The timbers in the Moruya Silver Mine—the first silver mine opened in the Colony, laid down about 1861 or 1862—which have recently been exposed by unwatering the old workings, are in an excellent state of preservation. A more interesting fact, perhaps, is the condition of the ironwork: even the nails and ladder clips are capable of re-use; the latter, in fact, have been re-forged and used in the renovations. The Moruya ore is essentially arsenio-pyrite, with occasional zinc-blende. The preservative agent is, therefore, probably chiefly arsenic.

Copper mines in Portugal, worked by the Romans, are still in operation. The celebrated San Domingos Mine yielded 196,922 tons of cupriferous pyrites in 1894.[3]

Italian mines, worked by the Etruscans, and during the Middle Ages, were brought to a standstill in 1630 for more than a century, when operations were resumed and are still in force, the 1,000-foot level being passed.

Swedish copper mines have been worked from a very remote period. According to Vogt (quoted by Phillips and Louis), the Falun cupriferous pyrites deposit has produced 1,200,000 tons of copper, equal to 35–40 million tons of ore, since the year 1200; and now produces annually about 500 tons of copper.

In India very ancient copper mines exist, but copper is now only produced on a very limited scale.

An idea of the permanence—or persistence in depth—of more recent mines can be gleaned from the following figures relating to some of the prominent American mines. Even under most favourable circumstances the duration of mines in this age of severe competition, and enormous outputs to meet increasing demand, must necessarily be comparatively extremely limited, when contrasted with early historic mines worked by primitive methods to satisfy restricted needs, though the actual extraction will probably compare most favourably. It is necessary to note that the Lake Superior copper

[1] J. A. Phillips and H. Louis' Treatise on Ore Deposits, 1896, pp. 190 and 229.
[2] Stevens' The Copper Handbook, 1906, pp. 866–868.
[3] Phillips and Louis' Treatise on Ore Deposits, 1896, p. 515.

deposits are not lodes in the ordinary acceptation of the term, but bed-deposits (conglomerates), flow-deposits (amygdaloidal lavas), and vein-deposits (small fissures in the igneous flows), which are followed on the incline.

DEPTHS OF SOME AMERICAN COPPER MINES.

Name of Mine.	Depth—Vertical.	Depth—Inclined.	Dip.	Temperature.	References.	Remarks.
	feet.	feet.		degrees.		
Red Jacket, Lake Superior	4,300	....	..	87·6	United States Geol. Survey, 17th Ann. Rept., Pt. 3, p. 94.	
Tamarack, ,,	3,400	....	..	....	Stevens' Copper Handbook, 1906, pp. 954 and 955.	No. 1 shaft } Cutting the Calumet and Hecla bed on the underlay at 4,135 feet.
,, ,,	4,355	....	..	....		No. 2 ,,
,, ,,	5,139	....	..	....		No. 3 ,,
,, ,,	4,450	....	..	....		No. 4 ,,
,, ,,	3,300	....	..	....		No. 5 ,,
Quincy, ,,	....	5,000	..	....	*Ibid.*, p. 838.	
Calumet and Hecla, Lake Superior.	4,748	8,290	37½	....	*Ibid.*, p. 310.	
Butte, Montana	2,600	....	..	....	Mineral Industry, 1906, p. 211.	

The rich secondary (subsulphide) ores of Butte are estimated by Ledoux[1] to decline at the rate of 2 per cent. per 100 feet, but this diminution lessens according to Dr. Peters, as greater depth is reached, and is about stationary at 1,300 feet. The actual smelting yield at the present time is computed to be about 3·25 per cent. of copper, and average values of $1·75 to $2 gold and silver per ton.[2] Owing to improvements in metallurgical treatment, and to consolidation of properties, the Butte mines are reported to be making more profit out of this lower grade than was possible with double the yield before.

The Lake Superior ores are reported to have an average value of about per cent. of copper, but some mines yield only ·75 per cent. The Tamarack output in 1905 averaged about 1 per cent.[3] The profitable working of these low-grade deposits to the immense depths quoted above depends upon the unique occurrence of the copper in the native state, which dispenses with costly reduction plants. The copper is so pure that simple concentration and melting are alone necessary to secure for it the highest market values.

"THE COPPER MINES OF THE WORLD."

By Walter Harvey Weed, Geologist, United States Geological Survey.

Production.

"***Future supply and demand.***—The question arises where the future supply is to come from. Copper mines are not inexhaustible; and every pound of ore extracted means just so much less in the ground. The old sources of

[1] Modern Copper Smelting, 9th edition, p. 20, 1898.
[2] Stevens—Handbook of Copper, 1906, p. 194. [3] *Ibid.*, p. 954.

supply, though not exhausted, are getting nearer and nearer to extinction an reaching more or less rapidly the point of exhaustion. Though the long lif of copper mines is well established, they cannot last for ever. As Ricka has said, 'Even Methuselah died.'

"Some of the Huelva mines of southern Spain, worked since Roman day are already exhausted; the Rio Tinto ores are gradually getting leaner an leaner, and the region is barely holding its own as a copper producer, despit the prevailing high prices. The Montana mines have increased their outpu to nearly 20,000 tons of ore a day, and several mines are 2,400 feet deep they cannot last for ever, and the district must see a decline some day, though fortunately it is not yet in sight.

"Lake Superior will hold its own for many years to come, owing to th opening of new mines; but the older ones, the best payers, are already a mil deep, and working costs, if not leaner ore, will limit their downward extension.

"Europe, Asia, Australia, and Africa produce copper, but the productio is stationary or declining. South America is said to have untold wealth in copper, but the economic conditions are so unfavourable that, with the exhaustion of the rich secondary ores, the deposits are often abandoned.

"The present and future increase will, it is believed, come from North America; first from Nevada, Utah, and Mexico; next from British Columbia and Alaska.

"Copper mining is becoming a more stable industry with the development of great bodies of low-grade ore, rather than the rich but usually limited deposits of the earlier stages of mining. The development and operation of low-grade deposits necessitates large plants, cheap fuel, and cheap transportation, as well as a very large amount of invested capital. In undeveloped and remote regions it is only the very rich ores that can yield a profit, and hence in the opening up of a new country or section, as in western North America, Central Africa, and Asia, the low-grade deposits are the last to be developed."

"The Mineral Industry during 1906."

Edited by W. R. Ingalls.

"*Consumption.*—The domestic consumption of copper in 1906 was far in excess of anything previously known in the United States, the average being about 55,660,000 lb. per month against about 51,000,000 per month in 1905. All the mills manufacturing sheet, wire, and other finished forms of copper, all the brass mills and all the manufacturers of machinery into which copper and brass enter in part, were extremely busy throughout the year. The great extension of electrical work of all kinds, the construction of new electric roads and the application of electricity on existing railroads were largely responsible for the demand, which shows every sign of continuance through 1907. The capital stock of the American Brass Company, the largest consumer of copper was increased from $12,500,000 to $15,000,000, on 26th February, 1907. About 15,000 men were engaged in the brass industry at Waterbury, Conn. in 1906. There were considerable additions made to the various manufacturing plants, including those of competitors as well as subsidiaries of the American Brass Company. In some of the shops the men worked on relays and in the casting mill they were employed for twenty-four hours daily. The Waterbury Brass Company erected a new rolling mill."

Depths of New South Wales Copper Mines (Vertical or Inclined).

The depths attained in New South Wales are, with two exceptions, comparatively, very superficial :—

	Feet.
Burraga (following underlay)	2,135
Great Cobar	1,000
Crowl Creek	730
Nymagee	720
Cobar Cheaney	700
Lake George Mines (Captain's Flat)	700
Cangai (by tunnels and winzes)	600
Queen Bee	563
Great Cobar North	560
Girilambone	544
C.S.A.	...
Belubula	504
Conrad Stannite	500
Shuttleton	450
Cobar Gold-mines	437
North Nymagee	400
Mount Hope	400
Frogmore	373
Bundarra	360
Cobar Copper (late Mount Pleasant)	340
Phœnix	340
Blayney	337
Ace	321
Adeline	310
Goodrich	300
Milburn Creek	300
Budgery	283
Icely	275
Federal	269
Mount Boppy Copper-mine	259
Snowball	259
Attunga	258
Bumbery	250
Apsley	240
Carangara	240
Cash-Essington	235
Belara	212
Mount Stewart	210
Budgerygar	203
Mount Royal	200
Underlay	200
Gulf Creek	200
Summerhill	200
Nadbuck	200
Mount Laut	200
Ophir	200
Currowong	186
Coombing Park	180
Belmore (near Lewis Ponds)	180
Cow Flat	180
Mountain Run	180
Mulloon	175
Big Wertago	170
Gurophian	170
Canbelego	170
North Wiseman's	162
Summer's Copper-mine	155
Balmoral	155
Copper Well	150
Vychan	150
Bogan River	150
Orange Plains	150
Elizabeth	150
Lobb's Hole	147
Copper Hill	146
Mount Everest	145
Bobby Whitlow	142
Belmore (Cow Flat)	140
Quigley's Hill	140
Sydney—Walleroo	140
Eclipse	140
Mount Ragan	138
Green Swamp	135
Sugarloaf	135
Box Ridge (Summerhill)	130
Kyloe	130
Cooma	129
Mayfield	125
Ophir	120
Nelson	120
Bob's Mount	120
Cootralanta	118
Lucky Hit	115
King of England	110
Dartmoor	100
Monaro	100
Mount Jasper	100
Native Bee	90
Merilla	86
Namoi	83
Kangiara	83
Wilpina	80
Boro	80
Cadia Extended	80
Willi Willi	75
Cowfell	75
Cyclops	70
Esmeralda	70
Bredbo	64
Little Copper Hill	64
Moonta	60
Pluck	50

Bedded Copper Deposits (Sedimentary).

The celebrated Keupferschiefer, or copper schist of Mansfeld, Harz, Germany, is the most important example of this form of deposit, apart from those of Lake Superior, which consist of lava flows with interbedded conglomerate. A brief description of its occurrence will be found in another

portion of this work. The Mansfeld copper-beds belong to the Perr period ; those of New South Wales to the Triassic. The latter wil described at some little length because of the scientific interest attachin the occurrence, which otherwise has no value. The association of co ores with Permian strata is as world-wide as it is remarkable. In Soutl Russia, Germany, America, and Great Britain, beds of the Permian a closely approximating period, contain copper impregnations. Thos America, in California, Colorado, and Mexico, according to Dr. Peters,[1] of Triassic Age, and therefore more closely allied in time to those of Sydney Coal Basin, which received a good deal of attention from Geolo Surveyor David, B.A., F.G.S., now Professor of Geology at the Syc University.

The American deposits are of special palæontological interest in that copper ore—glance—replaces fossil shells, fish, and plants.[2]

In a paper read before the Australian Association for the Advancen of Science in 1887,[3] Professor David stated "that cupriferous shales h been discovered at the following places :—

"1. At the 1,312-foot diamond drill bore, completed in 1879, Newington, on the Parramatta River, near Parramatta, wher was observed by Mr. Waterhouse.

"2. At Bulli. The shale is said to outcrop on the hills at a leve about 700 feet above the Bulli coal-seam.

"3. At the 2,307-foot diamond drill bore, completed in 1887, at De Creek, on the Holt-Sutherland Estate, between Port Hacking Botany Bay.

"4. At the 1,586-foot diamond drill bore, completed in 1886, at He cote, on the Illawarra line, 27 miles southerly from Sydney.

"At Holt-Sutherland, out of a total thickness of 71 feet, at least 3 showed native copper, more or less freely. At Heathcote, al 7 inches of core altogether were cupriferous."

The following analysis of the tuff (Holt-Sutherland) has been made Mr. J. C. H. Mingaye, F.C.S., Analyst and Assayer to the Departmen Mines :—

Combined moisture	5·32
Moisture at 100° C.	3·38
Silica	56·28
Alumina	24·21
Oxide of iron	7·34
Metallic copper	·08
Lime	1·10
Magnesia	2·36
	100·00

Professor David, in the article quoted, discussed the economic value of cupriferous tuffs, and summed up the question in the following terms :—

"At Holt-Sutherland the total thickness of the copper-bearing portion the shales is at least 3 feet. This thickness, however, is made up of a nu of different layers, several of which are separated from one another by b of shale, which do not show copper freely, though they probably conta small proportion of the same metals which occur in the more produ

[1] Modern Smelting, 7th ed., p. 18. [2] Eng. and Mining Journal, 18th November, 1882.
[3] Trans. Aust. Assoc. Adv. Sci., I, pp. 275–290.

bands. The thickness of the metalliferous bands is respectively 1 inch, 2½ inches, 12 inches, 7½ inches, 5 inches, 2 inches, 2½ inches, and 6 inches. The highest ore-band is about 24 feet above the lowest, and the beds are separated from one another by from 1 foot to 9 feet of comparatively barren shale.

"At Heathcote there are two thin beds showing native copper, the upper 6 inches thick, and 7 feet above the lower, which is only 1 inch thick.

"Assuming, therefore, that a continuous bed of cupriferous shale extends from Heathcote to Holt-Sutherland, a distance of 8½ miles, having an average thickness of 1 foot, there would evidently be a large body of metalliferous strata.

"The average specific gravity being taken as 2·6, every acre of shale would contain 3,160 tons of copper-bearing rock, which would yield on the average (the average yield being assumed to be 0·15 per cent.) 3 lb. 5¾ oz. of metallic copper and 7 dwt. 7 grs. of silver per ton. If, therefore, the value of the gold be left out of consideration, and, as already stated, gold was only found in appreciable quantity in one doubtful assay, the value of copper and silver in the aggregate would be only 3s. 9d. per ton, so that the shale is far too poor to work at present for these metals.

"The cupriferous tuffs and tuffaceous shales are evidently partly of volcanic and partly of sedimentary origin, as proved by the presence in them of both basalt lapilli and rounded quartz grains. Two facts indicate Kiama, or the line of volcanic country between Kiama and Mittagong, as the probable source of the volcanic particles: first, the presence of minute segregated veins of metallic copper in the basalt at Kiama; second, the resemblance of the Kiama and Mittagong lavas to those of which the fragments in the tuff at Holt-Sutherland are composed." . . . .

In three slides of the Kiama basalt Professor David detected minute segregated veins of metallic copper, about 1-40th of an inch thick. The local horizon of the cupriferous basalt has been designated the "Bombo" lava.

The cupriferous shales outcrop on the coast at Narrabeen, a few miles north of Port Jackson. Here a little prospecting has recently been done under the impression that a lode existed. Carbonates and native copper occur, the latter, in some instances, forming concentric scrolls in fossil wood. The organic matter of the latter is carbonised, and has been the means of precipitating the copper in metallic form.

The cupriferous tuffs are noticeable in the cliff sections of the Blue Mountains on the same geological horizon.

South Australian Copper-mines.

The first lode discovered in South Australia, according to Mr. H. Y. L. Brown, Government Geologist of South Australia,[1] was the Wheal Gawler, a silver-lead mine on the western slopes of the Mount Lofty Ranges, 4 miles east of Adelaide, opened in 1841.

The first copper-mine—the Kapunda—was discovered in 1842; the next in order being the Montacute in 1843, the Burra in 1845. The Moonta and Wallaroo Mines were found between 1861 and 1864, and proved the richest in the Colony. They are situated on Yorke's Peninsula, on the eastern shore of Spencer's Gulf. The Moonta and Wallaroo Mines are about 9 miles apart, but are worked by the same company. The Moonta occurs, according to Mr. L. G. Handcock, in felspar porphyry, the Wallaroo in metamorphic schist.

[1] A Record of the Mines of South Australia, 1887-1890, opposite p. 26.

Mr. Brown describes the Moonta in the following terms :—

"There are five main lodes on the property, and from each of these various spurs and minor lodes branch out, and are connected with the main lodes by occasional cross veins. Including these, there are twenty-seven lodes. Their direction is north-westerly, and their underlay varies from 3 to 6 feet in the fathom. The main lode bears N. 20° E., and the others vary from that up to N. 45° E. Their width ranges from 6 inches to 20 feet, and the ores obtained from the lodes in the present workings are chiefly chalcopyrite and bornite. The bulk of the veinstone—chiefly quartz, and at times portions of the bed-rock—as raised ore and gangue gives from 2 to 5 per cent. of copper, but sometimes clean chalcopyrite gives 20 to 30 per cent., and bornite from 30 to 50 per cent.

"The quantity of ore raised from the Moonta Mine from the commencement to June, 1886, equalled—in gross tons of 21 cwt.—476,180 tons, and the average percentage of copper on net dry weight of dressed ore equalled 20 per cent.

"The deposits of copper ore are chiefly along the lead of the lodes associated with gangue, at the present supplies being chiefly chalcopyrite and occasional bornite. An exceedingly small proportion of green carbonate ore was found close to the surface, but a large proportion of the green ore was atacamite. The deposit did not extend more than a few inches, or occasionally a few feet, from the surface.

"The peculiarity of this cupriferous district was disclosed by the removal of these ores and the sinking of the shafts, and was that although the lodes continued regular, no further ore was met with; and, as a rule, no stain of copper was seen until the depth of 5 to 10 fathoms (30 to 60 feet) was reached, when rich oxides and malleable copper deposits were struck, and after that black and grey sulphides."

Mr. Brown states that five lodes occur in the Wallaroo property, which is situated 10 miles north of Moonta Mine.

"The main lode is nearly vertical, although occasionally the underlay is a little to the north, and sometimes a little to the south. The lodes vary in width from 6 inches to 20 feet, and the ore they contain is chiefly chalcopyrite. As raised from the mine, it varies from 3 to 10 per cent., with occasionally small quantities of rich ore." Country, talcose schist.

To Mr. L. G. Handcock, son of the well-known late manager of these mines, the Writer is indebted for the following particulars of these mines in 1898 :— The lodes of Moonta vary in thickness from 3 to 8 feet, those of Wallaroo up to 20 feet. The Moonta ore at the present time does not average more than about 2 per cent. of copper in the crude, but it can be dressed to a much higher grade than that of Wallaroo, owing to the amount of pyrites in the latter, which, when cleanly concentrated, does not grade above 12 per cent.

The method of treatment at Moonta may be briefly described as typical of both. The ore is tipped on to a platform, where the attle or waste is picked out by boy-labour, a large percentage of the bulk thus being removed. The ore is then passed through rock-breakers and Cornish rolls. The screens average about five holes to the inch. The crushed ore is then jigged—water being obtained from the mine—and the "firsts" and "seconds" sent to the smelters, the tailings being discarded. Before, however, going to the jigs, the ore passes through agitators in which the coarse particles pass through the bottom holes, whilst the finer (slimes) are carried off by the current and

over buddles. The concentrated slimes from the buddles are dried by spreading in the sun, and are subsequently charged in the furnaces with kiln-roasted ore.

The value of the outputs of the Moonta and Wallaroo Mines, which are now worked in conjunction, according to Mr. Brown, are as follows[1] :—

Moonta Mine, from commencement to 31st December, 1898, £5,113,252.

Wallaroo Mine, from commencement to December 31st, 1898, £3,906,277.

The greatest depths reached to end of 1898 being—Moonta, 1,500, 1,600, and 2,340 feet in different lodes; and Wallaroo, 1,170 feet.

Burra Burra Copper Mine, according to Mr. Brown, was found by a shepherd in 1845, about 100 miles a little north of west from Adelaide, situated on bald hills standing 120 feet above the surrounding country. The prevailing rock is limestone. The ores obtained from this mine have been chiefly red oxide, and very rich blue and green carbonates. Native copper was also found. For many years the average yield was from 10,000 to 13,000 tons of ore, averaging from 22 to 23 per cent.

In Mr. Conigrave's "Handbook of South Australia," it is stated that during the twenty-nine years in which the mine was worked, the Company expended £2,241,167 in general expenses. The output of ore during the same period amounted to 234,648 tons, equal to 51.622 tons of copper. This, at the average price of copper, amounted to £4,749,224. The mine ceased working in 1877. Greatest depth reached 600 feet.

The following particulars are extracted from the Official Catalogue of the International Exhibition, London, 1851, at which ores from the mine were exhibited :—Mine started 5th September, 1845, with a capital of £12,320. To September, 1850, the following amounts of ore were raised :—

	tons	cwt.
September 30th, 1846	6,359	10
,, 30th, 1847	10,749	17
,, 30th, 1848	12,791	11
,, 30th, 1849	7,789	16
,, 30th, 1850	18,692	9
Total	56,428	2 in 5 years,

varying in quality from 30 to 70 per cent. The money value of the output was £738,108.

Prior to September, 1850, the ore was shipped to Swansea, but at the local smelting-works then established and at the mine 1,000 men were employed.

It is worthy of note that no calls were made after investment of the working capital—£12,320—and that the value of the original £5 shares rose to £200. The shares returned £40 per annum in dividends, a total of £800,000 being so paid. The mine was afterwards sold to a new company, but for many years has not been worked.

Mr. Brown describes the mine as follows :—"In the deeper levels regular lodes are met with, running north and south, containing very rich ore, malachite, red oxide, and grey sulphuret of copper; but above the 30-fathom level (180 feet) there is no appearance of lodes, the ores (malachite and azurite) being deposited with the greatest irregularity. The blue carbonate often occurred in round nodules, with crystals of the

[1] Record of the Mines of South Australia, 4th ed., 1908, pp. 139, 140.

greatest regularity projecting from the surface. The malachite was found in the form of stalactite, in slabs encrusting fissures, and irregularly-shaped masses, which had been deposited in cavities in the rocks. The country rocks are much broken and twisted, and consist of cherty silicious rocks, crystalline white and gray limestone, blue slaty shales, and argillaceous sandstones."

Queensland Copper-mines.

Peak Downs Copper Mine was discovered in 1862, according to Mr. W. H. Rands,[1] who stated that the lode could be "traced 1½ mile, running in an east and west direction. It has an underlie varying from 40° to 70° to the south.

"Country consists of foliated and contorted micaceous and hornblendic schists, dipping south-east. The outcrop is a gossan, consisting chiefly of red and brown hematite, with a little oxide of manganese and carbonates of copper. The ores were oxides and carbonates of copper to a depth of about 75 feet vertical from the surface, a mixture of oxidised ores and sulphurets to a depth of 120 feet, and below that depth they were ordinary sulphides of copper. The gossan at the surface was auriferous; assays of it gave from 4 dwt. to 1 oz. 16 dwt. of gold per ton, and also up to as high as 5 oz. of silver per ton.

"The deepest workings were 396 feet. Most of the lode was taken out to a depth of 240 feet for a distance of half a mile.

"From 1862 to 1878, when the original company was wound up, about 100,000 tons of ore, averaging 17 per cent., were smelted at the company's works, the value of which was £1,250,000."

Chillagoe.—Great results were anticipated from these copper-mines when railway communication with the seaboard was established. The lodes, according to Dr. R. L. Jack,[2] late Government Geologist of Queensland, occur as segregations or replacements of mechanically and chemically formed sedimentary rocks, also filling true fissures. The granite and porphyry of the neighbourhood also contain copper lodes. An important feature is the occurrence of silver and gold in the copper ores, which will probably have an important bearing on the metallurgical treatment to be adopted. The proximity of large and easily available water-power in the Barron Falls will, as Dr. Jack points out, prove a potent factor in ensuring commercial success in connection with the latter.

Mount Morgan, Queensland.

The famous Mount Morgan Gold-mine since 1906 has come prominently to the front as a copper producer. The Writer is indebted to the directors and officers of the Mount Morgan Company for facilities and information afforded during inspection of their mine and plant.

Mount Morgan offers a fascinating field for geological investigation and mapping. The oldest strata of the immediate locality are of Permo-Carboniferous age[3]; the youngest—Upper Cretaceous.[3]

The former have been extensively metamorphosed by massive hornblendic granite and quartz felsite intrusives; and by, at least, two later eruptions of andesitic dolerite dykes.[4]

The predominant rock in the vicinity of Mount Morgan is the hornblendic granite, which forms bold ridgy outcrops on the south, south-west, and west

[1] On the Geology and Mineral Deposits of the Country in the vicinity of Clermont. (Fol., Brisbane, 1866
Jack and Etheridge, Geol. and Pal. Queensland, 1892, p. 33.
[2] Bull. Geol. Survey Queensland, 1898, No. 9. [3] R. L. Jack.
[4] T. W. E. David and W. Anderson, Records Geol. Surv. N. S. Wales, II, Pt. 3, 1891, pp. 87–93.

Open Cut, Mt. Morgan.

and is conspicuous on the north-east in railway cuttings and elsewhere. From the main western mass, a narrow dyke-like extension severs the pyritic quartzite (Jack's geyser overflow) between the West works and the Consolidated Mines shaft.

Quartz-felsite bounds the auriferous deposit on the east, and is seen in the river bank in that direction, where it has the appearance of being interbedded with the sedimentaries.

Through the acid intrusives and the altered sedimentary rocks (Gympie[1]) a network of later doleritic dykes penetrate in all directions, and at all angles of inclination, from nearly vertical to approximately horizontal.

It is probable that the older intrusives—quartz-felsite and hornblendic granite—were one of the original inciting causes of the metalliferous impregnation of the Mount Morgan deposit. That the latter was antecedent to the doleritic dykes, so prominent in the workings, is evident from the fact that a large block of the auriferous stone is engulfed in one of them.

David and Anderson, from petrographical examination of rock sections, regarded the doleritic dykes as probably of two ages; a prediction subsequently verified in the open-cut workings, where displacement of some dykes by others is exposed.

Though the intersecting dykes antedate the metalliferous deposit, it is highly probable that they, or rather their solfataric agencies, exerted an important influence on its silicification, kaolinisation, and subsequent enrichment. The phenomenal richness of the upper zone, however, was unquestionably due to decomposition, or oxidation, of the auriferous pyrites brought about by ordinary atmospheric agents, and subsequent leaching and redeposition of the gold in concentrated bulk by chemical action and interaction.

All gradations are visible, from the leached cellular silica (sinter of Jack) to the massive silico-pyritic ore of the lower levels; likewise all stages of the process of decomposition and removal of the investing sulphides.

It would appear from the aforegoing that the original mineralisation is of considerable age; the secondary silicification of intermediate, and the extraordinary superficial gold enrichment, comparatively recent and progressive.

The mode of occurrence of the copper is entirely in harmony with the gradation of the gold. Entirely removed from the leached cap, partially removed beneath it, and enriched by redeposition at a lower level.

If the genesis of the deposit be approximately indicated, gradual depreciation in values will be coincident with depth until the primitive zone of deposition is reached; the mining limit being the commercial.

Judging by analogy, it is probable that a zone is reached in copper lodes where values, though low, are fairly constant. Mount Morgan ore—as a smelting proposition—is decidedly silicious, but its gold values are high, which enables a considerable amount of barren ironstone and limestone flux being used at present. Utilisation of profitable pyritic flux from Many Peaks, near Gladstone, will, however, immensely increase the commercial working limit.[2]

Mount Morgan lodestuff is naturally divisible into three classes, which are treated separately:—

1. Oxidised, non-cupriferous ore—free milling. Above 300-feet level.
2. Slightly cupriferous pyritic ore—roasting and leaching. Between 300 and 650 feet level.
3. Cupriferous pyrites—smelting. Below 650-feet level.

[1] R. L. Jack. [2] Composition: copper, 2·67; silica, 6·16; iron, 39·9; sulphur, 35·0; carbonate of lime, 5·8; alumina, 3·54 per cent.

The first offers no special features in connection with the present work, inasmuch as its original copper contents have been entirely removed by natural processes of decomposition and leaching, the gold contents being recoverable by ordinary milling and chlorination.

The second, revealing partial impoverishment, and the third, enrichment, are of special interest.

The second, or slightly cupriferous ore, containing about 1 per cent. of copper, is treated in a separate plant—the Mundic. After grinding in ball mills, with screens of 400 holes to the inch, it is roasted in reverberatory furnaces. From the latter it passes to hoppers, from which it is charged into vats of large capacity—several holding 1,000 tons. Here it is first washed with a weak solution of sulphuric acid (waste liquor from cementation canals) to dissolve out the bulk of the copper, the cupriferous solution passing again to the cementation canals. The roasted and washed ore in the vats is treated with chlorine solution for gold recovery, a little more copper being dissolved in this process. The solution, after removal of the gold by precipitating on charcoal filters, is passed through copper-precipitating canals, brought up to proper chlorine strength, and again circulated.

The copper ore remaining in the tailings in the insoluble form of oxide gradually decomposes on exposure, and yields eventually to percolating acid solutions; these are collected in a filter dam and pumped to the precipitating canals. Throughout the entire process the acid solutions are in constant circulation.

The cement copper, amounting to about 50 tons of pure copper per month, is sieved, dried, packed in barrels, and sent to America.

The third, or direct smelting ore, has about the following average composition :—

Silica	43·5 per cent.	Gold, about 8 dwt. per ton.
Iron	23·5 ,,	
Sulphur	23·0 ,,	
Alumina	2·5 ,,	
Copper	3·8 ,,	
	96·3 ,,	

The balance being moisture and undetermined.

The ore is fluxed with limestone, iron ore, and converter slag in the following proportions :—

Auro-cupriferous pyrites	100 lb.	Weight of charge, 31 cwt.
Limestone	60 ,,	
Ironstone	20 ,,	
Converter slag	10 ,,	
Coke	8 ,,	

The limestone is brought by rail from the Mount Morgan Company's quarries at Marmor, and has the following composition :—

Carbonate of calcium	96·5
Silica	3·5
	100·00

The ironstone from the Company's mine at Iron Island, consisting of magnetite and hematite, has the following composition :—

Iron	63·0 per cent. = 81·0 FeO.
Silica	5·0 ,,

The coke contains about 15 per cent. of ash.

Instead of barren flux, it is hoped ere long to use Many Peak cupriferous pyrites, containing about 2½ per cent. of copper.

Blast Furnaces, Mt. Morgan.



The smelting plant consists of four blast-furnaces, of a capacity of about 200 tons of ore each per day. Three only, however, are kept in constant use, one being for emergency.

The matte runs about 45 per cent. in one operation. The slag runs about —silica 39, ferrous oxide 32, and lime 23·5 per cent.

The converter plant consists of nine shells of 3½ tons capacity each. The converter vessels are 8 feet by 6 feet diameter, and electrically operated.

Linings are renewed after six charges, the material being prepared of ore from the open cut, containing 88 per cent. of silica and 3½ dwt. of gold, and silicious shale from the Desert Sandstone Series (Jack) which cap the ranges in the vicinity.

Excellent fire-bricks are also manufactured from the latter, which contains about 86 per cent. of silica.

The Blister copper runs about 99·2 per cent. copper, and contains about 12 oz. of gold per ton and 2½ oz. silver.

The furnaces have circular fore-hearths 14 feet in diameter (outside measurement), and small auxiliary fore-hearths.

Double-bowl slag cars are used, each holding 1 ton.

Owing at present to insufficient elevation, the matte is conveyed in roller-bearing matte-pots by manual labour to ladle, which, when filled, is hoisted by travelling crane to converters.

The ore-bins at smelting-house consist of four rows, each containing sixteen bins; the capacity of each bin being 160 tons ore, 120 tons limestone, 320 tons ironstone, or 60 tons coke, according to the nature of the material stowed.

Total Production of Copper.

Year ended 31st May.	Yield of Copper Precipitate.	Proceeds from Copper Precipitate.	Ore Smelted.	Yield of Blister Copper.	Containing—		Proceeds from Blister Copper.
					Copper.	Gold.	
	tons.	£ s. d.	tons.	tons.	tons.	oz.	£
1902.....	25	57 7 10	.....	.....	.....	.....	.....
1903.....	106	2,672 14 0	.....	.....	.....	.....	.....
1904.....	*344	15,484 13 8	.....	.....	.....	.....	.....
1905.....	†501	25,751 11 7	.....	.....	.....	.....	.....
1906.....	389	16,375 14 8	22,153	182	179	2,700	25,500
1907.....	470	39,068 7 9	123,135	3,757	3,723	47,215	479,500
1908.....	496	17,616 10 10	163,078	5,167	5,120	67,497	532,854
	2,331	117,027 0 4	308,366	9,106	9,022	117,412	1,037,854

* This includes 157 tons of Matte, which realised £9,084 12s. 5d.

† „ „ 326 „ „ „ „ £16,713 7s. 5d.

The following table shows the total quantity of ore chlorinated and smelted in each year since the formation of the Company in July, 1886; the total yield of gold bullion, and the proceeds of gold and copper, the expenditure, and the amount of dividends paid. The yield of auriferous blister copper and of copper precipitate is shown in the preceding table:—

Year ended 31st May.	Ore Chlorinated.	Yield of Gold.	Proceeds from Gold.	Total Proceeds.*	Expenditure.	Total Dividends Paid.
	tons.	oz. dwt.	£ s. d.	£ s. d.	£ s. d.	£ s. d.
1887.....	13,071	58,027 5	238,547 3 11	238,547 3 11	80,531 17 11	133,333 6 8
1888.....	17,241	90,623 16	374,082 18 6	374,082 18 6	156,686 0 5	200,000 0 0
1889.....	49,276	235,190 15	966,447 12 9	966,447 12 9	195,086 9 3	800,000 0 0
1890.....	76,215	258,949 18	1,066,705 6 1	1,066,705 6 1	205,287 18 8	866,666 13 4
1891.....	74,741	201,582 8	828,973 13 5	828,973 13 5	209,451 18 10	600,000 0 0
1892.....	59,789	124,296 12	504,205 8 7	504,205 8 7	188,558 2 2	300,000 0 0
1893.....	62,190	119,909 13	495,535 11 5	495,535 11 5	187,039 17 11	360,000 0 0
1894.....	65,076	118,630 14	489,001 0 10	489,001 0 10	177,288 6 6	300,000 0 0
1895.....	82,448	123,803 18	513,230 1 6	513,230 1 6	163,328 16 5	300,000 0 0
1896.....	91,597	141,148 17	578,677 12 3	578,677 12 3	239,290 3 9	300,000 0 0
1897.....	105,244	159,817 6	656,780 9 11	656,780 9 11	302,160 4 7	300,000 0 0
1898.....	153,297	172,029 6	698,172 2 6	698,172 2 6	307,083 7 7	300,000 0 0
1899.....	204,502	164,909 18	664,143 8 4	664,143 8 4	370,496 0 11	350,000 0 0
1900.....	239,276	187,352 10	748,918 19 3	748,918 19 3	356,090 8 3	350,000 0 0
1901.....	215,461	173,833 0	693,273 2 6	693,273 2 6	236,718 19 10	350,000 0 0
1902.....	213,907	147,628 4	570,337 4 6	570,394 12 4	290,560 13 6	204,166 13 4
1903.....	233,568	143,584 3	566,400 19 11	569,073 13 11	317,307 18 7	275,000 0 0
1904.....	237,461	122,251 18	467,427 19 1	482,912 12 9	326,520 6 8	150,000 0 0
1905.....	240,913	137,894 18	518,115 2 4	543,866 13 11	396,840 14 4	150,000 0 0
1906.....	248,946	125,694 9	482,801 1 5	524,676 16 1	379,280 7 0	150,000 0 0
1907.....	235,839	103,464 17	413,552 14 1	932,121 1 10	558,120 14 8	162,500 0 0
1908.....	241,239	89,611 17	359,838 2 8	910,308 13 6	631,588 18 10	237,500 0 0
Grand Totals	3,162,297	3,200,026 4	12,895,167 15 9	14,050,048 16 1	6,432,368 6 7	7,079,166 13 4
					13,889 3 3	Less Refunds Sundry Accounts.
					6,418,479 3 4	
		Cash for Sundries		8,452 14 3	244,992 16 2	Add Dividend Duty and Income Tax.
					84,764 12 0	Add Royalty.
					73,593 17 11	Add Depreciation.
				14,058,502 10 4	6,821,830 9 5	

* Includes value of copper, *vide* preceding table.

Tasmania.

Mount Lyell Mine.—The following notes are extracted from a report made by Dr. E. D. Peters, jun., on the property of the Mount Lyell Mining and Railway Company (Ltd.) in 1893.

Dr. Peters' theory of the formation of the immense pyrites deposit of Mount Lyell is that the pyrites particles containing valuable metals, originally sparingly distributed through the older Silurian stratified rocks, gradually decomposed, and were carried away in solution by waters flowing into a lagoon or bog-hole. In contact with the organic acids always present in swampy waters, the metals were precipitated in the state that they were originally in the rock, but in a massive, concentrated form. In time the pyrites filled the swamp-hole, and gradually became covered to a depth of hundreds of feet by the pebbles, sand, and mud forming the new overlying conglomerates, slates, and schists. Subsequently the whole series became elevated and tilted into its present position.

According to this theory, the present width (300 feet) of the lode represents the depth of the original swamp-hole, and the direction of the present depth its longitudinal extension.

Mount Lyell is specially favoured by an abundant and easily-available water-power. Though the lode is a low-grade proposition, viewed as a whole, yet exceedingly rich bunches of ore occur, particularly closely adjacent to the mass of ironstone (resulting from decomposition of pyrites) on the foot-wall side, yielding over 1,000 oz. of silver per ton and 20 per cent. of copper. The width of the lode at the time of the report was 300 feet, and the walls were diverging. Its length, so far traced, is 960 feet. The composition of the average ore, according to Dr. Peters, is as follows :—

Iron pyrites	83	per cent.
Copper pyrites	14	,,
Heavy spar	2	,,
Silica	1	,,
	100	,,

The average contents in valuable metals being :—

Copper	4·5 per cent.
Silver	3 oz. per ton.
Gold	2·5 dwt. per ton.

The freedom of the ore from silica is most remarkable. It contains from 45 to 50 per cent. of sulphur (33 per cent. is sufficient for pyritic smelting); 20 per cent. of quartzose flux is required for blast-furnace treatment.

Pyritic smelting was adopted at Mount Lyell, and soon the original breaking and roasting portion of the metallurgical scheme was abandoned, the ore being so suitable for the pyritic process that no preliminary treatment is found necessary. Just as it comes from the faces it is fed into the furnaces with about 1¼ per cent. of carbonaceous fuel. The almost pure pyritic smelting now in progress is largely quoted by Dr. Peters from data supplied by the General Manager, Mr. R. C. Sticht.[1]

Mount Lyell has been most recently described by Professor J. W. Gregory, F.R.S. From his work[2] the following extracts are taken :—

Page 85.—"The ore deposits of Mount Lyell consist of two types—(1) Mineralised bands of schist, and (2) great lens-shaped masses of very pure sulphide ores. Bands of pyritiferous quartzite also occur in the conglomerate series, and may be regarded as of similar origin to the bands of mineralised schist, but only the latter contain sufficient ore to be of any economic importance.

"The minerals which occur in the bands of mineralised schist are chiefly iron pyrites and fahlore, associated with copper pyrites and bornite. These minerals are in places loosely disseminated through the ordinary schist; elsewhere they occur in the silicious schists, forming acid copper ores, and some bands of low-grade material that has hitherto only proved of value as a flux in smelting the pure pyritic ores of the great ore bodies."

Page 90.—"The great masses of sulphide ores are the source of the wealth of the Mount Lyell field. There are two main ore bodies. The largest is that of the Mount Lyell Mining and Railway Company, known as the "Big Mine," or "Parent Mine," and as the "Iron Blow." . . . . The ore body trends N.W. by W., and its length on the surface was 800 feet, and its width 200 feet. It is worked by an open cut in a series of nine terraces or benches.

"It is irregularly boat-shaped in form, consisting of an elliptical mass, which tapers gradually downward, and is then cut off below with a rounded base." (At a depth of about 700 feet.)

"The ores in this body are of remarkable purity and uniformity. Peters remarked that in a width of 300 feet across the mass 'in the entire distance, there is not a piece of gangue rock as large as a walnut' (p. 10). The ores

[1] Principles of Copper-smelting, 1907.
[2] The Mt. Lyell Mining Field, Tasmania.—Austr. Inst. Mining Engineers, 1905.

consist almost entirely of iron pyrites, containing copper, gold, and silver. There is a little galena and less sphalerite (zinc-blende). The only two important minerals forming gangue are quartz and barite.

"The average composition of the ore which it pays to extract is:—

Iron	40·30
Silica	4·42
Barium sulphate	2·50
Copper	2·35
Alumina	2·04
Sulphur	46·50

"The mine is by no means equally rich throughout, for the ore on the hanging-wall side contains less copper and precious metals than on the eastern or footwall side, and the ore is also, as a rule, richer near the surface than at the deeper levels.

"Some masses of rich ore occur in the ore mass, but most of them have already been removed by underground excavation. These ores are silicious, and the copper-bearing minerals they contain are bornite and chalcopyrite. The average analysis of these ores is as follows:—

Iron	24·75
Silica	30·69
Barium sulphate	1·48
Copper	5·33
Alumina	6·30
Sulphur	30·00

Page 98.—"More important shoots of the richer ores have been found on the footwall side of the mine. The largest, known as the Mount Lyell Bonanza, was discovered, and worked out in 1894; it yielded 850 tons of ore, which was sent to London and sold for £105,000. . . . It consisted of a vein of copper glance (redruthite, Cu_2S) and bornite, with fahlore and argentite (silver glance Ag_2S). The entire shipment averaged 1,011 oz. of silver per ton."

Page 101.—"Actual work has proved that the average of the ore used up to the end of September, 1902 = 1,320,134 tons smelted—yielded an assay value of copper, 2·92 per cent., silver, 2·74 oz., and gold, 1·94 dwt. per ton."

The silicious flux ore from the Royal Tharsis Mine is given as:—

Copper	1·68 per cent.
Silver	·24 oz. per ton.
Gold	·026 „ „

The Mount Lyell Mine was subsequently amalgamated with the North Mount Lyell, Lyell Tharsis, South Tharsis, and Royal Tharsis Mines, worked by the Mount Lyell Mining and Railway Company, incorporated 11th August, 1903.

The magnitude of this Company's operations may be seen from the following extracts from its report for the half-year ending 31st March, 1908:—

"The average assay value of the half-year's output from the Mount Lyell Mine—139,691 tons—was:—

Copper	0·87 per cent.
Silver	1·90 oz. } per ton.
Gold	0·069 oz. }

"From the North Mount Lyell, the assay value of the output of 63,250 tons was:—

Copper	5·94 per cent.
Silver	1·49 oz. } per ton.
Gold	0·004 oz. }

"Composition of North Mount Lyell, Lyell Tharsis, and South Tharsis, metal-bearing fluxes:—

Copper	1·21 per cent.
Silver	0·33 oz. } per ton.
Gold	trace }

The Mount Lyell ore was raised from the open cut, and no new developments in depth were proved. In the North Mount Lyell, however, the ore bodies at 850-feet level were traced down to the 1,000 feet.

Ore Reserves.—The reserves estimated as available in the above two mines at the end of March, 1908, are as follows :—

	Tons.	Copper.	Assay. Silver.	Gold.
		per cent.	oz.	oz.
Mount Lyell Mine—				
Available for open-cut excavation.....	909,471	0·60	1·93	0·043
,, underground ,, ...	2,613,945	0·52	1·97	0·025
Total	3,523,416	0·54	1·96	0·030
North Mount Lyell Mine (including Lyell Tharsis Mine).....	606,658	5·75	1·33	0·005

Smelting results since 10th August, 1903, are as follows :—

	Treated Dry Weight.	Average Assay.		
		Copper.	Silver.	Gold.
	tons.	per cent.	oz.	oz.
Mount Lyell Mine—aggregate	1,329,091	0·92	1·90	0·071
North Mount Lyell (including Lyell Tharsis)—aggregate.....	518,104	6·06	1·76	0·005
South Tharsis, Royal Tharsis, North Mount Lyell, Lyell Tharsis (Siliceous metal-bearing fluxes.) aggregate	56,052	1·49	0·39	0·0018

	Matte treated.	Blister Copper produced.	Average Assay.		
			Copper.	Silver.	Gold.
	tons.	tons.	per cent.	per ton. oz.	per ton. oz.
Products—					
Since 10th August, 1903	111,580	38,927	98·79	87·36	2·628

	Copper.	Silver.	Gold.
	tons.	oz.	oz.
Total Metal Output—			
Produced by former Mount Lyell Mining and Railway Company, Ltd.	48,577	4,121,401	155,752
Produced by present Company from 11th August, 1903, to 31st March, 1908.....	38,457	3,400,840	102,304
*Total Output	87,034	7,522,241	258,056

* These figures do not include the output from the North Mount Lyell Mine prior to 11th August, 1903, such not being obtainable.

Dividends and Bonuses.—Former Company paid £996,574 9s. 8d. ; present Company, from 11th August, 1903, to 31st March, 1908, £1,020,000 ; total dividends and bonuses, £2,016,574 9s. 8d.

Smelting Plant.—Six furnaces running, four on full time ; number of men employed—Mines, 800 ; reduction works, 875 ; railway, 170 ; total, 1,845.

Working costs per ton of ore treated, half-year ending 31st March, 1908 :—Mining, 6s. 4·35d. ; smelting, 7s. 9·60d. ; Bessemerizing, 1s. 2·44d. ; total, 15s. 4·39d.

Mansfeld Copper Deposit, Harz, Germany.

According to the authority quoted by J. A. Phillips and H. Louis[1]—"Der Kupfershieferbergbau und der Hüttenbetrieb zur Vararbeitung der gewonnen Minern 1881,"—mining was commenced in the County of Mansfeld, on the southern declivity of the Harz, in the year 1199, and has, with but little interruption, continued flourishing up to the present time.

"In 1852 the various companies interested were consolidated into one (the Mansfelder Kupferschieferbauende Gewerkschaft) for working the Mansfeld copper schist, which produces annually about 15,000 tons of copper, together with 75 tons of silver, and affords employment to nearly 13,000 miners. This was the first place where steam-power was applied to mining, in 1785, a Watts fire-engine being imported from England to keep down the water by driving the pumps in place of horse-power."

The strata of the Mansfeld copper district "form a comparatively regular basin, round the edge of which the copper schist crops out for the greater part of its circumference; its width is about 11 miles and its area about 193 square miles. Most of the present workings are restricted to the northern and western sides of the basin, where the copper schist occurs with a flat dip of from 5° to 8° over a length of about 14 miles."

"The bituminous marl constituting the copper schist, or copper shale, lies everywhere with the greatest regularity on the *Rothliegendes* [the formation forming the base of the Kupferschiefer or copper schist.—J.E.C.], so that it can be followed as a thin black band. [About 19 inches in thickness.—J.E.C.]

"The metalliferous contents of the Kupferschiefer seam occur, as a rule, in the form of *Speise*—that is, sprinkled in the form of a very fine dust, which, on a transverse fracture, causes a metallic reflection in sunlight. It has either a golden colour from the presence of copper pyrites in predominant quantity, or a violet, blue, and copper-red colour from the presence of erubescite; more rarely the colour is steel-grey from copper glance, or greyish-yellow from iron pyrites, and finally sometimes bluish-grey from the presence of galena. Although the speise principally consists of sulphuretted ores of copper, there also occur, in greater or less quantities not visible to the eye, sulphide of silver, blende, galena, iron and copper pyrites, copper nickel, and arsenical cobalt, as well as compounds of manganese, molybdenum, and selenium; oxidised compounds and salts also occur as secondary products.

"The term *Flotz* (seam) is usually applied to the productive bed only, the thickness of which varies from 2½ to 5 inches."

The roof being softer than the floor is removed to a height of 16 to 22 inches, sufficient only to allow of the width of the workman's shoulders as they work reclining.

The following analysis of the copper shale in 1879 is taken from the work quoted for comparison with that given by Professor David from the cupriferous shales of the Triassic Series of this State:—

Analysis of the Mansfeld Kupferschiefer (average from three shafts).

Silica	33·59
Alumina	13·53
Lime	12·66
Magnesia	2·70
Carbonic acid	8·97
Iron	2·69
Copper	2·59
Silver	0·017
Sulphur	3·43
Bitumen by loss	13·91

The Kupferschiefer of the Mansfeld District contains on an average from 2 to 3 per cent. of copper, with about 10 lb. of silver to the ton of copper.

(Zinc, lead, manganese, nickel, and cobalt not quantitatively estimated.)

[1] J. A. Phillips and H. Louis. A Treatise on Ore Deposits, 1896, pp. 395–404.

Spain.

Rio Tinto and Tharsis Pyrites Deposits.—The following description of the Rio Tinto Deposits, by J. A. Phillips and Henry Louis,[1] applies closely to both mines:—"These deposits of cupriferous pyrites consist of a series of more or less continuous lenticular masses running parallel with the bedding of the enclosing slate, sometimes extending to a great length, occasionally having a width exceeding 50 fathoms, and composed of an intimate admixture of iron pyrites with a little copper pyrites, through which strings of the latter mineral sometimes ramify. Small strings of black sulphide of copper less frequently traverse the mass.

"The deposits are developed in the immediate neighbourhood of a series of dykes of porphyry that traverse the stratified rocks, and with the presence of which that of the deposits is evidently very closely connected.

"The Rio Tinto Company's property is situated in the Province of Huelva, in the south of Spain. The amount of ore extracted in 1907 reached 1,906,948 tons, averaging 2·81 per cent. of copper. The Company possesses immense deposits of low-grade pyrites, and it is estimated that at the present rate of production—as above—it has seventy years output in sight.

"About 200,000 tons only can be calcined at the mines annually under the terms of concession. About 550,000 tons are exported; the remainder is thrown on the reserve heaps, where it is spread over a large surface and drenched with water. This and the rainfall leaches out the soluble copper sulphate produced by oxidation or decomposition of the pyrites. The cupriferous solution is collected in pools and the copper precipitated with scrap-iron."

"Wet Methods of Extracting Copper at Rio Tinto, Spain."[2]

"By Charles H. Jones, Santiago de Cuba.

"The ore treated at Rio Tinto is a massive iron pyrites containing up to 3 per cent. of copper, which has been disseminated through the mass by a secondary enrichment.

"The well-known method adopted for the extraction of the copper consists simply in allowing huge heaps of the mineral to oxidise under the influence of moisture and air, and subsequently washing out the copper sulphate as soon as it is formed, by running water through the heap.

"At the outset it may be well to have it clearly understood that the successful and economical application of this system depends largely on the state in which the copper occurs in the mineral. If it exists as chalcopyrite, $CuFeS_2$, the copper will not oxidise by simple exposure to the air, in one case it having taken many years to oxidise 10 per cent. of the copper originally present in the ore. If the copper is in the form of CuS, the oxidation proceeds very slowly. The best form for solution is Cu_2S, or copper glance, which constitutes the bulk of the copper in Rio Tinto pyrites. These statements may be made clearer from the following account of the reactions that take place during the oxidation.

"When the mineral is exposed to free access of air and moisture, some ferrous sulphate is formed in accordance with the following reaction:—

(1) $FeS_2 + 7O + H_2O = FeSO_4 + H_2SO_4$.

This ferrous sulphate becomes readily oxidised by the air to ferric sulphate.

(2) $2\ FeSO_4 + H_2SO_4 + O = Fe_2(SO_4)_3 + H_2O$,

---

[1] A Treatise on Ore Deposits, 1896, pp. 499–500.
[2] Trans. Amalgamated Inst. Mining Engineers, XXXV, 1905, pp. 8–11.

and it is due to the action of this ferric sulphate on the copper sulphides that the copper is rendered soluble, as is shown by the following chemical equations :—

(3) $Fe_2(SO_4)_3 + Cu_2S = CuSO_4 + 2FeSO_4 + CuS$.

(4) $Fe_2(SO_4)_3 + CuS + 30 + H_2O = CuSO_4 + 2FeSO_4 + H_2SO_4$.

The reaction No. 3 takes place fairly rapidly and causes half the copper to go into solution within a few months, while the reaction No. 4 proceeds much more slowly, and requires, under the most favourable conditions, about two years to extract 80 per cent. of the remaining half of the copper.

" Here I may add that in the laboratory at Rio Tinto (under the direction of Mr. W. A. Jenkin), a method has been worked out to determine the state of combination of the copper in any particular mineral. This method depends on the action of the mineral on various solutions under constant conditions of dilution and temperature, and, though necessarily somewhat arbitrary, it shows with considerable accuracy the form of sulphide in which the copper exists, and consequently whether the copper can be readily extracted by washing in heaps.

" In practice the method adopted to bring about the desired oxidation is as follows : A site is chosen for the formation of the heap where the ground is sufficiently concave and sloping to enable the copper liquor that is formed to collect and run out at the base of the heap. On the ground is first arranged a network of air-flues, made of rough stones and having an internal diameter of 12 inches. Vertical chimneys, 50 feet distant from one another, are built in the same manner and connect with the ground-flues. Care is taken that the mouths of the ground-flues are kept open and not covered by the ore. The mineral, the lump portion of which has been passed through jaw-breakers to be reduced to pieces not larger than from 2 to 3 inches across, is now tipped from side-tip waggons at the highest part of the selected site over and around the stone-flues. 'Lump' and 'fines' are alternately dumped until the height of the mass at the edge is about 30 feet, the upper surface of the mineral being kept level. A heap of this form approximately contains 100,000 tons of ore.

" As the mineral is added, the building of the stone chimneys keeps pace, in order to have a clear opening to the top of the heap. The surface of the heap is formed into squares by means of ridges of the mineral, the size of these squares depending on the porosity of the heap. The function of these ridges is to enable the water to be run on locally over the surface of the heap in order to insure that all parts are equally washed and that the water does not run through the heap in channels. A system of gutters is also arranged so that the water can be run on to all part of the mass. As the heap is being formed water is run on, and the copper sulphate existing in the mineral is extracted ; the water also provides the moisture necessary for the oxidation in accordance with the equations given above. The mineral in the heap is then allowed to oxidize, which it does pretty rapidly, as evidenced by the heat produced, the temperature in the chimneys rising to from 170 degrees to 180 degrees F. As the temperature increases, the surface openings of the chimneys may be closed in order to allow the oxidation to spread through the heap. The surface gradually shows a brownish colouration due to the dehydration of the buff-coloured basic ferric salt that forms on the top of the mass, and its gradual heating-up may be noted by this drying action. The greatest care must be taken not to allow the heap to fire, for a fire once started is very difficult to extinguish. When the oxidation has proceeded as far as it is safe to allow it, water is run on at the rate of about 50 cubic metres per hour, until the soluble copper is leached out ; the heap is then allowed to reoxidize and the washing is repeated. After about a year has elapsed the surface requires

"retilling," and the squares are rearranged so that the places where the ridges were before are now the middles of the squares; the gutters also are shifted. At the edge of the heap, for a distance of some yards, the mineral, which has become cemented, holds a considerable quantity of copper salts and is dug down into terraces in order that this copper may be extracted by washing. When the copper is reduced to 0·3 per cent. the heap is considered washed, and the mineral, containing 49·5 per cent. of sulphur, is removed and exported as 'washed sulphur-ore,' and utilised for the manufacture of sulphuric acid.

"Successful heap-washing depends on the efficient ventilation of the mass, the trouble usually being a too great excess of 'fines' produced in mining the ore, which cement hard and clog up the air passages.

"The copper liquor, as it runs from the heap, contains some ferric iron in solution, which, as will be shown later, is very objectionable. In order to remove the ferric iron, the liquor is run over a smaller heap of fresh mineral, known as a 'filter bed,' which reduces the ferric iron. This 'bed' is laid inside a reservoir formed by a masonry dam across a small ravine, and the liquor, after percolating through the mineral, remains in contact with it until it is required to be drawn off to the precipitating tanks. When the mineral is fresh, the reduction of the ferric iron takes place rapidly, due to the Cu_2S, as shown by equation 3; but the iron pyrites itself has an effective reduction action on ferric iron in solution according to the following equation:

(5) $7Fe_2(SO_4)_3 + FeS_2 + 8H_2O = 15FeSO_4 + 8H_2SO_4$.

"The principal constituents of the liquor as it enters the cementation tanks are as follows, the figures given representing the grammes per cubic metre or units per million parts:—Copper, 4,000; ferric iron, 1,000; ferrous iron, 20,000; free sulphuric acid, 10,000; and arsenic, 300. The large quantities of ferrous iron and free sulphuric acid present are due to the fact that the waste liquor from the cementation tanks, after the copper has been precipitated ('salida' liquor, as it is called), is pumped back and used for washing the heaps, in addition to fresh water, and consequently these solutions tend to become concentrated. The liquor is then run from the reservoirs at about 300 cubic metres per hour through the precipitation tanks over pig iron, in order to precipitate the copper in the form of so-called 'cement copper' or 'copper precipitate.' These cementation tanks are arranged in series on the slope of a hill, the liquor passing backwards and forwards until it is discharged from the lowest tank of the series free from copper.

"Each series consists of three tanks in parallel, arranged so that the liquor can be divided up and passed along as many tanks as necessary, depending on the quantity of liquor that is being run through and on the varying temperature of the liquor with different seasons; the hotter the solution, which in summer reaches 100 degrees F., the faster the rate of precipitation. Each tank is about 320 feet long, 5·5 feet wide, and 2·25 feet deep, and has a slope varying from 2 per 1,000 in the first series to 11 per 1,000 in the last, the reason for the increase in slope being that as the liquor becomes impoverished in copper, the free acid present is more active in wastefully dissolving the pig-iron—an action which is considerably diminished by increasing the velocity of the liquor by means of the increased slope of the tanks. The tanks themselves are made of 9 inch by 3 inch boards, attached to wooden frames, set in cement, the space between parallel tanks being filled in with stone and cement, constituting a wall supporting the sides of the tanks.

"No metal is used in the construction, hard wooden pegs being employed to attach the boards to the frames. The spaces between the boards are carefully caulked with oakum and pitch, in order to render the tank water-tight. At each end of the tank is an arrangement by which a door can be dropped in and luted so as to cut out that particular tank, and there are also wooden plugs that can be removed, so that the liquor from that tank can be run off, thus allowing for the removal of the precipitated copper. A few old boards are placed on the bottom of the tanks for their protection, and on these are piled up the pigs of iron, which are laid across the tank at the bottom, the next layer being at right-angles to the first, and so on, until the tank is filled; each foot-length of the tank contains about 1 ton of iron. The liquor is allowed to run through the system of tanks, and needs no attention, except to remove the precipitated copper and to add fresh iron. The 'salida' liquor, containing from 15 to 20 grammes of copper per cubic metre, is allowed to run to waste, for the reason that with this copper-content the amount of iron required to precipitate the copper equals the value of the copper recovered. Daily some of the tanks are cleaned out by being closed as described above, the liquor meanwhile passing down the other tanks of the series; the liquor is run off into settling tanks, and copper in suspension being there recovered. All of the iron is removed from the tank and piled on to the dividing wall; at the same time the copper adhering to the iron is knocked off and thrown back into the tank. The dirty looking precipitate is then transferred to the cleaning and concentrating plant, the iron is replaced in the tank, and the liquor again allowed to run through it. This crude precipitate, containing about 70 per cent. of copper, is thrown a little at a time on to a perforated copper plate placed at the head of a long launder or tank, and is washed through the plate by a strong stream of water from a small nozzle. The material that does not pass through the screen consists of leaf-copper and small pieces of iron; this material is thrown into a heap, and afterwards sorted over by girls, who remove the pieces of iron. The precipitate that passes into the launder is repeatedly turned over against the stream of water, and by this simple means a concentration is effected.

"The first few yards of the launder contain a red precipitate known as 'No. 1 precipitate,' containing 94 per cent. of copper and less than 0·3 per cent. of arsenic; following this is 'No. 2 precipitate,' containing 92 per cent. of copper and 5 per cent. of arsenic, while below is the 'No. 3 precipitate'; this is in a state of very fine division, and contains on an average 50 per cent. of copper and 5 per cent. of arsenic. This last-named portion, which carries all the graphite from the pig, contains the bulk of the antimony and bismuth that is also precipitated from the liquors. Classes Nos. 1 and 2 are removed to the drying sheds, and are bagged for shipment to the refinery; the No. 3 precipitate is removed, moistened with acid liquors, made into balls by hand and dried in the sun. These balls become cemented hard and can be readily transferred to the smelter, where they form part of the charge for the blast furnaces and are run down to matte to be subsequently bessemerized, thus effectively removing the arsenic, antimony, and bismuth that they contain.

"The reactions that take place in the cementation tanks are given in equations 6, 7, and 8.

"The first reaction that occurs in the liquor running over metallic iron is the reduction of the ferric sulphate to ferrous sulphate, the final result being in accordance with the equation:—

(6) $Fe_2(SO_4)_3 + Fe = 3FeSO_4$.

This action causes the consumption of the pig-iron without any corresponding yield in copper, and, consequently, should be avoided as far as possible by having all the iron in the ferrous state.

"The second reaction is the precipitation of the metallic copper, brought about by galvanic action. The iron becomes coated with copper, and thus the iron and copper in the acid liquor constitute a galvanic couple with a considerable difference of potential. It is due to the electrolytic action that the copper, and all other metals present that are electro-negative to iron, will be precipitated. The ultimate action of the precipitation may be chemically expressed by the following equation :—

(7) $Fe + CuSO_4 = FeSO_4 + Cu$.

Besides the reactions above mentioned, there is one that causes the liberation of hydrogen, as evidenced by the bubbles of gas that may be observed to arise in the tank liquor. This action, which causes a wasteful consumption of the iron, may be expressed as a final result by the following equation :—

(8) $Fe + H_2SO_4 = FeSO_4 + H_2$.

"These three equations constitute the main reactions that take place in the precipitating tanks.

"While the liquor is fairly strong in copper, the copper is mostly precipitated in a coherent form ; but in the later stages as the liquor becomes impoverished it is precipitated in a powdery state—a condition which is more effective in its galvanic action with the iron, and thus unfortunately causes a larger precipitation of arsenic and other impurities than in the earlier stages. In the later stages, also, the 'solution reaction' of iron in sulphuric acid, as given in reaction No. 8, goes on to a proportionately greater extent than does the precipitation of copper, and, consequently, the cost of pig-iron in precipitating the copper varies inversely as the quantity of copper in the liquor.

"By keeping careful watch on the reduction as far as possible of the ferric iron before the liquor enters the tanks, and by giving it sufficient velocity through the tanks, a strongly acid liquor, such as given above, during a year's working will not consume more than 1·4 units of pig-iron (containing 92 per cent. of iron) to 1 unit of copper precipitated. A valuable check on the iron being consumed can easily be kept by the laboratory by analyzing the liquors before entering and after leaving the tanks, and from these analyses the quantity of iron that is being consumed can be calculated."

United States.

Lake Superior and Montana Copper Deposits.

The Lake Superior copper deposits consist of two lava-flows with interbedded conglomerates. Dr. M. E. Wadsworth, President of the Michigan College of Mines, Houghton, Michigan, states[1] that the copper deposits occur as—

"1. Vein-deposits (fissure veins).
"2. Flow-deposits (melaphyrs or amygdaloids).
"3. Bed-deposits (conglomerates).

"In the veins the copper is found intimately mixed with the gangue, or in sheets or irregular masses. In sheet form the copper extends downward, or has its sides approximately parallel with the vein. Often the vein is divided, and holds between its parts some of the gangue or melaphyr. . . . The

[1] "The Origin and Mode of Occurrence of the Lake Superior Copper Deposits." Trans. American Inst Mining Engineers, 1898, XXVI, pp. 667-696.

melaphyrs themselves are often impregnated with copper adjacent to the veins. Good illustrations of the veins can be seen at the Phœnix, Cliff, Central Copper Falls, and other mines in Keweenaw County.

"In the vicinity of Hancock, Houghton, and Opechee some of the old lavas are mined. As stated before, these old lava-flows which now form melaphyrs (amygdaloids) have been greatly acted upon by water, and have had deposited in their mass different minerals associated with more or less copper. The copper is generally deposited in an irregular manner in the melaphyr, forming strings, globules, irregular masses, &c. These deposits are not in the form of veins, but are impregnations of old lava flows, and hence, are in the form of beds. As an example of mines worked upon these old lava-flows, there may be cited the Quincy, Franklin, Osceola, Atlantic, Huron, and the Copper Falls in part. . . .

"Besides the veins and lava-flows, the conglomerates have also been found in places to have had their interstices filled in with copper and other minerals. In them the old cementing mud, and oftentimes the pebbles of melaphyr, have been removed by percolating waters, and their places filled with copper, which penetrates even the minute cracks in the hard rhyolite (quartz porphyry) pebbles. These old sea-beach conglomerates are now worked in the Calumet and Hecla, the Tamarack, the Allouez, and other mines.

"The conglomerates are known to be old sea-beach deposits, like those that are now forming along the lake or ocean at the present time. This is proved by the rounded and waterworn character of their pebbles and grains; by the observed water-action on the surface of the underlying lava-flow; and by the fact that at their base the conglomerates contain considerable basaltic mud and pebbles derived from the underlying lava, both of which diminish in amount or are entirely wanting as the distance from the underlying trap increases.

"That the copper was deposited from water, with or without electro-chemical action, is shown by the fact of its being found enclosed entirely in minerals known to be formed by water only; also by its enclosing such minerals; by its being found in disconnected or isolated masses in the lavas and elsewhere; and by its greater abundance where there are to be seen the most signs of water-action. Had the copper been deposited by igneous agencies subsequently to the formation of the melaphyr and conglomerates it would have had a channel or line of passage, and would have been continuous along that line, so that all the different masses of copper would have been connected downwards, unless separated by fractures or faults. . . . From the fact that the copper is generally found most abundantly under the heavy lava-flows, and associated with minerals evidently the product of the decomposed lava, it appears probable that the copper was once finely disseminated through the lavas, and has since been concentrated by waters percolating through them. This view is advocated by Müller, Bauermann, Marvine, and myself, while a similar view has been advanced by S. F. Emmons to account for the origin and concentration of the Leadville ore-deposits.

"That the copper ore was deposited after the copper-bearing series was complete, is shown by the fact that it is found in fissures extending across the beds that could only have been produced after the beds were in place; by the fact that the copper was deposited subsequently to the jointing of the lavas, owing to its now being found wrapped around pieces formed by jointing; and by the extension of the copper from one flow down into another as a continuous mass.

"The means by which the copper was concentrated and deposited as native copper, instead of occurring in the form of the usual copper ores, is an interesting and, as yet, unsolved problem. . . . .

"The structure of Keweenaw Point may then be summarised as follows:—A deposit of sandstone overlain by lava-flows mingled with more or less of interbedded conglomerates, and finally overlain by sandstones. Subsequently, these beds suffered longitudinal and cross fracturing and faulting. Later, all were acted upon by percolating waters—both hot and cold—by which the rocks were altered to a greater or less extent, and the copper was concentrated and stored up in the conglomerates, lavas, and veins, in which it is now found."

The greater proportion of the Lake Superior copper comes from the conglomerate beds, which, according to Dr. Peters,[1] in 1893, amounted to 75 per cent. of an output of 85,662,000 lb. (38,241¼ tons). This large proportion comes from an ore chute about 3 miles in length, and penetrated to 8,290 feet in depth, worked by the Calumet and Hecla, Tamarack, and Atlantic Mines. Dividends paid by the first-mentioned mine to the end of 1905, amounted to $92,850,000, equal to over £18,570,000.[2]

The grade of the ore is stated to range from ¾ to 1 per cent. of copper to about 1½ per cent., save in the case of the Calumet and Hecla, whose early richness, 4½ per cent., made it an extraordinary exception.[3] The average contents of the ores now mined at Lake Superior may be placed at about 2·9 per cent. or less. The output has greatly increased of late years; the Calumet and Hecla alone produced 95,100,610 lb. of fine copper in 1905 (according to Stevens, *Ibid.*): equal to 42,455·6 tons.[4]

It must be pointed out with reference to the successful exploitation of these low-grade deposits that the copper of Lake Superior occurs in the metallic state, which obviates the costly processes of roasting and smelting. Simple concentration alone being requisite to prepare the metal for a simple fusion and refining process. The remarkable freedom of the native metal of this region from deleterious impurities renders it naturally of the highest market grade.

Copper Lodes of Butte City, Montana, U.S.

The following description of the occurrence of the Butte lodes is extracted from a paper from Dr. E. D. Peters, junior.[5] The metalliferous area of interest to miners is enclosed within a rectangle of 2½ miles by one mile. The lodes are described as true fissures in granite, in which felspar is limited:—

"The copper lodes usually appear on the surface as wide bands of quartzose rock, much decomposed and heavily stained with oxides of iron. Carbonates and oxides of copper mostly appear only as stains, so that, as will be seen, there being little indication of the immense value below. This surface ore invariably carries silver, generally in a free milling condition, and in most of the larger veins in sufficient quantities to pay for treatment. In fact, nearly all the mines that are now considered distinctly as copper lodes were first treated exclusively as silver properties—assaying from 10 to 60 oz. per ton, and averaging, perhaps, 20 oz. Perhaps the most noticeable feature of the Butte copper veins is their great size and remarkable continuity."

In the ninth edition of his work,[6] Dr. Peters gives the following description of these important lodes:—

"The ore occurs in irregular lodes in the granite, having an east and west strike, and an average dip of some 12 degrees to the south from the vertical,

[1] Modern Copper Smelting, 9th ed., 1893, p. 17. [2] Stevens—Copper Handbook, 1906, p. 309. [3] *Ibid.*, 5th ed., p. 9. [4] *Ibid.*, 9th ed., 1893, p. 17. [5] U.S. Geol. Survey, Mineral Resources, 1883-84, pp. 374-396. [6] Modern Copper Smelting, 1893, pp. 19-21.

though in places this becomes as much as 45 degrees. The distribution of the ore is also very irregular, extensive bodies of the same being frequently found on breaking through what appears to be a well-defined wall. Again, there will be no definite line between the vein and the adjacent country rock. [These features are common also to several New South Wales lodes.—J.E.C.] The ore is usually found in chutes that often extend for several hundred feet along the strike before pinching out. Their depth is frequently even greater than their length, though they are sometimes broken by small faults.

"The veins are rarely banded, and vary in size from a few inches of compact ore up to 100 feet or more, as in the Anaconda Mine. Five or six feet may be regarded as the ordinary width, though a large proportion of the ore raised in Butte comes from stopes of much greater width than this. The gangue rock is usually granular and silicious, but not quartzose.

"The croppings of the copper veins are moderately prominent, and consist of the usual brownish iron-stained quartz that may be found at almost any point in the great American Mountain Chain [Rocky Mountains and Andes.—J.E.C.] from Alaska to Patagonia. Just below the surface, red and yellow oxides of iron appear, carrying high values in silver and gold, but usually low in copper.

"These decomposed ores extend to the water-level, which is reached at a depth of from 40 to 300 feet, depending upon the surface irregularities. At this point begins the zone of rich secondary copper ores that have made Butte famous. The copper minerals of this zone are difficult to determine, as they pass through all gradations from pure chalcocite down to chalcopyrite, bornite being also of very frequent occurrence. Iron pyrites is usually present in considerable amounts.

"Naturally, these rich, secondary ores have fallen off in depth, Ledoux estimating their average decline at 2 per cent. copper per 100 feet. But this diminution lessens as greater depth is gained, and the ore raised from the Butte mines at present, omitting a few bonanza bodies, averages about 6½ per cent. of copper and 5 oz. of silver to the ton of 2,000 lb. (0·017 per cent. silver). There is a loss of some 18 per cent. in concentration, and to this must be added the smelting loss, which will reduce the yield of the great bulk of the Butte ores to 5 per cent. copper and 4 oz. (0·014 per cent.) silver.

"Notwithstanding this great decline in percentage and values (which, to be sure, has resulted partly from the ability to work lower-grade ores to advantage) the Butte mines are making more profit to day from a 6 per cent. ore than formerly from one of double this richness. This results from the consolidation of mining properties, and from the astounding and radical improvements made in the metallurgical treatment of the ore. The rich surface ores of the district have furnished the capital that was needed to design and construct the improved plants, and to gain experience necessary for treating the lower grade ores at a profit."

Below the rich secondary ores of Butte the ordinary yellow sulphide—chalcopyrite—has made its appearance. The grade of the ore sent to the Anaconda Company's smelters in 1898 equalled 4·26 per cent. of copper and 3·48 oz. of silver and 0·01 oz. of gold per ton.[1] For later yields see footnote [2].

The following notes made during a visit of inspection to the Butte mines by the Writer in January, 1894, will perhaps be of interest.

---

[1] Mineral Industry, 1899, VII, p. 209.

[2] In 1905 the averages are given by Stevens as:—copper, 3·25 per cent.; silver, 3 oz., per ton; and gold to the value of $1·75 to $2 per ton.—Copper Handbook, 1906, p. 195.

Montana Ore-producing Company.

Average value of ores about 7 per cent. copper, concentrated through sizing machines and Harz jigs, calcined in O'Hara roasting furnaces, about 3 to 6 per cent. sulphur remaining in roast. Fed in charges of 8,000 lb. into reverberatory furnaces; product—matte containing 55 per cent. copper. Matte bessemerised in converters in 3,000 to 8,000 lb. charges; brought up to 99—99·8 per cent. blister copper in from twenty to eighty minutes.

Butte and Boston Smelting Company.

Best ore from mine sent direct to smelters, other ore concentrated by Harz jigs and Frue vanners, and roasted in O'Hara roasting furnaces in preference to revolving cylindrical furnaces; smelting by water-jacket blast furnace and reverberatories, former preferred. No flux used; one consists of bornite, enargite, and pyrite, containing over 40 per cent. of sulphur. Basic slag formed. Matte sent to Great Falls for further treatment, where water-power is available. Copper refined by electrolysis.

The Parrott Smelting Works, Butte.

Ore, consisting of bornite and pyrite, averages about 4½ per cent. of copper. Part-roasted in stalls; concentrates from Harz jigs and Frue vanners roasted in an improved Spence furnace. No fuel used after first firing, the sulphur in the ore forming the combustible.

The improved roasting plant consists of two furnaces built side by side, each containing six hearths, one above the other; between them is an iron framework with carriers running on rails, each being level with a hearth. The carriers are worked by a hydraulic press and belting on narrow drums. The carriers are fitted with rakes or ploughs extending into each furnace, which, as they travel in one direction, turn the ore on the hearths, and then return and take a fresh horizontal position so as to catch the ore between the furrows made in the previous trip.

The ore is fed from a hopper on to the top hearth, and there dried by the ascending heat. As the ploughs or rakes move to the end of the hearth, they scrape a portion of the ore into an opening, through which it falls on to the second hearth, and so on is transferred to each hearth in succession, meeting in its descent greater heat. The necessary firing is communicated from a small furnace at one end of each roaster. The capacity is stated to be about 50 tons per twenty-four hours, and all work is automatic, the roasted ore being raked by the carriers from the lowest hearths into trucks.

The slag from the smelting furnaces is removed by granulation in a stream of water, which transports it to the slag dumps. When required, the slag is moulded for building purposes; all the walls, floors, stalls, &c., being constructed of this material.

The ore is smelted without flux, being silicious in some parts of the mine, it is mixed so that a slag with about 40 per cent. of silica is obtained. The matte is converted into blister copper (99 per cent.) by Bessemer converters.

The converters—three in number—when first charged, hold perhaps about 1 ton of the molten matte from the cupola furnace; but as the lining is eaten away the charge increases to about 4 tons. Each charge requires about one and a half hours to reduce to metallic copper. After the flame from the converter becomes clear, the slag—iron oxide—is poured off, and the remaining copper subsulphide is further blown upon until the required purity is reached by elimination of the remaining sulphur.

The copper is further treated at Great Falls—electrolytically—for separation of the contained silver (which in the ore averages about 6 oz. per ton).

The converter lining lasts about twelve hours, and consists of a mixture of silica and plastic clay, ground up and mixed together in proportions suited to the different portions of the converters.

All the flue-dust and slimes are smelted in reverberatory furnaces.

Anaconda Copper Mining and Smelting Company's Reducing Works at Anaconda.

The Company possess two large reducing plants of a total capacity of 14,000 tons of copper per month. The Anaconda plant is most advantageously situated to allow of transfer by gravity from the different treating floors. The ore brought by rail from the company's mine at Butte is first crushed by steam stamps of a capacity of 300 tons each per twenty-four hours. The crushed material then passes through a series of Harz and Cullen jigs, of succeeding fineness of gratings or screens. The slimes pass on to circular tables—buddles—about three sets, one below the other, the last stage being to allow the slime water to pass into settling vats, from which the finest and lightest particles are carried over into large settling tanks. When these have settled, the water is drawn off, and the surface of the muddy slimes is covered with about 6 inches of lime, which absorbs sufficient of the moisture to convert the whole into the consistency of mortar, in which state it can be handled readily.

The concentrates are conveyed wet to the roasting house, in which ninety-six Brückner cylindrical revolving furnaces of a capacity of about 16 tons each are in operation. Each charge requires about twenty-four hours to roast, this being done with wood. The calcined ore is then charged into reverberatory furnaces—no blast furnaces being used—the resulting matte is converted into blister copper in Bessemer converters, and about 10 per cent. of the product passed to the electrolytic department, which was not open to inspection.

Copper Mines of Japan.

From "Copper Mines of the World," by Walter Harvey Weed.

The country contains thirty-eight out of the two hundred and fifty greatest copper mines of the world, besides having as many more mines of small production, but considerable extent and value. Three great mines furnish one half of the annual production of 31,000 metric tons, and there are fourteen mines, each producing 1,000,000 lb. or more yearly. As the production of the country is gradually increasing, and two-thirds of the output is exported, Japan is an important factor in the world's copper market. The production comes partly from silver mines, of which the copper is an important by-product, and from copper ores which contain gold and silver values.

The Japanese deposits are of three main types—(1) veins; (2) impregnations or stockworks, in acid volcanic rocks; (3) lenses of cupriferous pyrite in crystalline schists. The three greatest mines of the country represent these three types, to which most, if not all, the lesser producers may be referred. These three, Ashio, Kosaka, and Besshi, will therefore be briefly described.

Ashio.—The Ashio mines are the largest in Japan. They are located 101 miles north-west of Tokio, and 18 miles from Nikko, in middle Japan. The region is one of Palæozoic clay slates and hornstones cut by the intrusive masses of dacite (and rhyolite) in which the veins occur. There are literally hundreds of veins, some thirty of them being worked. These veins form a

co-ordinated system of conjugate fractures, with two main directions, viz., north-east to south-west, and north-west to south-east. Each system consists of veins, in pairs, with opposed dips of 60 to 70 degrees. The veins are not wide, averaging 5 to 6 feet thick, and so far have been worked but 400 feet below the lowest adit. The ore consists of pyrite, chalcopyrite, and quartz, and is relatively high-grade, the smelting ore averaging 15 per cent., though lower-grade ore is also mined and milled. The ore shoots are long, averaging 1,000 feet, and are 6 feet thick. The production was 14,622,500 lb. in 1904.

The veins of other localities, as, for example, those of Ani, belong to the class of quartz veins with predominant carbonates, together with barite and fluorite. The Ozarugawa, Kusakura, and Arakawa deposits are of this class, the veins occurring in tuffs and intrusive bodies of rhyolite and propylitic augite andesites that cut Tertiary beds. The ores consist of pyrite and chalcopyrite with hematite, and lead, zinc, and silver sulphides, besides quartz, calcite, rhodochrosite, and barite. In the Kusakura mine, the proportion of specular hematite increases downward. Similar lodes in Palæozoic strata occur at Yoshioka, Sassagatani, and Dogamaru, being dependent on granite and diorite intrusions near by.

Kosaka.—The Kosaka mine, representing the second type, is situated in a hilly region in the extreme northern end of Japan. It is an old silver mine, formerly supposed to be worked out, but now likely to prove the largest copper deposit in all Japan. The region consists of andesitic rocks, mostly tuffs, cut by intrusive masses of rhyolite. The ore deposit is an impregnation of porous volcanic tuff beds alongside of a rhyolite (or dacite) contact. There is a sharply defined hanging wall, but the ore fades gradually into the foot-wall country. The deposit is of enormous size, being from 100 to 600 feet thick, known for 2,500 feet in extent, and proved by drill-holes to 1,700 feet in depth. In the open cuts the deposit varies from 20 to 140 feet across, the deposit extending with the bedding of the tuffs. The ore consists of chalcopyrite and pyrite, with more or less associated sphalerite, cementing and impregnating a volcanic tuff of varying character, being partly a conglomerate and partly a fine grit or arkose. Three grades are mined:—(a) "black ore," a zinciferous sulphide ore with 2·2 per cent. Cu, 2 oz. per ton of silver, and 65c. gold per ton. This ore carries 12 to 18 per cent. zinc, and from 20 per cent. up to 35 per cent. of barite. (b) The pyritic ore proper; carries but 1·8 per cent. copper, and rarely holds tetrahedrite and galena. (c) Silicious ore, low-grade, but necessary in smelting. The production was 9,500,000 lb. in 1905.

Besshi.—The Besshi mine is located in the great island of Shikoku, near Kyoto, in Southern Japan. The deposit is 3,600 feet above tide, in a mountainous region. The district is one of chloritic and graphitic schists, which near the mines contain bands of piedmontite schist, the whole generally enveloped in quartz-schist.

The deposit—an immense mass 6,000 feet long, 4 to 30 feet thick, and over 1,750 feet deep—is intercalated in crystalline schist, and is often called a bedded deposit. The course of the ore body is north 30 degrees east, and it has been worked for 6,000 feet in length. It is usually 10 to 20 feet thick, and not over 60 feet. The bed dips 45 degrees north-east, and is worked by an inclined shaft.

The ore consists of chalcopyrite streaks in crystalline pyrite, with bands and curved and broken slivers of blackish schist. The ore averages between 3 and 4 per cent. copper. The vein is faulted by east to west step-faults, at 45 degrees to the strike, that dislocates the ore body 10 to 20 feet, and never over 60 feet. The production was 10,425,800 lb. in 1902.

The Kune mine is of the same type, there being three lens-shaped ore bodies in Palæozoic schists, resembling those of Besshi. The upper bed is 6 feet thick, and the middle one 12 feet thick. The largest ore body is the lowest, and is 80 feet thick, 1,000 feet long, and opened to a depth of 400 feet. The production in 1904 was 30,000 tons of 6 per cent. ore. The ore bodies are 60 feet apart, lying one over the other. The dip is 50 degrees north-north-west. The Hibira, Hyuga, and Itsuki pyrite ore bodies are of similar type, but occur in Carboniferous slates, near intrusive bodies of quartz porphyry.

Among the lesser but important copper mines of the country, those of Ani, Ozarugawa, Kusakura, and Ogoya are of interest, as being of the spathic copper type. In the Kusakura mine, the largest of those named, the specular iron increases with depth.

Similar veins, cutting the Palæozoic rocks near plutonic intrusives (granites and diorite), occur at Yoshioka, Sasagatani, and Dogamaru.

The Ozarugawa deposit consists of a breccia of propylitic andesite, a greenstone probably in part, at least, an andesite tuff, with a cement of pyrite, bornite, chalcopyrite, and green quartz. The ore is vuggy, and the quartz in place shows curly structure. In part the ore consists of coarsely massive chalcopyrite, showing cavities left by removal of pyrite, or of finely granular pyrite, with quartz vugs and secondary veinlets. It suggests the Kosaka and Boundary Creek type. The mine belongs to the Mitsu Bishi Company.

The Arakawa ore varies from a mixture of chalcopyrite and bornite, showing post-mineral fractures filled by white quartz veinlets and vugs, to a compact mixture of chalcopyrite and quartz. The country rock is a mottled green brecciated rhyolite and a dense propylitic andesite.

The Makimini deposit consists of finely granular chalcopyrite in lenses in a slaty greenstone and lustrous clay slate, the latter showing interbanded chalcopyrite.

P.S.—Japan produced 42,740 tons of copper in 1906.

AUSTRALIAN Copper Production, 1842 to 1906. Prepared by G. H. Knibbs Commonwealth Statistician.

Year.	New South Wales.	Victoria.	Queensland.	South Australia.	Western Australia.	Tasmania.	Total Commonwealth.
	£	£	£	£	£	£	£
1842 ...	.....	.....	.....	103	.....	.....	10
1843 ...	.....	.....	.....	127	.....	.....	12
1844 ...	.....	.....	.....	4,000	.....	.....	4,00
1845 ...	.....	.....	.....	17,179	.....	.....	17,17
1846 ...	.....	.....	.....	140,794	.....	.....	140,79
1847 ...	.....	.....	.....	171,983	.....	.....	171,98
1848 ...	.....	.....	.....	310,387	.....	.....	310,38
1849 ...	.....	.....	.....	216,819	.....	.....	216,81
1850 ...	.....	.....	.....	353,890	.....	.....	353,89
1851 ...	.....	.....	.....	309,324	.....	.....	309,32
1852 ...	.....	.....	.....	374,778	.....	.....	374,77
1853 ...	.....	.....	.....	176,347	8	.....	176,35
1854 ...	.....	.....	.....	94,706	.....	.....	94,70
1855 ...	.....	.....	.....	151,827	26	.....	151,85
1856 ...	.....	.....	.....	407,665	1,018	.....	408,68

Copper Production of the World.

(*The Engineering and Mining Journal*, 30th March, 190
Statistics compiled by Aron Hirsch and Son, Halberstad

Country.	1904.	190
		Metric
United States	366,522	397
Spain and Portugal	50,000	48
Mexico	52,500	60
Chile	33,000	33
Japan	32,700	31
Germany	24,500	25
Canada	21,500	24
Australia	30,000	35
Peru	7,000	8
Russia	10,700	9
Cape Colony	7,250	9
Norway and Sweden	6,000	6
Italy	3,250	3
Newfoundland	2,000	2
Bolivia	2,000	2
Austria-Hungary, including Servia and Bosnia.	1,500	1
Turkey	1,500	1
Other countries	1,300	1
	652,522	697

Of the increase for 1906 over 1905—the United States (19,866 ton per cent. Australia followed with 20·5 per cent., and Japan third increase.

Of the total estimated world's production of copper between 1 Commonwealth Statistician places the Commonwealth's contribution

Copper Production of the World, collected and estimate Merton & Co., London.

(*The Engineering and Mining Journal*, 2nd May,

Country.	1906.	1907.	Country.	
United States	409,650	395,090	Sweden	
Canada	25,460	25,615	Norway	
Mexico	60,625	56,565	Italy	
Newfoundland	2,295	1,730	England	
Chile	25,745	26,685	Austria	
Peru	8,505	10,575	Hungary	
Bolivia	2,500	2,500	Turkey	
Argentina	105	220	Algeria	
Spain and Portugal	49,320	49,675	Cape of Good Hope	
Germany	20,340	20,490	Japan	
Russia	10,490	15,000	Australasia	
			Total	7

Aron Hirsch and Sohn's estimates of production for the same perio 1907, 706,460. Their estimates of consumption being :—1906, 787,5(

Estimates compiled by the Metallgesellschaft and the Metallu Annual Issue, 1898-1907—March, 1908, p. 5) :—World's production, 1907=712,800 tons. World's consumption, 1906=722,500 tons; 19

6, in English tons (2,240 lb.).

llschaft, A.-G., Frankfort on the Maine.

	Production. tons.	*Consumption* tons.
	408,443	
	.....	295,260
	20,373	
	.....	148,712
	10,581	
	.....	26,180
	2,854	
	.....	18,208
	492	
	.....	105,900
	60,627	
	25,786	
	25,490	
	8,464	
	2,460	
	2,264	
	98	
	.....	2,165
	49,308	
	6,102	
	492	
	394	
	.....	3,936
	42,714	
	36,218	
	6,496	
	394	
	.....	97 558
	1,181	
	197	
	.....	24,310
	.....	64,465
	.....	8,858
	.....	2,362
	711,378	727,914

SONS engaged in connection with production of copper in New South Wales and Commonwealth.

(*Commonwealth Year Book, No.* 1, 1908.)

Year.	New South Wales.	Commonwealth of Australia.
1901	2,964	8,103
1902	1,699	6,478
1903	1,816	7,427
1904	1,850	8,038
1905	2,171	10,500
1906	3,047	13,335
1907	3,764	.....

Descriptive Register of New South Wales Copper Mines and Occurrences arranged in Mining Districts.

ALBERT MINING DISTRICT.

Broken Hill Division.

Alexandra Mine, 1 mile S.E. of Silverton Railway Station, parish Bray, county Yancowinna.

Inspector Carthew reports copper veins in quartz traversing schist, striking N.E. Prospects being encouraging, aid granted to sink 20 feet shaft, a further depth of 60 feet.

Alpine Copper Mine, about 11 miles westerly from Broken Hill, and ½ mile from Red Flag Mine, on parallel vein.

Inspector Milne reported (P.B. $\frac{2\,0\,2\,7}{0\,4}$) veins of copper iron ore in schist, strike N.E.; dip, south-east; channel, about 2 feet wide, containing about 6 inches of ore on footwall.

Aided to continue 43 feet shaft to 93 feet, and to drive 50 feet at bottom. At 93 feet, prospects not as encouraging as at 43 feet. Aided to cross-cut 50 feet; country hard. (No further report.)

Balaclava Iron and Copper Mine, south of Rockwall Paddock, about 10 miles S.S.W. from Broken Hill.—Copper ore was first worked here in 1887 by a company bearing the title of the Balaclava Iron and Copper Company, but operations were not extensive. In 1894, Mr. J. B. Jaquet, Geological Surveyor, reported on the ironstone and copper deposits in the following terms:—"They consist of a series of well-defined parallel lodes, occurring in gneiss and schist. All the lodes dip west at a high angle. One of them, which has a width of 12 feet, can be traced nearly a mile, while others can be traced for several hundred yards. The ore consists of massive hematite, which, on account of its freedom from silica and other impurities, forms a valuable flux for silver-smelting, and large quantities have been used in the smelting works of Broken Hill. The hematite is associated with copper carbonate in some places, and it is possible that the points where the carbonates occur represent the outcrops of shoots of copper ore. No attempt has been made to prove these lodes below 50 feet. In view of the fact that so many of the rich copper deposits in the Australian Colonies and elsewhere are capped by masses of hematite, I would recommend these lodes being prospected to a depth of (say) 200 feet."

In 1896 it was reported that the Wallaroo Copper Mining Company of South Australia was reopening this mine, and had applied for several adjoining leases. The trial was, however, soon abandoned.

NOTES.

(*a*) Unless otherwise specified the assays and analyses herein quoted have all been made in the laboratory of the Department of Mines and Agriculture, under the supervision of Mr. J. C. H. Mingaye, F.C.S., Analyst and Assayer.

(*b*) The registered numbers of assays or analyses are given over the year in which they were made, for example, $\frac{2\,4\,0}{0\,6}$.

(*c*) Official reports quoted will be found in the Annual Reports of the Department of Mines on the pages given under the year of issue, viz., $\frac{1\,8\,9\,4}{p.\ 6\,0}$.

(*d*) The principal copper occurrences can be located in a comparatively small area by reference to the Mining Divisions on the accompanying map. Some discrepancies may, however, occur, owing to difficulty in ascertaining exact location of some minor occurrences.

In 1901, Mr. Jaquet further alluded to this mine as one of the most important copper mines in the district, and described the locality as "a belt of country about 2 miles long, and perhaps 300 feet wide, which includes more or less disconnected masses of ironstone. Beneath the ironstone excellent copper ore has been discovered in places.[1] Tributers are reported to have done well in this mine during the same year.[2]

Barrier Range.—In addition to the Broken Hill line of lode, copper ores occur with silver and silver-lead ores in the following mines in the Barrier Range Silverfield, viz.:—War Dance, Red Flag, Copper Blow, Balaclava, Diamond Jubilee.

Twelve miles N.E. of Mt. Gipps copper ores assayed in 1885 from 25 to 43 per cent. of copper.

From the Princess Midas Mine, Purnamoota, auriferous quartz and copper ores were exhibited at the Melbourne Centennial Exhibition, 1888, and similar lodestuff from the Red Jacket Mine.

Inspector J. Hebbard reported (P.B. $\frac{2}{12}\frac{0}{0}\frac{2}{2}$) on the Barrier Queen Copper Mine, which contains lead and silver in addition. Situated about 12 miles from Broken Hill, on the road to Thackaranga, in an easterly direction from the Pinnacle line. Lode 2 feet thick. Formation patchy. Aid granted for proving.

Mr. Hebbard reported (P.B. $\frac{1}{8}\frac{3}{3}\frac{1}{0}$) on the Augusta Mine- M.L. 101, parish Sentinel, county Yancowinna, 23 miles S.E. of Broken Hill. The following extract has been taken from the report:— "Lode traceable by its outcrop for 1½ miles. Lode material consists of heavily iron-stained quartzite, carrying copper and lead in discernible quantities, and well worthy prospecting. Previous efforts in early days of the field confined to deep vertical shafts without touching the lode."

Aid granted to sink from the bottom of an open quarry following the underlay. The lode hereabouts is 4 feet thick.

Aid was also granted for driving at the 200-foot level in the Nine-mile Claim, 6 miles N.W. of Broken Hill, where a strong lode carrying zinc, lead, and copper ore occurs. The copper ore occurring on the west wall of the lode.

Lady Dorothy (formerly Euro) Mine, 9 miles west of Broken Hill, in schist country. Two thin interbedded veins of copper were tested under aid from the prospecting vote (P.B. $\frac{2}{10}\frac{1}{0}\frac{1}{0}$).

Barrier Silver and Copper Syndicate's Mine, M.Ls. 140, 141, and 146, parish Bray, county Yancowinna, about 3 miles N.E. of Silverton. The following particulars of this property were extracted from a report in 1896 by Mr. Joel Phillips, Manager of Broken Hill Junction and Junction North Silver Mines:—"You have on your claims what appears to be a well-defined copper lode, that has been traced and worked upon in places for the full length of your property. On section 140 a shaft has been put down to a depth of 120 feet following the underlie of the lode from the surface. The bearing of the lode is north 11° 30′ west, with a slight dip to the east. By sinking a few feet below the surface, large boulders of green carbonate of copper were met with, and a quantity of ore was broken and sold to the

[1] Ann. Rept. Dept. Mines for 1901, p. 167. [2] *Ibid.*, p. 99.

English and Australian Copper Company, Port Adelaide. At a depth o about 30 feet the green ore gave place to black and grey ores, intermixe with chalcopyrite and quartz. This class of ore was followed down to th present bottom of the shaft. A little stoping has been done near th bottom, some good parcels of ore having been raised. The lode now standin near the bottom of the shaft I am informed, varies from 2 to 6 feet i thickness of a similar class to the abovementioned. The ore when dresse averages about 30 per cent. of copper. The country rock is decomposed schist."

White Cliffs Division.

Big Wertago Mine, portions 41, 42, parish Wertago, county Yungnulgra.—In 1900 aid granted to sink 100 feet. At 55½ feet Mr. Warden Fletcher reported a fair percentage of copper in lode matter. No walls visible. Ironstone at 60 feet, followed by ore, then ironstone (gossan) to 80 feet. Good ore at 85 feet, then gossan. At 100 feet ore chiefly carbonate and oxide. Driven 10 feet west to foot-wall, and 25 easterly without wall.

Aided to continue shaft to 150 feet. Ore showing at 146 feet. Water coming in. Work suspended.

In 1901 Chief Inspector J. B. Jaquet, reporting on the Big Wertago and adjoining blocks upon the western slopes of the Cootawundy Range,[1] stated:—"We find here a belt of country—conglomerates, sandstones, and quartzites—more or less impregnated with copper carbonates, and including bunches of rich ore. The belt can be traced for at least 5 miles, and copper ore, or country stained with copper carbonates, can be seen outcropping at intervals along its course."

Upon Block 41, one of the blocks owned by the Big Wertago Company, an open cut has been carried for a distance of 50 feet upon an ore body, which has an average width of about 4 feet, and several tons of excellent carbonate ore have been raised. Two shafts have been sunk upon this block to depths of 60 and 154 feet respectively. These shafts encounter bunches or pockets of carbonate ore. Small quarries have been opened upon ore-bodies at many other places along the belt.

In September, 1907, Inspector Sawyer reported that the Main South Shaft had been carried down to 177 feet, and cross-cuts put in east and west. An option over the mine by Messrs. Riechers provides for erection of a small concentrating plant to deal with ore at grass and in sight. The plant to embrace engine, jaw-crusher, roller, shaking screen, May Bros. jigs, and, if necessary, Wilfley tables. Water for mill to be obtained from shaft, estimated as equal to 3,000 gallons inflow daily. A concrete storage reservoir of 10,000 gallons capacity to be built on an elevation overlooking the mill. A large earthen dam has been erected across an adjacent gully.

Broken Hill Division.

Black Lead, about ¾ mile east of White Lead Tank.—Inspector Miln reported (P.B. $\frac{1052}{1}$) a quartz vein impregnated with grains of bornite an chalcopyrite in schist. Formation about 15 feet wide. Copper-bearing vei on hanging wall.

Aided to continue 94 feet shaft, other 175 feet. Prospects reported mor promising at 144 feet. At 191 feet 6 inches occasional small rich bunches c ore met during sinking. (No further work).

[1] Ann. Rept. Dept. Mines for 1901, p. 168.

ALBERT MINING DISTRICT—*continued.*

Birdite Mine.—Portion 10, parish Ophara, county Yancowinna, about 14 miles north-westerly from Cockburn Railway Station. Reported to have been discovered by Thomas Calderwood in 1883.

Inspector Carthew reported quartz with copper veins, thickness 15 feet, strike N. 30° W., dip S. 60° W.; schist country; ores, carbonate and oxide of copper carrying silver.

Maximum length of proving, 40 feet; depth, 80 feet; gross output, about 20 tons, averaging 16 per cent. of copper and 8 oz. of silver per ton.

Aided (P.B. $\frac{1}{0}\frac{5}{7}\frac{9}{2}$) to sink 100 feet following underlay; also to crosscut 100 feet.

White Cliffs Division.

Brady's Proprietary Mine, Wertago.—M.L. 117, parish Wertago, county Yungnulgra.

Chief Inspector Jaquet reported[1] two important lodes in this mine, trending N.E. and S.W. Upon the outcrop of ore an open cut has been carried for a distance of 100 feet, and ore quarried for a width of from 3 to 10 feet.

Rich ore raised from this quarry, and smelted at Wallaroo, yielded:—

4½ tons = 29·5 per cent. copper.
4 tons 18 cwt. = 20·5 per cent. copper.

The parallel lode is well defined, and from 1 to 2 feet wide, and has been traced in trenches for many chains. The outcrop is stained with copper carbonate in places, and from some of the trenches a few tons of excellent ore have been raised. An underlay shaft has been sunk to a depth of 40 feet on the lode, and ore was met with all the way down.

Inspector Godfrey reported (P.B. $\frac{1}{0}\frac{1}{4}\frac{1}{1}$) a well-defined lode, dipping at about 70°, and about 4 feet wide; hanging wall defined, but impregnated with copper ore; no defined foot-wall. Ores consisted of erubescite and carbonates with gypsum.

Aid granted to continue 38 feet shaft other 50 feet, but does not appear to have been availed of.

Broken Hill Division.

Broken Hill Proprietary Silver Mine.—In the famous Broken Hill lode copper ores are disseminated in the form of carbonates, red oxide, and native copper, with other rarer varieties, including a new mineral—Marshite—(iodide of copper).

Copper (in matte) produced since inception of company to 30th November, 1906, amounted to 4,576 tons. None produced in 1907.

Broken Hill District, about 6 miles N. of Purnamoota, and 25 miles N.W. of Broken Hill.—Inspector Milne reported (P.B. $\frac{0}{0}\frac{0}{2}\frac{0}{}$) schist rock with veins of copper carbonate, fairly well defined, and about 9 feet thick.

Aided to sink from 75 feet to 105 feet and to drive 50 feet at bottom.

At 97 feet copper vein continuing, but no improvement visible.

At 101 feet 6 inches prospects only moderate, veins much pinched.

Aided to sink a further 50 feet; at 114 feet nothing payable disclosed.

At 120 feet veins of copper ore in quartz in schistose rock.

Abandoned at 127 feet, small veins in bottom.

Broken Hill District.—M.L. 36, parish of Tara, county Yancowinna, Mt. Darling Creek, about 10 miles easterly from Broken Hill.—Chief Inspector J. B. Jaquet reported (P.B. $\frac{0}{0}\frac{0}{0}\frac{0}{}$) an outcrop well defined cutting across the

[1] Ann. Rept. Dept. Mines for 1901, p. 168.

bedding planes of the schists. Traceable for several chains. Lode consists of gossany ironstone impregnated in places with copper carbonates. No payable ore to 30 feet.

Aided to continue underlay shaft from 30 feet to 80 feet, and to drive 50 feet at bottom.

Inspector Godfrey reported (P.B. $\frac{4}{0}\frac{8}{0}\frac{1}{7}$) that at 67 feet ore consisted chiefly of porous ironstone without copper from 30 to 63 feet in shaft, when stains of green carbonate appeared.

Aided to sink an additional 50 feet instead of driving. At 91 feet prospects about the same as at 63 feet. At 115 feet passed into barren country.

Broken Hill District, about 4 miles N.E. of Acacia Dam, and 12 miles S.W. of Broken Hill.—Inspector Milne reported (P.B. $\frac{4}{0}\frac{4}{4}\frac{1}{7}$) vein of copper ore in schist, consisting of cuprite, black ore, and carbonates. Vein well defined and carrying pockets of rich ore.

Aided to continue 55-foot shaft to 105 feet, and to drive 50 feet at that level.

At 86 feet, a small quartz and ironstone vein which at 103 feet varied from 3 inches to 8 inches in thickness, and carried rich bunches of red oxide.

At 29 feet in drive from 100-foot level, prospects not good. Nothing payable disclosed.

Broken Hill District, about 8 miles southerly from Broken Hill, near the North Pinnacle, parish Alma, county Yancowinna.

Inspector Carthew reported (P.B. $\frac{7}{0}\frac{4}{8}\frac{4}{8}$) a copper lode striking N. 30° W., width 20 feet.

Aid granted to sink from 15 to 65 feet. At 25 feet, lode reported as improving. At 41 feet, lode reported encouraging. At 49 feet, country very hard; more ore than formerly. No further record.

Broken Hill District, 20 miles northerly from Broken Hill, about half a mile west of Yanco Glen Hotel, parish Waukeroo, county Yancowinna, about 2 miles from Tarrawingee tram-line.

Inspector Carthew reported (P.B. $\frac{1}{0}\frac{1}{2}\frac{2}{5}\frac{7}{7}$) a quartz reef carrying copper ore; strike, N. 30° W.

Aid granted to continue centre shaft from 9 feet to 59 feet. At 36 feet two small veins of copper ore showing, not encouraging in appearance. At 50 feet prospects improved; copper vein opened out.

Additional 50 feet of sinking allowed. At 64 feet water struck; lode 3 to 9 inches thick of copper pyrites. Abandoned; water too heavy; capital insufficient.

Broken Hill District, 15 miles due N.E. of Broken Hill, on north side of Mulga Springs Creek, and about three-quarters of a mile N.N.W. of platinum deposit, parish Moorkaie, county Yancowinna.—Inspector Sawyer reported this occurrence, 18/2/07.

Mr. G. W. Card epitomised results of elaborate testing of this ore by Mr. J. C. H. Mingaye, as follows ($\frac{1}{0}\frac{1}{7}\frac{7}{2}$):—

Nickel present	0·3 to 4·3	per cent.
Copper ,, ...	0·7 to 10·8	,,
Cobalt, up to.....	0·2	,,
Platinum, up to	9½	dwt. per ton.
Palladium, up to	16	,,

Iridium in excess of platinum and palladium.

(Ore from the above locality forwarded by A. Figgins, prospector, Broken Hill.)

Albert Mining District—*continued.*

Resemblance to famous Sudbury nickeliferous pyrrhotite of Canada, pointed out by Mr. Mingaye.

Very similar metallic association has been determined in ore from the Walhalla or Thompson's River Copper Mine in Victoria. The following analysis of concentrates from a sample of this ore is by Mr. P. G. W. Baly, A.R.S.M.[1]

Analysis of Concentrates.

Insoluble matter	19·0 per cent.	
Iron	30·0 ,,	
Copper	8·1 ,,	Impossible to isolate indications of gold and platinum.
Nickel	0·7 ,,	
Sulphur	30·4 ,,	
Magnesium carbonate	7·0 ,,	
Calcium carbonate	3·7 ,,	
Cobalt	trace.	
	98·9	

Other assays, by A. E. Glover and C. M. Lyons, yielded the following results from hornblendic rock with chalcopyrite from the above mine :—

	A	B	C		
Gold.....	2 dwt.	12 grs.	12 grs.	1 dwt.	2 dwt. per ton.
Silver ...	18 grs.	8 dwt. 11 grs.	5 dwt. 21 grs.	13 dwt. 7 grs.	1 oz. 2 dwt. per ton.
Platinum	7 dwt. 20 grs.	5 dwt. 18 grs.	2 dwt. 18 grs.	5 dwt.	2 dwt. 14 grs. per ton.
Copper..	6·93%	3·47 %	1·70 %	3·25 %	5·027 %

25 tons of this ore yielded at Cockle Creek,—copper, 6·5 per cent. ; silver, 2 oz. ; and platinum, 2 dwt. per ton.

Broken Hill District, Boomerang Hill, 3 miles S.E. of Mount Hornsby and 30 miles N.E. of Broken Hill, about half a mile north of Broken Dam.—Inspector Sawyer reported (P.B. $\frac{10}{04}$) a quartz reef in this locality carrying copper carbonates and pyrites in schist country. Strike E. and W. Small rich vein of copper ore showing in shaft. Aid granted to sink from 26 to 76 feet. At this level small vein of copper ore showing. No further report.

Broken Hill District, M.L. 119, parish Sebastopol, county Yancowinna, 10 miles west of Broken Hill.—Inspector J. R. Godfrey reported in connection with application for prospecting aid, that a copper lode occurs in this lease in talc schist. At 33 feet a good ironstone vein was going down strongly.

Aided to continue shaft to 100 feet. Progress of developments recorded (P.B. $\frac{33}{}$) are as follow :—At 56½ feet, prospects improving : at 79 feet, lode widening : small patch of malachite near that level ; cut off north-east by cross-course ; at 88 feet, large soft formation encountered on hanging wall, with traces of copper.

Fifty feet of cross-cutting granted ; splashes of copper ore in soft schist and slate met in cross-cut ; no further test ; abandoned.

[1] Bull. Geol. Survey Victoria, 1906, No. 20, pp. 8–10.

ALBERT MINING DISTRICT—*continued.*

McGrath's Copper Lode.—Chief Inspector W. H. J. Slee reported[1] that the ore was visible on the surface in a bunch, 20 feet in length. Five tons sent to Adelaide are reported to have yielded 12 per cent. of copper.

Two miles north of May Bell Mine, Inspector J. R. Godfrey (P.B. $\frac{2}{0}\frac{2}{3}\frac{2}{2}$) described a well-defined copper lode, striking north-east, in schist; about 4 feet wide.

Aided to 58 feet; no record.

Broken Hill District, 1 mile from Fairy Hill, 30 miles north-east of Broken Hill.—Inspector Godfrey reported (P.B. $\frac{4}{0}\frac{6}{4}\frac{3}{}$) copper lode in schist; strike, E.N.E.; dip, E.S.E.; nearly vertical. Ores consisted of quartz with grey ore and carbonates, about 2 feet wide. (1 ton of picked ore yielded 35 per cent. of copper.) Lode described as well-defined between good walls. Aided to sink 80-foot shaft to 130 feet. At 80½ feet, small but rich vein of copper ore, consisting of native copper, cuprite, and grey ore.

At 99½ feet, a bunch of cuprite, copper glance, and pyrites cut.

Fifty feet of driving along lode allowed, a small vein in face of E.N.E. drive. In face of W.S.W. drive 12 inches of quartz; prospects poor.

Fifty feet additional sinking granted, but not availed of.

Broken Hill District, about 2 miles south of Purnamoota-road, in parish Stephen, county Yancowinna.—Inspector Carthew reported (P.B. $\frac{1}{0}\frac{2}{6}\frac{2}{2}$) quartz containing copper; strike, E.N.E.; dip, nearly vertical.

Small vein of copper ore carried down 27 feet in shaft. Though aid was granted to continue to 100 feet, it was not availed of.

Broken Hill District, portion 16, parish Narradin, county Yancowinna.—Inspector Hebbard reported (P.B. $\frac{2}{0}\frac{8}{9}\frac{1}{0}\frac{2}{}$) quartzite with zinc-blende in schist country. Proved for 200 feet in depth, and by drives aggregating 150 feet at 60 feet and 100 feet levels. Examination of results disclosed a strong body of zinc-blende and copper ore.

Broken Hill District, 2 miles south of Pinnacles, in parish Alma, county Yancowinna.—Inspector Carthew reported (P.B. $\frac{2}{0}\frac{0}{3}\frac{1}{3}\frac{2}{}$) a copper vein in quartz and ironstone in this locality, striking E. and W., and dipping north; promising outcrop traceable for a long distance.

Aid granted to sink 20 feet shaft to 70 feet, but was not used as copper was reported to have cut out at a shallow depth.

White Cliffs Division.

Bunker's Hill Mine, M.Ls. 25 and 26, parish Wertago, county Yungnulgra.—Chief Inspector J. B. Jaquet reported[2] that the outcrop of the lode was traceable for nearly half a mile on a N. 30° E. strike. It consists of quartz stained in places with copper carbonates. An open cut has been made along the lode for 100 feet, to a depth of 16 feet. From this two parcels of ore, despatched to Wallaroo, yielded:—

2 tons 7 cwt. = 29·5 per cent. copper.
2 tons 10 cwt. = 23·8 per cent. copper.

About 40 feet from the open cut a vertical shaft has been sunk 100 feet, the bottom being in quartz, with a little copper. The lode has a slight underlay, and shaft does not appear to have reached the foot-wall.

[1] Ann. Rept. Dept. Mines for 1883, p. 126. [2] *Ibid.*, 1901, p. 168.

ALBERT MINING DISTRICT—*continued.*

Bunker's Hill No. 3 Block the same lode is being worked; a large being opened in the outcrop, and a shaft sunk 100 feet.
ector B. Sawyer reported, 10th September, 1907, that the Bunker's aim was worked by Barron and party, and a small output of mixed ates obtained from a new underlay shaft a little to the south of the t vertical shaft. At 40 feet, lode appeared to average 12–18 inches; ore raised during past three years.

Broken Hill Division.

er Blow Mine, 3 miles N.E. from Thackaringa Hotel, near Silverton parish Albert, county Yancowinna.—Inspector Carthew reported) a copper vein in schist. Strike, N. 32° E. Dip, N. 58° W.
d to continue 29-foot shaft a further depth of 50 feet. Whip erected with water.

er King Mine, M.L. 55, parish Tara, county Yancowinna, 10 miles Broken Hill.—Mr. E. F. Pittman, Government Geologist, reported) that country consists of banded quartzites close to mica schist. te stained with copper carbonates for a considerable width; and ppeared to be a lode of somewhat richer material had been exposed in cut dipping westerly towards the shaft. Previous holders had sunk er to 60 feet.
granted to continue to 100 feet, and to cross-cut 50 feet at bottom.
ress: At 91 feet, traces of black ore occasionally, not encouraging. feet in cross-cut, prospects bad. At 50 feet, only specks of ore. urface-show only. Output from shallow openings, about 40 tons of ore, containing 10 per cent. copper.

White Cliffs Division.

er Well Mine, Wertago, M.Ls. 113, 114, parish Wertago, county ulgra.—Chief Inspector J. B. Jaquet reported:—"The lode here is fined, and, as seen in the workings, has an average width of over 2 feet. was sunk, thirty years ago, in search of copper ore, and a good flow r being met with, it was utilised as a well for watering stock Shaft, deep; levels driven at 100 feet for 60 feet south-westerly, and 90 feet. asterly, upon the lode. Excellent carbonate ore can be seen in many both in the floors and backs of the levels. The lode is nearly vertical, ses to west of shaft at 100 feet in depth.
out 500 yards from the shaft northerly, two veins carrying copper en discovered. These veins are respectively 1 foot and 8 inches wide, ed by 7 feet of country. Outcrops traceable for several chains.
o small parcels of ore have been despatched from the mine:—

1 ton 13 cwt. yielded 30·75 per cent. of copper.
1 ,, 1 ,, 28·75 ,, ,,[1]

1906 the Copper Well Mining Company (Limited) was formed, and into possession in September; work being started towards end of Four tons of 25 per cent. ore despatched.
February, 1907, 10 tons of ore from the 100-foot level, assaying 31·25 per cent., were despatched to Adelaide. In March, 10¼ tons £26 per ton net."

[1] Ann. Rept. Dept. Mines for 1901, p. 168.

ALBERT MINING DISTRICT—*continued.*

Inspector B. Sawyer, in September, 1907, reported:—"These leases were lately exploited by a Cobar syndicate, but after carrying a cross-cut, 60 feet to the lode at the 150-foot level of the shaft, and then driving along the lode 30 feet each way, the mine was let on tribute to Grey and Field, who have raised about 10 tons of grey ore containing about 29½ per cent. of copper. The lode in the lower levels is said to be about 10 inches wide, and carries gossany veins impregnated with copper."

Broken Hill Division.

Diamond Jubilee Mine, M.L. 150, parish Robe, county Yancowinna, 23 miles northerly of Silverton.—A company was registered in 1897 to work this property. Shaft sunk 67 feet. A 20-ton trial of the ore reported to have yielded 19 per cent. of copper, and 17 dwt. of gold per ton.

Inspector Hebbard, who examined this occurrence in 1898 (P.B. $\frac{44}{98}$), states that it occurs close to Para Creek, about one mile west of Yuba Silver Mine, in parish Robe, county Yancowinna, and described the locality in the following terms:—"There are evidences of abundance of ore all over the property, but so far it does not seem to make down. The ore deposits have been opened in forty or fifty places on the property, and everywhere have proved copper and gold bearing. Parcels of picked ore have yielded up to 2 oz. of gold per ton, and 24 per cent. of copper, and several tons of this class of ore have been disposed of."

Mr. Hebbard was of opinion that there was a great quantity of ore on the surface that would pay to concentrate.

At a later inspection no defined lode had been proved. A shaft had been sunk 60 feet in one deposit—ore was visible at 20 feet, but none at bottom.

The ore consists of copper-stained, gossany quartzite, and invariably contains gold associated with the copper. Aid granted to further prospect.

Inspector Carthew reported in 1904 (P.B. $\frac{27}{74}$) that three or four parallel veins occur.

White Cliffs Division.

Eclipse Copper Mine, M.Ls. 1 and 117, 80 acres, parish Wertago, county Yungnulgra, 60 miles from Wilcannia.—Reported to have been discovered by E. Barron in 1892.

Strike, N. 60° W.; dip, N. 30° E. in micaceous schists and slates. Width about 4 feet.

Inspector J. Carthew stated that the maximum length of proving in 1906 was 200 feet, and the depth 125 feet.

Inspector B. Sawyer reported in September, 1907, that Blocks 1 and 117 were being worked by Barron and party. Shaft, 140 feet; drive, N.E. along lode extended 50 feet to intersect winze from level above.

At 108-foot level the lode carried good grade copper sulphides up to a maximum width of 2½ feet.

Output during past three years (1905 to 1907) amounted to 200 tons, yielding from 25 to 30 per cent. Appears to be so far the only mine at Wertago producing sulphides.

Blocks 125 and 126 held by the same party furnished 7 tons of ore in 1907, realising £104.[1]

[1] Ann. Rept. Dept. Mines for 1907, p. 51.

ALBERT MINING DISTRICT—*continued.*

Broken Hill Division.

Fairy Hill, M.L. 56, parish Gardner's Creek, county Mootwingee, 34 miles N.W. of Broken Hill, and 2 miles from Fairy Hill.—Inspector J. R. Godfrey reported (P.B. $\frac{2}{0}\frac{0}{2}\frac{2}{2}$) two copper lodes in schist; strike, N.W., dip, N.E. at 70°; separated by 4 feet of mullock. Followed down to 70 feet between well-defined walls containing seams of copper ore. The lode broke into strings at that level. Shaft continued to 100 feet.

Aid was granted in sinking to 62 feet, and for driving 50 feet at 70-foot level. At 22 feet in drive, lode ran about 3 feet wide, with a little copper ore on hanging wall. At 42 feet lode pinched very small. Apparently not followed further.

Nine tons of ore despatched during operations yielded 8½ per cent. of copper.

Federal Copper Mine, about 7 miles north of Silverton, parish Umberumberka, county Yancowinna.—Inspector Hebbard reported (P.B. $\frac{3}{0}\frac{1}{0}\frac{0}{0}$) a quartz lode 2 feet wide containing copper ore, but not in payable proportion. Shaft down 60 feet. Aided to continue to 160 feet.

About 3 tons ore despatched from shaft and drive netted about £9 per ton.

Inspector D. Milne reported (P.B. $\frac{2}{0}\frac{3}{1}\frac{2}{0}$) ironstone and quartz, with small bunches of ore at 161 feet. Aided for further 25 feet of sinking.

At 190 feet ore reported as improving. Aided to drive south along it for 150 feet.

At 20 feet in south drive a 6-inch vein of red oxide in schist encounted, worth 20 per cent. copper. Vein continued at an equal thickness.

Aided to sink from 218 feet to 268 feet.

Inspector J. Carthew reported (P.B. $\frac{2}{0}\frac{4}{4}\frac{5}{0}$) that shaft had been sunk all the way in a "pinch" or narrow part of the lode.

Aided to drive south at 269-foot level.

In driving 42 feet about 3 tons of ore raised. From 250 feet an ore vein 12 inches wide was stoped upwards. Forty-four and a half tons of ore despatched averaged about 19 per cent. of copper.

Florence Mine, one mile west of Silverton, and about one mile east of the Umberumberka Silver Mine, parish Bray, county Yancowinna.—Inspector Carthew reported (P.B. $\frac{2}{0}\frac{3}{7}\frac{3}{0}$) quartz containing copper ore in slate and schist. Strike, N.E.

Aided to sink to 80-foot level, and cross-cut 60 feet from the latter.

At 65 feet a parallel vein was cut through, dipping south. Additional aid for cross-cutting granted. Several small veins of copper met.

Glencoe Mine (also Lady Dorothy), portion 311, parish Stephen, county Yancowinna, about 10 miles north-westerly from Broken Hill.—Inspector D. Milne reported (P.B. $\frac{1}{0}\frac{5}{4}\frac{6}{0}$) a vein of green carbonate of copper about 1 foot 6 inches thick in schist.

Aided to sink No. 2 shaft from 75 feet to 105 feet. At 103 feet patches of good ore exposed, but not in payable quantity.

Also examined by Inspector J. Carthew, who described the lode as quartz containing copper and silver, and striking N.W. Further aid granted to drive 50 feet along the lode at the 105-foot level (P.B. $\frac{1}{0}\frac{1}{4}\frac{1}{7}$).

ALBERT MINING DISTRICT—*continued.*

Mr. E. F. Pittman, Government Geologist, describes the country as hig inclined schistose rocks, with a couple of copper veins interbedded with schists. The veins containing promising ores consisting of carbonate oxide of copper, only a few inches wide (P.B. $\frac{8}{9}\frac{1}{8}\frac{1}{9}^{a}$).

Inspector Carthew again inspected in 1907, and reported the veins of as widening with depth. Hard sinking and increase of water ca abandonment.

White Cliffs Division.

Grassmere Mine.—Inspector B. Sawyer reported in September, 1907, t M.Ls. 1 and 2 of 40 acres forming this property, are situated in pa Daubney, county Yungnulgra, 8 miles from Grassmere Station, and 43 m from White Cliffs, on Euriowie-road. They were then being exploited Messrs. Francis and Dreher. Old shaft, 40 feet deep; lode extensiv opened by surface cuts; strike, E. and W.; lode mostly grey ore; some 2 tons at grass. A trial parcel of 50 tons of about 30 per cent. (according owners), being ready for despatch.

It was further reported that some 500 tons of ore were raised during 19 of which 200 tons were disposed of for an average return of 10 per cent. copper.[1]

Broken Hill Division.

Hampton Copper Mine, about 6 miles easterly from Broken Hill.—Ch Inspector J. B. Jaquet reported[2] that a shoot of rich copper ore, of average width of 8 inches, and a length of 20 feet, had been followed do 85 feet. About 33 tons of ore, assaying 25 per cent. of copper, bei despatched to South Australia.

Hornsby Range, about 22 miles from Broken Hill, and 8 miles from t Tarrawingee tram-line. According to the *Barrier Miner*, of the 13th Jul 1898, a number of copper lodes were being opened at the above locality. first parcel of 10 tons, of about 12 to 15 per cent. ore, had been prepared f shipment.

Invincible Copper Mine, 11 miles S.W. of Broken Hill, and 1 miles from Acacia Railway Siding.—Inspector J. Hebbard report (P.B. $\frac{3}{9}\frac{1}{8}\frac{8}{8}^{a}$) that three shafts have been sunk on the lode, the course which is regular and well-defined, and about 4 feet thick. The richest sho had been worked to a depth of about 60 feet, when the shaft passed throu it. A drive to the south proved the continuance of the lode in that directio though poorer; numerous indications of copper and other ores occur in t vicinity.

Milparinka Division.

Kooningbery Mountains, near Packsaddle and Wonaminta.—The Warde under date 29th July, 1898, stated that a mineral prospecting protection ar was pegged out for copper in this locality. The prospects were fair, but n developmental work had been done on which to base an opinion of th deposit.

Samples, numbered $\frac{3372\text{ to }3374}{98}$, yielded 25 to 40·82 per cent. of copper. They consisted of red oxide and green carbonate.

In 1904, 20 tons of copper ore raised from J. Sullivan's mineral lease a Kooningbery Range, sent to Adelaide for treatment, yielded 15 per cent Shaft down 130 feet in lode; 6 feet wide at bottom.[3]

[1] Ann. Rept. Dept. Mines for 1907, p. 51. [2] *Ibid.*, 1901, p. 167. [3] *Ibid.*, 1904, p. 46.

ALBERT MINING DISTRICT—*continued.*

During 1905 little work was done, 16 tons despatched from an open cut yielded 25 per cent.[1]

Broken Hill Division.

Lady Hampton Mine, 6 miles east of Broken Hill, parish Bolairo, county Yancowinna.—Inspector J. R. Godfrey reported (P.B. $^{2\,2\,1\,6}_{0\,2\,\frac{1}{2}}$) a copper lode in schist; strike N. 10° W.; dip. S. 80 W. at 75°.

Some good ore obtained from a pipe lens down to 100 feet; 49½ tons despatched, of an average grade of 27 per cent. copper.

Aided to continue 113 feet shaft to 163 feet, and to drive from bottom 75 feet on lode.

At 153 feet a well-defined lode formation reported, but little ore (no further record).

Mootwingee Copper Mine (also referred to as Mannerings).—In 1880 the Mining Registrar reported that four men were employed in this mine. Copper carbonates had been struck at 9 feet, assaying 29 per cent. copper. Sample $^{2\,2\,2\,2}_{9\,\frac{1}{2}}$, from Mootwingee, yielded copper 41·40 per cent., and 20 oz. of silver per ton.

Nadbuck Copper Mine.—Five miles from Broken Hill, parish Nadbuck, county Yancowinna.

Iron-stained quartz and gossan copper-stained. Outcrop strong. Bunch of ore at 10 feet yielded 24 per cent. ore.

Aided to sink to 80 feet. At 60 feet prospects reported very poor.

In 1901, Chief Inspector J. B. Jaquet reported the width to vary from 1 to 3 feet. Proved to 200 feet; yielding a quantity of rich ore. During eight months ending 15 June, 1901, about £900 worth of ore raised.

In 1906 it was reported that 335 tons of ore had realised £2,280 net.

White Cliffs Division.

Nuntherungie Copper Mine.—Embracing the Cootra, Tarella Consols, and the recently named Wertago Mines. Situated about 72 miles from Wilcannia, on the Milparinka-road, and about 15 miles from Nuntherungie home station, parishes Wertago and Woraro, county Yungnulga.

In 1892, J. B. Jaquet reported that more than twenty years prior several tons of copper ore, raised from shafts sunk near the western base of the Cootawundy Range, were sent to South Australia, *vid* Wilcannia, for treatment. Notwithstanding the high price of copper then prevailing, it was found that the lodes could not be worked at a profit in that isolated district.[2]

Mr. Jaquet further states that several lodes, composed of quartz with copper carbonates and decomposing copper pyrites, occur in the sandstones on the eastern side of the field. In some places carbonates, resulting from decomposition of pyrites, have been deposited in the interstices of the sandstone, which, from its copper-stained appearance, has given rise to an erroneous impression of a vast broad outcrop of a copper-bearing lode.

Warden J. W. Fletcher, under date 21st March, 1899, stated that the copper-bearing country lies along the base of the Cootawundy (sometimes

[1] Ann. Rept. Dept. Mines for 1905, p. 44. [2] *Ibid.*, 1892, p. 138.

called the Copper Mine) Range, the cupriferous belt having a length of about 6 miles, by a width of 4 miles. Sixteen leases were taken up in February, 1889. The following extracts are from the Warden's report:—

"M.Ls. 125 and 126, parish Woraro.—The copper outcrop runs the length of the two blocks, the lode being of good size. An old shaft, 25 feet deep, sunk on the lode in the early workings; 20 to 25 tons of ore at grass. There is also a fair-sized ironstone lode on the ground, carrying silver and copper.

"M.Ls. 113 and 114, parish Wertago, lying south-east of M.Ls. 125 and 126, contain the old copper mine well. These blocks were formerly known as the Tarella Consols. The lode in them is reported to have been sunk on 110 feet. About 6 tons of dressed ore are lying at the mine, and a quantity of unsorted. The lodestuff consists of grey ore and green carbonates, in a gossan formation of good width. The lode is traceable through the length of the blocks, the width varying from 3 to 10 feet. An assay of the sorted ore is reported to equal 39 per cent. of copper, with traces of gold and silver.

"M.Ls. 118 and 119, south of M.Ls. 113 and 114.—A large lode of calcspar is reported traversing these leases, with occasionally black oxide of copper.

"M.L. 121.—A large outcrop of blue and green carbonates and black oxide reported visible in this lease. A shaft 10 feet deep on a rich vein shows the latter rapidly increasing in width.

"M.L. 117, adjoining 118.—Bold outcrops of copper ore reported to be traversing this block, capable of being quarried.

"Adjoining 117.—A 20-acre lease has been taken up, covering a number of 'blows' of similar character and quality.

"M.Ls. 41 and 42, formerly known as the Cootra Mine, now the Wertago.—On these blocks outcrops stand out many feet above the surface, with blue and green carbonates and black oxides, for a width of from 60 to 100 feet wide. These outcrops are of lower grade than those further north, but easily available by quarrying.

"A large deposit of limestone is reported within a short distance, and abundant ironstone within 8 or 9 miles.

"M.Ls. 40 and 43 cover lodes exposed in small creeks falling from the range, showing carbonates and black oxide."

In connection with the above extracts from the Warden's report, it will be well to bear in mind the latter part of Mr. J. B. Jaquet's report quoted above, touching the deceptive appearance imparted to large outcrops of sandstone by the stainings of copper carbonates, arising from decomposition of a little disseminated copper pyrites. (See also Wertago Mine.)

Broken Hill Division.

Orient Mine, 2½ miles easterly from Silverton, parish Bray, county Yancowinna. Inspector Carthew reports (P.B. $\frac{1}{5}\frac{5}{5}\frac{2}{2}$) copper vein in quartz; strike N. and S. Stoped from 80 feet to surface.

Paragon Lode, Waukeroo Paddock, 35 miles north of Broken Hill, near Gum Well Creek, parish Tarrowingee, county Farrel.—Inspector B. Sawyer reported (P.B. $\frac{3}{0}\frac{9}{0}\frac{5}{0}$) a very strong quartz and calcite reef carrying copper carbonates along the outcrop runs through the lease. 16 tons of ore sent to Adelaide returned about 8 per cent. of copper.

Aid granted for 50 feet of sinking. Later it was reported that prospects were not so favourable.

ALBERT MINING DISTRICT—*continued.*

Pinnacles.—The following particulars of copper lodes in this locality were obtained through the local Warden :—

"Several copper bearing outcrops occur within a radius of about 15 miles, the two most important and promising being one prospected by Messrs. Lord and party, about 4 miles west of Pinnacles. This outcrop is reported traceable for a considerable distance. Copper indications occur in it at intervals. Assays have yielded from a trace to 50 per cent. of copper.

"The second promising lode is situated about 2½ miles south-west of Pinnacles. It was opened about thirty years ago, and a consignment of copper ore is reported to have been despatched to Adelaide. This lode is stated to be strong in the outcrop and traceable for a considerable distance."

Ponto Mine, 15 miles from Morden Station, and 7 from Induna Park Hotel, on Broken Hill to Cobham road.—Inspector B. Sawyer reported (10th September, 1907) that a small company had been formed to work this lode, which is said to be of fair width. Shaft 102 feet driven 50 feet along the lode at 90-foot level.

Output, 50 tons of 18½ per cent. ore.

Purnamoota, 6 miles N.W. parish Robe, county Yancowinna.—Inspector J. Carthew reported (P.B. $\frac{3}{0}\frac{0}{7}\frac{3}{3}$) ore veins striking N.E. carrying copper, lead, and silver, traceable for about half a mile.

Aided to sink from 15 to 65 feet.

Seven miles N.W. of Purnamoota homestead, near Mount Robe, parish Lewis, county of Yancowinna.—Inspector J. Carthew reported (P.B. $\frac{3}{0}\frac{1}{7}\frac{4}{3}\frac{7}{3}$) a vein striking N.W. carrying copper, lead, and silver. Apparently a continuation of the Mount Robe lode.

Aided to sink from 40 feet to 90 feet.

Purnamoota.—Messrs. Davison and Ayliffe reported through the Warden (1898) that good surface indications of copper occur in several localities in the neighbourhood of Purnamoota, but are of no great depth. At Terrible Dick very good specimens were obtained at surface, but carried down only 30 or 40 feet. Similar conditions prevail at the Paragon Mine.

Red Flag Copper Mine, 12 miles westerly from Broken Hill, parish Stephen, county Yancowinna.—Inspector J. Carthew reported (P.B. $\frac{1}{0}\frac{1}{5}\frac{9}{3}\frac{3}{3}$) copper lode in quartz; strike E. and W., dip. S. Payable ore stoped from 60-foot level to surface.

Aided to sink from 133 feet to 183 feet. At 146 feet copper vein about 9 inches thick in schist and iron oxide. At 154-foot vein 18 inches thick in eastern end of shaft; water troublesome. At 161 feet same thickness, dipping east (found impracticable to continue without machinery).

Rockwell Paddock, half a mile south of Rockwell Post Office, parish Sebastopol, county Yancowinna.—Inspector Hebbard reported (P.B. $\frac{3}{0}\frac{1}{0}\frac{0}{0}\frac{4}{3}$) copper, lead, and silver ores in mica, schist, and quartzite. At 71 feet proved poorer than at surface.

Ruby Copper Mine, about 10 miles from Broken Hill, just off Day Dream road.—Chief Inspector J. B. Jaquet reported[1] that the shoot of payable ore in this mine varies from a few inches to 1 foot 6 inches in thickness, and has a length of 60 feet. Shaft sunk 120 feet; 200 tons reported to have been despatched.

[1] Ann. Rept. Dept. Mines for 1901, p. 167.

ALBERT MINING DISTRICT—*continued.*

Silverton.—The following particulars of copper lodes in the neighbourhood of Silverton were supplied to the local Warden by Mr. R. H. Srezise, under date July, 1898:—

"We first tried in the hills to the west of the Umberumberka Mine for four weeks, but abandoned the site after obtaining 30 cwt. of 10 per cent. copper ore in the time mentioned. We then tried in the hills on the east side, and succeeded in raising 10 tons of 11¼ per cent. copper ore in eight days; but it proved only a pocket in a big lode formation, and as it cut out entirely at 9 feet, we abandoned this site also, and pegged out a third area about 2 miles north on the same line of lode. In twelve days we have raised about 9 tons of ore, averaging about 13 per cent., and are now sinking a shaft.

"Barron and party are obtaining good results from near Mount Robe. Several trucks of ore have been despatched, believed to contain 33 per cent. of copper.

"Near the old racecourse Casey and party are reported to be raising payable ore."

Two other parties were at work near the Old Silverton Copper Mine, one of which had despatched a parcel of ore, from which good results were anticipated.

Trinidad Copper Mine, 3 miles from Silverton, on Thackaringa-road, parish Bray, county Yancowinna.—Inspector Hebbard reported (P.B. $^{3}\frac{44}{93}$) copper ore in mica, schist, and diorite. Strike, N. 10° E.; dip, S. 80° E. Ore bands 3 to 15 inches wide.

Aided to continue 28-foot shaft to 78 feet. At 34 feet iron and copper stained schist. At 43 feet lode almost entirely pinched out.

White Cliffs Division.

Wertago Copper Mines, parish of Wertago, county Yungnulga, 70 miles N.W. of Wilcannia, and 100 N.E. of Broken Hill.—Chief Inspector J. B. Jaquet examined these deposits in 1901, from his report the following particulars are extracted:—

"Occurrence of copper ore at Wertago long known. Thirty years previously parcels of ore were despatched, but only since end of 1898 that much developmental work has been carried out, and public attention directed to the field.

"Dominant geological features, schists, quartzites, sandstones, and conglomerates of lower Silurian (?) age. These rocks are intruded by dykes of amphibolite and quartz felsite. Recent deposits of amorphous limestone, similar in character to those of Acacia Siding and elsewhere, in vicinity of Broken Hill, are found capping the older rocks in places.

"The copper ore occurs partly in well-defined lodes, and partly as detached bunches or pockets, which are found more or less in a line with one another along certain zones of country.

"Summary.—The field is capable of yielding considerable quantities of ore. There are two great obstacles which impede the progress of the mines; their isolated position, and the difficulty of obtaining an adequate and regular water supply. Only the very richest ores can be profitably carted 80 miles to the River Darling at Wilcannia. A reverberatory furnace was erected

[1] Ann. Rept. Dept. Mines for 1901, p. 168.

some few months ago, and many tons of carbonate ore were reduced. Ironstone and limestone obtained locally were used as fluxes, and the fuel employed was wood.

"Smelting operations do not appear to have progressed favourably, and the furnace has been closed down for some time past. I am informed that less than 3 tons of copper were produced. I am not in a position to discuss, in detail, the circumstances which caused the enterprise to fail. However, it is apparent to anyone examining the various mines upon the field, that the ores hitherto discovered are chiefly of one kind—acid (silicious) carbonate ores. These ores could be best smelted in conjunction with basic sulphide ores, and it is probable that ores of this character will be found occurring beneath the zone of oxidation. Should it be decided to sink in search of sulphide ore, I would recommend that a site be selected upon a well-defined lode, such as that occurring in the Copper Well Mine, rather than upon an impregnated belt of country, where the ore is to be found in disconnected bunches, such as is the case in the Big Wertago and adjoining mines."

The principal mines will be found more fully described under their distinctive titles.

Block 118.—Mr. Jaquet, in the same report, states that a quarry 70 feet long has been opened along the side of a creek in this block, upon an ore body, from 2 to 3 feet wide, composed of schist impregnated with copper carbonates.

In Block 5, one-quarter of a mile N.E. of surveyed town of Robertson, parish of Wertago.—Inspector J. Carthew reported (P.B. $\frac{2}{0}\frac{5}{6}\frac{8}{8}$) ironstone and quartzite containing copper ores. Strike, N.E. in slate and schist. Prospects in 24-foot shaft encouraging, vein about 15 inches wide. Aided to sink to 100 feet.

Progress.—At 65 feet a few veins noticeable. At 71 feet work stopped by water. No immediate prospect of payable lode.

BATHURST MINING DISTRICT.

Blayney Division.

Annandale South Copper Mine, M.L. 1.—First opened about twelve yea ago under aid from the Prospecting Vote. At 80 feet carbonate of copp occurred. Shaft continued to 150 feet. Lode about 1 foot wide. Two o 3 tons of ore raised; picked samples reported to have yielded from 2½ to 6 per cent. of copper.

About 10 chains S. 20° E. of the above, another shaft was sunk abou 40 feet on a quartz reef carrying copper and iron pyrites; the forme apparently increasing in proportion with depth. The oxidised ore at surfac was reported to prospect about 8 dwt. of gold per ton; the sulphid about 8 per cent. of copper. The reef strikes N. 70° W. in andesite, and dips S. 70° W. Thickness at 40 feet, about 1 foot 6 inches.

Bathurst Division.

Apsley Copper Mine, parish Ponsonby, county Bathurst, about 5 mile from Perth Railway Station.—The earliest reference to this mine is con tained in the "Mineral Statistics of New South Wales," 1875, p. 92. A that date it had been proved to a depth of 100 feet. Thickness of lode 3 fee to 5 feet. Strike north and south; dip easterly. Ore assaying from 4 t 18 per cent. of copper. 150 tons were being raised monthly and disposed o to the Eak Smelting Company, which had a reverberatory furnace runnin intermittently near by, the sole tariff being 85s. per ton for 10 per cent. ore and rising 13s. per unit. Eighteen men employed.

The yield in 1876 is given as 20 tons of copper.

In 1877 the lode was traced further to the north. Operations during 187 were confined to near the surface for carbonate ores; and continued so fo the better part of 1879. During the latter part 60 tons of ore were raise yielding 7 tons 16 cwt. of copper, valued at £429. In 1880 the mine change hands, and continued in work without interruption. 191 tons of ore wer raised and sold to the Bowenfels Smelting Works for £750.

In 1881 only 28 tons of ore were raised, producing 3½ tons of copper, valu £220. Lode 6 inches thick in a 40-foot shaft. In this year the mine wa reopened by Mr. Lewis Lloyd; but no further particulars are available o the result of operations. For many years it remained idle. In 1898 it wa restarted; and in December of that year it was visited by the Writer. A new shaft had been sunk 186 feet, cross-cut east 30 feet to the lode on whic a winze was sunk 63 feet following the slight underlay to the east; th course of the lode being about N. 20° E. At the bottom of the winze th lode was solid and about 9 feet wide. Hanging wall well defined, foot-wal broken. Lodestuff largely blende with chalcopyrite and pyrite. The or raised during these prospecting operations was broken and sorted into "firsts, "seconds," and "waste," the "firsts" being despatched to Mr. L. Lloyd' Smelting Works at Lithgow; 38 tons yielded 7 per cent. of copper. A sample, 4302–98, yielded 7·93 per cent. copper; 16·53 per cent. zinc; an 2 oz. 7 dwt. 22 grs. of silver per ton. No gold. Country schist, partly hornblendic.

Subsequent Development.—In February, 1907, a syndicate, under manage ment of T. K. Longton, secured control, and re-opened the main shaft Operations were, however, suspended after a short period.

An option was then secured by Mr. Francis Drake, who unwatered the new shaft section to the lowest level attained, viz., 240 feet. The ore body exposed in the stopes at 180 feet and 240 feet was carefully sampled by Mr. J. F. Carey, with the following results :—

(a) Ore body at 180-foot level, over an exposed length of 45 feet, and a width of 5 feet to 10 feet, averaged 7·13 per cent. copper.

(b) In winze between 180-foot and 240-foot level, averaged 11·56 per cent. copper.

(c) Ore body exposed at 240-foot level, length 53 feet, width 7 feet 6 inches, averaged 7·92 per cent. copper.



Whilst the mine was unwatered a further inspection was made by the Writer on 5th December, 1907, and the following check samples taken :—

Average sample north end of stope, 180-foot level, 5 feet wide :—

No. $\frac{1940}{07}$	Copper	10·34 per cent.
	Gold	a trace per ton.
	Silver	3 oz. 5 dwt. 8 grs. per ton

Average sample from centre of ore-lens, 180-foot level, width 7 feet 9 inches :—

No. $\frac{1941}{07}$	Copper	6·36 per cent.
	Iron	16·24 ,,
	Zinc	8·88 ,,
	Sulphur	15·23 ,,
	Silica	24·06 ,,
	Gold	a trace per ton.
	Silver	2 oz. 14 dwt. 10 grs. per ton.

Average sample near south end of lens, 180-foot level, 5 feet wide :—

No. $\frac{1942}{07}$	Copper	3·52 per cent.
	Gold	a trace per ton.
	Silver	2 oz. 14 dwt. 10 grs. per ton.

BATHURST MINING DISTRICT—*continued*.

Average sample from south end of stope, 240-foot level. Width, 16 feet:—

No. $\frac{1}{5}\frac{3}{7}\frac{1}{2}$	Copper	5·51 per cent.
	Iron	22·82 ,,
	Zinc	8·25 ,,
	Sulphur	19·95 ,,
	Silica	16·55 ,,
	Gold	a trace per ton.
	Silver	2 oz. 0 dwt. 7 grs. per ton.

Average sample from north end of stope (240 feet level). Width, 10 feet:—

No. $\frac{1}{5}\frac{3}{7}\frac{1}{2}$	Copper	4·42 per cent.
	Iron	15·45 ,,
	Zinc	8·11 ,,
	Sulphur	11·30 ,,
	Silica	27·35 ,,
	Gold	a trace per ton.
	Silver	1 oz. 12 dwt. 16 grs. per ton.

The principal line of workings strike about N. 10° E., but another (western) intersects on a strike of N. 20° E. The provings—old shafts—extend for about 410 feet, and a width of 250 feet at the south end. Traces of copper carbonates are visible in the tips. Iron pyrites, cubical and granular, is also abundant owing to decomposition of the soft schist.

The ore occurs as impregnations in the schist, without definite boundaries. A cross-cut at 180 foot level in main shaft, after passing through the main ore lens, cut a 3-inch vein of ore; beyond this ore is again showing in face of cross-cut. A sample of the 3-in. vein yielded:—

No. $\frac{1}{5}\frac{3}{7}\frac{1}{2}$	Copper	14·99 per cent.
	Zinc	1·82 ,,
	Iron	20·16 ,,
	Sulphur	18·58 ,,
	Silica	29·90 ,,
	Gold	a trace per ton.
	Silver	2 oz. 10 dwt. 2 grs. per ton.

The average results of independent sampling tests in the two levels, by the Writer and Mr. J. F. Carey, work out as follow:—

Mines Department assays, 180-foot level	=	7·13	per cent. copper.
J. F. Carey's ,, ,,	=	7·52	,, ,,
Mines Department assays, 240-foot level	=	5·09	,, ,,
J. F. Carey's ,, ,,	=	7·97	,, ,,

The Mines assays in the latter representing a width of 16 feet, against 7 ft. 6 in. for Mr. Carey's.

Similar tests at the north end of this level worked out at 4·42 and 5·95 per cent.

A solid block of ore exists between the two levels, which have only been stoped up a few feet.

The ore consists, where massive, of copper and iron pyrites and zinc-blende. In other parts of impregnated schist chiefly hornblendic. Water makes at the rate of about 2,200 gallons per twenty-four hours.

The furthest south-western ore occurrence proved in this property—327 feet from the main shaft, in a shaft 33 feet deep—is reported by Mr. Carey to yield an average of 6·25 per cent. of copper, from a width of 5 feet.

Bathurst Mining District—*continued.*

Blayney Division.

-Blayney Copper Mine, 2 miles south of Blayney.—Athole-Blayney e (No-liability) formed to prospect this deposit during recent copper Shaft, 100 feet deep; trimmed down 7 ft. x 4 ft. in clear; driven r at 50-foot level for a distance of 40 feet; two shoots of ore reported wing in drive; about 20 tons raised; highest assay for check sale per cent. of copper; ore reported in north end of shaft all down, nning to show in south end at 70 feet.

Rockley Division.

ral Copper Mine M.Ls., parish Ponsonby, county Bathurst, between and Sugarloaf Mines, near Cow Flat, about 1 mile south of Belmore Country micaceous and hornblendic schist and limestone.

, N. 20° W.; dip, S. 70° W., at 50 to 58°. Opened in the days of t smelting by shallow shafts; nothing known of early output.

ned by the Balmoral Syndicate about November, 1906. At date of n (6th December, 1907) shaft 155 feet deep, driven north from 150-l 40 feet and south 28 feet.

of ore followed about 3 feet, consisting of splashes and strings of yrites in hornblendic schist, with blotches of calcite; zinc-blende not ous.

ng wall, schist; footwall, limestone; evidently not true footwall; a ss-cut into it revealed 2 feet of limestone, then strings of ore which showing in face, and should be further cross-cut.

esent owners have sent to Lithgow 8 tons dressed ore, which yielded per cent. of copper; 5¼ tons dressed ore, which yielded 8 to 9 per copper.

re Copper Mine, near Cow Flat, M.Ls. 25, 26, and 27, parish y, county Bathurst; about 5 miles from George's Plains Railway —The earliest official record of this mine is that by the Mining r in 1875, to the effect that the mine was being worked by with payable results. (Tributers were also at work on Messrs. nd Co.'s property, 2 miles S.W. of Cow Flat, with advantage to them- In this year it is also recorded that Messrs. Croaker & Co. erected g furnace about 1 mile from the Cow Flat Mine, and rented it to the lting Company; this was probably identical with the furnace run by r near the Apsley Mine.

'7 payable sulphides were reported below the oxidised zone. In 1878 rk was being done, about 7 or 8 tons of ore per month only being In this year the late Government Geologist, Mr. C. S. Wilkinson, he mine, and described the ore bodies as "small, irregular veins of re in greenstone, at its junction with the Silurian Sedimentary

'9, 190 tons of ore were raised, and sold for £440. The ore at this reported to be too low grade for remunerative working at the low copper ruling.

80, 172 tons of ore were raised, and sold for £317.

81, 118½ tons of ore were raised, and sold for £163.

rther returns are obtainable. The deepest shaft was reported to have the 100-foot level

[1] Ann. Rept. Dept. Mines for 1878, p. 150.

On 28th April, 1898, the *Australian Mining Standard* reported that the mine had been taken over by the Anglo-Australian Exploration Company, which proposed to re-open and prospect it.

In June, 1899, aid was granted from the Prospecting Vote to cross-cut at 90-foot level drive, 50 feet south.

Black slate and limestone in cross-cut; streaks of copper sulphide at end of drive; lode split by "blows" of limestone.

Further aid granted to continue shaft to 180 feet. Sinking through slate, limestone, and lodestuff; lode dipped west, just showing in shaft at 130 feet = a little copper sulphide occasionally met during progress.

Examined by the Writer in the same year. Lode strikes N.E. and S.W. in hornblende and micaceous schist, in close proximity to limestone. In the New Belmore shaft, the lode appears to strike N. 40° E., and to dip N. 50° W. About 12 feet of lodestuff, much mixed with country and quartz exposed in workings; concentrating material.

In 1901, small blast furnace erected; about 620 tons of about 3 per cent. ore smelted. (Ann. Rept., 1901, p. 54.)

Four hundred and fifty-six tons of ore were raised during 1902 (*ibid.*, 1902, p. 49.) Re-opened in March, 1905; 140-foot shaft retimbered; roverberatory erected (*ibid.*, 1905, p. 45).

Prospecting continued in 1906 from old shaft, a little ore proved for a considerable width in strings and bunches in limestone and hornblende schist; its distribution increasing cost of production.

In 1907, 52 tons of dressed ore obtained whilst sinking new shaft to a depth of 200 feet, which was sold at a profit, at Lithgow. Work ceased during year.

During operations from October, 1905, to cessation in 1907, 188 tons of dressed ore were disposed of for a return of 12¼ tons of copper, equal to 6·6 per cent. in the ore.

Canowindra Division.

Belubula Copper Mine, portions 4 and 5, parish Malengulli, county Bathurst, Licking Hole Creek, about 16 miles from Canowindra.—The late Mr. W. M. Rothery, of Cliefden Station, informed the Writer that in 1845, or earlier, copper ore was discovered outcropping on portions 2 and 3, adjoining those abovementioned, but as nothing defined was found below the surface indications, attention was directed to the site of the above mine on Cliefden pre-emptive lease, and portions 4 and 5 were purchased by Messrs. Want and Donaldson. Extensive prospecting operations were carried out, the main shaft reaching the 84-fathom (504 feet) level, and drives were extended at various levels. Mr. Rothery, who acted as paymaster for the proprietors, stated that absolutely nothing beyond traces of copper were ever discovered. Ores purporting to be from this mine according to the catalogue were exhibited at the Paris Exhibition of 1855.[1]

Rockley Division.

Black Mountain Mine, portion 29, parish Arkell, county Westmoreland.—Opened in early days of western copper mining. Strike, north 50° west, with a flat dip at about 25° south 40° west.

At surface a thin bed—about 2 feet—of chlorite schist in decomposing liberates copper carbonates as stains in the foliation. In sinking on this following the underlay, it pinched out between quartzite foot and hanging walls. The latter was driven through for some distance to the bottom of the

[1] See pp. 274, 275.

present shaft—about 150 feet—where a little softer rock is showing, carrying a little pyrites and faint splashes of copper sulphide. No defined ore body.

A small bunch of carbonate ore was worked out near surface, by McGregor and party, about 1899. Thirteen tons sent away are reported to have yielded 10 to 13 per cent. of copper.

A sample of the ore at grass from recent operations yielded—

No. $\frac{13.9}{0.8}$—Copper, 7·42 per cent.
Gold, a trace.
Silver, 13 dwt. 1 gr. } per ton.

Blayney Division.

Blayney Copper Mine (formerly *Annandale*).—This mine, at which operations have been recently renewed, is situated on a part of the Marsden Estate, close to the town of Blayney. The Blayney to Harden Railway line passes within a few yards of the mine, which possesses a private siding. The lode occurs in andesite, and is of considerable width. Over 2,000 tons of iron oxide are reported to have been quarried from the outcrop for the Lithgow Iron Smelting Works before any trace of copper was discovered.

In 1881 traces of copper ore were exposed in a small quartz vein. In following it down a little copper ore was met at 90 feet from the surface. The mine was then taken on trial by Sydney investors, and subsequently purchased by them for £10,000.

The Great Blayney Copper Mining Company was then formed (in 1882), and smelting works erected. At 110 feet the lode was proved 40 feet wide. The deepest shaft was sunk nearly 300 feet. Unfortunately, particulars of the early operations are not obtainable; work was, however, not continued for any length of time.

In 1889, under the name of the Annandale, the mine was again worked with reported fair results, the company operating being a small one. A furnace was erected at this time, according to the local Mining Registrar, on a new principle, which, however, was unsuccessful, and another had to be erected in its place. At this date several shafts had been sunk on the lode, ranging from 110 to 292 feet, well prospecting the lode to that depth. Six tons of copper were produced, realising £57 10s. per ton.

In 1891 it was reported that the mine was shut down, owing to the low price of copper and the low grade of the ore.

In 1892, 10 tons of copper were produced, valued at £435.

The mine then remained idle until 1897, when it was again taken up by a syndicate, who began unwatering it. After nearly twelve months' baling by kibble, the water was lowered sufficiently to allow of ore being stoped at the 90-foot level for trial smeltings. The ore from this level—just below the zone of oxidation—consisted of magnetic iron pyrites and chalcopyrite, which was roasted slightly in heaps and then smelted in reverberatories without flux, as a fair percentage of lime (calcite) occurs in the ore.

The magnetic pyrites (pyrrhotite) possesses the deceptive appearance of flesh-coloured copper sulphide, and this resemblance gave an inflated idea of its true value. A massive sample of the mineral was tested in the Departmental laboratory for gold, silver, and nickel, but none of these metals were detected; copper was only present to the extent of 0·22 per cent. The

curious fact that pyrrhotite, though often rich in copper pyrites and nickel, rarely carries more than traces of gold has already been mentioned in this work.

Smelting operations were begun in 1898 in two reverberatory furnaces erected by the previous company, the second consignment of copper being despatched in May.

In July it was announced that a public company had been formed with a capital of £100,000, and that two water-jacket blast furnaces were to be erected.

The mine was visited in June and December of 1898. At the first date the 90-foot level of one shaft only was open for inspection. The walls and surfaces of the old workings were glistening with copper sulphate and in some places with fine crystals of native copper deposited from solution during flooding of the workings.

In December no fresh features had been developed in the mine, active operations so far as stoping and smelting were concerned having ceased pending the erection of the new haulage, pumping, and smelting plants. The two first were already nearing completion, and the foundations were being prepared for the latter.

A shaft (180 feet deep) in the east wall of the lode, started by the previous owners, was converted into the main shaft of the new company; substantial poppet-heads being erected, whilst prospecting operations proceeded by means of a small portable engine. A cross-cut then being driven from the 180-foot level had already pierced 30 feet of lodestuff, according to Captain Cock.

There is little question that such of the lodestuff as had been exposed at the 90-foot level was suitable for blast-furnace treatment at a low cost, the grade, however, is undeniably very low. If, as is surmised, the ore is of a kindly smelting nature, it behoves the proprietary to ascertain the amount of silicious flux—if any—that it can safely absorb, and if appreciable, to endeavour to secure gold and silver bearing ores for the purpose. If the Blayney lode should prove a fluxing base—like Cobar—the natura poverty of the ore would be counterbalanced by the possibilities opened up for spirited enterprise in connection with silicious, refractory, and low-grade gold and silver ores of the surrounding mining districts approachable by rail. It might also be the means of opening up the old copper lodes around Byng and Lewis Ponds, some of which would probably afford remunerative employment for small parties, if the dressed ore could be disposed of in the district.

The numerous small copper veins and lodes of the Carcoar and Woodstock districts might also profit by the erection of a central smelting plant at Blayney.

Recent Development.—In full work during 1900, but operations considerably reduced at end of year pending more extensive exploration of the lode. The value of the copper produced during the year was estimated at £40,250.[1]

During 1901 18,666 tons of ore were raised, which yielded 418 tons of copper. A second blast-furnace erected. Mine closed towards end of year.[2]

In January, 1907, the present Blayney Copper Mines and Smelting Company, N.L., was incorporated. The blast furnaces were renovated, and smelting began on the 25th July on about 2,000 tons of purchased ores.

[1] Ann. Rept. Dept. Mines for 1900, p. 54. [2] *Ibid.* 1901, p. 54.

Winch converted into a Shell of Copper, Blayney Copper Mine.

It having been ascertained that the mine water warranted construction of precipitating vats for recovery of copper in solution, a plant was laid down before baling began. The result has been phenomenal, a recovery of 39·65 to 43·5 lb. of copper per 1,000 gallons being obtained Wire scrap from Lysaght's wire works being used to advantage for precipitation, the recovery reaching 90 per cent. 67½ tons of cement copper were obtained from 4,600,000 gallons of water, this product being purchased by the Great Cobar, Limited.

At commencement of baling the mine water stood 80 feet from surface. The cause of its enrichment is the large extent of very low grade ores undergoing the process of decomposition or oxidation at and about water level. The early open excavations of the irony outcrop for smelting purposes at the first Lithgow ironworks, moreover, greatly aided the process of leaching by catching the rainfall and drainage and leading it down through the sphere of decomposition by numerous extensive cracks caused by subsidence. If the mine was permanently unwatered below the true water-level, the copper in solution would probably be insignificant. On the other hand, failing profitable mining developments below water level, the natural process of leaching above it can be successfully utilised at intervals by allowing the water to accumulate.

The lode occurs near the junction of augite andesite and Silurian Sedimentaries. Strike N.W. and dip N.E. Part of the channel rock is a highly crushed and sheared igneous rock of schistose appearance, probably the altered selvage of the intrusive andesite.

The lode has been proved for about 680 feet in length and 337 feet in depth, the lowest level being 277 feet, below which a winze has been sunk to the recorded depth.

So far as unwatering has proceeded below the 277-foot level, little workable ore has been exposed. The massive pyrrhotite at the 90-foot level in the south-western shaft, previously mentioned by the Writer as a kindly flux, was apparently not extensive. As far as inspection is possible at the present time, no massive pyritic ore, even of low grade, is in sight.

It is highly desirable that the Company, which is laying down an extensive Customs smelting plant, embracing gold and silver concentrates, should at least have command of abundant basic flux even if of low copper value.

The plant consists of two blast-furnaces, each of a nominal capacity of 120 tons; a converter plant—the first in New South Wales; and a small cupola for matte melting.

A large reverberatory furnace and an Edwards' roaster are in process of construction. The mine and works are connected with the State railway system.

A satisfactory trial run of the converter has been made, the linings being formed of crushed auriferous quartz, with sufficient local clay to bind it. Small compressor rammers are used in lining.

Limestone flux is obtained from a lease on private land about 1 mile distant; firebrick from J. Dewar, Bathurst; and coke from Bulli.

The following description of the Company's smelting plant has been furnished by the General Manager, Mr. F. L. Piddington:—

Blayney Copper Mines and Smelting Company, N.L.

The smelting plant of this Company comprises two blast furnaces, a converter plant, and Edwards' roasting furnace, and a reverberatory smelter, the two latter in course of construction.

The blast furnaces are 168 inches by 40 inches at tuyere level, and 9 feet high from tuyeres to downtake flue which is taken off below the feed floor. There are thirty-two tuyeres each 3 inches in diameter. Blast is supplied by two No. 7 Roots' blowers direct coupled to horizontal engines by Fraser and Chalmers.

The converters are of the Leghorn type 8 feet long by 6 feet diameter, fitted with patent ball valves. The turning gear is actuated by two speed Westinghouse motor with reversing switch. The matte remelting cupola is 36 inches diameter, and is tapped direct to a 5-ton ladle handled by 20-ton travelling crane. Linings are crushed in a 6-foot Chilian mill, driven by motor. Blast for the converters is supplied by horizontal compressor 12-inch steam cylinder 30-inch air by 24-inch stroke fitted with spring valves of the Rand type. Its capacity is 2,500 cubic feet free air per minute at a pressure of 15 lb. per square inch.

Power for motors and lights is supplied by 60 k.w. Parker generator direct coupled to Alley and McLellan engine. Steam for generator and compressor is provided by a four-drum Stirling boiler, 230 nominal h.p.

The Company has its own railway siding on which is installed a 20-ton Avery scales. The Sampling Mill is equipped with No. 3 Dodge breaker, and one set 14-inch by 7-inch Roger rolls together with sample grinder, and the usual bucking plates.

The storage bins for ores, fluxes, and fuel have a capacity of 3,500 tons.

Blayney (*See* Blayney, South Annandale, Wright and Osborne's, and Quigley's Hill Mines.)

On Stinson's property, west of the cemetery, a copper lode was opened to a depth of 60 feet, its thickness being 3 feet. About £300 worth of ore is reported to have been despatched from this lode to the Lithgow Smelting Works.

On Glasson's properties, and Clauson's, close to Blayney, a little copper ore has also been discovered.

Orange Division.

Bob's Mount.—Emu Swamp, Springfield Estate, between Orange and Lewis Ponds. Copper ore originally discovered by R. Atkins. First shaft sunk by T. Payne, about 1899. The lode traverses the southern slope of Bob's Mount, on a north 10° west strike, and was intersected by a 140-foot cross-cut tunnel from the level of Emu Swamp, about 120 feet below the highest outcrop, where a shaft was being sunk.

Where the tunnel cut the lode but a few feet of backs occur owing to the slope of the hill. A few feet from the intersection a winze was sunk 15 feet in the lode, and from this level the lode was driven on northerly for 280 feet. At time of inspection (February, 1908) water was standing almost level with the top of the level, work being concentrated on the shaft. As the latter is to be connected with the tunnel the surface water to that level only will be drained; pumping or baling will still have to be faced when the lower levels are attacked.

From the tunnel level a total of 127 tons of ore were despatched after hand dressing for an average yield of 10 per cent. of copper.

The ore sunk in the shaft is of a highly silicious nature. An average sample yielded:—

No. 1	Copper	9·85 per cent.	
	Gold	a trace.	per ton.
	Silver	1 oz. 14 dwt. 20 grs.	



Converter Plant, Blayney Mines and Smelting Works, March, 1908.

Bathurst Mining District—*continued.*

Britannia Mine, M.L. 10, parish Worcester, county Bathurst, near Lewis Ponds, close to Bell Mount.—Worked by the Great Western Copper Mining Syndicate in 1872. At present held by H. B. Thomas and party. No record of old workings other than a brief record of depth and thickness of lode. Captain W. R. Reynolds informed the Writer in 1898 that it was worked to the 210-foot level, and that the thickness varied from 3 to 5 feet.

Two lodes appear to junction in this lease, the Britannia striking north-west, and another north 10 degrees west. If the latter is persistent so far, it should intersect the main line in the old workings. These, however, are not now open to inspection. The latter extend for a distance of about 260 feet.

Present efforts are confined to testing the northern and southern extension of the lode.

A few chains north of the old Britannia workings, a shaft has been sunk 60 feet on the lode, which here consists of soft, partially enriched sulphides, of a reported width of 12 feet, a few tons of which have been raised in sinking. The quality of this ore is shown by the following assay :—

No. $\frac{573}{08}$—Copper, 18·93 per cent.
Gold, a trace per ton.
Silver, 1 oz. 1 dwt. 19 grs. per ton.

At the southern end, 65 feet from the old workings, a shallow shaft (not in ore) has been deepened from 50 to 60 feet. At 53 feet on a south-west dip, sulphide ore began to make in the southern end of shaft. Its quality is revealed in the following assay :—

No. $\frac{573}{08}$—Copper, 21·10 per cent.
Gold, a trace per ton.
Silver, 1 oz. 10 dwt. 11 grs. per ton.

Persistence and quantity have yet to be proved.

In the shaft (80 feet deep), sunk by the Noller Mining Syndicate on the flank of Bell Mount in the intersecting lode, copper carbonates were struck at 25 feet in an 8-inch vein. At 80 feet it was driven on south for 20 feet. Further south are old workings from which good ore is reported to have been raised in the early days of the field.

An average sample of the ore gave the following returns :—

No. $\frac{574}{08}$—Copper, 21·48 per cent.
Gold, a trace per ton.
Silver, 16 dwt. 8 grs. per ton.

The Noller Syndicate obtained 9 tons of ore in sinking the 80-foot shaft, 6 of which yielded 15 per cent. of copper, and 3 tons 20 per cent. About 2 tons of dressed ore at grass represented by assay No. 574.

Rockley Division.

Brown's Creek, about 10 miles north-west of Rockley, adjoining Prosser's mine on south side at junction of Brown's and Edward's Creeks, parish Ponsonby, county Bathurst.—Inspector Hooke reported (P.B. $\frac{18}{07}$) a quartz reef in slate showing copper carbonate stains and small blebs of yellow ore.

Aided to sink 28-foot shaft to 78 feet following lode.

Brown's Creek, near Back Creek, Rockley, parish Ponsonby, county Bathurst.—Inspector Hooke reported (P.B. $\frac{21}{99}$) copper-bearing veins in chlorite schist. Aided to sink to 150 feet and cross-cut 60 feet, but subsequently altered to cross-cut at 80 feet.

Progress: At 112 feet country very hard; formation serpentine with calcite streaks.

Three shafts had been sunk in bed of Brown's Creek, 30 feet, 110 feet, and 90 feet where lode outcropped. From one shaft a cross-cut under bed of creek cut lode formation with streaks of copper ore—not payable.

Aid granted to drive along course of lode. Copper veins showed no improvement, being thin, with bunches.

Copper ore in slate country also reported by the same officer on N. Wilson's improvement lease, close to the north boundary of Hill View Estate (P.L. $\frac{A\,2\,3\,A}{0\,0}$).

Oberon Division.

Bull's Creek, parish Jenolan, county Westmoreland.—Copper ore (bornite) occurs about 1 mile north of portion 5, on Bull's Creek, also about 1 mile south of the same portion on the same creek, near its junction with the Jenolan River. Shafts have been sunk on both outcrops. The ore occurs in chlorite in very rich, small bunches, assaying up to 37 per cent. copper.

Cowra Division.

Burley Jacky Copper Mine, situated on the Redfern Estate, about 4 miles from Woodstock Railway Station, on the Blayney to Harden Railway.—The following particulars were supplied by Mr. Hemsley, of Blayney:—Burley Jacky lode was discovered in 1877. Two waggon loads (about 12 tons) were sent to Cadia Smelting Works, near the Canoblas; this apparently exhausted the ore in sight, for nothing more seems to have been done in the way of raising ore until 1890, when a very rich bunch of copper sulphide (bornite) was discovered upwards of 30 feet in width, and of an equal length. This chute was followed to the 230-foot level, when it cut out. The ore averaged 30 per cent. at the English and Australian Smelting Works, Waratah, and is stated to have realised a net return of about £47,000.

The lode occurs in andesite at the junction of sedimentary rocks. The lode channel is filled with boulders of andesite of all sizes up to several tons. Between the boulders, soft, crushed, or clayey filling occurs, stained with copper carbonates and containing bornite in bunches. The main bunch was cut off northerly by a cross joint in the andesite. Since the exhaustion of the rich ore chute, attention has been directed to the outcrop further north. Very kindly gossan occurs both at the main workings and at the northern extension, several chains distant. Several shafts have been sunk hereabouts in promising gossany carbonates with red jasper and chalcedony. The mine requires a deep test with adequate levels along its course. The richer (secondary) ores are likely to occur in isolated bunches, such as already discovered, but at greater depths the original yellow sulphide may prove to be more equally distributed in the lode. The rich and profitable chute already describedwas found only a few feet below the original workings after the mine had long remained idle. Two other lodes were discovered in the property during 1898; the furthest west, half a mile from the main lode, was opened to 70 feet. The lodestuff, 2 ft. 6 in. thick, consisted of quartz with copper sulphide, but not rich enough to bear cost of carriage and treatment. Gold is reported to have equalled 2 oz. to the ton of metallic copper; a sample of bornite, taken at random, yielded but a trace (under 2 dwt.) of gold per ton, and 9 oz. 14 dwt. 4 grs. of silver per ton. It does not appear that the owners derived any benefit from the presence of the

precious metals. About three-quarters of a mile northerly from Burley Jacky Mine, on the adjoining land, a little copper carbonate is showing in the andesite, and in a quartz reef some evidence of early superficial testing is apparent. From Burley Jacky several parcels of ore were raised and treated at Lithgow since previous inspection.

Burraga Division.

Burraga or Lloyd Copper Mine (formerly *Thompson's Creek Mine*).[1]—According to Mr. T. Russell, of Blayney, brother of one of the original proprietors, the Burraga Mine was discovered by a shepherd named McIntyre prior to 1877, taken up by Mr. Brownlow, of Briar Park, and transferred by him to Messrs. Russell and Clarke. The lode is reported to have been very thin at surface, with very little gossan. At 18 feet it opened out to a width of 18 feet of black ore, equal to 19 per cent. copper.

The following report was furnished to the Warden in ($\frac{1}{p.61}$), by Messrs. Russell & Co.:—"We commenced work on the 3rd January last with two men, and now employ thirty-three, including teamsters. Clarke's shaft is sunk to a depth of 62 feet. The lode in this shaft is about 8 feet wide from the bottom to near the surface of 20 per cent. ores. The lode is disordered at the bottom of this shaft, this being the place of junction with an east and west and north and south lodes. The lode going south from this shaft is about 4 feet wide of black and yellow ore, and is continuous to No. 1 shaft north.

"No. 1 shaft is 40 feet deep, the lode being from 2 to 3 feet wide of yellow ore. Other prospecting has been done further north with good prospects."

From Clarke's shaft a drive was put in on the east and west lode, which was reported about 8 feet wide of yellow ore. Shaft No. 1 east was sunk 57 feet in a strong lode of sulphides. At the eastern end red oxide was reported. The last parcel of ore sold from this lode gave 43⅛ per cent. copper. No. 2 shaft, 60 feet, in yellow ore at bottom. No. 3 shaft, 60 feet, lode 5 feet wide; value, 22 to 26 per cent. (Extracts from Russell & Co.'s report.)

The ore was at this time being carted by teams to the Cow Flat smelters at a cost of 35s. per ton.

In 1879 work was continued, but the want of local smelting furnaces was militating against the development of the mine. Subsequently it passed into the hands of Mr. Lewis Lloyd, who had erected smelting and refining works at Lithgow, on the Western Railway line.

In 1880 the erection of reverberatories at the mine was commenced, the ore meanwhile going to the Lithgow works, 427 tons being raised and despatched during the year.

In 1881 the mine was in full work. The original name of Thompson's Creek Mine was in this year altered to Burraga. Four reverberatory furnaces were in full work and three others were in course of erection. One hundred and ten men were employed, 2,500 tons of ore being raised, producing 250 tons of refined copper, valued at £16,000.

The method then adopted is still in force, viz., reducing the ore to regulus of about 40 per cent. grade and refining at Lithgow, where coal and fireclay and easy freightage to market are available. The regulus is carted to Perth Railway Station, a distance of about 40 miles.

[1] Parish Jeremy, County Georgiana. Height above sea level, 3,400 feet.

copper for ten months amounted to £61 16s. 2d. per ton, owing to the extremely low grade of material treated. Higher grade having been obtained from the adjoining property (Hockey's) recently acquired, the cost of production for the last two months was reduced to £49 2s. 1d. per ton. For the twelfth month, the cost was £48 15s.

Working costs (as above) amounted to £1 0s. 6·6d. per ton of ore.

For the year ending 30th June, 1907, 58,159 tons were treated for 1,374 tons of copper—equivalent to 2·36 per cent.

Working costs were increased by amount of dead work involved by faulting displacement to £1 7s. 1·28d. per ton of ore. Detailed expenditure being as follows :—

	£	s.	d.
Mining, including transport to mill	0	11	4·9
Concentrating, including tranfer to calciner	0	5	2·8
Calcining concentrates, and picked ore	0	1	4·8
Smelting calcined concentrates and stalled ore to matte	0	3	8·5
Roasting matte at Burraga	0	1	1·5
Roasting blister copper and matte at Eskbank, and refining same	0	1	8·4
Freight and f.o.b. charges, Sydney (road, 40 miles; rail, 150 miles)	0	1	5·4
Ore purchased at Eskbank	0	0	5·8
	£1	6	6·5
Mine development work	0	0	6·7
	£1	7	1·2

The average cost of producing refined copper, f.o.b. Sydney, was £56 3s. 8d. per ton.

The working costs are increased by the very flat dip of the lode, amounting on an average to only about 25 degrees from the horizontal. Handling ore in the stopes between levels is thus not facilitated by gravity.

Miners descend and ascend by walking; the lowest level, No. 14 (2,135 feet from the brace), is but 705 feet vertically below it.

The width of the lode varies from a few inches to 10, 20, or even 40 feet in places. Its special feature is its cutting across the stratification of the country without defined "walls" or other evidence of fissuring, the ore dying away in the country without definite boundaries. It appears as an impregnation, and in the larger makes as replacement. Possibly this mode of deposition accounts for the obliteration of the actual fissuring or line of weakness along which investing mineral solutions percolated, and wholly or partially saturated and replaced the country for varying distances from the circulating medium; the latter depending on the relative degree of permeability of the different strata encountered.

The lode being antecedent to the faulting encountered, the latter has no influence on its persistence. Denudation limits its western extension until lower levels are reached. Eastward, reversal of dip of the country takes place, viz., from east to west, forming a shallow syncline. Hence it is not unreasonable to anticipate connection between the ore body worked in the Burraga Mine and that opened in the east shaft over 3,000 feet distant.


South cross-cuts to pick up lode as displaced by No. 1 (Main) Fault
do do No 2 do
do do No 3 do
OLD 20' LEVEL
South
An Extension of the Lloyd lode may be located for Approx.
Workings are situated
No. 2 SOUTH CROSS-CUT
No. 1 Fault
No. 3 SOUTH CROSS-CUT
CROSS-CUT as thrown by
by No. Fault
as thrown by No. Fault
Taken from Mine Manager's Plan
North

The faulting is probably an expression of the relief of the dynamic movement which broadly folded the strata enclosing the lode.

The Burraga lode has been faulted extensively into a series of step-like planes, as shown on the accompanying plan and section kindly supplied by Mr. W. H. Corbould. From the nature of the early workings, it is apparent that down throws on a minor scale occurred affording a clue to the nature of the more serious displacement encountered in the eastern extension of the later developments, which for a time baffled progress. To quote Mr. Corbould's report to the Lloyd Company, dated 30th July, 1907: "East from the places mined in the past, in the early part of the year a fault was found to displace the lode to a distance of nearly 300 feet. When the lode was again located and further exploited, it was found that eight subsidiary faults had displaced the lode, although to a lesser degree than the main fault. Still these displacements so disturbed some of the ore lenses as to render them almost unpayable, and made the working of the mine more expensive" Locating the ore east of the faults, and ventilating the cross-cuts, entailed 4,760 feet of driving, sinking, and rising.

After the nature of the disturbance, and the direction and amount of throw had been determined in the first or main east fault, succeeding ones were met with confidence and systematic attack. The strike of the faults being more or less meridional and coincident with the dip of the lode, and their throws eastward; it was necessary to turn almost due south at the intersections to pick up the lode on a level course. In every case the eastern extension of the lode has been determined in the manner described, as will be seen by the south cross-cuts on the accompanying plan of the workings. The main east fault being defined approximately by the eastern boundary of the main stoping (shaded area).

In regard to major and minor faulting Mr. Corbould writes: "With respect to faults it has generally been proved that wherever large displacement has taken place in a particular area, a second big displacement seldom occurs, but that several subsidiary faults may be looked for in that vicinity. Such being the case we can hope that as we get further eastward from the main fault, the country will become more settled, as we have close on 2,600 feet to go eastward to our boundary, there is ample room for long lenses of payable ore to be yet located." (Under date of March, 1908, he informed the Writer that developments in that direction were improving.)

Location of the lode eastward of the main east fault directs attention to the western which appears to cut off the lode in that direction. It is highly probable that the lode exists at a higher level west of the fault which threw its eastern extension down to the main working plane. In this case it will be necessary to drive north to intersect it on the dip. From No. 7 West Drive a level in this direction has been started.

The existence of the lode west of the west fault, however, depends upon the amount of displacement; if it exceeds the amount of cover—about 400 feet above the No. 7 level—then of course the quest is hopeless until deeper levels are reached. It is very probable that the outcrop north of the furnaces will yet prove to be the western continuation of the lode.

In this outcrop an underlay shaft has been carried down 142 feet in a reported strong lode, parts of which show good grade copper ore, further progress was abandonded in favour of the western cross-cut from No. 7 level the main shaft.

The faults strike, at the different levels, from N. 24 degrees E. to N. 3 degrees W., but mostly to the east of north. The dips vary from 40 degrees to 85 degrees, and are all eastward.

The main west fault, which bounds the lode in that direction, strikes N. 6 degrees E. and dips east at 50 degrees.

The fault planes, particularly the main east and west, afford instructive evidence of the force and direction of the sliding movement accompanying the dislocation. As Mr. Corbould reports: "There is in some instances a distinct drag of the ore on the line of fault." Where such occurs, resistance of fragments of the harder silicious lodestuff has developed smooth lens-like kernels in the soft "dig" resulting from shearing of the country along the line of rupture. At one level the metallic face of the fractured lode was striated and polished, or "slickensided."

The extent of the dislocation may probably be gauged by the width of the crushed material in the fault plane.

A sample of the rock 15 feet west of the main west fault at No. 7 level was petrologically examined by Mr. G. W. Card, who determined it as crushed quartz porphyry. This rock is seen outcropping on the west. East of the fault the rock proved to be talcose schist.

Below the lode on the track from the mill a fragmental rock was regarded as quartz-felspar-porphyry tuff.

A typical quartz porphyry outcrops at the Assay Office.

Process of milling and concentration.

The crude ore, averaging about 3·5 per cent. of copper, is tipped from the shaft into a shoot terminating in an ore bin, from the latter it falls into trucks which are hoisted by cable tram-line to the concentrating mill.

(a) From the ore hopper, into which the crude is tipped, the ore is fed into two Jaques' stone-breakers, where it is reduced to 2½-inch gauge. As it passes the feeders to the breakers, the lumps of first grade ore are thrown out by boys tending the feed.

(b) From the breakers it passes through percussion launders with a stream of water into two similar breakers, which reduce it to 1 to 1½-inch mesh. From the feed launders the "firsts" are picked for direct smelting.

(c) The broken ore then passes to two Cornish rolls running at twenty-five revolutions per minute, and is further reduced to ¼-inch gauge.

(d) From the rolls it passes to trommel screens; the over-sized being elevated by bucket-lifts back to same rolls.

(e) The fine material passing the ¼-inch mesh is led into sixteen-hole (to the inch) trommels. The over-sized passes to May Bros. jigs, working at 170 pulsations per minute; the fines to Handcock jigs.

All crushed materials, save the May jig crudes, pass through the Handcock.

(f) Tailings from May jigs, and "middlings" from the Handcock, are re-crushed in Cornish rolls, running seventy-two revolutions per minute. The over-sized, through a ten-hole trommel, is elevated to same rolls, and returned. The fines pass back to Handcock jigs.

Concentrating Mill, Lloyd Copper Mine, Burraga.

BATHURST MINING DISTRICT—*continued.*

(g) Tailings from Handcock jigs are elevated and passed through a sixteen-hole trommel. The over-sized is carried to a small May jig, working at 240 pulsations per minute. The dredgy material from this jig being carried back to fine rolls, and the tailings to dump.

The fines, passing the sixteen-hole trommel, pass through spitzkastens, to be classified for Wilfley and Phœnix-Weir tables. The spitzkastens are divided into six compartments, with spigots.

(h) The coarsest material from the first two spigots of the first spitzkasten passes to Wilfley tables. From the next three on to one Wilfley, and one Phœnix-Weir. The last spigot material, and that from the last two spigots of second spitzkasten, pass on to one Phœnix-Weir table.

The first three spigots of second classifier lead to two Phœnix-Weir tables, and the remaining (or fourth) spigot to a Frue vanner.

(i) Middlings from all tables are re-elevated to classifiers, and repeated on to first and second Wilfley's.

(j) Tailings from all tables and jigs are carried to an agitating classifier, and the fines therefrom pass into a spitzkasten; the coarser material being treated on Phœnix-Weir tables, and the fines on Frue vanners.

The concentrating plant working two shifts, as at present, treats about 168 tons, or at the rate of 224 tons per twenty-four hours.

The loss in the tailings varies from ·9 to 1 per cent.

The water supply is continuously circulated from the spitzkasten levels up.

The average composition of the Burraga ore as mined, and of the milled concentrates therefrom, is shown in the following analyses by the Company's analyst, Mr. E. G. Ritchie:—

	Ore.	*Concentrates.*
Silica	64·0	34·00
Iron	7·6	23·60
Alumina	11·0	9·60
Lime	2·0	1·20
Magnesia	3·6	trace
Sulphur	6·6	18·00
Copper	3·7	13·30

Calcining and Reducing Plant.

The picked "first" grade ore is roasted in stalls of 25 tons capacity, blinded with Frue vanner fines; four days completing the process.

The mill concentrates are fed damp into three Edwards' roasters, of a capacity of 14 to 16 tons each per twenty-four hours. Six hours are occupied in passage from entry to outlet, when the sulphur has been reduced to the desired proportion of about 8 per cent.

The concentrates are charged hot into the reducing furnaces by means of canister trucks running on overhead tramlines to permanent hoppers above each charging hole, five in the large furnace, three in the small, the hoppers having a capacity of about 3 tons each.

BATHURST MINING DISTRICT—*continued*.

The smelting plant consists of :—

2 reverberatory furnaces, 32 x 13—capacity, 30 tons per day.
1 „ furnace, 52 x 13 „ 45 to 50 tons per day.

The actual capacity varies with the character of the ore. In charging, the roasted lump ore and concentrates are mixed. In the process of smelting, the large furnace is kept constantly reducing, and one of the smaller blistering, the other helping both operations at intervals.

The reducing furnaces receive three 12½-ton charges per twenty-four hours —sometimes varied to twenty-five hours in the smaller furnaces. With 8-ton charges, about seven in forty-eight hours.

An average grade of 50 per cent. matte is produced in the first operation, and is tapped into ordinary slag pots, which ensures a cleaner product and saves labour in handling as compared with the customary sand moulds. The slag is also tapped over a small settling pot into large double pots carried on trucks on tram rails, and is removed to the dump by horse traction.

The ore is self-fluxing, but difficulty is experienced when the silica runs high, as shown in the following analysis of the slag by Mr. Ritchie :—

Silica (SiO_2)	49·00
Ferrous oxide (FeO)	33·00
Alumina (Al_2O_3)	12·80
Lime (CaO)	2·80
Magnesia (MgO)	·70
Sulphur (S)	·40
Copper (Cu)	·70
	99·40

If the proposed tram-line for ensuring constant wood-fuel supply be constructed, as proposed, it may also bring the necessary limestone flux within economic reach when the ore runs high in silica.

Smelting is continually faced with shortage of fuel, owing to ever increasing distance of team cartage. The daily consumption at the Lloyd Mine and Works, ranging from 125 to 200 tons is sufficient, to prevent accumulation, *pari passu*, with current requirements. Hence when droughts, strikes, or inclement weather supervene, the furnaces have to be closed down.

The 52-feet furnace is a practical result of the fuel problem, ensuring greater smelting capacity with reduced fuel consumption. This—the largest wood furnace in Australia—reduces 45 to 50 tons of ore on a consumption of about 30 tons of wood, against 30 tons on a 25-ton consumption for the 32-feet furnaces.

A noticeable feature of the Burraga furnaces is the perfect maintenance of symmetry, no bulging or distortion being visible. This desirable result is attributed by the management to secure foundations and thorough under bracing.

Fire Brick, Ordinary Brick, and Fettling Clay.

Utilisation of local clays and ground quartz for manufacture of all classes of bricks effects a considerable saving.

Smelting Works, Lloyd Copper Mine, Burraga.

al analysis by H. B. Gurney reveals the composition of the principal

No. 08–906.—Moisture at 100° C.	·57
Moisture above 100° C.	1·70
Silica (SiO_2)	89·60
Alumina (Al_2O_3)	2·61
Ferric Oxide (Fe_2O_3)	1·70
Ferrous Oxide (FeO)	·36
Lime (CaO)	1·05
Magnesia (MgO)	·72
Potash (K_2O)	·47
Soda (Na_2O)	·35
Titanic dioxide (TiO_2)	·95
Phosphoric anhydride (P_2O_5)	·05
	100·13

xture of this clay with a small proportion of a more binding under- ised for manufacture of bricks for all purposes in kilns and furnaces. hotter parts of the latter, 50 per cent. of crushed quartz is added to

SUMMARY of Output from Burraga Mine.

	Tons of Ore.	Tons of Copper produced.	Value.	Remarks.
			£	
.....	120	.....	.....	43⅛ per cent. of copper.
.....	2,500	250	16,000	
.....	4,450	465	32,550	
.....	6,150	520	36,400	
.....	....	582	40,740	Estimated value.
.....	4,215	440	22,500	
.....	.....	281	14,000	
.....	.....	120	7,500	Three months' work.
.....	.....	499	36,000	
.....	.....	.....	.....	No returns. Mine closed for several months.
.....	.....	420	24,150	
.....	.....	....	....	No returns.
.....	800	80	3,600	Part only smelted.
.....	.....	.....	.....	Restarted.
.....	.....	622	24,880	
.....	3,311	331	14,895	
.....	.....	424	19,928	
.....	8,907	.....	34,896	
.....	8,518 (5,678 firsts smelted).	570	28,500	2,840 tons of seconds, estimated to contain 142 tons of copper; 150 men employed.
.....	10,256	552	36,400	
.....	9,083	667	48,690	
.....	21,508	1,059	64,599	
.....	29,442	1,131	56,500	
.....	65,397	1,852	100,375	Including 8,411 tons from surface dumps.
.....	30,338	802	44,110	Including 4,546 tons from surface dumps.
.....	60,916	1,207	82,076	Including surface material.
.....	60,000	1,223	100,000	
.....	48,000	1,154	98,000	
.....	18,150	536	30,000	To closing down in May, 1908.
	389,221	15,812	£1,020,825	

The Burraga Mine occurs in a belt of highly-altered rocks shading from porphyry into schist and slate? Samples selected by the Writer have been microscopically examined by Mr. Card, A.R.S.M., Curator and Mineralogist, and the following determinations arrived at:—"No. 3,308, a fine-grained rock with gneissose structure. It consists of quartz, plagioclase, calcite, and biotite, with iron ores. It has a fragmentary appearance, but is in all probability an acidic igneous rock altered by pressure. No. 3,307 is much finer grained and highly altered. It appears to represent a more highly-altered form of 3,308."

Burraga District.—About 1 mile south of the Burraga Mine the Mining Exploration and Development Company prospected private land. A lode channel from 3 to 4 feet wide was opened, having a N. and S. strike, and dipping E. at 50°. The lodestuff consisted of quartz, with copper and iron sulphides and a little zinc blende in crushed country. A sample, $\frac{A\,A\,A}{0\,8\,1}$, yielded—copper, 8 per cent; zinc, 16 per cent.; and silver, 2½ oz. per ton.

A short distance west, in the bed of a small creek, a very kindly-looking gossan is exposed for a considerable width. Traces of copper carbonate are visible in freshly-broken fragments. An assay, $\frac{A\,A\,0\,A}{0\,8\,A}$, yielded but a trace of copper—0·1 per cent.—and under 2 dwt. of gold per ton. It has all the appearance of a thoroughly leached cap of a pyritous lode; but subsequent test by shaft failed to discover any workable ore.

Inspector Polkinghorne reported (P.B. $\frac{A\,1\,\frac{1}{2}\,1}{0\,8\,1}$) slate with small veins of copper ore in joints, on Thompson's Creek, about 1½ miles north of Lloyd Copper Mine.

Aided to sink to 100 feet. Last 10 feet of sinking in curly slate, with splashes of copper sulphide. No further record.

McKinney, Hall, and party sank to a depth of 160 feet to the south of Lloyd Mine; nothing of value disclosed.

Bowie and party, on Thompson's Creek, 2 miles south of Burraga, sank and drove 100 feet; traces of copper only.

Eleven miles east from Burraga, adjoining Isabella Public School ground. Parish, Isabella; county, Georgiana.

Inspector Milne reported (P.B. $\frac{A\,8\,\frac{1}{2}\,A}{0\,7\,1}$) a well-defined channel in schist, about 18 inches wide, with bunches of gossan containing splashes of yellow copper ore.

Aided to sink from 13 to 63 feet.

At a later date pyrites, with a little copper sulphide, was reported in bottom of shaft. Vein underlying slightly to the west; water making.

The Burraga Copper Company, Ltd., which took over Stain, Cassell, and party's copper lease, 1 mile east of the Lloyd Mine, continued prospecting during 1900, the underlay shaft being continued to 255 feet. A main vertical shaft was then started, which was expected to cut the lode at 300 feet.[1]

The vertical shaft was down 200 feet in 1901, and was driven 60 feet in a large lode carrying a little copper ore.[2]

Orange Division.

Byng.—In addition to the Carangera, Ophir, and other copper mines near Byng, which receive independent notice, copper ores occur on Mr. W. Hawke's property, about 12 miles S.E. of Orange. The lode was discovered several years ago during fencing operations. It strikes N.E. and S.W., and dips

[1] Ann. Rept. Dept. Mines for 1900, p. 55. [2] *Ibid.* 1901, p. 54.

Lloyd Company's Reservoir, Burraga.

Cadia Copper Mine and Iron Duke Hill.

:. The outcrop is from 1 foot to 1 ft. 6 in. in thickness; at 8 feet ed to 2 feet; below this it appears to pinch. The ores consist of and black oxide, which have not yet been tested. (*See* Hawk's Ratscastle.)

. Webb's property, near Byng, a copper lode occurs, from which ring parcels of ore were treated at the English and Australian Co.'s Works, Waratah:—

6 tons	16 cwt.	yield	19½	per cent.	copper.
7 „	1 „	„	16¾	„	„
3 „	2 „	„	12	„	„

Springfield Estate, Byng, H. B. Thomas sank 90 feet and drove 60 tons of ore raised, stated to assay 10 per cent. copper and 5 dwt. on. (Ann. Rept., 1906, p. 46.)

opper Mine (Old).—The earliest official record of this mine is that in the Official Catalogue of the Sydney Exhibition of 1870; on the Cadiangulong Copper Company was reported to have extensive ve and below ground, including a complete range of furnaces. is situated close to Cadiangulong Creek, 15 miles south of Orange, ied by the Scottish Australian Investment Company, from whom s of past operations are not obtainable. In 1881 the late Govern-ogist—Mr. C. S. Wilkinson—reported the Cadia lode to be 6 feet ss, and the ore chiefly yellow sulphide associated with quartz. It W. at 75°. He also mentioned that about half a mile N.E. from large cupreous ironstone or gossan lode crosses the main creek. Duke.] It has a thickness of over 70 feet, and strikes N. 20° W. ested the lode was not rich enough to work for copper, but Mr. was of opinion that when sunk upon to water-level, where the would be found undecomposed, good ore would be met with.

, 48¼ tons of ore were obtained at Cadia, and a little tributing was 883.

lodes occur on the property, the principal ones being the Cadia Duke. The main shaft of the Cadia reached a depth of about 232 feet vertical, 60 on the underlay, and 40 feet in a winze. The lode 12 feet wide, with good ore at surface, and about 5 feet at bottom, ade and dredgy, with abundant iron pyrites. The main stope was feet long. Work has not been carried on for thirty or thirty-five his shaft. A substantial stone engine and pumping-house was The water, raised by a beam engine, was used for concentrating the remains of a set of jigs are still to be seen. The smelting ere erected on Cadiangulong Creek, a short distance from the mine. n Duke lode in 1898 had been opened by tunnel and shaft. The 300 feet long, according to the Manager of the Scottish Australian Company (which owns the property) starting from the west bank of the sed through the ironstone lode, in which a little copper ore was visible

For a considerable distance after passing the ironstone the tunnel n a most erratic, winding manner, solid andesitic country destitute ce of lode formation.

oss-cuts had been driven from the tunnel in the ironstone lode, and able amount of stoping done, following a vein of good carbonate ut 2,500 tons of ore, averaging about 16 per cent., are reported en extracted under the direction of the late Captain Holman.

Where the creek cuts across the lode a rich vein of carbonate and red oxide, 3 to 4 feet wide, was discovered about twenty years previously, about 40 tons being extracted. A shaft was started about 1897, close to the bank of the creek, to continue opening this find, but was stopped owing to litigation.

On the opposite side of the creek from the tunnel a large face of gossan is exposed, through which traces of copper carbonates are visible. A shaft was sunk at this point. A little ore from it can still be seen at surface, consisting of sulphides of iron and copper.

The latest previous smelting at this site was about 1888, when some 4,000 to 5,000 tons are reported to have been treated.

The tunnel had recently been cleaned out, and was in excellent condition when examined in 1898, but the greater part of its length appeared entirely off the course of the lode, The tunnel-level was too shallow for effective test of the lode; greater depth being required than that attained in winzes—about 40 feet—below the tunnel.

Certainly the shaft on the opposite bank of the creek pierced the sulphide zone, but it is doubtful whether drives, if any, from that level penetrated into the hill to the west. The frequent barrenness of ironstone caps of copper lodes, due to the unstability of copper salts in the presence of leaching solutions, encourages the belief that more concentrated bodies of the ores of that metal may be found below the oxidised capping in this instance. Certainly efforts should not be relinquished until the sulphuret zone has been explored under the main outcrop.

The abundant ironstone of the Iron Duke cap would be of excellent service in fluxing the sulphides from a depth, if such exist in payable quantities; failing this, as a suitable flux for public smelting works it will have a value in the future. The small percentage of copper carbonates disseminated through it may debar its use for iron smelting because of the deleterious effects of copper on iron, rendering it "red-short," or brittle at a red heat.

Whilst writing of Cadia, it is desirable to refer to a report by the first Government Geological Surveyor—S. Stutchbury—in July, 1851, in which he alludes to the existence of strong evidence of copper lodes in the neighbourhood. The following extract contains the reference:—"In a gully or creek called the Waterfall, running into the Cadiangulong or Oaky Creek, at the western end of a section of 640 acres, forming Lot 1, for sale May 7th at Carcoar, and at the extremity of a mountain spur known as the Rocky Range [Canoblas? these creeks rise in the Canoblas.—J.E.C.], there is an immense mass of oxydulous iron, forming in one solid mass a precipitous waterfall of about 60 feet in height. In this mass of iron, especially in the joints, there is brilliant crystallised iron pyrites, with a small quantity of yellow copper ore, and traces of blue and green carbonates of copper. A few yards below the waterfall large masses of yellow ochreous iron 'gossan' occur in the banks and bed of the creek. This gossan contains a considerable quantity of earthy green carbonate of copper, also plush-like malachite. Upon sinking a short distance into it on the eastern side, a rich lode of grey sulphuret of copper was found. In traversing the creek southwards numerous indications of other lodes were visible, together with large masses of mundic." (*See* "Cadia Extended.")

Cadia Copper Mine (*New*).—Portions 83, 86, 87, 27, 29, 30, parish Clarendon, county Bathurst. About 12 miles south-westerly from Spring Hill

Block of Iron Ore—Iron Duke Outcrop—with Canoblas in Background.

Railway Station, and 14½ miles from Orange. Worked under tribute to the Scottish-Australian Mining Company by the Cadia Mining and Smelting Company since June, 1905.

The principal scene of operations is the copper deposit associated with the Iron Duke iron lode, which has been brought into prominence as the most extensive deposit of iron-ore yet discovered in the State.[1]

The East and West Cadia lodes near by are also being worked by the syndicate on a lesser scale for fluxing purposes.

The Cadia or Iron Duke copper lode had already been extensively opened, in February, 1908, when again visited by the Writer, as will be seen in the accompanying plan and section.

The copper ore occurs as a flat sheet immediately under the iron oxide bed. The massive, flat, sheet like outcrop of the latter passes downwards into a mixture of specular iron and pyrite, with a little chalcopyrite and partially-altered andesite, affording evidence of derivation from andesite, as suggested by Mr. Jaquet (*ibid.*), with seggregation of the iron, and leaching and redeposition of the copper below the iron cap. The anhydrous form of the iron oxide is unlike surface oxidation.

Below the latter the enriched copper zone forms a thick bed of gossany ore with oxide of copper and native copper; the latter in places being heavily charged through the loose black oxide. The iron ore will have no value for iron smelting below the seggregated mass forming the superficial cap, unless leached to remove the copper, and roasted to eliminate the sulphur of the pyrite.

The copper lode dips eastward at an angle closely corresponding to the slope of Iron Duke Hill, but the dip is reversed near the creek. This reversal, and the probable identity of the same bed in the Cadia Extended, indicates wavy folding of the original andesite sheet from which the metalliferous deposits probably originated.

The cupriferous oxidised portion in the Iron Duke mine has a thickness of from 10 to 50 feet in places. Denudation, and the eastern rise of the mass at the creek, brings the lode now worked above the water level; hence, sulphide resources can hardly be anticipated in following it. Interest, therefore, centres in the developments *below* the main ore body, which have as yet only been attempted from the deepest, or No. 1 shaft, on the creek sunk. A drive 212 feet west from the bottom of this shaft pierces a low grade mass of specular iron, pyrite, and partially-altered andesite, with a little copper sulphide. An average sample, chipped from the first 56 feet from the shaft, is stated to have returned 2·6 per cent. of copper. It is doubtful whether mechanical separation is possible; hence, the amenability of this ore to blast furnace treatment is the problem to be solved.

Below the main ore-body the main shaft has been sunk 23 feet in a whitish, clayey deposit without change, but there are indications of the low grade body in the No. 1 shaft being at a lower level still. The oxidised copper ore rests, throughout the extensive blocking out drives and cross-cuts, on a similar whitish, clayey floor.

It is very desirable that the main shaft should be continued below the known ore bed in search of others that may exist.

---

[1] *Vide* J. B. Jaquet, Mem. Geol. Surv. N. S. Wales, No. 2, 1901, pp. 27-30.

The copper bed has been proved by several shafts for a width of abou 200 feet, and has been followed on its rising western longitudinal extensio under Iron Duke Hill for 780 feet from Cadiangulong Creek, which partiall intersects it.

The main shaft is the most western in the hill, it cut the copper zone at depth of 64 feet, immediately below the iron cap. The copper lode has he a thickness of 22 feet 6 inches, and, as already indicated, an eastern di Whether it persists to the rise under the whole of the iron cap, or whethe the leaching solutions followed the inclination of the bedding until sufficie cover or depth was reached, remains to be proved by a continuous weste level. Certain it is that at no great distance below the summit of the hil and a long way west of the workings, copper carbonates have been exposed t a small extent in the solid iron cap, the results of a bulk assay test which by the Syndicate's analyst, D. C. Winterbottom gave :—

Copper	4·1
Iron	57·0
Alumina	4·0
Silica	5·8

A further sample taken by the Writer, gave the following :—

No. 08–580—Copper	4·70	
Gold, a trace	}	per ton.
Silver, 8 dwt. 17 grs.	}	

In the 120-feet level from the main or No. 6 shaft, the lode includes large mass of specular iron and pyrites, with occasional bunches of chalc pyrite, the lode here having a thickness of 17 feet 6 inches to 22 feet 6 inche

From the 67-feet level in No. 5 shaft a winze was being sunk, at the corne of south and south-west drives, in rich black oxide heavily charged with mos or less granular metallic copper worth from 30 to 40 per cent. The lode in thi level runs up to 50 feet in thickness.

In the outcrop on the east bank of Cadiangulong Creek, opposite No. shaft, a shaft was sunk and a tunnel driven east, during earlier working Traces of copper carbonates are visible in the bluff face entered by the tunne Particulars of these provings are not available, but fragments of mine sulphides are still at grass.

Further east—up the slope of the ridge—is the section known as Ea Cadia, with Chilcott's shaft, now being worked by the Cadia Syndicate f sulphide flux. The latter was cut at a depth of 72 ft. At 100 ft. a le was opened for a length of 90 ft., and a width of 12 ft., containing sulphi of copper, in part bornite, the average copper value being about 4 to 5 p cent. The boundaries are not well defined owing to absence of walls any marked division between ore and country.

The West Cadia lode is distinct from the Iron Duke, and close to th original Cadia lode, opened about 1862.

It strikes about N. 70° E., and was extensively opened by seven shafts an a tunnel, the latter extending for over 1,000 feet, in the earlier days copper mining in this locality. Apparently the tunnel level is the lowe

vertical proving. The Cadia syndicate is cleaning out the latter and stoping up in places for sulphide fluxing ore, which is improved by association of limestone, having the following composition:—

No. 08-582—Calcium carbonate ($CaCO_3$)	96·78
Ferric oxide and alumina ($Fe_2O_3 + Al_2O_3$)	1·16
Gangue	1·48
Magnesium carbonate and undetermined	·58
	100·000

The copper ore is erratic in mode of occurrence, and not persistent in the channel. Bunches of good ore occur in places, but die out in the andesite country. Walls, or dig, or any marked lines of division between ore and country are absent. The limestone, as calcite, occurs in parts in irregular bands and lenses.

Judging by the plan of early operations a good deal of stoping, in the aggregate, has been done above the tunnel level, from shafts and intermediate levels, chiefly in isolated blocks or lenses. The greatest amount of backs above the tunnel level being 240 feet in the west, or Rodd's shaft, but stoping in the latter does not appear, by the plan, to have been carried below 90 feet from surface. The principal stopes lie between Gundy's and Johnson's shafts. The average value of the ore at present being mined in this section is 4 to 5 per cent.

The composition of the Cadia ores, sold, and smelted locally, is well shown in the following analyses by Mr. D. C. Winterbottom:—

Lode.	Ore.	Copper.	Iron.	Alumina.	Insoluble.	Sulphur.	Lime.	Remarks.
		%	%	%	%	%	%	
Iron Duke.....	Oxidised—"Firsts"*	12·8	32·1	9·4	23·0	6·0	..	Four weekly tests.
,, ...	,, "Seconds"	6·8	31·2	11·0	30·0	6·0	..	.....
,, ...	Sulphides from 56 feet, along west drive, No. 1 shaft.....	2·6	35·0	10·4	24·0†	6·0	..	†Silica.
,, ...	Specular iron and pyrites, west drive, No. 6 shaft, 79-feet level	2·1	44·6	8·0	17·5†	6·1	..	† ,,
Chilcott shaft—East Cadia.	Sulphide—one sample	6·3	24·0	6·5	39·0	..	5·0	.....
West Cadia	From winze below adit	5·7	7·0	7·0	50·0†	..	8·0	†Silica.
East and West Cadia.	Average of three weekly samples at furnace	4·2	19·5	9·2	52·0	8·0	..	.....
South Flux shaft	Specular iron and pyrites (Flux)..	Nil	20·0	..	36·0	22·6	11·2	.....
	Slag from reverberatories—average of three weekly analyses	·9	44·2‡	15·4	37·6	..	1·4	‡FeO.

* Average assay of all "firsts" sold to smelters for twelve months ending 25th January, 1908, was 13·3 per cent. (wet assay) of copper.

The value of the Iron Duke oxidised ores taken, by Mr. F. Danvers Power, from twenty-eight different faces in the workings ranged from 1·0 to 14·8 per cent. copper, and averaged 6·8 per cent.

The total output from June, 1905, to the end of 1907, amounted to 5,662 tons, the copper contents of which totalled 1,009 tons 17 cwt. 3 qrs. 16 lb., equal to 5·6 per cent.

Of the above amount part was marketed in the form of matte, ranging rom 41·6 to 72·8 per cent in copper contents.

BATHURST MINING DISTRICT—*continued.*

The Syndicate estimates that there were 3,968 tons of third the end of the year, of an assay value of 4 per cent copper.

During the period mentioned upwards of 3,300 feet of si driving, &c., were carried out in provings and blocking out.

Smelting plant.—The smelting plant consists of—

2 Reverberatory furnaces, 18 ft. x 11 ft., inside measurement	}	Capa
1 ,, ,, 21 ft. 6 in. x 11 ft., ,, ,,		tons
1 ,, ,, 22 ft. x 11 ft. ,, ,,		

Smelting charge.—Small furnaces { 8 cwt. sulphides ores, 32 cwt. oxidised ores } Matte, 50 pe produced tion.

,, Larger ,, { 10 cwt. sulphides ores, 40 cwt. oxidised ores }

Firebricks obtained from Lithgow, and from Bathurst (Dew red brick made on the estate.

Clay from Reserve 70A, parish Clarendon, county Bathurst, c for lining and plugging.

About 200 men are employed at Cadia, including wood-cutters The Syndicate dispatches first-grade ore to Newcastle, averag to 16 per cent. copper; the seconds being smelted locally.

Carriage by team to Orange costs 12s. 6d. per ton; rail the castle costs 11s. 10d. per ton; total, 23s. 10d. per ton.

Construction of a branch railway from the nearest point c Western—an estimated distance of about 12 miles—would gre the interests of the district, both mining and agricultural.

If the iron smelting industry at Lithgow prospers, as is de wished, tapping the iron ore resources of Cadia will become With such an accomplishment, the financial aspect of the rai confidently faced.

The clay used for fettling is obtained from Reserve 70A, parisl county Bathurst, about 3 miles from the mine. Its composition the following analysis by Mr. H. P. White:—

No. 08–511—Moisture at 110° C	**3·38**
Water above 110° C	**4·48**
Silica (SiO_2)	**73·52**
[1]Alumina (Al_2O_3)	**9·75**
Ferric oxide (Fe_2O_3)	**4·55**
Ferrous oxide (FeO)	**·36**
Magnesia (MgO)	**·58**
Lime (CaO)	**·52**
Potash (K_2O)	**·79**
Soda (Na_2O)	**·65**
Titanic dioxide (TiO_2)	**1·10**
Organic matter	**·16**
	99·84

Cadia Extended Copper Mine (formerly Canoblas) portions 28, parish Waldegrave, county Bathurst, about 2¼ miles from Cadia

Occurs in andesite, and after same manner as the Iron l probably forming part of the same extensive sheet.

In the bed of a small creek, which dissects the mass for perha feet, a large mass of oxide and sulphide of iron with a little co forms the waterfall described by Stutchbury in 1851 (p. 128.).

[1] **Including a very small amount of phosphoric anhydride (P_2O_5).**

View of Cadia Smelting Works and Village.

CADIA COPPER MINE

Iron Duke Workings



CROSS SECTION

Projected down from a N and S. line passing through ND Intermediate Level, No. 6 Shaft, and another N. and S. line through No. 3 W Adit Level

The workings are shown between these two points



CROSS SECTION

Showing workings between Air Shaft and No. 2 W. projected down from N. and S. lines drawn through these two points



Taken from Mine Manager's Plan

23423

PHOTO-LITHOGRAPHED BY W. A. GULLICK, GOVERNMENT PRINTER, SYDNEY, N.S.W.

On the east bank of the creek two shafts have been sunk, 40 feet and 80 feet and connected at the former level. In these shafts the ore is mostly pyrite, or a mixture of pyrite, specular iron, and andesite.

From the lodestuff extracted in driving 35 feet east from the 80-foot level, an average sample yielded :—

No. 08-583—Copper	1·30	per cent.
Iron	37·24	,,
Silica	20·75	,,
Sulphur	3·52	,,
Gold	1 dwt. 2 grs.	per ton.
Silver	5 dwt. 10 grs.	,,

From north-west drive at same level :—

No. 08-584—Copper	6·22	per cent.
Iron	21·56	,,
Silica	27·08	,,
Sulphur	14·33	,,
Gold	a trace.	
Silver	1 oz. 6 dwt. 3 grs.	per ton.

Fourteen assays by Mr. D. C. Winterbottom gave an average of about 3 per cent. of copper from what must be regarded as the enriched zone. Deeper tests are necessary to determine the true value of the sulphides.

A 60-ton blast-furnace was in process of erection in January, 1908, by the Cadia Extended Mining and Smelting Company.

A few hundred yards below the Cadia Extended a slightly pyritic mass in sedimentary strata, locally designated the "Sulphide Lode," has been intersected by the same creek. It differs essentially from the andesitic lodes, and is unpromising in its superficial character.

A sample chipped across the face of the bluff, and another selected from the most pyritic portions, gave no reactions for copper, and traces only of gold and silver.

Under the name of *Canoblas Copper Mine*, the Cadia Extended deposit was opened prior to 1859; but beyond a little sulphide ore being extracted occasionally to assist in fluxing the ores of the old Cadia Mine, little work was done.

Mr. S. L. Bensusan states :—"The copper lode was developed to a small extent about 1862, when several parcels of good-quality ores were forwarded to and sold in England. Since that period, some 300 or 400 tons of copper ore have been smelted at Cadia Copper Works, chiefly of low-grade percentage, obtained solely from the adit level extended about 30 fathoms into the eastern hill.

Canoblas.—Copper ores and native copper are associated with rocks of similar composition to those of the Canoblas in the Orange, Carcoar, and Wellington District, and their possible connection was referred to by Geological Surveyors David and Stonier ($\frac{1}{250}$) in the following terms :—

"Near Orange we inspected the Canoblas, the great extinct volcanoes of New South Wales, and found, as we had previously suspected, that the copper-bearing rocks of Waugoola and Walli, alluded to in previous geological reports, are probably lavas which have flowed from the vicinity of the Canoblas, and perhaps had their source in the Canoblas themselves. These lavas, as well as those seen at the 'Old Man Canobla,' are not basalts, but andesites, a variety of volcanic rocks, whose existence in extensive sheets like these has hitherto never been recorded in New South Wales. Copper

occurs locally, in a metallic state and as green carbonate, in the steam holes of this rock near Walli, and in a vein in the same rock near Wood's Flat at Waugoola."

Carangara (or Carangera) Copper Mine, Byng (formerly known as the Cornish Settlement).—On 12th April, 1851, Mr. S. Stutchbury reported, after an inspection of this property: "The rocks, or 'country,' as the miners term the strata in which the lodes occur, are principally composed of clay-slate, chlorite and talcose schists, with veins of quartz. No elvan has yet been seen; the lodes, large and small, are very numerous. No 'Champion' lode has yet been met with. The 'Master' lodes appear throughout the district to have a direction N. 20° W., with small, bifurcating, diverging, and large branches. The underlay is westerly, at an angle varying from 40° to 62°. At the level of the creek, and 27 feet to the north, they have commenced driving an adit which they find will clear them 18 fathoms from water."

Three shafts had been sunk at that time above the tunnel-level, but no particulars are given. The ores above the 10-fathom level are stated to have been similar to those of the Coombing Park Mine, near Carcoar: below that level sulphides occurred.

In August, 1854, a Select Committee of the Executive Council reported on the Carangara Copper Mining Company's Incorporating Bill, the company having been projected about sixteen months prior to that date—April, 1853. The object of the company, as stated in the Bill, was to work copper lodes in certain lands, and to purchase metallic ores, &c. The extent of the Carangara Estate being three portions of land 320, 156, and 320 acres respectively, in the parishes of Byng and Anson, county Bathurst, formerly the property of Messrs. Lane and Glasson.

Copper ores from the mine were exhibited by the company at the Paris Exhibition of 1855. Mining and smelting were carried on in this locality for a number of years, but no particulars are obtainable of the output.

In the vicinity, and extending to Lewis Ponds, the following mines were opened and worked about this time, and later, viz.:—Britannia, Belmore, Moonta, Nelson, Gurophian, Ophir, Icely, East Block, Mt. Fraser, Algar and others. Under the title of the Great Western Copper Mining Company Ltd. (which *see*) most of these mines were floated into a public company in 1872; the first half-yearly report being issued in February, 1873.

In the Mineral Statistics of New South Wales prepared for the Philadelphia Exhibition in 1875, the following particulars are given of the lodes worked at that time by the Carangara Company:—

Thickness of lode at	30 feet =	3 inches	Strike, N. 15° W. Dip, 60° westerly.
,, ,,	180 ,, =	12 ,,	
,, ,,	240 ,, =	18 ,,	

5,600 tons of ore raised yielded 784 tons of copper. Method of treatment being heap roasting and reverberatory smelting.

In [illegible] p. 131 the late Government Geologist, Mr. C. S. Wilkinson, visited Carangara; the mine was then idle. Mr. Wilkinson described the main shaft as being in a lode striking N. 15° W. through altered serpentinous schists and conglomerates, and dipping W. 20° S. at 53°. Near its southern end a wide quartz reef striking E. 10° N. meets the lode almost at right angles. Five chains higher up the creek is a wide quartz porphyry elvan 20 feet wide, apparently running with the strike of the beds. Two other

large quartz reefs occurred about half a mile further north. Mr. Wilkinson expressed the belief that the reefs and copper lodes would be found auriferous, which was subsequently proved. In 1886 both gold and silver were found to be present in the copper ores, and operations of late years have been confined to winning these metals. Tributing for gold was carried on in the old mine for five years, but ceased in 1898, owing to the owners' intention to work the mine.

The Gold and Copper Fields Syndicate reopened this mine in 1900. Mr. L. Parker, A.R.S.M., under date March 12th, 1900, stated:—"That from the 'Bull' lode, about 200 feet west of the main lode, the greater part of the ore mined, was taken at one period."

An adit on main lode was driven 1,050 feet, and a vertical shaft sunk 200 feet to the west of the lodes, all previous to 1890.

In 1898 the vertical shaft was repaired and sunk to 214 feet, and a cross-cut put out to meet lodes.

An attempt to smelt Mount Fraser (P.G.L. 14) ore was made by the Springfield Pastoral and Estates Company, which owned and worked the mine, but was not persisted with.

Carcoar Division.

Carcoar District.—In April, 1851, Mr. S. Stutchbury, after describing the Coombing copper lodes, goes on to state that "the ranges south of the Carcoar Creek, east of the Coombing Estate, and west of Mount Lachlan 'Cambulla,' consist of alternating schists and syenite or granitic rock.

"On the two spurs from the little Mount 'Cambulla-narang' [Little Mount Macquarie?—J.E.C.], I have opened several lodes of copper. The first appears to take a course W. 12° N. and E. 12° S. This lode close under the grass carries a thickness of 2 feet, with its underlay to the southward, and much valuable ore, principally tile ore and green carbonate of copper.

"In the creek about 150 yards north the back of another lode appears nearly 6 feet wide; this may be traced direct north over the next range until it reaches the main creek. On the summits of its course it is overlaid by rich crystalline magnetic iron ore.

"There also appear in the escarpment at the north end evidence of two parallel lodes, one on the eastern and one on the western side of the lode before described; these three lodes would not extend beyond 200 yards in lateral distance."

From camp near Curragurae, he wrote further of this district, on the 18th July, 1851: "A few yards above the spring [on Lundy Swamp where Couragee Rivulet takes its rise.—J.E.C.] there are several lodes of 'gossan' carrying iron pyrites. At the mouth of the second gully below, several veins of chloritic, talcose, and quartzose stuff with great abundance of mundic; those I have but little doubt are the backs of lodes of yellow copper. On the west side of the main creek, immediately opposite the second gully below the upper fall, by moving a large body of rock containing pyrites, I discovered a fine vein of yellow sulphuret of copper, accompanied by green carbonate of copper; its width is about 1 foot 6 inches; from appearance it was likely to be joined by two other thin branches or veins of yellow copper.

"At the first waterfall on the Maramur or Flyer's Creek, direct south from the spring heads, in Long Swamp, there is a lode of yellow sulphuret of copper crossing the creek direct east and west from section 1, Church and

School Lands, into section of land consisting of 443 acres 3 roods 1 perch, for sale at Carcoar, 7th May [1851.—J.R.C.] There is a small lode-crossing in the same direction a few chains further south."

Between Carcoar and the Coombing Park Estate, at the north boundary of the latter, Messrs. Links discovered traces of copper carbonates dipping rather flatly westward in schistose—or crushed—hornblende porphyry. Two shallow shafts were sunk, and a third was being put down to cut the lode at a depth. A sample of copper pyrites from this site yielded $\frac{1}{15}$ copper, 26¾ per cent.

In $\frac{1}{p.d.}$, a copper lode was discovered whilst making a road from Carcoar to the Cobalt Mine on McKillop's property. The Mining Registrar reported that a shaft was down 25 feet, and ore was being raised for despatch to Newcastle, but evidently the quantity was very limited. A sample yielded $\frac{1}{8}$ copper, 11 per cent. From Stoke's Estate, half a mile east of Carcoar, samples of copper pyrites, $\frac{1}{8}$, and $\frac{1}{11}$, yielded 26 per cent. of copper, and 2 to 3 oz. of silver per ton.

Rockley Division.

Cash-Essington Mine, portion 2, parish Adderley, county Westmoreland, Native Dog Creek, Essington.—The Cash Shaft is a new opening on the southern extension of the old Essington lode in the adjoining portion. Strike N. 20° W., dip S. 70° W. at 30° to 40°.

In 1905 aid was granted to sink the 20-feet shaft to 100 feet, on a lode reported by Inspector D. Milne as 3 feet wide (P.B. $\frac{1}{0}$). Later, on sale of mine to the Lloyd Copper Company, this aid was refunded.

The shaft is 250 feet deep, and driven at the 150-feet level 100 feet north and 80 feet south. No stoping done. The lode averages 2 feet to 2½ feet wide, making in places to 4 feet. At 200-feet level, driven 25 feet on course of lode.

The ore consists in the lower levels of sulphide of good quality, but mixed with quartz and country in part.

During the above development, in 1906 and 1907, 121 tons of ore raised yielded an average of 8·7 per cent. of copper.

The Old Essington Mine is situated on the south bank of Native Dog Creek, a few chains along the northern strike from the Cash Shaft. On the opposite side of the creek is the original North Essington, also on the same lode, where a shaft was sunk 30 feet, and a tunnel driven from the bank for 30 feet.

West of the Cash-Essington lode, three parallel lodes occur in portions 3 and 5, within a distance of about 20 chains. These appear to strike from N. 50° to N. 70° west, and are of silicious character. A fair amount of ore has evidently been extracted from some of them, judging by the dressing heaps.

The Essington lodes occur in a schistose rock of hornblendic character, which alternates with several quartz-felsite dykes; the copper ore is confined to the former.

Definite particulars of early developments in the Essington and Western lodes are not available. The former is stated to have been sunk on for 100 feet, and driven south at that level for 80 feet or more. About 1899 this shaft was unwatered and cleaned out by C. Richardson, who extracted some ore. A tunnel was also driven in from the creek bank in the early days of copper-mining in this locality.

In connection with the above lodes a reverberatory furnace was erected about 1873 or 1874.

Eastward, on the opposite side of Native Dog Creek, several other adjacent lodes occur, on which are the Fullback, Prosper, Integrity, and Murphy's mines (which see), all occurring in the hornblendic schist, in close proximity to quartz-felsite.

It would appear, from the number and nature of the copper lodes in this locality, that there is room for the operation of a company controlling the whole, with a central smelting plant on the permanent creek, where an adequate water supply could be conserved.

The direct smelting ore from a coarse breaker could be picked by hand, and the balance submitted to concentration; in which the predominant quartz gangue would insure good milling results.

Carcoar Division.

Coombing Park Copper Mine, about 2 miles S.W. of Carcoar.—After the failure of the Belubula Copper Mine (opened in 1845), the mining captain, Mr. Reed, proceeded to open the Coombing Park lode for the late Mr. T. Icely, the date being probably prior to 1850, for in April, 1851, the first Geological Surveyor—Mr. S. Stutchbury—reported that the lode had been opened to some extent. The report is valuable as the only one extant on this property. Of the mine Mr. Stutchbury wrote:—

"Its geological position is upon an 'elvan' course in greenstone slate with occasional bands of clay-slate; compact hematite iron with magnetic brown oxide of iron compose the 'back of the lode'; standing above the grass the strike or level course is N. 28° W., underlaying to the eastward at an angle of 61°. The shaft was sunk perpendicularly 10 fathoms, when it touched the footwall of the lode, which exhibits 'slickensides,' killas backed by elvan; at this point a 'plat' was formed, and a 'drift' cut across the lode to the extent of 30 feet. It is not satisfactorily known whether the 'headwall' or 'hanging wall' was reached. The shaft was then turned down vertically on the drift. The angle has since been cut away, and the back filled in; it now proceeds on the incline of the underlay.

"A plat 15 feet x 12 feet was cut at 16 fathoms; in this plat a 'slide' or 'fault' has shifted the metallic run of the lode 4 feet to the eastward. At this point some very encouraging evidences occur. There has not been any driving on the level course or drift, but merely an extension of the plat.

"At 20 fathoms a level course has been worked 31 feet to the northward and 33 feet southward. The level is 3 feet wide and 6 feet high. A cross-drift 27 feet in length has been made opposite the shaft, at which place the miners pronounce the headwall to be; this is not proved.

"At the north end of the level there is a considerable quantity of soft 'killas,' the joints and laminations of which are filled with beautiful vermilion red oxide of copper 'chalcotrichite' minutely crystalised. This appears to accompany the line of strike or fault. Upon driving about 4 feet in drift the face of the slide was observed. The shaft has been sunk 10 fathoms below. At 30 fathoms water was cut into; at present it is easily kept under by the 'kibble.'

"Of the lode itself, it will be evident, by the description of the workings on level courses, and on drift across the course, that there are 30 or more feet between the two rock walls."

BATHURST MINING DISTRICT —*continued.*

The mine appears to have been abandoned for a number of years prior to 1876, when Messrs. Samuel and Lloyd reopened it and erected smelting furnaces, one being in blast during that year. Operations were continued during 1877; but in the following year, after considerable unremunerative expenditure, the mine was handed over to the owner, Mr. Icely, who carried it on for a couple of years longer. The main shaft was sunk about 150 feet, and the lode driven on for a considerable distance. It is reported to have been very patchy, the ore bunches sometimes having a thickness of 1 foot or over.

During a visit to the site in 1898 a sample was selected from the old tip, consisting of ferruginous carbonates of copper with garnet rock, for the purpose of testing it for the presence of gold. A trace only was found (under 2 dwt. per ton).

A short distance from the mine, on the same estate, excellent iron ore is now being quarried for the Lithgow iron smelting furnace. Prior to the erection of the latter, the ore was largely used as flux.

Mr. Stutchbury, in 1851, was much impressed with the iron resources of the estate, and wrote :—

"In the great park at Coombing the summits of five small mountains or hummocks (of from 20 to 50 or more acres each) are composed of a very rich compact hematite iron, much of it magnetic.

"A similar ore of iron forms the back of a copper lode on the same estate

"The apparent quantity of iron is so immense, and if all things else were compatible with manufacture of iron, there is sufficient to supply another Sheffield for ages to come. At the present time I would suggest the examination by shaft or level of the interior of one of these mounds, as it is possible that the iron may be laying on the back of a 'room,' or the cross junction of metallic lodes of higher commercial value than the iron.

"Near Mr. Icely's residence, in one of the paddocks, a copper lode has been discovered and opened to some extent, but not more than was necessary to demonstrate its capabilities. In comparison with those I have examined in this Colony, it certainly is of high promise."

In 1900, a shaft was sunk 100 feet in the principal iron outcrop, under aid from the Prospecting Vote. A cross-cut at that level revealed 100 feet of iron ore.

Molong Division.

Copper Hill Copper Mine, part of portion 5, parish Copper Hill, county Wellington, about 2 miles south of Molong.—This was one of the first—if not the first—copper mines opened in New South Wales, its early discovery being doubtless due to its exposed situation close to the old Sydney to Dubbo road, which passed by the side of the hill, where the characteristic green and blue colourations of copper carbonates are still visible in the remaining portions of the rugged outcrop.

Mr. James Rankin states that he saw mining operations in progress in 1845. In 1847 a company was formed to work the lode—Mr. (afterwards Sir Saul) Samuel being managing director. Shafts were sunk 70 and 146 feet, and smelters erected. A quantity of ore was converted into regulus and carted to Sydney, but no records of the amount are available. The company ceased operations in 1851 when gold was discovered. In 1852 Geological Surveyor Stutchbury reported the mine as "deserted" and not accessible." He described Copper Hill as consisting of "elvans" and decomposed clay-slates, followed by porphyries, with occasional altered slates,

until it joins the granite of Molong mentioned in his former reports. The following information was derived from a Mr. Clymo, formerly manager of the mine. He first describes "Hood's" shaft to be 21½ fathoms (189) feet deep; the first vein or bunch of ore was struck at 45 feet; it consisted of green and blue carbonates with red oxides; a level was driven 180 feet north. The first shaft was sunk alongside a smooth slickensided wall on which were found strings of native copper. Another level or cross-drift was cut 60 feet east, when a lode of quartz and ore was found 9 feet wide, and dipping to the east at an angle of about 20 degrees. Some unsuccessful attempts at smelting had been made, the failure of which Mr. Stutchbury attributed to probably the unsuitable open-mouthed furnaces adopted.

In 1871 the Molong Consols Copper-mining Company was formed, according to local report, on the strength of statements of the large amount of ore available at grass. Three reverberatory furnaces were erected, but only one was charged; but it is evident from its internal and external condition no regulus or refined copper was produced. Practically little prospecting was done by this company beyond surface work.

In 1885, C. S. Wilkinson, Government Geologist, visited Copper Hill, and described it as a huge mass of felsite, with hornblende porphyry in places, traversed by numerous lodes or dykes of porous ferruginous quartz. In connection with the latter, it is interesting to note that the late Mr. J. E. Kelly, on whose estate the hill occurs, submitted 14 tons from it and neighbouring outcrops to battery treatment for a return of 4 dwt. of gold per ton. A sample of the copper ore lying at surface was selected by the Writer, but yielded under 2 dwt. of gold per ton by assay.

About 1888 a Newcastle syndicate carried on a little surface prospecting higher up the hill.

A good deal of copper carbonate is mixed in the fines and screenings from the old workings, but are unsuitable for direct furnacing. The outcrop has a very deceptive appearance at a distance, owing to the strong blue and green colourations in sheltered crevices and excavations, arising from the internal leaching of the thinly-distributed copper ores and redeposition in the form of sulphates and carbonates in sheltered spots by evaporation of the percolating solutions.

The Copper Hill Copper-mining Company was formed in 1907. After unwatering and prospecting the mine was abandoned, and the machinery removed; nothing workable being discovered.

Oberon Division.

Copper Hill (Foran's) near Wiseman's Creek.—Old workings reopened by two new shafts following underlay in oxidised zone only.

Lode in the principal new shaft strikes north and south and dips east at 38°, and consists of about 1 foot of dredgy quartz and country with copper carbonates. The workings extend over a distance of about 200 feet.

A sample of the dressed ore at grass yielded :—

No. 08-915—Copper	.....	9·22 per cent.
Gold	.....	a trace per ton.
Silver	.....	2 oz. 3 dwt. 13 grs. ,,

Two loads of ore despatched in July, 1907, were reported to have yielded 16·4 per cent. at Lithgow.

Copper Mine Creek.—See p. 274.

BATHURST MINING DISTRICT—*continued.*

Tuena Division.

Cordillera Hill, parish Tuena, county Georgiana.—Mr. Warden T. A Smith states that this lode was discovered in the early 80's by Phillip Hyde. The Cordillera Hill Silver-mining Company, which started operations during the silver boom of 1888, extracted 222 tons of copper from their silver ore during that year. The exact figures, according to the Warden, $\frac{1888}{p.188}$, being: 9,000 tons of ore treated, yielding 82,800 oz. of silver, 404 oz. of gold, 227 tons of lead, and 222 tons of copper, valued at £37,343.

A depth of about 180 feet was reached before closing down in 1889.

The kindly gossan ores of the outcrop at Cordillera, just as those of the neighbouring Mount Costigan and more distant Lewis Ponds and Sunny Corner mines, gave place at water-level to refractory mixtures of sulphides of zinc, lead, iron, copper, and arsenic, of low grade, which so far have baffled every attempt at profitable working, especially since the serious fall in silver value.

It is noteworthy that scheelite (tungstate of lime) and stolzite (tungstate of lead) occur in the Cordillera Mine.

(Reopened in 1907 by the Mt. Costigan and Cordillera Company. Under suspension in 1908.)

Rockley Division.

Cow Flat Copper Mine, about 7 miles from George's Plains Railway Station.—According to Captain W. R. Reynolds, the first ore raised from Cow Flat was shipped to England. The earliest official record is contained in the Annual Report of the Department of Mines for 1875, p. 59. At that time eighty men were employed, and a statement is made that the yield had not decreased during the past twelve months, considering the number of men employed. Six furnaces had been erected, but only two were in use, owing to the sheds being leased to the Esk Smelting Company, who reduced the ore to regulus, and forwarded the latter to their refining works at Lithgow.

In 1872 the mine was floated into a public company by Mr. S. L. Bensusan.

In $\frac{1871}{p.211}$ Mr. C. S. Wilkinson reported that "the general formation of the Cow Flat district consists of Silurian sandstones, shales, limestones, and talcose, chloritic, and micaceous schists, traversed by numerous quartz reefs, some of which are of great thickness, and termed by the miners 'blows.' The general strike of the strata and reefs is N. 25° W., dip easterly, though near Bell Creek they strike N. 30° E., and dip westerly. Copper ore occurs in many of the reefs. The green and blue carbonates of copper are generally found near the surface, and passing downwards the black oxide, or 'coated' ore, is met with, and below this the grey and yellow sulphurets with galena, occasionally the red oxide and a little native copper are found. The irregular and uncertain mode of distribution of these ores is the chief cause of so much fluctuation in the copper-mining industry of the district."

In $\frac{1877}{p.97}$, the Mining Registrar reported that thirty men were constantly employed during the year, 80 to 100 tons of ore per month being raised of an average value of about 8 per cent., which was disposed of to the Esk Smelting Company at about 60s. per ton. Depth of shaft, 180 feet; lode from 6 inches to 10 feet in thickness.

In $\frac{1878}{p.72}$, the work performed was not equal to that of former years, owing to the low price of copper. About 220 tons of ore were raised, which yielded 20 tons of copper, valued at £1,100.

In 1880 the mine was leased to Mr. Lewis Lloyd. A new shaft was sunk 72 feet, about 400 yards from the old workings; the result, however, was

not as satisfactory as expected, the lode was well-defined and 2 feet thick, but the grade was low. 376 tons of ore were raised during the year, and sold to the Bowenfels Smelting Works for £813.

In 1881 three new shafts were being sunk. The deepest level in the mine was 180 feet. 387 tons of ore were raised, and sold for £876 17s. 3d. Being smelted at Lithgow, it yielded 28 tons of copper, valued at £1,620.

The Cow Flat lode has a very strong iron outcrop, which doubtless induced hopes of good things below, unfortunately not to be realised so far as testing has proceeded. The lode, judging from the outcrop, practically consists of hornblende and choritic schists impregnated with iron and a little copper pyrites, which under atmospheric influences have become converted into iron oxides and copper carbonates for shallow depth only, for the unaltered sulphides are visible in the open cuts. A sample of the unaltered pyrites selected from one of the shaft tips during a visit in 1898 yielded 5·20 per cent. of copper and a trace of gold (under 2 dwt. per ton).

In 1900, according to the Annual Report of the Department of Mines, p. 55, the Cow Flat lode was secured by a syndicate, which continued prospecting for some time. Frequent small bunches of ore were met with; 400 tons raised, valued at £400.

Cow Flat District.—In 1899 Inspector Polkinghorne reported on an application for aid (P.B. $^{1}\frac{8}{9}\frac{1}{9}^{8}$) for a site about 1½ miles north-west of Cow Flat Mine, carbonate of copper having been extracted from old workings some years previously. Aided to sink from 15 feet to 100 feet. Sank 50 feet, then apparently abandoned, there being no further record.

Dolomite mixed with calcite, about 3 miles from George's Plains, is being quarried for basic lining in the iron smelting furnace at Eskbank :—

Composition—Carbonate of lime ($CaCO_3$)	54·28
,, magnesia ($MgCO_3$)	39·34
Alumina and oxide of iron ($Fe_2O_3 + Al_2O_3$)	0·46
Gangue	5 78
	99·86

Mount McDonald Division.

Cowra District.—Ballantyne and party's shaft, G. Lockyer's private land, parish Cowra, county Bathurst, 3 miles east-north-east from Cowra.

Inspector G. Smith reported (3rd November, 1906) copper ores in quartz porphyry—striking east and west, and dipping south. Depth of shaft 46 feet. Length of outcrop 300 yards.

Blayney Division.

Diamond Hill, Guyong.—J. H. Glasson's private land. Copper lode reported traversing this property, containing a little gold. Opened to a depth of 100 feet by three shafts; driven 60 feet. (Annual Report, Department of Mines, 1902, p. 49.)

Rockley Division.

Dolcoath Mine, 3½ miles north of Essington, about half a mile west of Mount Stromlo, on north side of Stony Creek.

Inspector H. Hooke reported (P.B. $^{1}\frac{4}{9}\frac{3}{9}^{2}$) copper vein traversing hard schistose rock. Veins small, in channel a few feet wide. Aided to sink 100 feet. No record after 24 feet; probably abandoned at that level.

Burraga Division.

East Burraga Mine, parish Jeremy, county Georgiana. Strike N. 10° W. dip S. 80° W. at 55°.

Several shafts sunk, representing extensive prospecting in and near a small ferruginous outcrop resulting from oxidation of pyritic strata. The gossan, however, at low levels is not solid enough for pyritic flux, and, moreover, is very silicious.

A little silicious carbonate ore is at grass, but was evidently in very limited quantity.

An average sample of the ore yielded :—

No. 06-907—Copper, 0·87 per cent.
Gold, a trace per ton.
Silver, 2 oz. 3 dwt. 23 grs. per ton.

Mount McDonald Division.

Eldorado Copper Mine.—South of, and adjacent to, Millburn Creek Mine. Parish Dunleary, county Bathurst. Inspector Hooke reported (September, 1901) strike of lode north and south, vertical in schist. Width 9 inches to 2 feet. Three shafts sunk 20, 42, and 44 feet, about 50 feet apart.

Yield to that date—8 tons "firsts," assaying 20 per cent. copper; 12 tons "seconds," estimated 10 per cent. copper.

Bathurst Division.

Esmeralda Copper Mine, 3 miles from George's Plains Railway Station, M.L. 254, parish Ponsonby, county Bathurst.—Discovered by T. Rankin about 1877, and opened to about 50 feet. Strike N. 33° E.; dip N. 57° W. at 78°.

Reopened by J. Thomas and party, May, 1906, who drove south 50 feet from bottom of old shaft, and despatched from it 18 tons of ore, returning 9 per cent. copper.

The Esmeralda Syndicate took over mine, July, 1907, and deepened shaft to 68 feet at time of inspection, December, 1907. An average sample from about 12 tons of dressed ore at surface, and the screenings therefrom, gave the following results on partial analysis :—

	No. 07-7945—Dressed ore.		No. 07-7946—Screenings.	
Copper	11·06	per cent.	6·37	per cent.
Zinc	11·61	,,	6·91	,,
Iron	16·52	,,	11·62	,,
Sulphur	21·64	,,	12·09	,,
Silica	24·20	,,	36·50	,,
Gold	a trace.		traces.	per ton.
Silver	3 oz. 5 dwt. 8 grs.		1 oz. 12 dwt. 16 grs.	per ton.

The country consists of micaceous and hornblendic schist, with garnets. The ore of copper pyrites and zinc-blende, mixed with country in part; width, 3 feet to 4 feet. Pinched at south end, but going under foot. At 68 feet level, from 2 feet 9 inches to 3 feet of sulphides occur.

About a quarter of a mile south on strike quartz was quarried for furnace bottoms at the old Cow Flat furnaces; stains of copper carbonate are sparingly present in the quarry.

Bathurst Mining District—*continued.*

Rockley Division.

Essington.—Hope and party's shaft, portion 31, parish Adderley, county Westmoreland. Opened in 1907 to a depth of about 70 feet on underlay. Vein of silicious copper ore, a little of which was sent for sale. Quartz with carbonates in chloritic or hornblendic schist. Strike N. 10° E., dip west.

Fitzroy Mine.—See p. 275.

Fullback Mine (originally the *Dingo*), M.L. 1, parish Baring, county Westmoreland.—Opened many years ago; reopened in 1907. (Closed at date of inspection in March, 1908.) Unable to descend on account of foul air. Worked by whim. Average width of lode reported, 1 foot 6 inches to 2 feet. Strike apparently N. 10° W., dip S. 80° W. at 64° in hornblendic schist, close to junction of quartz felsite. No apparent outcrop. Some good grade dressed ore at grass, the quality of which is represented in the following assay :—

No. 08-918—Copper	17·37	per cent.
Zinc	1·24	,,
Iron	26·04	,,
Sulphur	22·53	,,
Silica	18·50	,,
Gold	a trace	per ton.
Silver	1 oz. 6 dwt. 9 grs.	per ton.

About 25 chains N. 20° W. from Fullback Mine two shafts in similar country have been sunk about 50 feet apart on a very flat-lying vein of quartz with carbonates about 12 inches thick, striking N. 10° W., and dipping S. 80° W.

According to the Annual Report of the Department of Mines, 1901, p. 54, about 200 tons of ore were disposed of during that year from the Fullback Mine, being sold to the Lloyd Copper-smelting Works at Lithgow.

In 1907 the old shaft (300 feet) was cleaned out, and 11 tons despatched in May are reported to have yielded 15 per cent.

Orange Division.

Great Western Copper-mining Company, Icely.—The prospectus of this company, issued by Mr. S. L. Bensusan in November, 1872, embraced a number of lodes previously opened and partly worked near Byng and Lewis Ponds. The first half-yearly report, dated February, 1873, enumerated these as follows :—The Britannia, Icely, Belmore, Moonta, Nelson, Gurophian, East Block Mines, and other property to the south. (*See* Carangara Mine.)

In Mineral Statistics, $\frac{1895}{96}$, it is stated that the company was working the following lodes at Icely, viz. :—The "Williams" lode having a thickness of $2\frac{1}{2}$ feet at surface, 5 feet at 125 feet, and 3 feet at 270 feet Strike N. 30° W., dip easterly; 4,000 tons of ore raised yielded 560 tons of copper.

The Icely lode was proved to a depth of 125 feet; average thickness, 1 ft. 6 in. Strike N. 30° W., dip 1 in 6 easterly; 1,000 tons of ore raised yielded 100 tons of copper.

The company held several other lodes, four of which had been worked, the strikes and dips being similar to the Icely and Williams lodes; 100 tons of ore raised from them yielded 12 tons of copper.

The company was also working eight lodes at Lewis Ponds Creek; average thickness, 3 feet. Strikes N. 20° W., and dips about 1 in 5 easterly; proved to 168 feet; 4,000 tons of ore raised yielded 640 tons of copper.

According to Captain W. R. Reynolds, at one time mine-manager for the company, smelting-works were erected in connection with the Icely Mine,

at which the ores from the others were treated. The company also purchased ores at the rate of 10s. per unit for all over 4 per cent., the latter amount being deducted in lieu of smelting charge.

Captain Reynolds also supplied the following particulars of the mines that came under his supervision during the operation of the company, which were worked chiefly by contract instead of day-labour:—

	Opened to.	Thickness of lode.
Icely	275 ft.	1 to 4 ft.*
Ophir	about 200 ,,	6 in to 5 ft.
Gurophian (afterwards Tom's Lewis Ponds)	,, 170 ,,	9 ,, to 4 ,,
Britannia	,, 210 ,,	3 ,, to 5 ,,
Belmore	,, 180 ,,	1 ft. 6 in.
Moonta	,, 60 ,,	.....
Nelson	,, 120 ,,	1 ft.

* Worked ten years.

Mr. F. Danvers Power states, that at the Mt. Fraser Mine, near Byng, a new shaft was sunk 110 feet; driven south, 109 feet, north 100 feet, with rise to meet winze in old workings. A sample taken along 110-foot level, 8 in. wide, assayed by Mr. A. Orr, yielded copper 6·46 per cent.; silver, 1 oz. 13 dwt. 6 grs. No gold.

Bathurst Division.

Green Swamp Mine, M.C.P. 112, parish Yetholme, county Roxburgh, about 13 miles from Bathurst, close to Sydney road.—Specimens from this lode are reported to have been exhibited at the Crystal Palace Exhibition in 1851.

About 1898 it was reopened by a syndicate, who sank a shaft and drove a tunnel at the north end. From the eastern lode, cut in a crosscut at the 55-feet level in the main shaft, 25 tons of oxidised ore were despatched for a reported yield of 8 to 12 per cent. of copper. From a small underhand stope in the tunnel, 15 tons are reported to have yielded 14½ per cent.

The mine was again opened in the early part of 1907, and 10 tons extracted are reported to have yielded a little over 10 per cent. at Blayney.

In January, 1908, the Amalgamated Green Swamp Copper Mines, Limited, was formed to work the property.

Strike of main lode about N. 17° W., dip N. 73° E. at 30°.

The developments to date are two main shafts—"Hyde's" and "South"—depths 135 feet and 110 feet respectively. Sixty-one feet south of the latter is a 61-foot shaft, used as a ladder-way, and connected at bottom with the South shaft.

From the South shaft a cross-cut east is being driven to intersect the east lode; the shaft having been sunk in a joint fissure underlying west, without ore. A little ore was cut in chlorite schist when the east cross-cut was started, thence all in hard felsite, which appears to form the footwall side of the east lode.

The main, or "Hyde," shaft lies about 250 feet north of the South shaft. At 55 feet a cross-cut east furnished the ore despatched. At about 112 feet a cross-cut east, after passing through the felsite, cut about 13 feet 6 inches of low-grade sulphide ore, of about 2 per cent. grade. In the bottom of the shaft the best ore exposed occurs about 2 feet wide on footwall. A greater width is lightly impregnated with copper, but is very hard and of low grade.

Above the 55-feet level in the South shaft is an area of stoped ground, about 35 feet long by 30 feet high.

Between the main shaft and the tunnel on the north—about 400 feet—are two shallow shafts, one connecting with the tunnel, where the latter first cuts the lode. The tunnel, if continued, would about reach the bottom of the deepest shaft (Hyde's), 135 feet.

There appear to be three parallel lodes in this site, two of which have been opened.

The country consists of chloritic, or hornblendic schist, and felsite. Dolomite and calcite occur in small nodules and veins. The sulphide ore is of good grade, when clean, but is much mixed with country.

An average sample of bagged ore at Hyde's shaft gave very disappointing results on assay :—

No. 08–908—Copper	1·62	per cent.
Iron	19·32	,,
Sulphur	10·96	,,
Silica	17·88	,,
Gold	1 dwt. 2 grs.	per ton.
Silver	14 ,, 3 ,,	,,

A sample of the dolomite yielded the following composition :—

No. 08–923—Carbonate of lime	45·91
Carbonate of magnesia	34·63
Ferric oxide and alumina	4·18
Gangue (quartz)	15·12
	99·84

Molong Division.

Gumble, L., M.L. 7, parish Manildra, county Ashburnham, about 4½ miles from Manildra Railway Station.—The Gumble lode affords one of the rare instances in the State of the association of tin and copper ores in the same lode; other instances being Bald Nob, near Emmaville, and Royal George, near Tingha. Unfortunately at Gumble neither metal is sufficiently represented to pay for working.

The most deceptive feature to miners in this lode is the dissemination of magnetic iron oxide in small grains, which imparts to it considerable gravity, leading to the belief that the latter is due to cassiterite (tin oxide).

A concentrating test made at Parke and Lacy's works, Pyrmont, during operations at Gumble, was reported to have been successful in producing concentrates containing 60 per cent. of tin and 15 per cent. of copper, but this statement is discounted by the absence of any data and the closing of the mine.

The following description is from the Report of the late Government Geologist, C. S. Wilkinson, $\frac{1}{p}\frac{8}{1}\frac{8}{3}\frac{6}{2}$:—

"The lode commences at the junction of granite and altered Silurian slates, and traverses the latter for about 100 yards in a N. 30° E. direction. It varies in width from 1 to 8 feet, and consists of ferruginous felspathic and silicious lodestuff, more or less impregnated with green and blue carbonates, grey sulpides, and red oxide of copper, brown oxide of tin, and magnetite. The tin ore principally occurs in the central and southern portions of the lode. . . . .

"In a drive on the 100-feet level on the eastern side of the lode, for a distance of 15 feet, the country rock, altered rubbly shales, with serpentine in the joints, is found to be impregnated with native copper in bright crystalline small grains and scales; and on the west side, at the 60-feet level, the rock for a distance of 14 feet is in places stained with carbonate of copper. It is thus evident that the rock on both sides of the lode has been more or less affected by the agencies, probably thermal water holding minera's in solution, which formed the lode. . . . .

BATHURST MINING DISTRICT—*continued.*

"Seven average samples taken by myself across the lode yielded on assay at the rate of copper traces to 2·85 per cent., tin traces to 0·5 per cent., and silver traces to 4 oz. 1½ dwt. per ton.

"A sample of the country serpentinous rock showing native copper, assayed 4·2 per cent. of copper, with traces of tin and silver.

"One picked sample of brown ore showing tin oxide and carbonate of copper from the lode at the 60-feet level, south drive in the middle shaft, yielded on assay—copper, 3·85 per cent.; tin, 58·70 per cent.; silver, 8 oz. 19½ dwt. per ton.; and no gold. It is thus seen that the ores occur in patches, and not disseminated regularly through the lode.

"Three-quarters of a mile south from the Gumble Mine, and at the line of junction of the Silurian and the granite, a lode somewhat similar to the Gumble lode occurs. It consists of soft felspathic lodestuff, with yellowish-green silicate of iron, silicious clinker, and hard quartzite, with quartz veins containing pyrites, and a little fluorspar, together with carbonates and sulphides of copper.

"About 20 chains further south occurs another outcrop of quartz containing carbonates of copper and fluorspar, which should be prospected."

Copper ore is also mentioned as occurring in altered slates and limestones about 1 mile north of Red Hill (1½ miles north of Gumble).

Inspector H. Hooke reported (P.B. $\frac{5}{0}\frac{8}{0}\frac{24}{0}$) that three shafts had been sunk about 90 feet; lode being traceable for about a mile. Aid granted to sink from 84 feet to 158 feet. At 143½ feet fair prospects were reported, but not payable. Lode 16 feet wide. Driven 40 feet at 140 feet. No further sinking. Balance of aid cancelled.

Inspector Polkinghorne reported (P.B. $\frac{2}{9}\frac{1}{0}\frac{1}{0}\frac{0}{0}$) carbonate of copper and oxide in decomposed formation in portion 64, parish Gumble, county Ashburnham, about 14 miles west from Molong on Gumble road. Aided to sink 100 feet. At 55 feet good bunches of ore, but not in payable quantity.

Orange Division.

Hawk's Nest Lode.—Portion 15, parish Byng, county Bathurst, alongside Orange road, near Byng. Three lines of copper-bearing strata occur in this locality. The western stretching from Diamond Hill to Rats' Castle shafts; the centre, or Hawk's Nest line, about 10 chains east; the east, or Thunder Castle, about 9 chains further east.

The Diamond Hill outcrop is reported to have been opened by a Melbourne company in 1903.

About 3 miles north-westerly along the same belt the "Oaky-Smut" shaft was sunk 100 feet, and about three-quarters of a mile further, the Rats' Castle shaft to 40 feet. Between the two latter a little copper ore has been superficially exposed about S. 50° W. from the Hawk's Nest shaft.

The Hawk's Nest lode was discovered by W. Thomas and party in 1907, and opened to a depth of 60 feet by February, 1908. It strikes N. 50° W., and dips N. 40° E. at 67°.

At the south end of the shaft at 60 feet, about 3 feet 6 inches of good sulphide ore, mixed with country, made fairly solid on the hanging-wall side, but died away in strings on the foot-wall. Country consists of chlorite schist.

Forty tons of dressed ore sent to Blayney averaged 10 per cent. of copper and a trace of gold.

The "Thunder Castle" line is reported to have been opened about 40 years ago. A little copper ore shows at surface.

Cowra Division.

Holmwood Copper Company.—About half-a-mile from Holmwood Railway Station, and 4 miles east-north-east of Cowra, on G. Lockyer's land, parish Coota, county Bathurst.

Inspector G. Smith reported (P.B. $\frac{2599}{08}$):—"Copper veins in porphyry (?). Four of these occur at the site some little distance apart. A shaft has been sunk in the middle in solid country in expectation of intersecting some of the veins on their underlay.

"One of the veins opened contains bunches of copper ore, and is from 12 to 18 inches wide. An assay of the ore yielded :—

No. 06-5933—Copper, 8·22 per cent.
Gold, 3 dwt. 6 grs. per ton.
Silver, 3 dwt. 6 grs. ,,

"Aided to sink to 62 feet. At 58 feet it was reported that lode formation continued down in the shaft, and was impregnated with green carbonate at bottom. (No further record.) Reported output, 60 tons."

Holmwood.—Two miles south of Holmwood Railway Station, on Mr. Campbell's land.

Inspector J. James reported (P.B. $\frac{1562}{05}$) :—"A copper lode in slate and diorite, striking north and south ; with a vein of copper carbonate 3 inches to 8 inches wide.

"Aided to sink to 50 feet. At 33 feet cupriferous formation about 17 inches wide ; country hard. At 50 feet copper ore making in south end. Aided for 25 feet of driving at south end. Driven 10 feet, a little ore showing. No further record."

Rockley Division.

Hopeful Mine.—Half a mile from Phœnix Mine ; 8 tons of carbonate ore raised, yielded 17 per cent. copper.

Orange Division.

Icely Mine, parish Byng, country Bathurst.—Since the first edition of this work the water was baled out of this mine, and an attempt made to precipitate the copper in solution by the local Payne process, but was not financially successful.

Carcoar Division.

Infirtaris Copper Mine, parish Beaufort, county Bathurst.—In private land close to Growanbang Station Homestead.

Inspector G. Smith reports that it was found by a Chinaman, whilst prospecting for alluvial gold, about 1880.

Patches of copper and iron pyrites occur in andesite. Strike E. and W., dip S. ; width not apparent. Maximum length of proving, 80 feet ; depth, 90 feet. Gross output 30 tons of 11 to 12 per cent. copper ore ; no gold or silver.

Mr. E. R. Cocks who worked the mine states that the ore recorded was extracted from a patch 16 feet. No other stoping or driving done. A little ore showing in a crosscut at 60 feet. Not much at 90 feet.

BATHURST MINING DISTRICT—*continued*.

Little Gem Mine, Mount Ragan, near Lewis Ponds. M.L. 6, parish Worcester, county Bathurst.

Strike, N. 20° W.; dip, N. 70° E., in schist. Opened by two shafts, 40 and 46 feet deep, and 35 feet apart, connected at 40 feet.

About 6 inches of grey ore for a length of about 9 feet between shafts, backed by about 2 feet of country with splashes of black ore, probably chalcocite.

At the bottom of the 46-feet shaft, yellow sulphide is showing in fine strings on hanging wall side, making stronger on footwall at south end partially enriched black ore.

The quality of the ore is demonstrated in assays of average samples:—

No. 08-578—Enriched ore from bottom of 46-feet shaft—
Copper, 27·35 per cent.
Gold, a trace
Silver, 6 oz. 12 dwt. 20 grs. } per ton.

No. 08-579—From end of 46-feet shaft—
Copper, 12·88 per cent.
Gold, a trace
Silver, 8 dwt. 17 grs. } per ton.

Bathurst Division.

Locksley, about 1½ miles north-east of the Locksley Railway Station, on the Great Western Railway Line.—Opened about 1888; reopened in 1898. Shaft 80 feet deep. Lode reported to have cut out. Walls well defined.

In 1907 Mr. Francis Drake partially unwatered the old workings. The lode strikes E.N.E. in granite. At 70 feet a bunch of sulphide ore was encountered. A little driving had been done to the W.S.W.—about 15 feet—in ore of very low grade.

It is reliably reported that at 94 feet a level was driven 50 feet E.N.E. along the lode, which at the end had narrowed to 6 inches. From this level stoping was carried up 20 feet.

At 100 feet the lode is reported to have cut out on a solid granite floor. No further sign at 110 feet.

Oberon Division.

Louther, 15 miles from Mount Victoria.—Copper and silver ore was discovered hereabouts in 1897, which yielded ($\frac{4177}{97}$) 39·9 per cent. of copper and 15 oz. 5 dwt. 23 grs. of silver per ton; a further sample ($\frac{153}{98}$) yielded 32·24 per cent. of copper and 20 oz. 18 dwt. 21 grs. of silver per ton but, unfortunately, a workable deposit could not be found. Samples from Garbenang Road, Louther, which is probably identical with the copper locality ($\frac{2700}{98}$, $\frac{2701}{98}$, and $\frac{2838}{98}$), yielded from 19 to 23·5 per cent. of copper, and 5 to 6 oz. of silver per ton.

Rockley Division.

Lucky Hit Mine, 6 miles from Rockley, on west side of Trunkey road, about 1½ miles from old Summerhill Mine, on Mrs. Shepherd's land.

BATHURST MINING DISTRICT—*continued.*

Inspector B. Sawyer inspected in 1904. Aid granted to sink from 48 feet to 80 feet (P.B. $\frac{53}{54}$). Work discontinued at 89 feet as prospects were not sufficiently encouraging.

Inspector D. Milne reported (P.B. $\frac{75}{76}$) the lode to consist principally of quartz, hard and of poor character, with small bunches of pyrites. Further aid refused.

Mandurama Division.

Mandurama.—About 4½ miles north-west of Mandurama and 3 miles south of Burnt Yards. Mr. J. A. Watt, Geological Surveyor, reported that blue and green carbonates of copper were plentifully scattered through andesitic rock at this site, from the surface down to the depth attained, 27 feet, and that the prospects were favourable. Aid was granted to sink 77 feet and drive 50 feet on the course of the lode. The result of this exploration, however, did not sustain the surface indications. No sign of a lode was visible. The occurrence of copper in the Carcoar andesite and its deceptive indications have been specially alluded to in this work.

Mount McDonald Division.

Milburn Creek Copper Mine, parish Dunleary, county Bathurst.—This mine has had an eventful history, involving both legal and political issues. Briefly stated, the cause of trouble was a disputed title, as set forth in a petition presented to Parliament, in the 1873–4 Session, on behalf of one Robert Martin (Vol. IV, Parliamentary Proceedings, p. 857). Therein it is stated that petitioner selected a mineral conditional purchase at Milburn Creek, on or about the 15th September, 1872, entered into possession and commenced work. At time of survey his right was disputed by Baker and party, to whom subsequently a lease was issued by the Department of Lands prior to the formation of the Department of Mines. Baker and party erected three reverberatory furnaces about 1 mile from the mine, and extracted a considerable amount of copper. Their title to the mine was, however, upset by the Supreme Court. Compensation was granted in 1879 to Baker and party for loss of lease granted to them. The distribution of the sum voted by Parliament to the Milburn Creek Copper Mining Company (which was floated by Baker and party after the lease was secured by them) caused so much dissatisfaction and adverse comment amongst certain shareholders, which was intensified by the explanation offered, that Parliamentary notice and action was invoked, followed by the appointment of a Royal Commission of Inquiry, the results of which are matters of political history. Naturally, these proceedings cast a shadow on the mine as an investment, notwithstanding that the inquiry revealed the existence of proved bodies of sulphide ores of good grade.

Probably the first ore raised from the mine is represented by the following parcels sent to the Newcastle Smelting Works in June, 1873:—

2	tons	13	cwt.	18½	per cent.	copper.
2	„	4	„	9	„	„
2	„	7	„	25½	„	„
4	„	11	„	11⅞	„	„
3	„	13	„	22¾	„	„
3	„	17	„	19½	„	„
2	„	2	„	23	„	„

The Milburn Creek Copper Mining Company consisted of 72,000 shares of £1. Soon after its formation a furnace was erected, brick and fireclay being obtained from Bowenfels for the purpose.

At the second annual meeting of directors for the year ending 30th June, 1876, 1,445½ tons of ore were reported to have been raised, of which 500 tons of 13 per cent. ore were smelted for 67 tons of copper, the balance of the ore—945½ tons—were sold to the Esk Smelting Company, Bowenfels, for £4,001, averaging 11¼ per cent. Forty men and boys were then employed.

An arrangement was made during the year with the Esk Smelting Company to rent the Milburn Creek Company's furnace, and to erect two additional furnaces, and to purchase all the latter Company's copper ore on an agreed scale of prices.

A portion of the lower level of the mine was let on tribute (in yellow ore). A lode of black ore at the south end of the workings was averaging 16 to 21 per cent. of copper.

The directors report at the third annual meeting ending June 30, 1877, states that the mine was worked up to within a few days of the above date, when it was suspended pending the Supreme Court decision as to the validity of the lease.

During the year ore to the value of £6,697 was sold to the Esk Company, and 200 tons were at grass.

The following description of the mine and its workings is from the report of the late Under Secretary for Mines, Mr. Harrie Wood (Ann. Rept. Dept. of Mines 1878, pp. 23-24):—

"The mine is situated in lightly timbered box ranges, composed of altered (Upper Silurian) slates and sandstones, dipping W. 10° S. at about an angle of 70°. About three-quarters of a mile from the mine the slates give place to ternary granite, while in a W.S.W. direction the nearest granite is distant about 1½ mile. It will thus be seen that the copper lodes occur in a belt of altered slates, bounded by granite. The surface indications of the several lodes are characteristic. They appear as quartz veins, containing much gossan (the result of the decomposition of copper and iron pyrites), and a few stains of carbonate of copper.

"At a slight depth the gossan gives place to carbonates and oxide of copper, while below these appear the sulphides, &c.

"The greater part of the work done in the Milburn Creek Mine has been the extraction of the oxidised ores of copper (carbonates and oxides) which necessarily occur nearest the surface; two distinct lodes have been worked, and on these have been sunk no less than eighteen shafts on what are known as the 'North and South lodes.' An adit has been driven from the side of the hill, and reaches a depth of 56 feet below the crown of the range. From this adit nearly up to the surface the carbonates have been removed by stoping.

"From one of the shafts, at a depth of 25 feet below the adit another adit has been driven northward. Good ore (copper glance, yielding in the company's furnaces 8 to 20 per cent. of copper) has been worked in this level, the lode here being from 4 ft. 6 in. to 5 feet wide. A specimen of this ore was assayed by Mr. Dixon, F.C.S., F.I.C., and yielded 27·9 per cent. copper.

"From this level a winze has been sunk to a depth of 27 feet, and from the bottom a drive has been worked northwards. Very good ore has been

obtained here, viz., grey sulphide of copper, which in the Company's smelting works yielded 20 per cent. of copper; while Mr. Dixon found in a sample submitted to him 45·9 per cent. The lode in places is as much as 11 feet wide, though somewhat irregular, narrowing occasionally to 5 ft. 6 in.

"The South Shaft is vertical to a depth of 65 feet from the surface, and at this depth a drive has been put in east and west along the lode. A winze has been sunk 29 feet through yellow sulphide of copper and peacock ore, forming a fine lode, which increases rapidly in width as it descends.

"The South Shaft has been continued down on the underlie to a further depth of 140 feet, through the same ore, which at the bottom shows a splendid solid lode 11 ft. 6 in. in width, and without any gangue visible. The lode at this point dips at an angle of 63°. A sample of this ore was assayed by Mr. Dixon and yielded 16·7 per cent. of copper, though in the Company's smelting works it only averaged 9 per cent.

"The water of the mine holds a quantity of sulphate of copper in solution, which, while the shaft is being bailed, colours the creek a strong emerald green for a distance of more than a mile from the mine."

The quantity of copper in the Milburn Creek Mine water was found by Mr. W. A. Dixon to be 328·9 grains per gallon, equal to 4·698 lb. per 100 gallons. This water contained a considerable quantity of sulphate of iron in solution, but no free acid.

In the South Shaft the lode was found to improve in solidity and width as it descended, and at a depth of over 200 feet it was fully 11 ft. 6 in. from wall to wall.

In 1877 the mine changed hands under a Supreme Court decision. In 1878, it is stated that operations were continued during the year, and a considerable quantity of regulus was sent to Bowenfels to be refined. The Warden stated that, though badly worked, the mine was reported to be looking well.

In 1888 another lawsuit was pending. Nothing further appears in the records until 1888, when 14 tons of copper were despatched, work having been resumed by C. J. Campbell. In 1898 prospecting was being carried on along the line of strike outside the property.

When the first edition of this work was being printed, as briefly intimated, arrangements were being made for reopening Milburn Creek.

Under the title of the Milburn Copper Corporation an option was secured over the property in 1899; after unwatering and a little prospecting the option was forfeited. The mine being now again full of water, the owner—Mr. H. Haege—has placed at the Writer's disposal reports by Mr. F. Danvers Power (Lecturer in Mining, Sydney University) on the latest developments before closing down:—

Following are extracts therefrom:—

Report dated 9th October, 1900.

"Position of lode traceable by underground workings for a distance of 640 feet, and on the surface from the northern to southern boundary of M.C.P. 20.

"The average width of vein, which runs about north and south, is about 4 feet; but at the No. 1 and Water Shafts it widens to 12 feet.

BATHURST MINING DISTRICT—*continued*.

"The gossans left unworked have been leached out. The rich oxidised ores have been stoped out from the North Shaft to past the Crown Shaft.

"Where the stopes end south of the Crown Shaft, the ore appears to pitch underfoot to the south at an angle of 25 degrees, so that for the rest of the adit there is a blank, though the track of the lode has been followed to where it junctions with the east and west vein.

"Two leaders run into the main vein in this blank, and ore commences to make again where the second one meets it.

"Where the so-called east and west vein junctions with the main one, a large body of ore has been formed, and it is this that has been followed down in No. 1 Shaft. Except near the junction, the east and west vein does not appear to be of any value.

"The lower part of the North Shaft, and Pilkington's Shaft, being full of water, were not open to inspection.

"Most of the work has been concentrated in and about No. 1 Shaft, which has been converted into an underlay all the way.

"*Davies' Winze in No. 1 level, west drive.* Nos. 2, 3, and 4 are new levels driven from this North Shaft.

"No. 2, on west side of shaft, has followed some good ore in what I consider the east and west lode, until it made a bend where it appears to have been lost. The drive was curved round, and eventually cut the main lode.

"No. 3 was driven in country away from the lode, which is visible in face.

"No. 4 is near the bottom of the shaft, and is driven 24 feet in the lode; face 4½ feet wide without footwall.

"No. 1 Shaft has been deepened 40 feet, ore followed down all the way and still underfoot. The ore on the eastern side of shaft appears narrower than on western, due to the lode dipping south-west. Presumed footwall not definitely proved to be true wall.

"The other work consists of a foot or two driven on the east and west lode, east of the Eastern Shaft; also a few feet of cross-cutting on same level; and a short drive in the main lode below the adit level.

"Andrews' shaft, sunk 50 feet deeper—believed off the lode—not open to inspection owing to water.

"Pilkington's shaft, sunk 30 feet deeper on the lode, but in very poor stone, apparently above the shoot of ore.

"At time of inspection, face of every drive put in by the Corporation—excepting those hopelessly off the lode—showing good ore. Good ore also in the bottoms of the No. 1 Shaft, and Davies' and Pilkington's winzes."

Report dated 28th December, 1900.

"Lode originally approached in adit 380 feet long, and numerous shafts.

"The main shaft is sunk on an underlie in the wide portion on the junction of two veins, for a depth of 300 feet, being on good ore all the way.

"A sample taken right across the lode, where it is 12 feet wide, assayed 9·35 per cent. copper.

"A sample from the bottom of Davies' winze, also on the big ore body, and west of the main shaft, assayed—where it was 8 feet wide—7 per cent. copper.

"A sample from Pilkington's winze, east of the main shaft, assayed 8·95 per cent. copper.

"There are four drives from the main shaft, and all the faces of them, except when off the lode, are on ore.

"A sample taken from No. 4 level at the bottom of the main shaft assayed 5·07 per cent. copper.

"A sample taken along No. 2 level, the good with the bad, assayed 4·29 per cent. copper.

"A general sample taken from a heap of about 400 tons at the mouth of the main shaft (extracted from the lower portions of the shaft and from the drives), all mixed together and averaged, assayed 5·46 per cent. copper.

"The ore has not been driven on for more than 24 feet on the south-west side of the main shaft.

"At the north end of the mine there has also been considerable work done, and more widened-out parts of the lode have been discovered and stoped.

"At this end it would appear as if the ore pitched to the north, and this may account for the ore in the lower part of Andrews' shaft (170 feet deep) being poor, as it is situated near to the crest of the hill, which appears to influence the pitch of the ore bodies.

"The North Shaft (140 feet) was full of water.

"*Conclusion.*—Ore still underfoot in deepest shaft (main), also to be seen in faces of all levels leading from it. Everything goes to show that there is ore below the adit level, where the shoot dips underfoot; for what would seem to be the cap of the same shoot is to be met in the face of No. 2 level.

"The ore is of a silicious nature, which lends itself to concentration by means of water.

"The mine water is in small quantity and easily kept down by kibble."

The Writer was informed by Mr. Woolcott, who had charge of the Corporation's operations, that the option was not exercised, because, in his opinion, the ore in sight was not sufficient to warrant payment of the stipulated sum required to secure the mine.

Sunny Corner Division.

Montana Silver and Copper Mine, Sunny Corner.—Re-opened by the Montana Copper Company in 1906. Winding plant erected. Rich leaders of copper ore reported in cutting down shaft. Prospecting continued during 1907. Main shaft sunk to 250 feet. Plant and buildings erected.

Bathurst Division.

Mountain Maid Lode, 3 miles south-west of Apsley Mine.—Two leases applied for by Marning and Hunt. Two shafts sunk 63 feet deep—20 feet apart—connected at 42. On small vein 4 inches to 6 inches wide of copper carbonates. An average sample of a few tons at grass yielded:—

No. 07-7944—Copper, 16·80 per cent.
Gold, a trace
Silver, 5 oz. 8 dwt. 21 grs. } per ton.

Rockley Division.

Mountain Run and Sugarloaf Mines, M.Ls. 2, 3, 9, 32, parish Ponsonby county Bathurst. About 10 miles from George's Plains Railway Station.

Two lodes, as named above, occur at this site in schist.

The Mountain Run, or eastern, was discovered about 1899; the western or Sugarloaf, about 1895.

The Mountain Run lode strikes N. 50° W. and dips S. 40° W. at 34°. Aided to sink from 10 to 75 feet (P.B. $\frac{1\,8\,4\,8}{0\,1}$). Records to 62 feet show carbonates impregnating schist.

The Writer first examined this lode in 1899. Three shafts had then been sunk in it, 45, 50, and 125 feet; the average width of good ore being from 1 to 2 feet, though a greater width of very low grade occurred. About 340 tons of carbonate ore were reported to have been despatched to the Dapto Smelting Works by the Mining and Exploration Company then in occupation, for an average yield of 8 per cent. copper and 2 dwt. of gold per ton.

The leases were secured by R. S. Garbutt in October, 1905. The shafts were deepened in 1906 to 120 feet and 180 feet, and erection of a small circular water-jacket furnace (from Sunny Corner) begun; capacity about 25 tons per day, including fluxes. The main shaft cut into old workings at 170 feet on underlay.

The furnace started in March, 1907, and ran intermittently until October. About 1,400 tons smelted for the following consignment of matte:—

1,400 tons ore { 8 tons, 50 per cent. matte; 9 „ 43 „ „; 7½ „ 41 „ „; 34 „ 25 „ „; 20 „ 33 „ „ } Equalling about 1·8 per cent. of copper in the ore.

The presence of numerous "sows" down the slope from the furnace, evidences difficult or bad metallurgy, and may account for poor recovery.

A later campaign under the supervision of W. B. Dunstan reduced 260 tons for 35 tons of matte of 24·7 grade. Gossany ironstone for flux being procured from the Sugarloaf lode.

Recent examination of latest developments revealed about 3 ft. 6 in. of sulphides at a depth of 180 feet in the main shaft. A drive north 16 feet at this level showed about 2 feet of good grade sulphides on floor, with about 3 feet of very dredgy ore above. Driven 16 feet south—ore lens dipping underfoot.

An average sample of this ore yielded:—

No. 08-909—Copper, 7·32 per cent.
Gold, a trace
Silver, 1 oz. 1 dwt. 19 grs. } per ton.

Sugarloaf Lode.—On north-east slope of Sugarloaf Mountain. Strike N. and S., dip W. Shaft sunk in kindly ochreous gossan to 100 feet, thence into limestone, and again into ochreous gossan with a little carbonate of copper at 134 feet. A drive west through manganiferous ochre and occasional limestone, reached a belt of sulphide-impregnated rock, striking N. 15° W. and dipping S. 75° W., and several feet wide, bounded on west by chloritic schist, then crushed granulite.

From an enriched portion of this belt a sample was taken which yielded:—

No. 08-911—Copper, 5·20 per cent.
Gold, 1 dwt. 2 grs. }
Silver, 9 dwt. 19 grs. } per ton.

About 5 chains west of Sugarloaf lode a massive lode of iron pyrites was cut in a shaft at 60 feet. At the 100-feet level it was driven on for 117 feet, where it had a thickness of 16 feet. Unfortunately it carries but a trace of copper.

BATHURST MINING DISTRICT—*continued.*

An average sample yielding:—

No. 08-910—Copper, 0·72 per cent.
Gold, 1 dwt. 2 grs. } per ton.
Silver, 5 dwt. 10 grs. }

Though its composition makes it a useful flux for the dredgy Mountain Run ores, its poverty depreciates its usefulness.

The soft ochreous residual material found in considerable quantity in vugs in the Sugarloaf Mine—resulting from precipitation of insoluble oxides during process of dissolution of limestone—may prove of value as an ochre. Its composition is shown in the following analysis:—

No. 08-912—Total water	32·64
Manganese binoxide	29·21
Ferric oxide	8·60
Metallic copper	1·17
Gangue	8·87
Silver, 4 dwt. 8 grs. } per ton.	
Gold, a few grains }	

The other constituents present being alumina, lime, magnesia, a trace of zinc; also, a small quantity of sulphur trioxide and chlorine.

Orange Division.

Mount Bulga Copper Mine, on J. B. Lane's private land, parish Clinton, county Bathurst, 9 miles east of Orange.—Slate country. Strike of lode N.W., dip S.W. An impregnation—reported up to 25 feet in width. Depth of proving, 245 feet. Maximum length, 120 feet.

In 1901 the Mount Bulga Company erected machinery, deepened main shaft, and opened out at 200 feet (Ann. Rept., 1901, p. 54).

In 1902 a small blast furnace was delivered at the mine (*ibid.*, 1902, p. 49).

In 1903 the main shaft reached 245 feet, and the south drive 140 feet, A shaft was sunk 110 feet in M.L., in ironstone, carrying a little gold and silver (*ibid.*, 1903, p. 47).

In October, 1904, the mine was taken over by Messrs. Zobel and Gander, and unwatered to the 200-feet level (*ibid.*, 1904, p. 46).

The following analyses by D. C. Winterbottom show the composition of the Bulga ore:—

Character of Ore.	Copper, per cent.	Insoluble, per cent.	Iron, per cent.	Alumina, per cent.	Sulphur, per cent.
First Ore—Sold to smelters	7·2	23·0	32·6	7·5	Not determined.
Seconds—Average	3·1	36·0	23·0	8·4	.....
Carbonate ore from Whip Shaft	4·7	34·3	24·0	8·4	.....

The blast furnace ran for a short period, treating up to 40 tons of mixed firsts, seconds (sulphides), and carbonates. The slag, according to Mr. Winterbottom, had the following composition:—

Silica	39·0	per cent.
Alumina	18·0	,,
Ferrous oxide	33·2	,,
Lime	7·5	,,
Copper	·5	,,

BATHURST MINING DISTRICT—*continued.*

Limestone flux obtainable about 1 mile from the mine yielded on partial analysis:—

No. 08-588—Calcium carbonate	96·78	per cent.
Magnesium carbonate	1·55	„
Ferric oxide and alumina	·46	„
Gangue	1·12	„
	99·91	„

Mr. M. Zobel states that the mine was opened about 1893 by a prospector named Phœbe. Some small parcels of carbonates were disposed of for yields up to 15 per cent. During 1907 some 3,000 tons of sulphides yielded an average of 6½ per cent. at public smelters. Progress has been delayed by litigation, and work is now suspended.

Tuena Division.

Mount Costigan.—Discovered by J. Maguire in the early 80's. Copper sulphides made their appearance below water-level, in a refractory combination with sulphides of lead, zinc, and iron, very similar to the ores in the lower levels of the Lewis Ponds and Sunny Corner Silver Mines.

Mount Costigan was worked as a silver-lead proposition until 1889. A depth of about 200 feet was reached before the mining and smelting plant was dismantled in the above year.

Re-opened in 1906, by the Mount Costigan and Cordillera Company, for copper and other ores below water-level.

In 1907 it was reported that 50 tons of ore had been despatched for shipment to Europe, averaging by bulk assay over 12 per cent. of copper, from a lode 4 feet wide. Assays have also shown gold 2 dwt. 4 grs., and silver 12 to 20 oz. per ton.

Orange Division.

Mount Fraser Copper Mine, Springfield Estate, near Icely.—This mine was re-opened in 1907, 50 tons of ore valued at £600 being raised. Shaft, 100 feet, driven at that level 120 feet north and 80 feet south. Lode varied in width, 8 inches to 2 feet.

Mount Lindsay Copper Mine, M.Ls. 55 and 56, parish March, county Wellington. Rosedale, near Orange.—Strike N. 25° W., dip 1 in 5 in slate and quartz-felsite. Opened by cross-cut tunnel. Lode 2 to 4 feet wide; driven on for about 30 feet.

The ore is of refractory nature, as disclosed in the following partial analysis:—

No. 08-565—Copper	4·40	per cent.
Lead	4·65	„
Zinc	17·63	„
Gold, a trace Silver, 20 oz. 9 dwt. 10 grs.		per ton.

Fifty tons sent to Blayney Smelting Works and 10 to Waratah averaged 4½ per cent. of copper; its composition, however, prevented further sale, and caused the closing of the mine.

Near Mount Lindsay the Federal Syndicate is reported to have sunk 140 feet in similar lodestuff—none of which was disposed of.

BATHURST MINING DISTRICT—*continued.*

Mount McDonald Division.

Mount McDonald.—About half a mile north of Mount McDonald, and the same distance south of Milburn Creek Copper Mine, in the parish of Dunleary, county of Bathurst.

Inspector D. Milne (P.B. $\frac{24}{1}\frac{2}{8}\frac{0}{9}\frac{0}{8}$) states that the country consists of slate with bunches of quartz, gossan, and blue and green carbonates; strike north and south. Apparently a continuation of the Milburn Creek lode. The only provings at the time of inspection were several shallow openings along the outcrop. Aid granted to sink 60 feet, and to drive 80 feet on the course of the lode. A sample from the outcrop, $\frac{1}{9}\frac{4}{8}\frac{0}{8}\frac{A}{}$, consisting of ferruginous blue and green carbonates, yielded 40·1 per cent. of copper, and 8 oz. 18 dwt. 14 grs. of silver per ton.

On the southern strike of the Milburn Creek Lode, shafts were sunk some eighteen years ago to depths of about 70 feet, and some rich ore is reported to have been raised.

Bathurst Division.

Mount Morris Copper Lode (? Mount Nome), M.L. 37, parish Ponsonby, county Bathurst, about 2 miles easterly from Apsley Copper Mine.—Carbonate and sulphide ore in schist:—

Sample 07-2638—Copper, 26·70 per cent.
Gold, a trace
Silver, 1 oz. 8 dwt. 7 grs. } per ton.

Orange Division.

Mount Ragan (*or Regan*), portion 6, parish Worcester, county Bathurst, near Lewis Ponds, about half east of Britannia Mine.—Discovered by Hayward Brothers, about 1878.

Aided in 1899 to sink from 55 feet to 145 feet, and to drive 50 feet (P.B. $\frac{1}{9}\frac{3}{9}\frac{0}{9}\frac{3}{}$). Progress:—At 65 feet a little black ore showing; 9-inch vein of black ore at 91 feet; 6-inch vein at 116 feet; small vein continuing down to 138 feet (last measurement).

Strike N. 30° W., dip N. 60 E. at 145°, in slate and schist. Depth of proving, 145 feet. Length proved by four shafts about 180 feet. Vein narrow, averaging about 7 inches; rich yellow sulphide at bottom. Stoped up from 60-feet level.

Samples of mixed sulphides in mica schist, and of better grade ore, gave the following returns:—

Assay No.	Description.	Copper.	Zinc.	Gold.	Silver.
					oz. dwt. grs.
07-5080	Mixed sulphides	3·92	26·76	A trace	1 1 19 per ton.
07-5714	First-grade sulphides...	13·92	.....	,,	2 15 13 ,,

The output from July, 1906, to about July, 1907, amounted to 38 tons 12 cwt. 2 qrs., averaging 22·7 per cent. of copper, the high price of copper then prevailing enabling this small vein to be profitably worked.

The South Block adjoins M.L. 6 on the south. Here two shafts have been sunk on a parallel vein on the south-west to depths of 45 feet and 75 feet.

Strike N.W. Width about 6 inches. Same character as Mount Ragan ore. Lost ore at 47 feet; drove 37 feet S.E. and sunk winze 28 feet. About 3 inches of rich sulphide at bottom of winze. Seventy-eight bags sent to Newcastle Copper Works yielded 19 to 20 per cent. of copper.

North Block.—Adjoining M.L. 6 on north. Strike N. 30 W., dip N. 60° E. (Mount Ragan line). Channel about 2 feet wide. Carbonates and oxides to about 35 feet. To this depth 250 bags of ore were extracted from a stope about 50 feet long.

In the lower levels of the 70 feet shaft zinc-blende largely predominates, as will be seen by the following assay:—

No. 08-577—Copper ..... 2·02 per cent.
Zinc ..... 32·29 „
Gold, a trace
Silver, 13 dwt. 1 gr. } per ton.

At the extreme north end of the original Mount Ragan workings, Dwyer and party sank 78 feet and drove 35 feet. Quartz on hanging wall side at 27 feet, carrying a little black ore in vugs. Channel very narrow at bottom of shaft. Ore dredgy, thinned to mere strings at south end. The composition of the ore is revealed in the accompanying assay:—

No. 08-576—Copper ..... 4·77 per cent.
Zinc ..... 11·97 „
Gold, a trace
Silver, 1 oz. 8 dwt. 7 grs. } per ton.

Mount Shorter.—P.G.L. 6, parish March, county Wellington. Rosedale, near Orange.—Worked superficially for gold, a little copper ore making for a width of 3 to 12 inches in shallow shaft. Strike N. 65 W., dip S. 25 W. at 1 in 5.

An average sample of the copper ore yielded:—

No. 08-566—Copper, 18·80 per cent.
Gold, a trace
Silver, 2 oz. 14 dwt. 10 grs. } per ton.

Sunny Corner Division.

Nevada Silver and Copper Mine, Sunny Corner.—Taken possession of by Sunny Corner S.M. Co. in 1901; unwatered, re-timbered, and connected by tram with smelting works. 300 tons smelted with Sunny Corner Mine ores. (Ann. Rept., 1901, p. 54.)

Blayney Division.

Newbridge District, 10 miles S.E., parish Bringellat, county Bathurst.—Inspector G. Smith reported copper pyrites striking N. and S. and dipping E., in chlorite schist. Shaft, 60 feet.

Rockley Division.

North Essington Mine, Native Dog Creek, parish Baring, county Westmoreland. (*See* Essington Mine.)—Inspector B. Sawyer reported (P.B. $\frac{21}{04}\frac{83}{}$) pyritous slates and schist. Aided to sink to 80 feet. At 37 feet fair percentage of copper reported. Bulk sample at Lithgow yielded 9½ per cent. of copper.

BATHURST MINING DISTRICT—*continued.*

Orange Division.

O'D Mine, parish Calvert, county Bathurst, 9 miles north of Millthorpe.—Worked for gold about 1880. Inspector Smith reported copper pyrites in igneous rock, strike N.W., dip S.W. Thickness, 3 feet. Maximum depth of proving, 69 feet; length, 30 feet. Outcrop traceable for about 400 yards. No records of early workings. Six tons raised, estimated to contain 8 to 10 per cent. of copper.

Ophir Copper Mine, south-east of Lewis Ponds, parish Byng, county Bathurst.—In 1852 a company was formed to work this mine, and a Bill to incorporate was presented to Parliament in 1853. Ores from the mine were exhibited at the Paris Exhibition of 1855. No particulars are available of the early operations. In *Mineral Statistics of New South Wales*, 1875, p. 91, the Company is referred to as working a lode at Brown's Creek having an average thickness of 2 feet; a north and south strike, and an easterly dip of 1 in 6; proved to 150 feet. Ores consisted of carbonates, oxides, and sulphides (containing gold) in a quartz matrix. Two hundred tons had yielded 30 tons of copper. Twenty men were employed. This lode was afterwards worked by the Great Western Copper Mining Company, which see.

Re-opened by the Ophir Gold and Copper Mining Company under agreement with owners during 1906–7. Cleaned out a tunnel for over 600 feet; cleaned out and re-timbered old shaft to 120 feet; sank a new shaft 85 feet, all on the same line.

The tunnel section reported from 2 to 12 feet wide. A big deposit of low grade material reported at bottom of 120 feet shaft 8 chains further south.

The 85-feet shaft on the south-eastern strike, 300 feet south of the latter, is also in ore of low grade.

The quality of the ore raised from these recent workings is very low, as will be seen in the assays of average samples:—

Assay No.	Description.	Copper, per cent.	Gold, per ton.	Silver, per ton.
				dwt. gr.
07-571	Quartz and pyrites from tunnel	0·25	a trace.	3 6
07-567	Quartz and pyrites from bottom of 120 feet shaft.	1·00	,,	15 6
07-568	Carbonates and sulphides from 85 feet shaft.	1·77	,,	4 8

The early workings along the Ophir line of lode have been extensive, but evidently shallow, and confined to the oxidised and enriched zones; the sulphides evidently, as shown above, are very low grade.

Tuena Division.

Peelwood Copper Mine, 10 miles from Tuena.—Mr. Warden T. A. Smith states that this mine was discovered by W. Montague and W. Ford about 1874. They sold to the Peelwood Mining Company, who put up smelters and worked the mine for about four years, reaching a depth of about 400 feet.

F

The first official record of this mine is contained in *Mineral Statistics*, 1875 p. 91. The lode is herein stated to have been 4 feet in thickness, striking north and south, and dipping east at 15°. The footwall country is schist and the hanging wall soft slate. Silver and lead ores were associated with the copper ores. A shaft had been sunk 384 feet, and about 1,900 tons of ore raised to that date, 1,100 of which had been smelted for an average yield of 12½ per cent. of copper. Four reverberatory furnaces were in use.

During 1876 322 tons of ore were raised, which yielded 32 tons 4 cwt. of copper, valued at £3,220.

In 1877, the Mine Manager (Mr. Williams) supplied the local Warden with the following particulars:—"During the past year the mine has been sunk 120 feet diagonally [On the underlay of the lode.—J.E.C.], making a total depth of 420 feet from the surface. Bearing of lode north and south underlying eastward at an angle of 45°. The lode contains copper, lead, zinc, and silver, and varies in thickness from 1 foot to 20 feet. Throughout the mine there is abundance of lead ore, containing a good deal of silver, which is smelted with the copper ore, thus rendering the produce in regulus, which contains from 40 to 50 per cent. of copper, 30 to 40 per cent. of lead, and from 100 to 130 oz. of silver per ton. The mine, during 1876, has produced in regulus and lead 300 to 350 tons.

"The working plant consists of two large portable engines, with crushing and dressing machinery, four reverberatory furnaces, and a calciner. The latter is used for desulphurising and expelling fumes of zinc, preparatory to smelting operations, otherwise there would be great difficulty in obtaining separation of the slags and metals."

The progress of the mine from 1876 is briefly recorded in the following extracts from the Annual Reports of the Department of Mines:—

In 1877 mine reported steadily at work raising and smelting ores, but returns are not given.

1879 mine shut down, causing a great blow to the district; subsequently re-started by local men.

1880.—Mine worked regularly. 136 tons of copper produced, valued at £5,444.

1881.—Peelwood Tributers reported steadily at work, but no returns given.

1882.—950 tons of ore raised, valued at £2,910. Mine closed before the end of the year.

1883-4-5.—No records. Mine apparently closed.

1886.—Mine changed hands after being idle for several years.

1887.—No records.

1888.—Twenty-four men employed.

From this date no further work appears to have been carried on. The sulphide ores at bottom are undoubtedly very zinciferous, the proportion being about—copper, 4 per cent.; zinc, 25 per cent. A water-jacket furnace was erected in 1888, during the silver boom.

BATHURST MINING DISTRICT—*continued*.

It is interesting to note that the rare elements, "gallium" and "indium," have been detected in the blende (zinc sulphide) of Peelwood, by Mr. J. B. Kirkland, F.C.S. (Assistant Lecturer and Demonstrator of Chemistry, University of Melbourne), who made the following analysis of the Peelwood ore:—

Silica	6·05	
Lead	16·71	containing 11 to 12 oz. of silver per ton.
Iron	11·06	
Copper	5·00	
Zinc	29·77	
Sulphur	29·21	
Loss, &c.	2·30	
	100·00[1]	

The Peelwood mine and smelting plant were dismantled about 1889. The ground is held as a mineral conditional purchase.

Rockley Division.

Phœnix, late Larry's Hill Copper Mine, parish Jocelyn, county Westmoreland.—The Larry's Hill lode was opened about 1895, under the name of the Phœnix. A shaft was sunk 90 feet, and several parcels of dressed ore were sent to Lloyd's Smelting Works, Lithgow. Later, about 150 tons were forwarded to Lithgow, and there reduced to matte in a small furnace, by one of the parties interested, in which state it was shipped to London. The quantity and grade are unknown, but the transaction was financially unsuccessful.

The Larry's Hill Syndicate took possession about 1897, and began a new shaft about 40 feet north from the first. Later they received aid from the Prospecting Vote to continue to the 150-feet level. At the date of inspection, 14th November, 1898, a depth of 100 feet had been reached and a level driven 30 feet south. At the 50-feet level the shafts are connected.

The geological formations are quartz porphyry passing on the west, through much crushed schistose porphyry, into talcose schist in which the lode occurs striking nearly north and south. Its thickness varies from 1 ft. 6 in. to 2 ft. 6 in.

The oxidised zone extends to a depth of 50 feet, at which level the sulphides appear. The oxidised ores consist of kindly, and silicious gossans, with carbonates of copper and lead, thin streaks of grey sulphide, and a little barytes.

The composition of this class of ore may be judged from the following partial analysis:—

No. $\frac{1}{2}$, gossan ores from above 50-feet level:—

Copper	6·74	per cent.
Lead	12·10	„
Zinc	4·58	„
Iron	23·78	„
Silica	22·89	„

Silver, 4 oz. 12 dwt. 13 grs. per ton.
Gold, a trace (under 10 grs. per ton).

[1] Austr. Assoc. Adv. Science, 1892, IV, pp. 266-7.

BATHURST MINING DISTRICT—*continued.*

The composition of the sulphides is illustrated in the following table of partial analyses, selected to represent the highest and lowest grades, and an average of the two, the grade being determined by the amounts of copper and zinc present:—

Assay Nos.	No. 495, "Highest Grade."	No. 494, "Lowest Grade."	No. 493, "Average."	Average of 494 and 495.	"Mixed Ores"* from the Rammelsberg, Germany (for comparison).
	per cent.	per cent.	per cent.	per cent.	
Copper	8·45	5·80	6·54	7·12	4·78
Zinc	14·96	30·73	16·49	22·84	21·25
Lead	3·86	7·37	4·76	5·61	8·84
Iron	22·92	12·06	17·79	17·49	12·54
Silica	16·57	10·95	21·12	13·76	19·19 (residue probably silica.)
		Per ton. oz. dwt. gr.	Per ton. oz. dwt. gr.		
Silver	Trace.	5 19 18	10 5 19	.....	.....
Gold	Trace.	Trace.	Trace.	.....	.....
Sulphur	.....	.....	.....	.....	24·11

* NOTE.—This class of ore (closely approaching the Larry's Hill ore) is subject to special treatment at Oker, on account of the high percentages of zinc and lead. Several special operations are necessary for recovery of the economic metals. The composition of the ore is iron and copper pyrites, zinc-blende galena, barytes, &c. (C. Schnabel, Handbook der Metallhüttenkunde. Translated by H. Louis. Vol. I, pp. 155-6.)

These analyses reveal a refractory smelting mixture, owing to the high percentages of zinc and lead. Repeated heap-roasting with carbonaceous fuel would render this class of ore more amenable to furnace treatment, by eliminating a portion of the zinc and lead contents, but judicious blending with less refractory ores would be most advisable.

Five tons of the better grade of this class of ore were treated at the Cobar Syndicate Smelting Works, Lithgow, for a return of 7 per cent. of copper.

Progress.

In 1901 the main shaft reached 135 feet. Reverberatory furnace erected.

About 300 tons of ore were raised during 1902. Main shaft, 183 feet.

Smelting commenced in September, 1904, the mine being idle for the ensuing eight months. Value of matte produced, £920.

Worked intermittently during 1905. Output, 650 tons of ore. Value of copper contents, £1,707. Closed in 1906.

During 1907 prospecting work actively engaged in; main shaft being deepened 150 feet; furnace rebuilt.

One thousand three hundred and fifty tons of ore smelted for 108 tons of 42 per cent. matte, valued approximately at £5,000. Smelting ceased in September, grade of ore being found too low for remunerative smelting when value of copper fell. Aid granted for prospecting lower levels in 1908.

BATHURST MINING DISTRICT—*continued.*

***Position early in* 1908.**—The extent of development is shown in the longitudinal section below. Present operations under aid being a south drive from 340-feet level to intersect the shoot of ore cut in No. 1 winze from 240-feet level.



The composition of the Phœnix ore is shown in the following partial analysis of mixed sulphides from No. 1 winze (300 feet), and from the 140-feet level:—

No. 08–917—Copper		4·30	per cent.
Zinc		11·35	,,
Iron		20·16	,,
Sulphur		27·72	,,
Silica		26·25	,,
Gold, a trace Silver, 8 oz. 3 dwt. 8 grs.	}	per ton.	

A sample from the 140-feet level, tested separately, yielded:—

No. 08–916—Copper, 4·70 per cent.		
Gold, 2 dwt. 4 grs. Silver, 9 oz. 7 dwt. 7 grs.	}	per ton.

The reverberatory furnace—17 ft. x 11 ft. 6 in.—has a capacity of about 60 tons per week. Lithgow (Sandford) fire-brick being used in its construction, and Lithgow sand for bottoms.

Ironstone flux has hitherto been mined from the cap of a parallel lode on the west.

BATHURST MINING DISTRICT—*continued.*

Orange Division.

Pride of the Hills Mine, P.G.L. 1, parish March, county Wellington. Rosedale, near Orange.—Worked for gold. A little rich fahl ore at 180-feet level, width 1 to 8 inches, assaying:—

Assay No.	Description.	Copper, per cent.	Zinc, per cent.	Lead, per cent.	Gold, per ton.	Silver, per ton.
						oz. dwt. gr.
08-563...	Fahl ore, 180 feet level (1-8 in.)...	5·35	9·80	5·50	a trace.	194 2 22
08-564...	Lead-zinc ore, 180 feet level (3 feet wide).	0·50	23·55	13·40	,,	18 12 9

Strike of lode N. 25 W.; dip, S. 65° W. at 1 in 5. Country, slate and crushed quartz felsite. Stoped about 130 feet to north-west at 150-feet level; and for 70 feet at 80-feet. Depth of shaft, 200 feet.

Rockley Division.

Prosper Mine, parish Baring, county Westmoreland, near Essington.—Old workings re-opened in 1907. New shaft 60 feet on underlay in carbonate ore—width, 6 in. to 2 ft. 6 in. Strike N. 10° W.; dip, west. Two lodes about 500 feet apart. The western was opened some years ago, revealing low-grade silicious ore—partly chalcedonic; sulphides showing leanly.

The oxidised ores only extracted in the main or east workings; about 60 tons despatched for a reported yield of 8 to 10 per cent. copper. This lode dips at about 30 degrees only. The deepest workings being 60 feet. Stopes extend for a length of over 100 feet at the 40-feet level, and up to surface. A few feet of stoping only at 60 feet. In June, 1908, brick-making was in progress in connection with erection of a reverberatory furnace, which had been decided upon.

Blayney Division.

Quigley's Hill Copper Mine, about 5 miles south of Blayney.—A thin vein of copper pyrites was followed down in this mine for about 140 feet in sedimentary rocks—slates and sandstones. The channel rock consists of greasy jointed and cleaved slates. Inspector D. Milne states that at 100 feet the vein was about 6 inches thick. Nine tons of ore sent to Lithgow for trial yielded 9 per cent. of copper. This amount, judging from the tip, is all the ore raised during operations.

Orange Division.

Ratscastle Lode, portion 15, parish Byng, county Bathurst, on W. Hawkes' estate, near Byng.—Opened some years ago; 20 tons sent away. Re-opened in 1907 by Thomas and party; despatched 12 tons of seconds from old shaft for a return of 7 per cent. of copper. Country chlorite schist. Lodestuff silicious.

Bathurst Division.

Red Hill Mine, M.L. 31, parish Ponsonby, county Bathurst.—Prospected many years ago.

In 1901, 250 tons of ore were raised, 53 of which were disposed of (Ann. Rept., 1901, p. 54).

BATHURST MINING DISTRICT—*continued.*

Sulphides reported at 70 feet. Ore at grass consists of hornblende schist with cubical pyrites and some chalcopyrite. Limestone closely adjacent. No defined walls. Strike of sulphide bunch N. 25° W. Width 7 to 8 feet.

Ore raised in 1903 not rich enough to despatch.

Reopened in 1906 by J. Osborne—a little carbonate ore showing in open cut. Sinking on underlay.

Work resumed towards end of 1907.

Blayney Division.

Rise and Shine Mine, Brown's Creek, 9 miles S.E. of Newbridge Railway Station, portion 35, parish Ponsonby, county Bathurst.—Strike, N. and S.; dip, E. in schist; width, 5 feet to 8 feet; maximum length of proving, 200 feet; depth, 80 feet. Ore sulphides and carbonates carrying gold and silver.

Inspector D. Milne reported (P.B. $\frac{54}{08}$) a rich pipe of copper ore; 60 to 80 tons good ore obtained.

Rockley Division.

Rockley District. (*See* Cow Flat, Apsley, Belmore, Summerhill, and Mountain Run Copper Mines).—Copper ores occur in numerous places in this district. Besides those abovementioned, the following have been reported:—

Back Creek.—Sample assayed $\frac{20}{08}$ and $\frac{41}{07}$ yielded 30·16 and 11·86 per cent. of copper.

Rockley, 5 miles east.—Sample $\frac{96}{07}$, copper, 21·05 per cent. ($\frac{19}{08}$ and $\frac{19}{08}$); copper, 16 to 17·67 per cent.

Rockley, 8 miles north-west.—Sample $\frac{20}{07}$, copper, 32·52 per cent.; silver, 2 oz. 3 dwt. per ton.

About 7 miles north-west of Rockley, and 1½ miles west from the Rockley Bathurst Road, parish Ponsonby, county Bathurst.—Inspector Milne reported (P.B. $\frac{22}{08}$) that Byron and party were prospecting for copper in schist country. Shaft 110 feet, stoped at south end. Some years back a bunch of fair ore was worked from surface to the 110-feet level where sulphides were met. The oxidised ores were stoped out for a length of about 60 feet, pinching at each end of the stope. At this stage the mine was abandoned. The channel is described as well-defined, and the outcrop strong. From the shaft 6 tons of ore yielded 7·5 per cent. of copper. Aid granted to continue prospecting.

Rockley, 13 miles from, on south side of O'Connell to Essington Road, parish Baring, county Westmoreland.—Inspector D. Milne reported (P.B. $\frac{21}{07}$) a quartz reef with splashes of yellow ore in schist. Formation 3 to 4 feet wide. Aided to sink from 30 to 100 feet.

Rockley Farm, about 2½ miles east of Rockley.—Inspector G. Smith reported (P.B. $\frac{22}{08}$) quartz vein in porphyry (?), carrying small bunches of copper and iron pyrites with blende, &c. Shaft, 23 feet. Aided to sink to 50 feet.

Inspector Milne reported (P.B. $\frac{21}{08}$) copper-stained country about half a mile south of the above site; also about 100 yards north, but no sign of lode.

On south-east side of O'Connell-Essington Road, between Captain King's Creek and Brisbane Valley; an old mine reopened in 1907 by new shaft in north end of outcrop, by Kennedy and party. At south end old workings reopened under aid.

Rockley.—At junction of Back and Davy's Creeks a small vein of copper carbonate and oxide was opened for a few feet about 1902; and reopened by Ryan and Hanson towards end of 1907. Copper stains for a width of 2 or 3 feet; best indications about 15 inches wide.

About 1¼ miles south-easterly from Rockley green carbonate of copper showing slightly in quartz, opened for about 15 feet.

North end of Dog Rocks on the Brownlow estate, carbonates and sulphides occur; width not defined; opened in 1907 for about 13 feet.

In portion 153, parish Rockley, county Georgiana, copper vein opened by Cock and party some years ago. Shaft sunk to 84 feet under aid. Abandoned.

Ranger's Mine, portion 43, parish Rockley, county Georgiana, about 2 miles east of Rockley on Pepper's Creek. Shaft, 48 feet.

An irregular vein of copper ore (yellow sulphide) 2 or 3 inches thick in massive quartz, traversing a belt of hard quartzite. Several other similar but thinner veins occur in the rocky creek bed in a width of several chains.

About 8 chains south-easterly another shaft has been sunk a few feet, showing splashes of copper sulphide in country—no defined lode channel. Massive quartz forms a bluff outcrop between the shafts. Strike of veins about N. 50° W. Abandoned.

"*Shepherd's*" *Mine,* M.Ls. 33, 34, parish Ponsonby, county Bathurst, near Mountain Run Mine.—Originally opened by Thomas Quin. Country, crushed quartz felsite and chlorite schist.

Good carbonate ore reported to have been taken out in Cow Flat Smelting days, from an open trench or cut 30 feet deep. The mine was reopened about 1895 by Amos and Shannon, in another shaft a little further south.

Shaft sunk in 1907, 85 feet, and driven 15 feet north at 65 feet, on a vein about 1 ft. 3 in., which split into strings in hard country at bottom. Ore consists of carbonates, oxides, and sulphides associated with quartz.

In the same leases nearer Mountain Run, two other shafts have been sunk, revealing stains of carbonate in schist, and further east, in slate, neither of importance.

About half a mile east of the Shepherd Mine a cross lode was sunk on by J. Hunt about 1906, who cleaned out old shafts down about 70 feet, and drove west on a narrow vein from 9 to 10 inches in width carrying carbonates and sulphides—a few tons raised, none sent away.

Rockley, Brown's Creek, near Back Creek, Caloola.—Inspector H. Hooke reported (P.B. $\frac{2}{9}\frac{2}{9}\frac{0}{0}$): Copper-bearing veins in chlorite schist (carbonates and sulphides) in bed of creek. Aided to sink 150 feet, and cross-cut 60 feet.

Lode opened by four shafts ranging in depth from 30 to 110 feet. 110-feet shaft driven west 40 feet. Water struck at 90 feet. Lode pinched out at 60 feet.

Further aid ($\frac{1}{0}\frac{1}{2}\frac{0}{0}$) to drive 100 feet north and south on lode at 90 feet. No marked improvement.

BATHURST MINING DISTRICT—*continued.*

Mount McDonald Division.

Silver City Lode, parish Dunleary, county Bathurst.—J. Holden raised 24 tons of ore valued at £156 (Ann. Rept., 1903, p. 47).

Orange Division.

Slattery's Creek, in J. Kelly's Pastoral Lease.—Inspector H. Hooke reported (P.B. $\frac{8}{5}\frac{3}{2}$): Diorite dyke traversed by veins of copper pyrites. Aided to tunnel 100 feet and cross-cut 20 feet. At 62 feet, a little copper showing between good walls; at 98 feet, a little copper, gold and silver; at 101 feet, no improvement.

Slattery's Creek, 3 miles south of Forest Reefs Post Office.—Inspector J. James reported (P.B. $\frac{1}{0}\frac{8}{8}\frac{0}{4}$): A copper vein in slate showing about 8 inches thick at bottom of 45-feet shaft. Aided to sink to 100 feet. At 68 feet a little good ore. No further report.

Reported in March 1907, that Mills and party were working a small vein of copper ore; the last consignment realised £1 per bag.

Burraga Division.

Sprague's Mine (or Mount Burraga) M.L. 4, Parish Jeremy, County Westmoreland. About 1 mile east of Lloyd Copper Mine, Burraga.—Inspector H. Hooke reported (14/7/01): Strike, N. and S. Proving—depth, 87 feet; length, 340 feet. Being reopened by new shaft.

In 1902 was worked to end of April; shaft deepened to 162 feet. Driven 82 feet at 140-feet level. Lode cut in drive assayed 3½ per cent. (Ann. Rept., 1902, p. 49).

Examined by Inspector D. Milne (P.B. $\frac{8}{0}\frac{6}{7}\frac{8}{}$). Aided to sink the 70-feet underlay shaft a further 50 feet, and to drive 50 feet. Pyritic lode underlaying 1 in 5 to the west. Varied in width from a few inches to 4 feet. Contains fair grade yellow ore in parts.

At 80 feet pinched to a thread, widening again at 90 feet. Good patches of ore met in shaft and cross-cut, but always cut out in a few feet.

Rockley Division.

South Wiseman's Creek Copper Mine, on the south bank of Wiseman's Creek, on the same lode as the Wiseman's Creek Mine.—The earliest record of this mine is contained in *Mineral Statistics*, 1875, p. 92, in which the depth of proving is given at 120 feet. Assays returned 9 to 20 per cent. of copper, and 9 to 20 per cent. of lead, and traces of gold and silver. Two hundred tons of ore had been raised, and sold at £6 10s. per ton.

In 1876 and 1877 the mine was idle. In the latter year it was visited by the late Government Geologist, Mr. C. S. Wilkinson, who stated that it was apparently on the same line of fault as that in which the Wiseman's Creek Mine is situated. During $\frac{1}{p.}\frac{8}{97}\frac{1}{}\frac{8}{}$ a little work was done near the surface for carbonate ores. In $\frac{1}{p.}\frac{8}{61}\frac{8}{}\frac{4}{}$ the presence of silver in some quantity having been detected in the lodes of Wiseman's Creek, considerable attention was directed to them. A tunnel near the creek level was at this time started in the South Mine.

Attention was directed to the locality in 1899, chiefly owing to the substantial rise in the value of copper, and a little work was done in cleaning out and repairing the main shaft and tunnel. The Wiseman's Creek ores are unfortunately contaminated with zinc sulphide, which renders them refractory.

Blayney Division.

Sugarloaf Copper Mine (Wright and Osborne's), about 2 miles south of Blayney.—Discovered in 1896. Outcrop consists of magnetic and brown iron ore in andesite. The iron ore is of excellent quality. Under the oxidised cap, massive pyrrhotite (magnetic pyrites) occur, containing a little copper pyrites. The leaching out of the copper from the outcrop has been very thorough, and nearly as complete in the underlying magnetic pyrites. An assay of a selected sample of the latter yielded only 0·45 per cent. of copper whilst below this level a mixed sample of pyrrhotite and chalcopyrite yielded 12·68 per cent.

As work had ceased when the Writer visited this mine in 1898, an inspection of the lower levels was not feasible. It is reported by Mr. J. Russell, of Blayney, that the two shafts are 75 and 105 feet respectively. In the former a cross-cut has been extended 9 feet, and in the latter (at 50 feet level) 53 feet in lode-stuff. The ore consists of a mixture of copper and magnetic-iron pyrites, averaging about 7 per cent. copper. At the bottom of the 105-feet shaft a cross-cut has been driven 13 feet, also in lode-stuff. Fifteen tons 18 cwt. of ore from this mine, treated at the English and Australian Co.'s works, Waratah, yielded 5¾ per cent. of copper; gold, about 3 dwt.; and silver, 3 oz. per ton.

The Blayney Mining and Smelting Company prospected the old workings in 1907 without discovering payable ore. The lode made largely into pyrite, partly magnetic. The company sank to 165 feet, and cross-cut 100 feet.

Canowindra Division.

Sugarloaf, parish Malongulli, county Bathurst, near the Belubula River, on Cliefden Station.—The late Mr. W. M. Rothery, owner of this station, many years ago discovered a small, loose specimen of native copper close by a small creek. Later the lode was discovered. About three years ago arrangements to test it were made with the late Marmaduke Constable, and a shallow shaft and open-cut were sunk. Near the surface some fine specimens of native copper and cuprite were revealed by a blast. The country consists of highly-altered sedimentary rocks, close to the junction of hornblende porphyry. Superficial copper stainings marked the rock raised during operations; but nothing payable was discovered so far as these proceeded. A rough, rocky outcrop occurs, extending southerly, in which ferruginous bunches occur with stains of copper carbonates. This outcrop could be well tested by tunnel.

Carcoar Division.

Summer's Copper Mine, 3 miles south from Carcoar on the Coomba Road, on the west side of Coombing Creek, parish Summers, county Bathurst.—Inspector D. Milne, in October, 1896 (P.B. [illegible]), reported that the lode has a thickness of about 3 feet, with a gossan outcrop. Strike, north-

west and south-east; dip, nearly vertical. The ores consist of carbonates, black and yellow ore, but rather dredgy. At 105 feet the lode appeared to be making stronger. Aid granted to continue prospecting. At 155 feet the thickness was 3 to 4 feet. Five tons sent to a smelting works yielded 11½ per cent. of copper.

Rockley Division.

Summerhill Copper Mine, parish Rockley, county Georgiana.—One of the earliest copper-mines opened in the Colony. According to Mr. James Ranken, of Bathurst, work was in progress here as early as 1847. In the following year a company was formed in Bathurst to work this property. An extract from the prospectus of the Bathurst Copper-mining Company, published in the *Bathurst Advocate*, of the 30th December, 1848, is embodied in the introductory portion of this work.

In April, 1851, Mr. S. Stutchbury examined the mine, and reported as follows:—"The rocks or strata in which the mining is carried on are for the most part mica and grindstone slates. The strike or level line is west of south and east of north. The workings consist of three shafts—the Gilmandyke, Clymo's, and the present working shaft. The sinkings are on two lodes, parallel to each other. The ores which form the bulk for smelting are pyritic, viz., yellow sulphuret of copper, arsenical sulphuret of copper, and domeykite (?) of Waidinger. There are other varieties in small quantities. On the spoil heaps may be seen some very beautiful sulphates, formed by decomposition of the sulphides by exposure to the atmosphere At the bank of the eastern shaft there is a large heap of ore which, from its appearance, I take to be domeykite, or arsenical sulphuret of copper—a very rich ore. This has been thrown out as waste, under the impression that it was iron pyrites—'mundic.' There is also much valuable ore on the spoil-heaps and underground in one of the vugs. The experiment of smelting with green timber is in a fair way of being successfully proved. Although working under the disadvantages of an ill-constructed, half worn-out air-furnace, the produce of the first process was encouraging. The mine, with its present prospects, with care in the management, there is good reason to believe, might remunerate the adventure, although I do not think, without further discoveries, that it will ever be a first-class mine."

In the *Mining Journal*, London, 1854, vol. xxiv. p. 264, reference is made to this mine. Four shafts, from 100 to 300 feet deep, and numerous levels are mentioned, and the erection of a furnace recorded.

Mr. H. Clements, son of the original owner of the Summerhill Estate, informed the Writer that the mine was discovered by a stonemason named Rex, who was working the soapstone, in which the first indications of copper were found, on the Gilmandyke Creek, about a mile from its junction with the Campbell River. This first vein was about 2 feet thick, in hard rock. It was sunk upon or about 90 feet, but was abandoned for a more promising lode about a quarter of a mile distant. The second lode was opened by two shafts and an adit for about 300 feet or more. The lode consisted of yellow sulphide, from 4 to 6 feet in thickness, estimated to yield 10 per cent. dressed. Mr. Clements states that the smelting process on the ground consisted of heap-roasting and reverberatory smelting; but judging from the frequent occurrence of prills of metallic copper in the slag, the latter was badly performed. Probably not more than 20 tons of copper were despatched from the mine. Operations ceased upon the discovery of gold

in 1851, arrangements being made by the company for suspension of work for a year. Operations were subsequently renewed, and continued until 1858. After the company finally abandoned the property, work was carried on for a few months by a Mr. Peck. No particulars are available of the output after the renewal of work. Very little indeed was to be seen for the capital expended.

In $\frac{1883}{p.\ 126}$ Chief Inspector Slee reported that a shaft had been sunk about half a mile north of the old Summerhill Mine, on a chute of good ore, 1 foot thick, between well-defined walls. A large outcrop of gossan occurs further up the hill.

In $\frac{1897}{p.\ 72}$ the lodes were again being tried. Ore to the value of £500 is reported to have been sent away; 11 tons 4 cwt. of ore, picked from the old heaps, yielded 11¼ per cent. of copper at the English and Australian Company's Works at Waratah.

Taken up by F. Tapson in September, 1901. Unwatering completed in 1902; shaft deepened to 200 feet. Stoped on north side on a slant up to old workings.

Reverberatory furnace erected; produced about 50 tons of 50 per cent. matte.

Sank Buller's Shaft (on Box Ridge) about half a mile north, from 50 to 100 feet. Extracted 30 tons for test. Ore yellow sulphide making largely into pyrrhotite with depth.

The main shaft in Summerhill Lode, at 200 feet is reported to have cut through lode. At this level it was split by slate and quartz—1 foot 3 inches of good yellow sulphide on hanging wall, and 6 inches on footwall.

Inspector B. Sawyer reported (P.B. $\frac{1906}{0\ 4\ 6}$) three lodes striking N. and dipping E. The "Main," or "Summerhill" Lode, being opened by various shafts—Nos. 2 and 3 lodes (on Box Ridge) being each opened by shafts 100 feet deep. The latter are described by Mr. Sawyer:—"Box Ridge is situated northward from the old Summerhill Lode, at a distance of a quarter of a mile, here two ore bodies have been opened up. No. 1 was formerly worked by Mr. L. Lloyd to a depth of 100 feet, and a length of 150 feet. The No. 2 ore body runs parallel to No. 1, and distant therefrom about 100 feet. The shaft is vertical for 30 feet, then it follows the underlay of the lode down to 100-foot level, where the ore channel opened out and a body of chalcopyrite in a quartz gangue was worked for a length of 16 feet, and an average width of 2½ feet. This body appears strong in floor and southern end of shaft."

Aided to continue 100 feet shaft to 150 feet. Work ceased at 130 feet, as prospects had not improved.

Subsequently held for a brief period by the Lyndhurst Railway and Mines, Limited, in 1905, in an endeavour to procure copper flux for the Lyndhurst ores. Some ore raised, and some taken from surface.

Sunny Corner Division.

Sunny Corner, parish Castleton, county Wynyard.—Apparently the first official mention of copper at Sunny Corner is that contained in the Annual Report of the Department of Mines for 1876, page 78, wherein the Mining Registrar states that the copper mines at Sunny Corner were at a standstill. The ore had been taken to the Bowenfels Smelting Works, but had not paid expenses.

The lodes at Sunny Corner were first worked exclusively for gold; but about 1881, Mr. H. Y. L. Brown sampled them, and found that their principal value was in silver. Several companies were shortly afterwards formed, and blast furnaces erected. The first—a Pacific Smelter—was started in August, 1884. Whilst the kindly oxidised ores were abundant, smelting operations were successfully maintained. When, however, these were exhausted, great difficulties were encountered in treating the lower-grade refractory sulphides beneath, which consisted of a mixture of sulphides of iron, zinc, lead, copper, arsenic, antimony, &c. Operations were, however, carried on until the heavy fall in silver value, which banished any hope of profitable working under existing conditions.

All the Sunny Corner lodes carry more or less copper which, in smelting, is obtained as matte:—

In 1888 24,972 tons of ore from the Sunny Corner Proprietary Mine yielded 201 tons of lead, 309 tons of copper, and 1,256 tons of matte, containing 319,324 oz. of silver and 2,300 oz. of gold.

In 1890 the Phœnix Mine passed into the hands of the well-known copper smelter, Mr. Lewis Lloyd. Nine hundred tons of cupriferous ore were raised and despatched to his Eskbank Smelting Works.

In 1891 the Nevada Mine produced 110 tons of copper matte from 680 tons of ore smelted at the mine.

The Sunny Corner Proprietary produced 344 tons of copper from 34,046 tons of silver and gold ore treated during the year, and 77 tons in 1892.

Between 1888 and 1895 (inclusive) the Sunny Corner Company produced, according to its shipping register—6,162 tons 10 cwt. 3 qrs. 23 lb. of matte, containing 1,109·25 tons of copper; 10,752 oz. of gold, and 1,361,676 oz. of silver. The company paid fifteen dividends, amounting to £91,200, equal to 28s. 6d. per each £1 share. After the company ceased operations smelting was carried on by Mr. J. K. Charlston until the serious fall in the price of silver. According to Mr. Charlston's books, the average contents of the ores smelted have been—"Copper, 0·79 per cent.; silver, 7 oz. 8 dwt. 13·6 grs. per ton; gold, 1 dwt. 16·7 grs." The total cost of production, including rent of leases and additions to plant, amounted to 29s. 1d. per ton of ore.

Attention was directed to the Nevada Mine in 1898, as it was reported to contain a fair proportion of copper, which, with its gold and silver contents and silicious gangue, rendered it serviceable for fluxing copper matte. The following analyses were made from a sample selected by the late Government Geologist, Mr. C. S. Wilkinson. (Annual Report, 1886, page 140):—

	No. 1.	No. 2.
Oxide of iron and alumina	24·18	26·31
Insoluble silicious matter	46·63	51·02
Lead	9·34	6·25
Copper	5·06	4·02
Bismuth	·88	trace.
Antimony	·43	„
Arsenic	·90	„
Sulphur	12·42	9·32
Manganese	trace.	trace.
Chromium	„	„
Undetermined, loss, &c.	·16	4·08
	100·00	100·00

BATHURST MINING DISTRICT—*continued.*

Oberon Division.

Tarana.—Six miles from—along Tarana—Diamond Swamp road, in a north-east direction from Tarana in G. Kemp's C.L., portion 96, parish Eusdale, county Roxburgh.

Inspector D. Milne (P.B. $\frac{2}{0}\frac{3}{7}\frac{9}{4}$) reported a large quartz formation in porphyry. Strike N. and S., nearly vertical; showing specks of yellow ore, but not in payable proportion. Aided to continue shaft to 50 feet. Progress: Country hard. Ore shoot 9 to 10 inches wide at 40 feet. Another bunch showing at north end.

Trunkey Division.

Trunkey District.—Two copper lodes occur near Trunkey—one near Kempfield (which see) and the other near Bombah. The former was worked off-and-on, but not with much success. The latter was equally unproductive.

Copper ores are also reported at Scrubby Rush, Sounding Rock, and Tiger's Hut. A sample from the latter, $\frac{4}{10}\frac{8}{7}\frac{4}{4}$ yielded from 12 to 14·69 per cent. of copper.

Oberon Division.

Tuglow District, county Westmoreland.—For some years copper ores have been known to occur in this district, but little practical effort was made to develop them until about 1898. Mr. W. J. Bouchier, of Clover Hills, near Tuglow, who worked a lode in portion 52, parish Banshea, supplied the following information, under date of May, 1898:—"The lode in portion 52 has a thickness of about 5 feet. Two shafts have been sunk 30 and 45 feet. From one of these, 36 tons of ore were extracted for an average yield of 14 per cent. of copper, 10 per cent. of lead, and 5 oz. of silver, and 2 dwt. gold per ton. The outcrop is gossan, but at the depths quoted sulphides of copper and lead are encountered.

Inspector H. Hooke, who visited Tuglow about this date, states that Bouchier and party sank to a depth of 60 feet, on what appears to be a true fissure vein, averaging 3 feet in thickness, and containing ore rich in copper, and which has also yielded as high as 17 dwt. of gold per ton.

The lode has a N. and S. strike in slate country, and dips somewhat flatly towards the west. Walls well defined.

About half a mile south of this was Cunningham and party's claim, in which a vertical shaft was sunk to intersect a well-defined vein.

Still further south and within a quarter of a mile was Cotton and Fraser's claim. Their main shaft had been sunk to a depth of 45 feet, on a contact lode between diorite and slate country. Strike of lode N. and S., dip easterly. Bunches of good grade ore occur at the junction and extend for some feet into the slate.

Under date 15th March, 1899, Mr. McLeay, warden's clerk, Burraga, wrote:—"That at 60 feet water was getting troublesome. A sample of copper pyrites with galena and zinc-blende forwarded yielded ($\frac{2}{10}\frac{3}{7}\frac{4}{4}$)—copper, 10·73 per cent.; lead, 23·02 per cent.; zinc, 13·10 per cent.; and silver, 9 oz. 1 dwt. 20 grs. per ton."

Fourteen tons from Cotton and Fraser's Mine, treated at the Smelting Company of Australia's Works, Dapto, returned 9 per cent. of copper and 16 dwt. 22 grs. of gold per ton, the ore being unpicked. Thirty tons were ready for despatch. Native copper appears along the footwall of the lode.

The cupriferous belt at Tuglow can be traced for some miles, and limestone occurs in conjunction.

Aid was granted for sinking 50 feet on a copper vein in Dun & Co.'s C.P., parish Drogheda, county Westmoreland, on Shepherd's Creek (P.B. $\frac{2}{9}\frac{7}{9}\frac{1}{9}\frac{4}{9}$). Water proved heavy—evidently fruitless.

During 1900 prospecting was continued in Bouchier's, and Cotton and Fraser's sites. Twenty-five tons were raised from the former, and disposed of for £100. (Ann Rept., 1900, page 55.)

In 1906 Bouchier's Mine was reopened by a Yerranderie syndicate, who subsequently formed the Tuglow Copper Mining Company, Limited, in March, 1907.

In July, 1907, the main shaft in Tuglow Mine was 130 feet deep on a small body of 20 per cent. ore.

Fifty tons of ore shipped to Swansea for experimental purposes.

Orange Division.

Wallaby Rocks, between Cadia and Cadia Extended Mines (which see). Poor copper ore in felspar porphyry.

Cowra Division.

Waugoola Creek Copper Mine.—This mine (which was first opened some years previously), was reworked in 1898. Inspector D. Milne, stated that at the 104-foot level the lode was 6 inches thick in the shaft, but occasionally it increased to 3 feet in bunches. The following parcels of ore have been despatched to the Lithgow Smelting Works:—

30	tons realised	£600 net.
7	„	98 „
7	„	114 „
44	tons realised	£812 net, equal to £18 9s. 2d. per ton.

About half a mile south of Waugoola Creek, on the travelling stock reserve, a large quartz reef, about 2 feet thick, strikes north and south through slate country, and carries stains of copper carbonates, which also occur in the walls.

Orange Division.

Wellwood.—The Wellwood Copper Syndicate began prospecting operations in Wellwood paddock, near Lucknow, in 1907.

Cowra Division.

West Hill Lode, parish Killingworth, county Bathurst (on Cooley's Estate, 6½ miles from Woodstock on Cowra-road)—Inspector J. Polkinghorne reported (P.B. $\frac{2}{9}\frac{7}{9}\frac{4}{9}\frac{7}{9}$):—Gossan with small veins of copper ore in slate and schist. Aided to sink from 25 to 125 feet. At 43 feet—Small copper-stained leaders between well-defined walls.

At 94 feet.—Occasional bunches of copper ore, arsenical pyrites, and traces of gold.

At 115 feet—Lode 5 to 6 feet wide; carbonate ore on footwall in winze.

At 125 feet—Prospects reported good, but not payable.

Woodstock (*see* Burley Jacky, Belmore, and Waugoola Mines).—Woodstock, on the Blayney-Cowra railway line, is situated in a belt of andesitic rock, more or less cupriferous, which extends into the adjoining Carcoar and Blayney districts. A considerable amount of prospecting has been carried out in the neighbourhood of Woodstock, frequently occasioned by the superficial stainings on the andesite outcrops. These have often led to useless expenditure, as no defined ore bodies have been found in the solid rock, which owes its deceptive colouring to decomposition of sparingly distributed particles of indigenous metallic copper. Near Sugarloaf Mountain, on Cliefden Station, native copper occurs in Smith and McGuiness's shaft, and also in Rothery's Mine near by. In the former instance the copper is in an amygdaloidal andesite, both in the solid and in the amygdules.

In addition to the mines mentioned, copper ores occur in the following localities:—Purcell's land, about 2½ miles northerly from Woodstock; opened in 1895 by two shafts 40 and 60 feet deep. Carbonates and grey sulphides occur, much mixed with the country, but no true lode was proved.

From Nobby's Mine, Woodstock, the Under Secretary for Mines reported $\frac{1896}{p.\ 42}$, that 150 tons of ore were sold for £620.

In addition to the above lodes, the Writer has examined others at various times:—The Cowra Mine, at Bald Hills, about 3½ miles south-west; Russell and party's, 4 miles south-west, which had an outcrop of about 4 inches and a thickness of 2 feet at 17 feet; strike north and south. Phœbe and party's Mineral Lease 51, about 5 miles south-west of Woodstock, where a shaft had been sunk 70 feet on a lode consisting of quartz and clay with carbonate and oxide of copper; strike N. 60° W. Jones's claim, south-east of Woodstock, vein 4 inches, consisting of carbonates and sulphide. T. Austin and party's, half a mile north of Belmore Mine at the junction of sedimentary and intrusive rocks. Bartemote and Hudson's, portion 71, parish Kenilworth, county Bathurst; here shafts were sunk thirty-five years ago in soft schistose slate, striking north and south, and carrying a little copper carbonates with quartz veins; also at Wood's Creek, 4 miles south of Woodstock. In Cooley's Estate, Westville, 7 miles from Cowra, aid was granted to sink on a lode channel having well-defined walls. The slaty dig between the walls carries thin copper-bearing leaders. Aid granted for 100 feet of sinking.

In 1899 Inspector H. Hooke reported (P.B. $\frac{1899}{5}$):—Copper-bearing slate in F. Rowland's land, 3 miles north of Woodstock, and 1 mile south-east of Burley Jacky Copper Mine.

Aid granted to continue sinking to 100 feet. A thin seam of copper ore cut, prospects poor; apparently abandoned shortly after test began.

On T. Hemsley's land, 5 miles north of Woodstock, parish Kenilworth, county Bathurst, Inspector G. Smith reported (17/7/06):—Quartz containing copper ores, in andesite. Strike N. and S., vertical, shaft, 21 feet; aided to sink (P.B. $\frac{1906}{56}$) to 46 feet. At 32 feet very hard. Work abandoned.

BATHURST MINING DISTRICT—*continued.*

Rockley Division.

Wiseman's Creek Copper Mines (known also as North and South Wiseman's, and Eyrie South Mine), about 22 miles from Bathurst, and 12 from Brewongle railway station.—In October, 1873, the English and Australian Smelting Company, Newcastle, treated the following parcels of copper ore from Wiseman's Creek, which probably represent the first extracted:—

9 tons 5 cwt.; yield, copper, 13 per cent.
4 „ 14 „ „ „ 10½ „

The first official record is embodied in the *Mineral Statistics of New South Wales*, 1873, p. 128. In it the Wiseman's Creek Copper Mining Company was reported to be working a lode at Wiseman's Creek, striking N. 30° W., with a slight dip to the west. It had been proved to a depth of 120 feet, where it had a width of 20 feet. Seven hundred tons of ore had been raised and 350 sold at an average of £7 per ton. Assays yielded from 9 to 17 per cent. of copper, an equal amount of lead, and traces of gold and silver. Fourteen men were employed.

In the Annual Report of the Department of Mines for the same year, pages 142 and 145, assays by Professor Liversidge are published, viz.:—

Carbonate ores yielding, from 16 to 27 per cent. of copper.
Sulphides „ 9 to 10 „

The above were associated with zinc and quartz in a lode 18 feet wide; depth 100 feet.

In 1875, p. 77, the Mining Registrar reported that smelting works had just been commenced, and that the ore had been found to contain copper, lead, zinc, silver, and gold.

In 1876, p. 117, ore was being raised. In this year the mine was inspected by Mr. C. S. Wilkinson, who reported as follows:—"The lode is in talcose schists, which dip S. 79° 45′ W. at 63°. It occupies the fissure of a fault, and strikes N. 15° W., and has a varying dip generally to the east. The ore occurs in bunches along the course of the fault and in offshoots from it. These bunches and shoots of ore, together with some veins of quartz, are of irregular thickness, being from 1 to 18 feet. The ore is of a very mixed character. It consists of green and blue carbonates, sulphides, and black oxide of copper, with the sulphides of lead (galena), zinc (blende), and iron and arsenical pyrites; occasionally a little native copper is met with. Occupying, as it does, the fissure of a fault, the lode will doubtless prove to be a permanent one in depth."

In 1877, p. 97, under the head of "North Wiseman's," the mine was reported in full work. The main shaft had reached 162 feet and the lode was being driven on at that level. Thirty to 40 tons of ore per month were being raised of about 8 per cent. grade; twelve men employed.

In 1879, p. [illegible] work was continued up to November, £1,750 worth of copper ore being obtained.

In 1880 the mine was closed.

In 1884, p. 47 work was being carried on, but unremuneratively. Payable prospects of silver being obtained, a number of leases were taken up hereabouts.

In 1888 and 1889 a fresh attempt was made—by Messrs. E. A. Baker and Sons—to work the lode under the name of the Eyrie South Copper and Silver

Mine; but the effort was unsuccessful, and the mine, which is on private land, has since remained idle. The ores, as already described, are of a refractory nature, zinc sulphide predominating—a feature of the lodes in this locality. A reverberatory furnace was erected but never used.

In 1901 Hunter, Wiley, and party drove 580 feet, and sank shafts 30 and 140 feet in the southern or South Wiseman's Creek section. (Annual Report, Department of Mines, 1901, page 54.)

In 1907 a little prospecting in north tunnel was done by the Hon. A. J. Gould, under a purchase option, which was subsequently abandoned.

A considerable amount of work has evidently been done in the early days of copper mining in this locality, judging by the surface evidence.

The Writer is indebted to the late A. G. Thompson, solicitor, Bathurst, for the following particulars from early records in his possession:—

The North, or original "Wiseman's Creek Lode," is described as outcropping for a length of 20 feet or more, and a width of 6 to 8 feet. Operations began at this site, and later about 200 feet south. No capital put into the mine; which was worked so as to pay its way from the start.

A contract was entered into with the old Esk Smelting Company for sale of ore at a fixed price per ton on a minimum basis of 5 per cent.; the price believed to be £1 per ton, and rising 12s. 6d. per unit. This contract continued for about five years, during which about 6,000 tons are said to have been delivered. The only original vouchers and returns extant cover a period of three years, and to that extent can be verified. During this period about 3,400 tons of ore were sold, averaging 10·6 per cent.; returning something over £13,000.

This section of the workings is not now open to inspection, the shafts being beyond repair. It was opened by shafts and shallow open cuts at a considerable distance from the tunnel site in the north bank of Wiseman's Creek, and a surface height of probably 200 feet above it.

The sulphide ore lying at grass is very zincy, as will be seen in the following assay of an average of this class, taken from the small heap at surface:—

No. 08-914—	Copper	4·65 per cent.
	Zinc	21·57 ,,
	Iron	8·54 ,,
	Sulphur	23·16 ,,
	Silica	21·56 ,,
	Gold	2 dwt. 4 grs. per ton.
	Silver	4 oz. 4 dwt. 22 grs. ,,

From the north tunnel at the creek level, a small quantity of sulphides extracted during Mr. Gould's option yielded an average of:—

No. 08-919—	Copper	11·05 per cent.
	Zinc	5·73 ,,
	Iron	10·92 ,,
	Sulphur	14·92 ,,
	Silica	47·30 ,,
	Gold	2 dwt. 4 grs. per ton.
	Silver	2 oz. 18 dwt. 19 grs. ,,

The South Wiseman's Creek workings are across the creek on the southern continuation of the strike, which between the two sections bears N. 20° W.

BATHURST MINING DISTRICT—*continued.*

The southern section has been opened in the past by two tunnels and several shallow openings—and a large open cut—where a strong gossany lode is still showing in the face; south of this, however, costeens fail to discover it. The latter are about 180 feet above the creek level. The lowest tunnel is 25 feet above, and the second, 80 feet; the open cut 140 feet. The material tipped from the tunnels is largely pyritic schist.

Oberon Division.

Yates' Tarana Prospecting Syndicate, portions 2 and 29, parish Eusdale, county Roxburgh, 4½ miles east of Tarana Railway Station.—Shaft 18 feet, copper sulphide reported 2 feet 6 inches wide. Average assay value—copper, 10 per cent.; silver, 5 oz.; gold, 2 dwt. per ton.

Parallel lode—shaft 16 feet; silver-lead ore 1 foot 6 inches wide. Assay value—lead, 25 per cent.; gold, a trace; silver, 20 oz. per ton.

Other samples yielded:—

No. 06-6610—Magnetic and hematitic iron ore with copper pyrites:—
Copper, 6·05 per cent.
Gold, a trace, per ton.
Silver, 12 oz. 18 dwt. 1 gr. per ton.

No. 06-6611—Copper pyrites with quartz and zinc-blende:—
Copper, 16·92 per cent.
Gold, a trace per ton.
Silver, 3 oz. 17 dwt. 7 grs. per ton.

Yorkey's Creek, Bourke's property, about 1 mile from Mount Victoria—Jenolan-road, at 11-mile peg. Portion 214, parish Lowther, county Westmoreland.—Copper sulphide with specular iron.

CLARENCE AND RICHMOND MINING DISTRICT.

Copmanhurst Division.

Busy Bee Copper Lode, parish Pucka, county Drake, about 1 mile westerly from Fine Flour Mine.—Located by T. and C. Smith, after disc of shode stones by J. Torrance, in April, 1907.

In July, shaft down 20 feet, exposing a seam of rich grey ore 3½ thick. Width of ore channel not then proved, but thin seams of or crushed channel rock at intervals in width of shaft.

Strike N. 20° E.—vertical. The ores consisting of rich grey sul carbonate and oxide show derivation from intrusive hornblendic Insufficient development to indicate character and extent of lode.

A sample taken from a small opening on strike north of shaft, whe lode is capped with silicious gossan, yielded:—

No. 07-5415—Copper, 0·32 per cent.
Gold, 13 grs.
Silver, 1 dwt. 15 grs. } per ton.

Cangai Copper Mine.—Worked by the Grafton Copper Mining Com M.Ls. 1, 2, 3, parish Kaloe, county Gresham. About 26 miles by road from head of navigable water at Copmanhurst, Clarence Rive 46 miles from Grafton.

Strike about N. 60° W., dip S. 30 W., slight in M.Ls. 1 and 2.

Cangai country rock is puzzling in its petrographical aspect. The foll specimens have been examined by Mr. G. W. Card, Curator and Minera with indeterminate results; though in the field much of the rock close physical resemblance to felsite.

6992—*Granulite*, from footwall.

6995, 6997, 6999 } Very opaque fragmental rock, presumably tuffaceous. From cutting, west side.

6996—Apparently tuffaceous—between E. tunnel level and M.L.

Cangai lode was discovered accidentally by J. Sellars whilst w shooting in August, 1901. His attention being arrested by blue and carbonates showing in a large block on highest point of outcrop.

Taken up by Sellars and party as M.L. 1, in 1901. Prospectors despa about 5 tons of oxidized ore to Waratah, which returned 22 per cent. of c

From the first shaft sunk near point of discovery, about 80 t oxidized ore were raised, yielding from 22 to 34 per cent.

The outcrop on the top of the ridge, which carries a little carbonat thin films of cuprite, would, when crushed, be suitable for fettling.

McLean and party discovered western continuation of lode, taken P. Kritsch and party as M.L. 2.

Corry and party took up the eastern extension as M.L. 3. The was sold to Melbourne investors under the title of "Cangai Copper-m Company," who extracted about 300 tons of ore, despatched to New and Melbourne.

Scene of Original Discovery of Cangai Copper Lode, by J. Sellars, August, 1901.

M.Ls. 1 and 2 were subsequently acquired and amalgamated by the present Grafton Copper-mining Company, and subsequently M.L. 3; also the Sir Walter Scott Gold-mine and machinery, about 2½ miles distant, the auriferous ore in the latter being regarded as a potential flux for the Cangai basic ores, in possible future treatment.

Mr. Warden Fitzhardinge reported the discovery in 1901 (after about 40 tons of ore had been despatched), and recommended a reservation for mining purposes, the latter (No. 34,672) was proclaimed 12th July, 1902.

Progress of development.

1902.—The official report for this year was to the effect that in Harps and party's lease [? Sellars and party.—J.E.C.], Yantalla Creek, two shafts had been sunk, the deepest 40 feet. Four tons of ore had returned 22 per cent. of copper, 2 dwt. of gold, and 13 dwt. silver per ton. (Ann. Rept., 1902, p. 56.)

1904.—Grafton Copper Company formed; 350 tons of ore disposed of for a return of £4,660 (*ibid.*, 1904, p. 47).

1905.—Operations energetically carried on; 291 tons disposed of for £4,805 (*ibid.*, 1905, p. 46).

The enriched ores of the superficial zone continued to be despatched by team to Copmanhurst, until permanent smelting began at the mine in May, 1906.

In each of the lenses opened at a shallow depth, oxidized ores gave place to yellow sulphides, the latter of great purity. Whenever Customs smelting returns dropped below 20 per cent., lower levels were abandoned for higher, taking the zone of maximum enrichment, which rose from both east and west sections in conformity with the physical contour of the outcrop.

The following assays of average samples taken by the Writer at date of first inspection in June, 1905, convey an idea of the richness of the lenses then being opened. It may be noted that these grades were rejected when ore was being prepared for market, only the cream of the enriched sulphides being despatched:—

Assay No.	Description.	Copper, per cent.	Gold, per ton.	Silver, per ton.
			oz. dwt. gr.	oz. dwt. gr.
05-2356 ...	Compact sulphide ore, M.L. 1, east side, 7 feet wide.	17·57	0 3 9	1 2 21
05-2357 ...	Compact sulphide ore, "Wombat Hole," M.L. 2, west side, 8 feet wide.	16·80	trace.	1 7 5
05-2358 ...	Compact sulphides, No. 1 shaft, west side, 16 feet deep, 4 feet wide.	17·46	0 4 8	1 3 23
05-2359 ...	Dredgy ore, east end of drive from end of rich lens in "Wombat Hole," west side, 4 feet wide.	4·26	trace.	1 12 16
05-2360 ...	Gossan from cap of lode between tunnel and No. 1 shaft, M.L. 2, west side.	.....	0 4 8	1 1 19
05-2361 ...	Shipping ore from enriched or top portion of lens in M.L. 1, east side.	23·17	trace.	1 11 14

CLARENCE AND RICHMOND MINING DISTRICT—*continued.*

The average quality of the ores thus sold is illustrated by the following returns, received between 21st June, 1902, and 30th June, 1905[1]:—

Ore despatched, 760 tons 18 cwt. 3 qrs. 26 lb.=yielding copper, 207 tons 7 cwt. 3 qrs. 1 lb., equal to 27·2 per cent.

Total ore despatched to 1st September, 1905=944 tons.[2]

Total ore smelted to 30th June, 1908=7,912 tons for 1,529 tons of matte, containing 848 tons of copper.[3]

Smelting Plant—Cangai.

Erection of two 40-ton reverberatory furnaces begun in September, 1905. Smelting started January, 1906, for a brief period. Permanent smelting began May, 1906.

No. 3 furnace—70-ton—started June, 1907.

No. 4 under construction in May, 1908.

Temporary cessation of first smelting campaign due to inferior sand used in furnace bottoms; the granite detrital sand of the adjacent South River bed proving too fusible owing to admixture of basic materials. Satisfactory bottoms subsequently formed of pure silica sand from Whiteman's Creek, near Copmanhurst, derived from the Clarence Coal Measure Sandstones.

The first furnace difficulties were also increased by insufficient silica in the rich basic ores smelted, hence the resultant ferrous oxide attacked the fire-brick of the furnace.

Cangai possesses the advantage of very basic sulphides capable of carrying a large percentage of poor silicious or slaty ores—such as occur between the main lenses.

For fettling, an admixture of river sand and local clay answers satisfactorily. A local fire-brick is now also being substituted at about one-fourth the cost of the previously used Bulli brick.

Limestone is not used, sufficient lime occurring—as calcite streaks—in the lode channel, particularly in "A" level, to render the ore self-fluxing. If required at any time an excellent limestone occurs in M.L. 20, parish Braylesford, on Purgatory Creek, about 12 miles from Cangai, and 2 miles from the team road to Copmanhurst, which could be obtained as back loading.

The following analysis reveals its composition:—

No. 05-3839—Calcium carbonate	97·76	per cent.
Magnesium carbonate	trace.	
Alumina and oxide of iron	0·50	,,
Insoluble in acids	1·60	,,
Moisture at 100° C.	0·02	,,
Strontia	trace.	
	99·88	

The sulphide ore is roasted in clamps of one or two hundred tons each, a process requiring six to eight weeks, according to size of clamp.

Furnace charge of 40-ton furnaces.—2·5 tons roasted ore, with an occasional barrow of raw ore.
·5 ,, roaster slag.
Time, about 7 hours.

Furnace charge for 70-ton furnace.—3·5 tons roasted ore, with occasional barrow of raw ore.
·5 ,, roaster slag.

[1] Supplied by Mr. W. Zeitsch, Director. [2] Supplied by E. R. Woodward, Legal Manager.
[3] Supplied by J. H. Gibson, Secretary.

Cangai Smelting Works and Roast Heaps.

It is customary to run the three furnaces on ore for a time, then one on 1st matte.

The roaster charge is about 9 tons matte, which is brought up to 70 per cent. metal in a 24-hours roast.

Moulding sand is obtained from South River close by.

Cangai Mine is situated on the north side of a picturesque valley formed by Yantalla or Stockyard Creek and the Mann or Mitchell River, locally known as the "South Arm" (of Clarence River); practically shut in by high ranges. The bold eastern front of the New England plateau—here named the Gibralter Range—closes in the western view.

The valley of Yantalla Creek is most suitable for village settlement, possessing gentle lateral slopes. The creek joins the river about 120 chains below the smelting furnaces. A permanent water supply of great purity is thus within easy reach. The great fall of tributary perennial streams from the western plateau offers exceptional inducement for economic generation of electro-motive force; Dundahra Creek, the nearest and most suitable, being already contemplated by the company for this purpose.

If the mine continues to develop as at present indicated, cost of haulage, drilling, lighting, pumping, &c., can be considerably reduced by installation of an electric power plant.

From the accompanying plan and section it will be seen that the mine is most favourably circumstanced in regard to working conditions. Gravity transport is largely available from mine to smelters. Situated, moreover—in its highest outcrop on the top of a saddle formed by a spur from the main northern range—the lode is workable by tunnel to the 500-feet level on the west side, and to about the 300-feet level on the eastern.

"Mullocking," or filling, can also be economically effected from the steep natural slope above the passes in the channel.

Excellent mine timber and firewood are abundant. The greatest want is a properly constructed road to the head of navigation on the Clarence River. Recently the existing road has been considerably improved by a cutting obviating three crossings of the South Arm channel.

The company has constructed about 2 miles of excellent roadways between the smelters and the eastern and western workings, metalling them with mine waste.

On the east side an ore hopper of 200 tons capacity is connected with the mine tramways, all levels being connected therewith.

From this hopper a cable-line tram connects with 300-ton triple chamber ore-bins, in the valley, from which the ore is delivered into carts or trucks and thence along graded roadway to roast heaps and smelters—a distance of 65 chains.

On the incline cable between hopper and ore-bins the descending full trucks draw up the empties—a passing loop being constructed about midway.

On the west side, ore-bins have been constructed at A and B levels, of a capacity of 200 and 75 tons respectively. Ore passes from upper mine levels to lowest, thence trucked to ore-bins and hoppers.

CLARENCE AND RICHMOND MINING DISTRICT—*continued.*

Progress of development.

To July, 1907, four shoots of ore had been proved in the lode channel, 50 to 150 feet in length, with a width of 1 to 13 feet. Pitch of lenses almost vertical. Horizontal proving along strike of lode, 2,000 feet. Depth proved by shafts and levels, 510 feet.

Total distance between extreme end and west provings on ore—about 1,680 feet. Levels are being run to meet from both sides.

"*A*" *level.*—Starts in M.L. 2 from the west side 510 feet below the outcrop at site of original discovery on saddle. This represents the lowest natural level attackable by tunnel. Starting as an entering cross-cut at 115 feet, a branch drive north-easterly connects with McDonough's shaft sunk in ore.

At 315 feet the lode was cut in main drive, ore continued in channel in strings, small lenses, and particles in the crushed channel filling to 450 (at date, 3rd July, 1907). Width of channel not defined in places. Scabs of ore passing into walls. The class of ore here followed requires furnace or mechanical concentration, preferably the former so far as is possible. With the ore, and in the crushed channel filling, veins of calcite occur, which will aid in fluxing. At about 500 feet on this level, the winze in rich chalcopyrite followed down from surface through the upper levels, was encountered.

The ore channel in McDonough's shaft and branch drive dips towards main lode in "A" level at an angle of about 50 degrees, and should intersect at a lower level.

The quality of the ore from "A" level before striking the winze lens is shown in the following assay:—

No. 07-5412—	Copper	11·92
	Iron	25·48
	Sulphur	25·36
	Silica	22·50
	Gold, 1 dwt. 2 grs. per ton.	
	Silver, 5 dwt. 10 grs. per ton.	

This lens at "A" level was 15 feet wide but not solid (according to the manager, Mr. W. J. Mulligan), a fair proportion, however, being direct furnace ore, the balance to 2nd heap.

West side, "*B*" *level.*—70 feet above "A" level; was in 570 feet on the 3rd July, 1907. The channel at first carried 8 inches or 9 inches of carbonates, then sulphides as in "A" level, but not so wide.

At 340 feet, rich, solid yellow sulphide was struck and driven through for 60 feet, averaging about 8 feet wide. This was stoped up to within 20 feet of "C" level, where it was solid overhead.

For 150 feet beyond this lens, yellow sulphide continued, but thinner, widening, however, in one lens 20 feet long to full width of drive.

At 570 feet a blank occurred, with slight variation in strike, as in "C" level above, which lasted for about 20 feet, when sulphides again came in and continued as far as driven up to October, 1907.

West side, "*C*" *level*—Length, 210 feet (on 3rd July, 1907) along lode from entering cross-cut. Rich sulphides for about 70 feet, of a width of 6 to 13 feet solid. Ore continues along this level for 120 feet, from 1 to 3 feet wide, of a grade of 8 to 9 per cent. Similar troubled conditions encountered as in "B" level, fissure continuous, but lode blank for 20 feet, then ore again, which persisted so far as noted (October, 1907).

ove the eastern end of the lens rich carbonate ore was shipped away
e beginning of mining.
e "Wombat Hole," on back of "C" level, also yielded rich ore at the
e date.
st of the latter is an early shaft; beyond this again the lode outcrops
mall gully, which had not been prospected at date of inspection.
e principal ore bodies occur—so far as proving has extended—in the
n section, in M.Ls. 1 and 3. Two lodes occur here, and have been
d by shafts, tunnels, levels, and winzes. Cross sections 1, 2, and 3 on
ccompanying plan and section of the mine, reveal their thickness, as
d to 14th January, 1908.
e following notes were made of developments during inspection in 1907:—
t side, "E" level.—In main fissure, continued 236 feet along channel;
ut at 220 feet to "south" lode, distant 25 feet. Ore in main channel
rrow lenses, but of good grade. At intersection of lode at entering
cut tunnel, a "rise" to surface. Seventy feet to surface on hill-
Sulphides here overlaid by high-grade carbonates.
ween "E" and "F" levels, an intermediate level has been driven
et on ore, first black ore, then high-grade sulphide, part solid, part
ntrating grade.
'" *level.*—94 feet vertical below "E," and 120 feet below highest point
tcrop.
"South" lode, which intersects the main lode at an angle, and has
oped the best and largest ore-lenses. Driven—at time of inspection—
eet west along lode from entering cross-cut, and 68 feet east. Solid
ides for about 180 feet—to July, 1907—varying from 1 to 7 feet in
.
e strike of the south lode is N. 60° W.; that of the north N. 72° W.
ie 30th May, 1908, the intersection had nearly been reached,
nze sunk connecting "E" and "F" levels—in solid high-grade sulphide
7 feet wide, and widening; the ore tenor equalling 15 to 18 per cent.
st of this lens in "F" level, channel wider but containing only scattered

L. 3 section (Melbourne Block).—Main lode opened on level with "E"
Shaft 40 feet, driven west at bottom for 40 feet, and 30 feet east.
gh-grade sulphide, partly enriched, being stoped along this length.
wide at top, but narrowed below. Quality shown in assay of average
le:—

No. 06-5411—Copper	17·95	per cent.
Iron	30·66	„
Sulphur	26·69	„
Silica	9·13	„
Gold, 4 dwt. 8 grs. / Silver, 1 oz. 7 dwt.	per ton.	

e "South" lode differs from the main in that it has no appreciable
," or crushed filling. The cupriferous rock, however, contains films of
e.
ce inspection in July, 1907, a fresh lens of ore has been cut between
tunnel in M.L. 1, and the Melbourne block, M.L. 3. It has been opened
r the tram-line in Greenberg's tunnel. At 50 feet deep this lens showed
of 18 per cent. sulphide, dipping south. A cross-cut tunnel was started
en it up.

The nature of the ore bodies, and the systematic development of the mine, are illustrated in the accompanying plan and sections, for which the Writer is indebted to the Grafton Copper Company.

It is essential that the good policy of keeping development well ahead of stoping and furnace requirements should not be departed from, as vertical blanks are as certain to occur as horizontal. Depreciating values, moreover, assuredly wait on depth.

Only by persistently following the ore shoots vertically—to avoid dead work—can the future be insured against surprises.

In view of recent important developments in M.Ls. 1 and 3 below the lowest natural levels available, a main shaft should be started to prove the ore shoots below water-level, it is unwise to work out the richer superficial ores, and leave the lower, and unquestionably poorer, to bear alone the heavier costs of mining and treatment. The richer should carry a large proportion, at least, of the poorer through the furnaces.

The following descriptions of the cross sections of the lode exhibited on the attached plan were kindly supplied by Mr. W. J. Mulligan, general manager (under date 14th January, 1908, with additional notes to 30th May, 1908):—

No. 1 *section.*—Is on the eastern side of the mountain, M.L. 1, from "E" level up to "F," through No. 2 winze, which is 320 feet in from the cross-cut entering tunnel at "E" level. This shoot of ore in the "South" lode has been driven west 118 feet from the No. 2 winze, averaging over 3 feet of solid ore, for 80 feet, and reaching a maximum of 10 feet. It was twice faulted for a few feet, as shown on plan of part of "E" level. At the face at 118 feet it averaged about 3 feet.

No. 2 *section.*—Is the same ore body from "F" level to the surface, the upper portion being rich carbonates, which have averaged about 40 per cent. copper.

No. 3 *section.*—Is the recently discovered lens of solid ore in the south lode on the eastern side; it is about half way between the Melbourne section and "E" level. It was very small at surface, but widened quickly. Has been driven on 64 feet for an average width of 11 feet, with solid ore in both faces. There is every indication of it being the largest lens of ore yet discovered in the mine.[1] A winze has been sunk 10 feet from this level in solid ore.

No. 4 *section.*—Is through the principal ore lens on the western side of the mountain, from "B" level up to surface through "C" level. This lens commences at a point 320 feet from the mouth of "B" level, and extends for 80 feet, when it narrows to a little over 1 foot, and then widens to 3 feet, when it again narrows in, but 2nd grade ore up to the face. All the ore smelted from this lens has averaged over 10 per cent. copper. Owing to the important developments in the Eastern Section, little attention has been paid to the Western of late.

Cangai District.—Gap Creek (Lamb's copper shaft), on track Wongabri to Circular Flat, Cangai Road. Shaft, 25 feet. Quartz, with a little carbonate and sulphide of copper. Assay of an average sample:—

No. 05-2376—Copper, 5·75 per cent.
Gold, a trace (under 2 dwt.) } per ton.
Silver, 6 oz. 10 dwt. 16 grs. }

[1] It was reported in July, 1908, that a face of 10 per cent. ore, 20 feet wide, had been exposed in "D" level, west drive.

COPPER

GAI

UNTY OF GRE

BODIES



PLAN O

NORTH

CLARENCE AND RICHMOND MINING DISTRICT—*continued*.

Clarence River District.—The late Mr. W. Penrose, manager of Yulgilbar ation, under date July, 1898, stated that the first copper lode was dis- vered in this district about 1863 on Ewingar Creek, parish Ewingar, county rake. A shaft was sunk about 30 feet on a narrow vein assaying about) per cent., but no ore was treated commercially. Since that date two her very small lodes have been discovered on Nogrigar Creek, about miles south of the first-mentioned, assays from which are reported up to : per cent.; the ground was held, but no real work was being done in the ay of proving.

On Gordon Brook Station copper was found near Deep Creek, 12 miles rth of Copmanhurst, about 1873; a good deal of work was done, but the le, though rich, was too small to pay for working. Since that date a lode as opened, and abandoned for the same reason, at Oakey Creek, on the me run.

Mr. E. F. Pittman in $\frac{1818}{p.232}$, writing of this district, stated that "after aving Gordon Brook Station the track is over 2 miles of granite, and then gain a belt of 1½ miles wide of hard altered slates dipping west of north at an ngle of 70 degrees. In this formation occurs a lode of copper ore which as been pretty well prospected, and which, with better facilities for carriage, ould probably pay to work."

Messrs. Wilkinson and Slee in $\frac{1882}{p.204}$, stated that prospecting for copper Gordon Brook in serpentine revealed no signs of a lode, only a few small eins of copper ore of no value being met with.

The Jakoonbie Copper Mine, now known as Glamorgan, Gordon Brook, as sunk upon to 120 feet, and driven on at the 50-feet and 110-feet vels. Mr. E. F. Pittman, $\frac{1880}{p.247}$, described the lode as being 4 feet thick and earing N. 40° E. Sixty tons of dressed ore were smelted at Eskbank, the ighest yield being 14⅞ per cent. Near by Mr. Pittman examined a wide ossan lode in granite containing iron and copper pyrites, native copper, nd stains of green carbonate.

A sample from Tabulam ($\frac{1880}{p.248}$) yielded 32·27 per cent. of copper, and oz. 7 dwt. 2 grs. silver per ton.

In 1888 leases for copper were taken up at Yarrakalkiarra.

Camelback Mountain.—In a report, dated 1853, the Rev. W. B. Clarke ported abundant indications of copper and lead near the Camelback lountain.

Fine Flour Mine, M.L. 3, parish Pucka, county Drake, on west bank of ordon Brook or Fine Flour Creek.—Discovered in 1905 by J. Torrance nd T. Smith. Opened by Messrs. Smith and Wiley. The prospectors sank o. 1 shaft 23 feet and obtained from it 7 tons of dressed ore, which ielded 23 per cent. of copper at Waratah.

The mine was subsequently sold to the present Fine Flour Syndicate, hich sank Nos. 2 and 3 shafts 46 and 40 feet (at time of inspection, uly, 1907).

No. 1 shaft was full of water, but blocks of ore at grass revealed a thickness about 12 inches of silicious ore, consisting of massive pyrites in part, ith black oxide and carbonate of copper imparting a banded structure; ne average value being, probably, 5 to 6 per cent. The lode in these nafts strikes N. 19° E. and dips N. 71° W. at 58°.

No. 2 shaft contained a little soakage water, but was open to inspection to about 30 feet. Lode channel 12 to 20 inches wide, very poor and mullocky. A little powdery black oxide present, also iron and copper pyrites. Little or no ore at grass; none despatched.

No. 3 shaft.—Lode almost vertical, and distinct in character from that opened in other shafts. Probably a parallel lode. Thickness of fair ore exposed in shaft, 7 inches to 9 inches. A three-quarter inch vein of copper sulphide occurs nearer footwall. Stains of carbonate on footwall side. Native copper and cuprite are also present on west wall.

A cross-cut tunnel was being driven on the east fall from No. 3 shaft about 160 feet below it, which will, if continued, give about 100 feet of backs below the present shaft if not deepened. The distance to drive is considerable and the rock exceedingly hard, the value of the enterprise being very doubtful.

A parallel vein occurs near the creek, which has been opened close to the N.E. corner of M.L. 3, to a depth of 10 feet, revealing a thickness of 1 ft. 6 in. to 2 feet of quartz with heavy pyrites, and a little black oxide and yellow sulphide of copper. An average sample selected from the ore raised yielded:—

No. 07-5414—Copper, 0·45 per cent.
Gold, 13 grs.
Silver, 5 dwt. 22 grs. } per ton.

About 2 chains S. 30° W., a sample of gossan from a small cut in a parallel outcrop yielded:—

No. 07-5413—Copper, less than 0·10 per cent.
Gold, a trace
Silver, 6 dwt. 13 grs. } per ton.

There are indications of other veins west of the main which had not been opened. The latter occurs about 300 feet above Gordon Brook or Fine Flour Creek.

The Fine Flour rocks consist of fine-grained diorite (6989), and another of igneous origin (6988), not determinable from specimen obtained. Further west, between Fine Flour and Busy Bee Mines, an altered hornblende andesite (6991) occurs.

Flintoff's Copper Lode, parish Pulganbar, county Drake.—Subsequently held under the name of Cu Copper Syndicate. Opened about 1887. Re-opened by Flintoff in July, 1907. Strike of channel N. and S., dip W. at 83°. Thickness (at 62 feet) about 3 feet, mostly hard silicious channel rock with calcite joints. Best ore consisting of silicious pyrites with powdery black oxide or subsulphide of copper, worth about 3 to 5 per cent.

In August, 1907.—Arsenical pyrites from a level driven at 62 feet yielded high percentages of cobalt, the following results being obtained by assay from a 3-inch vein on the footwall:—

No. 07-6825—Metallic arsenic	18·04	per cent.
Cobalt	8·90	„
Nickel	0·03	„
Copper	trace.	
Iron	5·63	„
Gangue	53·68	„
Gold	trace.	
Silver	„	

CLARENCE AND RICHMOND MINING DISTRICT—*continued.*

A sample of copper ore in quartz and ironstone from face of drive 32 feet south, yielded:—

No. 07-6824—Copper, 9·22 per cent.
Gold, a trace
Silver, 1 oz. 1 dwt. 19 grs. } per ton.

In an old shaft 8 or 10 chains distant on south strike, poor silicious ore with stains of copper carbonate is exposed.

The latest developments being a drive south on the lode for 40 feet at the 62-feet level, the last 16 feet being in carbonate ore, assays of which yielded 9·2 per cent. Shaft sunk to 76-feet level. A crosscut from a lower surface level was also being put in to cut the lode—in driving 120 feet in it, two veins are reported to have been cut 1 ft. 6 in. and 2 feet wide, showing a little copper carbonates.

Cinnabar (sulphide of mercury) has also been found in this and the adjoining property. Rich nodules up to several lbs. weight have been found in alluvial, and lode samples assaying up to 1 per cent.

Gem Mine, portion M.C.P. 200, parish Pulganbar, county Drake.—Opened about 1886. Two shafts sunk, now fallen in. Recently re-opened by J. Malone and party. Lode apparently strikes N. and S. No outcrop visible. Large blocks of brecciated gossan raised to surface indicate strong lode of some promise. Thickness of lode probably not less than 2 feet.

Glamorgan Copper Mine, originally known as Jakoonbie, portion 22, parish Pulganbar, county Drake, on Gordon Brook Pastoral Holding.—Opened in 1875. It is recorded that "At Gordon Brook, in the Clarence District, a company has recently started, and has raised 12 tons of ore, but none of the ore has been treated."—(*Min. Statistics*, 1875, p. 92).

In portion 22, and adjoining portions 20 and 21, numerous reefs of quartz and arsenical pyrites occur, containing small proportions of cobalt in association with the arsenical pyrites. From main shaft in portion 22, samples have been obtained from nodular lumps about 6 inches thick, containing up to 3·34 per cent. of cobalt, gold to 1 oz. 17 dwt., and silver to 2 oz. 5 dwt. 17 grs. per ton.

Though copper has been the metal sought in the past, it is doubtful whether it can be profitably extracted from arsenical ores below water-level, unless gold and cobalt considerably enhance the average value. The transition at water-level into refractory arsenide of iron instead of ordinary sulphide, complicates metallurgy and increases cost.

In a new make in No. 2 shaft, however, near by, some silicious—but less refractory—ore has been raised. The copper value of some 30 tons at grass ranges from 7 to 10·5 per cent. No ore has been sent away since previous inspection in 1905.

No. 2 shaft has been deepened to 96 feet; over 5 feet of sulphide ore of the character mentioned above are reported in the bottom.

Casino Division.

Jones' Lodes, close to Wallaroo Lode, in Mugin Wybra Creek, parish Hamilton, county Drake.—Strike N. 35° E., dip N. 55° W.; width, 8 inches. Opened

by shallow trench and exposed in creek bed. Ore, ferruginous quartz and felsite (?) with zinc-blende, pyrites, and a few copper carbonate stains. An average sample yielded:—

No. 07-5310—Copper, 1·00 per cent.
Gold, a trace
Silver, 16 dwt. 21 grs. } per ton.

A larger lode near by strikes N. 45 E., dip N. 45 W. at 45°. About 4 feet exposed in shallow opening; footwall not visible. Lode carries thin veins of zinc-blende, and a little copper and iron pyrites, very hard and flinty gangue. An average sample yielded:—

No. 07-5311—Copper, 3·40 per cent.
Gold, a trace
Silver, 1 oz. 14 dwt. 20 grs. } per ton.

Just in Time Lode.—In branch of Mugin Wybra Creek, parish Hamilton, county Drake. Strike N. 35 E., dip S. 55 W. at 69°. Discovered by James Farrell in 1907.

Outcrop strong and well-defined—traversing rhyolite with strongly developed fluxion structure.

The main lode averages about 3 ft. 6 in. in thickness, and has been proved by a shaft and shallow openings for a length of nearly 4 chains.

About 8 feet west a vein of a few inches thick shows same character as main body.

Unfortunately the lodestuff is a zinc-copper problem, amenable only to magnetic separation. The close approximation of the specific gravities of the two minerals zinc-blende and chalcopyrite (4·1—4·3 and 3·9 to 4·2) preventing gravity separation. The extremely intimate association, moreover, prevents even rough hand-dressing and picking.

An average sample of the ore raised whilst sinking the shaft to 30 feet (since deepened to 40 feet) gave the following returns:—

No. 07-5315—Copper	.....	6·20 per cent.
Zinc	.....	34·54 „
Iron	.....	8·96 „
Silica	.....	20·22 „
Gold, a trace		
Silver, 1 oz. 6 dwt. 16 grs.		per ton.

Two other samples from superficial openings along the outcrop gave the accompanying returns:—

	07-5313.	07-5314.
Copper	5·92 per cent.	16·85 per cent.
Zinc	18·97 „	12·09 „
Gold	A trace per ton.	A trace per ton.
Silver.....	18 dwt. 12 grs. per ton.	2 oz. 3 dwt. 13 grs. per ton.

Copmanhurst Division.

May Queen Lode, M.L. 1, parish Pucka, county Drake, on Gilmore Range, Gordon Brook.—Lease taken up many years ago for copper; retaken in 1905. Rich magnetic and specular iron oxide occur at the site, associated with limestone and garnet, in hornblende and diorite country.

CLARENCE AND RICHMOND MINING DISTRICT—*continued.*

The intrusive diorite has absorbed part of the limestone and developed considerable garnet along the contact margin. Along this line prospecting for copper has been carried on, the copper ores being discovered in the garnet. Similar conditions extend along the contact for some miles.

Aid was granted to follow the copper indications on the Gilmore Range, but little was availed of as the prospects were not encouraging.

Casino Division.

Minnie Copper Lode, M.Ls. 10 and 11, parish Ewingar, county Drake.—Discovered in November, 1905. Opened by T. Bassetti, in quartz-felsite.

Strike N.E., dip N.W. at 58°. Opened by two shafts 30 feet and 83 feet, 70 feet apart. Hanging wall well-defined, with slight dig. Footwall probably not yet exposed. Ore on hanging wall, mostly pyrites with occasional patches of rich yellow ore, balance of channel filling crushed and jointed rock. About 1 foot of fairly solid pyritic ore, with other thin streaks in filling. Concentration necessary. Better grade likely to make in short lenses.

From the site of the original discovery—alongside the 30-feet shaft at the south-east end—6 tons of yellow sulphide close to the surface were taken from a small channel, which thinned rapidly both horizontally and vertically.

Four tons yielded 17·5 per cent. of copper at Waratah, and 2 tons yielded 10·5 per cent.

Aid was granted to sink from 55 feet to 105 feet, and to drive from the latter (P.B. $\frac{\text{A}}{\text{S}}\frac{\text{S}}{\text{C}}$).

Mr. Bassetti reports that at 83 feet the prospects are about the same as at 55 feet, described above.

The lode had also been opened 4 chains further north-east, with carbonates showing.

Coramba Division.

Mount Brown Copper and Gold Mine, Kangari, between Coramba and Coff's Harbour, P.G.L. 1.—Originally worked for gold. Taken up recently by Zeitsch, Kritsch, and party. Mine unwatered, exposing a 10-feet lode carrying 2 feet of high grade copper ore. A tunnel being driven which, in conjunction with pumping plant, will keep mine unwatered to 156-feet level.

Now held by the Mount Brown Copper and Gold-mining Company.

Three lodes reported—main lode 300 feet long, carrying a little gold.

Gold and copper lode 50 to 60 feet long and 9 feet wide.

Sixteen bags of copper ore yielded 12·2 per cent. of copper at Dapto, and 2 dwt. 19 grs. of gold and 3 oz. 0 dwt. 9 grs. of silver per ton.

Gold crushings totalled 280¼ tons for a yield of 103 oz. 6 dwt. of gold.

Mullumbimby Division.

Mullumbimby.—J. Dwyer's land, 6 miles from Mullumbimby. Thin arborescent films of native copper in quartz and felsite (?), discovered early in 1907. A few shallow openings, deepest 12 feet.

The Rev. W. B. Clarke in Report IX, dated June 24th, 1853, p. 11, stated that carbonate of copper occurs on the slopes of Mount Lindsay, in the Tweed River district.

A sample (08·641) reported to have been obtained near Mount Warning, returned 5 per cent. of copper, and about 11 dwt. of silver per ton.

CLARENCE AND RICHMOND MINING DISTRICT—*continued.*

Dalmorton Division.

Newton Boyd Silver and Copper Lode, on Mann River, between Glen Innes and Newton Boyd.—Galena and copper pyrites in granite; opened by T. Foley.

An average sample yielded:—

Copper	0·49 per cent.	
Lead	2·22 „	
Silver, 4 oz. 6 dwt. 14 grs.	per ton.	
Gold, a trace		

Casino Division.

Nil Desperandum Lode, on a branch of Mugin Wybra Creek, between Wallaroo and Just in Time lodes.—Strike N. and S. in quartz-felsite. Exposed in creek bed and in shallow cuts. Soft, kindly-looking lodestuff, which may yield bunches of payable ore. None proved at date of inspection, though carbonates freely stain channel filling. Exposed for about 2 chains. Iron and copper pyrites leanly distributed in harder parts.

Samples from the outcrop yielded:—

No. 07-5312—Copper	0·75 per cent.	
Gold	A trace	per ton.
Silver	4 dwt. 8grs.	

Nogrigar Copper Lode, M.L. 9, parish Ewingar, county Drake.—Opened by J. McColl in 1893. From ore then extracted, 3 tons sent to Dapto yielded 10·7 per cent. of copper.

Strike about N. and S. in serpentine near junction of sedimentary rock. Old shaft 30 feet deep. Apparently small bunch of ore in serpentine. Joints of rock stained with films of copper carbonate. Recent prospecting a few feet south failed to reveal any trace.

Close by a green-stained quartzite (like amazon stone in appearance) had been superficially prospected; the colour was, however, found to be due to chromium.

Copmanhurst Division.

Pluck Mine.—Prospecting area, parish Pulganbar, county Drake, near north boundary of portion 200. Gordon Brook or Fine Flour Creek. About 15 miles from the navigable waters of the Clarence River at Copmanhurst. Opened about 1883. Re-opened by the present owner, D. Hughes, in 1903.

Strike N. and S., dip west, 1 in 3. Three parallel lodes occur a short distance apart. Main or central lode worked by two shallow level tunnels, the lowest being but 50 feet below the highest point at south shaft. Main shaft required to compete with water making below level of Fine Flour Creek—from the bank of which the lowest tunnel starts.

Aid was granted (P.B. $\frac{a}{5}\frac{7}{4}\frac{s}{9}\frac{a}{2}$) for sinking the south shaft to 80 feet. The lode was reported 2 feet wide at 49 feet. At 69 feet no further sinking, abandoned on account of water and want of adequate appliances to keep it in check.

The lowest tunnel was thereupon driven for over 200 feet to secure 26 feet of backs below the upper tunnel. Further progress is not now possible without capital.

The lode averages about 4 feet wide, and is well defined and likely to be permanent. In the lower tunnel from 1 ft. 6 in. to 2 feet of good ore was

exposed at time of inspection in July, 1907, consisting of iron and copper pyrites with black subsulphide. The channel filling is partly brecciated, the solid ore being on one wall. Concentration is necessary for full advantage of the metalliferous contents; gangue silicious.

The total output to 15th July, 1907, according to the owner, was 80 tons dressed ore, averaging 13 per cent. of copper.

Potato Copper Lode, N.W. of Busy Bee Lode, parish Pucka, county Drake.—Strike N. 25° E., dip N. 65° W. at 50°. Discovered in 1907 by J. Taylor. Superficial proving only. About 2 feet of copper-bearing lodestuff exposed. Concretions of fair ore gave rise to name.

Walker's Pinch Lode, Scafte and party, parish Kahloe, county Drake. Close to road to Cangai, and to old antimony mine.—Reported 5 feet of quartz with copper pyrites, concentrating ore—best grade up to 7 per cent.

Casino Division.

Wallaroo Lode, parish Hamilton, county Drake, on a branch of Mugin Wybra Creek.—Massive outcrop about 12 feet wide, resembling Drake metalliferous country.

Ore quartz and quartzite with leanly distributed sulphides of iron, copper, and zinc, in intensely altered diorite country. Unopened—exposed in bed of creek. Strike N. and S.

An average sample from outcrop yielded:—

No. 07-5309—Copper, 2·35 per cent.
Gold, a trace
Silver, 1 oz. 8 dwt. 20 grs. } per ton.

Copmanhurst Division.

Wiley's Lode (Dolconda), M.L. 6, parish Pucka, county Drake.—Discovered by W. Wiley. Short tunnel driven before discovery of Fine Flour lodes. Strike N.E., dip N.W. at 73°. Thickness, 2 ft. 6 in. between walls. Orey part on footwall, about 1 foot wide. A little ore extracted, an average sample of which yielded:—

No. 07-5416—Copper, 2·62 per cent.
Silver, 7 dwt. 2 grs.
Gold, a trace } per ton.

Yulgilbar.—About 1½ miles from Yulgilbar Cinnabar Mine. Copper ores in serpentine. Shaft, 35 feet. Carbonate ores reported as cut out at 25 feet. 3 tons 16 cwt. sent to Dapto yielded 12 per cent. of copper, 6 dwt. of gold, and 6 oz. silver per ton.

COBAR MINING DISTRICT.

Canbelego Division.

Baalgammon Mine.—Stains of copper carbonate in gossan 3½ inches thick reported at this site. Company formed to prospect this occurrence on the Rookery Holding.

Bobadah Division.

Bobadah.—At the Overflow Mine copper ore occurs in one of the shafts (Booth's), associated with gold, silver, and lead. The lode strikes N. 30° W. in crushed porphyry; its chief value depends on the gold, silver, and lead contents, as the copper ores—carbonate and red oxide—are not very prominent.

Sullivan's lode, about one mile from Hillman's Tank, has been opened under aid from the Prospecting Vote, but no payable ore was discovered.

Aid also granted for site 6 miles south-west of Bobadah.

Copper ores occur about 1 mile N. of the Walker's Hill Homestead, where aid was also granted with unfavourable results. (*See* also Yellow Mountain and Recovery Copper Mines.)

Canbelego Division.

Bonnie Dundee Mine, parish Trenton, county Canbelego.—Originally opened for gold under aid recommended by Inspector Godfrey.[1]

No. 1 shaft 100 feet; No. 2, 300 feet. Strike of lode, N. 10 E., dip of copper veins S. 80° E. at about 65°.

Copper carbonates cut in No. 2 shaft at 230 feet. No. 1 shaft worked slightly for gold in oxidized zone.

At 230 feet about 14 feet of copper impregnated country struck, which dipped out of shaft in a few feet; a short crosscut here revealed the thickness stated. Hanging wall, or boundary of impregnation, not exposed on 29th October, 1907. Below the shaft passed into slate and schist country.

An average sample of this partially-enriched material chipped from 13 feet wide in shaft and crosscut, yielded:—

No. 07-7538—Gold, a trace Silver, 13 dwt. 1 grs.	per ton.	
Copper	2·12	per cent.
Iron	10·23	„
Sulphur	7·73	„
Silica	57·98	„

Boppy Mount.—Two miles by road W.S.W. from Boppy Mount Railway Station, parish Cohn, county Robinson. Quartz containing copper carbonate stains. Aided (P.B. $\frac{2}{5}\frac{5}{7}\frac{3}{2}\frac{0}{0}$) to sink from 22 to 100 feet.

Budgery Copper Mine, M.Ls. 1, 2, 9, parish Hermitage, county Canbelego. Discovered in 1906 by R. A. Sorensen whilst further prospecting a site previously tested for gold.

Inspector Polkinghorne reported that the copper ore was struck in a cross-cut 55 feet E.S.E. from the bottom of a 218-feet shaft.

The Budgery lode consists of a large impregnated mass of magnesian slates much crushed and jointed, with frequent slippy "heads" or "slides."

Loose friable gossan extends down to a considerable depth, but is abruptly divided from the "black" ore (subsulphide of copper) by a smooth, flat heading. The frequency of these headings striking and dipping in all directions, evidences the results of some disturbing influence at no great distance.

[1] Further aid granted to sink from 306 to 406 feet. (P.B. 08-1882.)

n the closely-adjoining South Budgery, and probably in Budgery itself, a
: crushed quartz-felsite (?) occurs. The magnesian slates, moreover, are
hly contorted on a small scale, and probably also on a large.

Copper ores, notwithstanding extensive prospecting all round the pro-
etary boundary, have not been proved outside of the original discovery,
:ept a few carbonate stains in the Budgery Reward North.

The enriched black ore, or partially altered sulphides, was of good quality,
t, as expected, proved to be superficial, the grade depreciating by, at least,
:-half in a few feet. The ore was mostly disposed of to the Great Cobar,
nited, at Lithgow, some little difficulty being encountered owing to excess
magnesia in the gangue.

Several applications failed to obtain an official statement of output to
l of 1907, but the following have been noted. To the end of 1906—
) tons of ore had been disposed of for £1,821; the copper contents equalling
·5 per cent. or 23 tons. (Ann. Rept., 1906, p. 45.)

As showing depreciation at lower levels, in August, 1907, it was announced
the Press that 23 tons 16 cwt. 1 qr. 5 lb. at the Great Cobar Works, Lithgow,
:lded 5·86 per cent. As the latter grade could not be disposed of at a
ofit owing to cost of carriage, active mining practically ceased on exhaus-
n of the available richer ore, and efforts were confined to sinking a new shaft.
.e nature of the ore so far proved is likely to render direct smelting difficult.

As stated elsewhere, great excitement followed the discovery of Budgery,
3 applications for leases being received, and numerous companies floated;
ery possible variation of the original name being used as an inducement
investment.

The latest official statement of the position of the mine is contained in
report of the Directors of the Budgery Mines, N.L., submitted to the
areholders at the general meeting on the 13th September, 1907. The
lowing extracts are from the mine manager's (Mr. J. R. Godfrey) report
pended thereto for the half-year ending 31st August, 1907:—

"Previous work consisted of an engine shaft 218 feet deep; a main cross-
t nearly due east from the shaft for 60 feet, where it cut the west wall of
e deposit; a crosscut north-east for 105 feet, the first 30 feet being in good
e, the next 40 feet in lode matter too poor to be of any value, and then
adually dying out in country rock."

During 1907 engaged on developmental work, including deepening the main
aft to 283 feet; 1,920 tons of ore were raised, of which 797 tons of dressed
e were sold for £3,695.

Budgerygar Mine, M.L. 5, parish Trenton, county Canbelego.—Strong
ossany outcrop in schist country.

The lode strikes N. 7° W., and underlays easterly, and consists of an
mpregnation highly pyritized, which at surface forms strong irony outcrop.

In the vertical shaft the impregnated belt was cut at 20 feet and passed
rough at 147 feet. From the 203-feet level a crosscut reached the foot-
all boundary of the mass in 62 feet, and was continued across it diagonally
r 46 feet without reaching hanging-wall boundary. From this point a
nze was down 45 feet (in October, 1907), where at bottom nearly pure
n pyrites was making.

The cross-cut at 203-feet level in the impregnated zone, passed through
in veins and finely disseminated pyrites—more or less black or sooty

in parts owing to alteration of the little copper sulphide present—into sub-sulphide. Across the full thickness of this enriched mass a sample was carefully taken, which yielded the following results:—

No. 07-7540—Gold, a trace
Silver, 3 dwt. 6 grs. } per ton.
Copper, 0·30 per cent.

A sample of the unaltered sulphides chipped across the full width at bottom of winze yielded:—

No. 07-7539—Copper, none detected.
Gold, a trace.
Silver, „

In June, 1908, more promising developments were reported in a new shaft, 270 feet deep, and a drive of 25 feet from that level.

Buppe Copper Lode, M.Ls. 53, 54, parish Buppe, county Mouramba, about 4 miles southerly from Mount Boppy Gold Mine, and between the Canbelego and Little Boppy Copper lodes.—Strike of lode north-west. Dip south-west at 43°.

Shafts 25 feet and 150 feet deep in M.L. 53, in October, 1907. New shaft cut lode at 75 feet, then followed on underlay to 150 feet from surface, under aid from Prospecting Vote.

Outcrop consists of rubbly quartz in quartzite and slate, with traces only of copper carbonates. Traces of gold only obtainable. Shaft in soft slate at 150 feet on hanging-wall side. Traces of carbonates in silicious material on footwall.

Canbelego.—Restdown Prospecting shaft, 15 miles from Canbelego—sunk under Government aid. Shaft 226 feet, in puggy kaolin; at junction of sedimentary rock, and intrusive quartz felsite.

In places along contact, kaolin converted into porcellanite is conspicuous, and sandstone into quartzite, arising from hydrothermal action following the intrusion. On surface superficial iron oxide occurs fairly solid, but silicious in places.

Shaft sunk 133 feet vertical, then on underlay to 226-feet level. Driven from this point 40 feet east in soft puggy clay, all picking ground. Pug ferruginous and manganiferous, with occasional kernels of crumbly silica, and quartzite.

No copper ores visible, but assays said to reveal its presence in small quantity—less than ½ per cent.

At a later date a sample from west crosscut in 23 feet, forwarded by the manager—showing copper sulphides partially enriched by subsulphide—yielded on assay:—

No. 07-7698—Copper, 3·02 per cent.
Gold, a trace.
Silver, 13 dwt. 1 gr. } per ton.

Canbelego Copper Mine (late Saunders').—Portions 17, 18, 36, parish Buppe, county Mouramba; 4 miles south of Canbelego, and 7 from Boppy Mount Railway Station. Discovered by J. J. Saunders in August, 1901; who sank shafts 96 feet, 50 feet, 35 feet, and 38 feet deep, extending along lode for about 200 feet. Costeens expose a further distance of about 50 feet. Strike, N.E. vertical in slate. Average width of outcrop about 35 feet, including bands of country carrying small veins and strings of ore.

COBAR MINING DISTRICT—*continued.*

Position in October, 1907:—Deepest shaft, 250 feet, which cut ore at 90 feet; water level, 158 feet.

Two faults slightly displace lode—at 78 feet to eastward, at 118 feet to north-east. Upper fault strikes N.W., and underlays S.W. at 45°; lower fault strikes N.E., and underlays N.W.

At the 155-feet level the lode has been driven on for about 50 feet. In north drive and cross-cut solid ferruginous ore exposed, containing considerable native copper. At 170 feet copper and iron pyrites occur in soft slate, signs of enrichment visible in the black powdery subsulphide coating chalcopyrite.

The gross weight of ore despatched by the discoverer totalled 63¼ tons, and returned an average of 28 per cent. of copper.

About 17 tons of dressed ore at mine of about 10 per cent. grade, seconds 2 to 3 per cent.

Canbelego District.—Canbelego West Mine, M.L. 21, parish Buppe, county Mouramba.—Prospecting shaft 135 feet deep, crosscut south-westerly for 30° at 116-feet level. A trace of copper only. Country, slate and schist, with quartz strings. Copper stains very slight in costeens further west. No indication of defined ore body.

Shango Mine, M.Ls. 14, 15, parish Buppe, county Mouramba.—Opened by Knight Bros. about 1902. Eight tons of copper ore from shallow open cut, reported to have yielded 15 per cent.

New shaft in country, 72 feet south of old shaft, and about 10 feet west of strike of lode; depth, 130 feet; no sign of ore. Strike N. 50° W.

Four and a half chains N. 15° W. of old workings, an 80 feet shaft has been sunk on a parallel vein. Both veins silicious.

Canbelego Queen, adjoining Canbelego North on the north-west, M.Ls. 37, 59, parish Buppe.—Three shafts 30 feet deep on M.L. 37. A few stains of copper carbonate in quartzite and slate. Cut out at 15 feet.

Canbelego North, M.Ls. 34, 35, parish Buppe, adjoining Canbelego Mine on north.—Prospecting for continuation of Canbelego lode. No ore; slate country. Shaft, 80 feet.

Bargin's Gold Lease (The Priests), parish Buppe.—Quartz and slate, with faint traces of copper carbonates in joints in crosscut on east side for a reported width of 20 feet. In west crosscut thin streaks of iron pyrites for 7 feet wide. This shows on surface as very ferruginous slate, with thin honeycombed bands after pyrites.

Quartz abundant; reported to assay at best about 1 dwt. 3 grs. per ton. Joints glazed with thin films of black iron oxide, imparting a metalliferous look to outcrop.

Shaft down 115 feet, and cross-cut 55 feet at 100-feet level.

North Shango, at N.E. corner, M.L. 16, parish Buppe, county Mouramba, about 90 feet from corner of lease.—Prospecting—by shaft—for supposed continuation of Canbelego lode. Shaft in country; no ore.

Canbelego Peak, parish Buppe, county Mouramba.—Shaft 174 feet deep, crosscutting west to brecciated belt under Peak. Country, quartz pebble conglomerate and quartzite, with bands of ferruginous slate. Shaft sunk in

latter, which shows faint traces of copper carbonate in cleavage. A little gold is reported in the breccia on surface about 70 feet west. If not payable in oxidized condition, unlikely to be in pyritic.

Canbelego West, parish Buppe, county Mouramba.—Shaft in schist country, with quartz strings; stains of copper carbonates in outcrop.

Shaft, 135 feet; crosscut at 116 feet for a distance of 30 feet. Formation 6 ft. 6 in. wide, with traces of copper only.

Cobar Division.

Cobar-Chesney Gold and Copper Mine, held by the Great Cobar, Limited.—This property consists of Mineral Leases 12, 19, 23, 44, 58, 61, 68, 106, and 107, embracing an area of 98 acres 0 roods 38 perches, also a freehold of 100 acres.

Originally worked as a gold-mine—the first in the field—the Cobar-Chesney afterwards assumed considerable importance as a copper proposition. A large quantity of the auriferous impregnated slate from the oxidised zone was treated by battery and amalgamation for an average yield approximating to 7 dwt. of gold per ton. The outcrop betrayed no evidence of the copper ores below; at 150 feet carbonate stainings became very marked. Sulphides began to show about 250 feet from the surface, the chalcopyrite being coated with melaconite (black oxide).

During a visit in 1898, when the main shaft was down 460 feet, a cross-cut at 360 feet through the lode revealed a thickness of 40 feet. A level had been driven 550 feet along the lode, from which two other cross-cuts intersected the lode, showing its width to be persistent throughout the distance proved. The assay values, obtained by chipping across the face of each cross-cut through the lode, were as follows:—

Cross-cut 200 feet south of main shaft—average yield, 5 per cent. copper.
,, (main) from shaft—average yield, 3 per cent. copper.
,, 350 feet north of shaft—average yield, 8 per cent. copper.

The gold contents approximated from 2½ dwt. to 3 dwt. per ton.

Further indication of the value of the ores in the Cobar Chesney lode is afforded by the following assay determination quoted by Mr. T. Longworth, in the prospectus of the Cobar Chesney Company, 1897, p. 16:—

"NOTE.—All the assays are fire assays, and should be fully worked up to.

Sample.	Copper, Fire Assay.	Corrected to Chemical Assay.	Gold, per ton.
	per cent.	per cent.	dwt. grs.
No. 1—Carbonate from No. 3 shaft, 155 feet deep.....	2½	3·8	3 6
No. 2— ,, ,, ,, 214 ,, ...	3	4·3	3 6
No. 3—Sulphides ,, ,, 275 ,, ...	2½	3·8	3 6
No. 4— ,, ,, No. 1 shaft, 360 feet deep, south drive.	4½	5·8	a trace.
No. 5—Sulphides from No. 1 shaft, 360-feet cross-cut..	3	4·3	3 6
No. 6—Sulphides as mined from the whole of the lode in Nos. 1 and 3 shafts.	3	4·3	3 6

The assay value of the ore as shown in these samples is about 1 per cent. lower in copper, and almost identical in gold with the ore at present mined and treated at the Great Cobar Copper-mine.—THOMAS LONGWORTH, Manager, Great Cobar Copper-mine, Cobar, 29th October, 1897."

Cobar Chesney Copper and Gold Mine.

(Main Shaft.)

COBAR CHESNEY MINE

CROSS SECTION

Scale 0 50 100 Feet



he carbonate ore between the 150-feet and 250-feet levels was estimated the same authority to average about 6 per cent. of copper; and the hides about 20 per cent. of iron.

he sulphides occur investing slate and quartz, a small proportion of direct lting ore could be hand-picked.

onsiderable interest attached at one time to prospecting operations in the rabungie Lease, on the south boundary of the Cobar-Chesney, where an :rop of ferric oxide occurs (west of the Chesney main line). A cross-cut :he 200-feet level to the west under this outcrop intersected a band of pyrites about 10 feet thick, part solid and part mixed with the slate ntry; it betrays little evidence of associated copper pyrites.

n 1901 about 4,500 tons of Chesney ore were treated in the Great Cobar lters for a return of 3 per cent. copper, and about 1 dwt. of gold per ton. n. Rept., 1901, p. 53.)

n 1904, the mine was purchased by the Great Cobar Syndicate, and since been worked in connection with the Great Cobar Mine. About per cent. of the smelting charge being from the former, the silicious nature ts matrix acting as a flux for the basic ore of the Cobar lode.

'he output of the Chesney Mine from 1904 to August, 1906, being as ows:—

1904	16,885·11 tons	Supplied by Dr. Richard Read, Managing Director, Great Cobar Syndicate.
1905	45,310·73 „	
1906	26,613·385 „	
Total ...	88,809·225 „	

'osition in October, 1907.—Greatest depth of proving, 700 feet; greatest gth, 820 feet; greatest width, 92 feet; average, 35 to 40 feet. Narrows outh end.

verage copper contents about 3 per cent.; gold, 15 to 24 grs.; and silver, 2 oz. per ton (smelting returns.)

short gold shoot on the north end has been followed down like a pipe n the surface, 3-oz. stone being procurable from it.

bout 75 feet east of the main lode, a 4-feet vein was worked to No. I el for gold. It has since been opened by cross-cut from a lower level, ere its gold value is estimated at 6 dwt. per ton, with fair copper value).

Water was met at 360 feet, equal to about 50,000 gallons per day. At feet, a fresh flow was struck in shaft, equal to 300,000 gallons per day; making about 250,000, and standing 85 feet below No. 5 level, present ips incapable of reducing it lower.

The ore from the Chesney lode is broken to about 6 inch gauge, then con-ed by travelling belt to ore hopper for trucking. Belt travels about feet per minute, boys on either side pick out portion of the worthless terial whilst ore is in transit. Fines go to furnace direct.

The Chesney chalcopyrite is of high grade when clean. It occurs dis-minated in the slate and quartzite, and in veins from a mere thread up to or 3 inches in thickness.

Cobar Copper, Limited.—The Cobar Copper, Limited, has secured the ll-known Mount Pleasant and Young Australia Mines on the metalliferous lt of impregnated slate and quartzite, which, with the exception of one

block, has been more or less profitably worked between the Cobar-Chesney and Occidental Mines. It strikes about N. 15° to N. 20° W., and varies in thickness up to 300 feet.

The Mount Pleasant and Young Australia, in common with the others along this line, were first entirely worked as gold propositions. As operations extended below the sphere of oxidation and leaching, copper gradually became sufficiently pronounced to seriously impair the efficiency of the economic cyanidation gold extraction process.

The difficulty was moreover enhanced by the extreme diffusion of the copper in the silicious rocks forming the lode.

In the Mount Pleasant lower levels more concentrated bodies of copper ore occurred, from two of which a considerable quantity of smelting ore was obtained in 1900 and 1901, for treatment in the Great Cobar smelters.

Copper sulphide appeared at the 160-feet level in the Young Australia section, but there is no record of any extraction, though the shaft reached 277 feet.

Position in October, 1907.—The new company was confining its operations to deepening the main shaft in the Mount Pleasant section from 340 feet to 530 feet, when, it is proposed, to cross-cut the belt in the permanent sulphide zone. The previous developments at the 150-feet and 215-feet levels disclosed three main metalliferous bands in a width of 300 feet. The intermediate country, in addition to a general dissemination of metallic ores in infinitesimal proportions, contains thin streaks of more pronounced value notably in the shaft at 340 feet.

The East lode has a width of about 4 feet, it consists largely of manganiferous quartz, with patches of fair grade copper ores. It lies 160 feet east of the main shaft, and has been stoped between the 215 and 150 feet levels, and proved in a winze below the latter to a reported depth of 70 feet. Between 150 feet and the surface it is unstoped. Sixty-eight feet west of the shaft, at both levels, a considerable width of auriferous ore has been stoped, between the levels, and from the upper to the open surface quarry, in which gold was first obtained. Below the 215-feet level this band has not yet been followed.

Eighty feet west of the Middle lode is the furthest western proving known as the West Copper lode, which has a width of about 8 feet. This band has been worked between the levels and sunk on 40 feet below the 215 feet.

From the East and West lodes the copper ores were obtained for the Cobar smelters. The gold ore from the open cut and lower stopes is reported to have yielded about 6 dwt. per ton.

C.S.A. Mine.—M.L. 4, parish Kaloogleguy, county Robinson, about 8 miles northerly from Cobar.—A well-known large gossany formation, which had received intermittent attention during a long period extending back to the early days of the Cobar Copper Mine, but which was not tested to water level until 1906.

Inspector D. Milne reported (P.B. $\frac{4}{96}$) that several shafts had been sunk on different veins of copper ore, and in the large gossan lode a shaft had been sunk 250 feet. The lode at this level was very wide, and carried a little gold all through, with occasional veins of lead carbonate, in gossan.

Aid was granted to sink to 350 feet and to cross-cut 50 feet at that level. After carrying the shaft down 332 feet operations were abandoned no payable ore being discovered at that depth in the still persistent porous gossan.

Inspector J. Polkinghorne recommended (P.B. $\frac{222}{05}$) further aid, which was granted to deepen the shaft to 482 feet, and to cross-cut 75 feet east and 50 feet west. Water-level was reached at 457 feet; and a cross-cut started west a few feet above it, in which rich carbonate of lead was struck; the redeposited, concentrated result of 450 feet of leaching. Below the water level the change to lean sulphides of iron, lead, and copper, was sudden.

The company, formed as a result of the rich lead strike, is now sinking the new main shaft well below the water level, for the purpose of testing the sulphide zone, the success of the mine depending upon the existence of sufficient copper sulphide to form matte in blast-furnace treatment. Until this is proved its future is problematical. In the north end of the property stains of copper carbonates are visible in the old shaft tips, but levels driven at 450 feet to these points have not been encouraging. In the bores to a depth of 150 feet below the 450-feet level fair copper values prevailed for a few feet, but soon diminished to unworkable proportions. In the drive from the main shaft to the lode at 450 feet, thin plates of native copper were encountered in a few feet of country.

In *Gardiner's Block* on south end, better grade copper ore has been cut in a winze from the 400-feet level.

Inspector J. Polkinghorne states (Ann. Rept., 1907, p. 90) that 80 tons of ore were raised from this mine during 1907, of which 47 tons were treated for a yield of 5 tons of copper, equal to 10·6 per cent.

J. Gainford & Co. state that 50 tons sent to Swansea yielded 11·1 per cent. of copper, a trace of gold, and a small percentage of silver, and gave a return of £5 19s. 10d. per ton. Traces of copper ore show very faintly in Block 19.

The following notes were extracted from a report on the Cobar Mining Field furnished by the Writer in 1906:—In the mines—other than the Great Cobar Copper—knowledge of the conditions obtaining in the lowest working levels is a *sine qua non* for intelligent report; for below a critical depth complete revolution in the methods of metal extraction will be enforced by changing conditions of mineral association. The ore reserves above this level also determine duration of present methods, and the urgency of timely decision as to future procedure. The opinion formed of the prospects of the Cobar Field whilst investigating the copper industry in 1899 has been strengthened and confirmed by subsequent recorded developments. At that time the Cobar Gold-mines, Occidental, Mount Pleasant, Young Australia, Great Western, and Peak Mines were producing free milling and cyaniding auriferous lodestuff, but even then were betraying signs of copper admixtures with increasing depth—presaging the stage reached in the Cobar-Chesney Mine, where free milling had given place to cupriferous lodestuff, unamenable to such treatment, and yet too lean for direct smelting as copper ore. The change entailing in the oxidised zone expensive leaching before cyanidation, and costly mechanical concentration in the unoxidised, in a region of low rainfall and slight catchment.

To a depth of about 150 to 200 feet, free milling and cheap cyanide extraction processes are possible and profitable; below that level for a hundred feet or more the lodestuff is stained with oxidised copper ores; then, after an intermediate stage of partial oxidation, the permanent copper sulphide zone is reached.

Mechanical concentration offers little prospect of successful achievement in the oxidised lodestuff. The experience on lean carbonates at Girilambone and Mount Hope was not encouraging, the difference between copper-stained and unstained lode material is too slight for gravity separation. In this zone, however, natural concentration—by secondary enrichment—may be expected to furnish limited bunches of direct smelting ore, bearing but little proportion, however, to the bulk of the lode.

A chemical process, viz.:—Leaching with sulphuric acid prepared locally from the sulphide ores, is possible, but impracticable—so far as present indications go—for any of the mines mentioned, owing to absence of solid sulphides suitable for roasting direct, and excessive cost of concentration for this purpose.

To establish leaching vats with imported sulphuric acid, as was recently done by the purchasers of the Cobar-Chesney tailings, would not, in the Writer's opinion, pay on a large scale, nor would it obviate the necessary cost of calcining the lean sulphides preparatory to leaching.

The possibility of smelting the cupriferous ores from the Fort Bourke (Cobar Gold-mine) and Chesney-Occidental lines of lode is, so far as indications go, discounted by the absence of sufficiently concentrated iron sulphides and the nature of the matrix. Judging by the Cobar-Chesney sulphides and the concentration products therefrom, the clean sulphides are comparatively rich in copper and low in iron. The matrix of these ores, consisting of slate, quartzite and quartz, requires a large proportion of iron for fluxing. Failing command of cheap and abundant supply, the mines along these lodes cannot hope to establish independent smelting plants on a profitable basis.

The disabilities under which they labour throw into strong relief the possibilities and potentialities of the immense solid pyritic resources of the Great Cobar Copper lode. This kindly fluxing base, in the Writer's view is the key to the situation, and must, if persistently basic, in the near future exert controlling influence, unless a radical change is discovered in yet untested levels in the other mines. The urgency of deep testing, preferably by diamond drilling, is therefore apparent.

The cogency of the opinion expressed in 1899 is quadrupled in 1905. The large fluxing base at the command of the Cobar Company opens up the most extensive problem of the field. Large as is the scale on which operations are now conducted, they are capable of still further development. However unpopular the idea of huge trusts and combines may be, there is no question that only under such conditions of consolidation will some of the extensive low-grade cupriferous gold and silver deposits of the vicinity be turned to best account. For though at present the Cobar-Chesney Mine is the only other of the Cobar group that has developed copper ores of commercial importance, there is every reason to anticipate, at all events, an amount of copper ore in the lower levels of the others sufficient to render unprofitable any method of extraction other than smelting in the way indicated.

Consideration of the present condition and future prospects of the copper mining industry of this State establishes clear-cut conviction of the advantages

of a closer union or concentration of interests. Instead of vainly contending with refractory ores, combination with those requiring just such economic admixtures in the reducing and refining processes would prevent one section struggling with costly experiments, the other using perforce valueless fluxes. Cobar-Chesney and Girilambone illustrate one division; Great Cobar, Nymagee, and the refining plants, at Lithgow, the other.

If community of interests and reduced railway freights could bring these divisions into touch, reciprocal advantage would accrue to both State and industry.

The future possibilities of the extensive pyritic lode at Captain's Flat, under some such reciprocal provision, loom largely ahead as affording the means of treating refractory auriferous and argentiferous copper ores, whilst adding to them its own small quota of these metals, and at the same time it is to be hoped, utilising its valuable sulphur contents.

The Cobar-Chesney Mine, after vain expenditure of capital and labour fighting the difficulties of a separate existance after the free-milling ores were extracted, was absorbed in the operations of the Great Cobar Copper-mining Syndicate.

Unless a vital change, as yet unindicated, occurs in the constitution of the lodestuff at lower levels yet unreached in the other mines under consideration, a similar fate appears to await them, *providing* always that the pyritic resources of the Great Cobar copper lode persist undiminished in solidity, and comparative freedom from silica.

Each of the mines mentioned has already, or will shortly, encounter the same difficulties that confronted the Cobar-Chesney, viz.—increasing copper contents preventing cheap gold extraction, yet insufficient for direct smelting. The fundamental difference between the cupriferous ores of these mines so far as proved, and that of the Great Cobar copper lode, lies—as already stated—in the nature of the matrix. Even if their copper contents were doubled, they would still be unsmeltable, save at considerable cost for concentration and fluxing.

The massive sulphides of the Great Cobar copper lode consist of magnetic and ordinary pyrite and copper pyrite (the latter itself a mixture of copper and iron sulphides), with a comparatively low percentage of silica. The advantages of a large body of this composition are:—(*a*) Its suitability for pyritic or partial pyritic smelting, whereby an enormous saving is effected in cost of fuel as compared with ordinary blast or reverberatory methods; (*b*) saving of whole or partial cost of initial roasting; and (*c*) production of clean and more silicious slags. The latter, an object of great importance at Cobar, where gold (and silver) ores are required to be worked (as flux) with the copper, for by keeping the slags silicious (and therefore fluid) the precious metals may be concentrated with the copper to any reasonable extent.

Silica is necessary in the furnace charge to combine with the abundant iron of the sulphides to form a fluid silicate of iron slag which may be floated off. The low-grade refractory ores of the neighbouring mines are just what is requisite for fluxing requirements. A silicious schist or slate, according to Dr. Peters, junr.,[1] is preferable to pure silica (quartz) in matte roasting, and doubtless also in smelting. The advantage to a smelting company of command of suitable flux, having of itself intrinsic value, is great, whilst an equivalent benefit should be derived by suppliers.

[1] Modern Copper Smelting, 5th ed., 1892, p. 271.

The appearance of copper ores in the lower levels of the principal gold-mines at Cobar induced a belief in the minds of some, that the lodes in them were at one time connected on a continuous strike with the Great Cobar copper lode, and subsequently disconnected by faulting. This idea, however, conflicts with readily discernible physical and geological facts. At least four distinct lodes are traceable on true and undisturbed courses parallel to each other. The absence of disturbance, or of intrusion, is a marked feature of the field. Inspector Milne informed the Writer that there was underground evidence of an eastern movement at the south end of the Great Cobar copper workings, in what was originally known as the South Cobar. But he is not aware of further evidence in the other lodes.

The Great Cobar copper lode occupies one vertical plane; the Fort Bourke or Cobar Gold-mines another; the Cobar-Chesney, Phœnix, Mount Pleasant, Young Australian, Great Western, and Occidental another; and the Peaks still another, more remote.

The great disparity in horizontal distance between the different parallel strikes of those lodes would necessitate separate faultings, of which there is no evidence.

The absence of indication in the outcrops of copper ores encountered at a depth, is especially likely in those instances where, as in the gold-mines of Cobar, the ores are leanly and evenly disseminated through a matrix consisting of slate and quartzitic country.

On the other hand, where large bodies of concentrated copper and iron sulphides were originally exposed in or near the outcrop, as at the Cobar Copper-mine and other big lodes, though the copper, from its greater solubility, may be more or less completely removed, the resulting insoluble iron oxide remains to indicate the pyritic mass beneath. In none of the gold-mines at Cobar were there any surface indications of massive metalliferous bodies beneath, excepting in the disappointing Burrabungie section, where a western outcrop of iron oxide betokened concentration, but its lower levels did not realise expectations.

The presence of copper ores between 150 to 200 feet in the present working gold-mines open the questions of free milling and cyaniding reserves still in view above these levels, upon which depend the duration of operations under existing methods, and the wisdom of establishing similar processes where quantity warrants.

Where supply justifies the latter, the experience of the Occidental and Cobar Gold-mines proves that only on a large scale can such low-grade deposits be attacked. To quote Inspector J. R. Godfrey:—"To work them in a small way is worse than useless, because it not only does not pay, but destroys the value of the mine by removing the better class ore, and thus rendering the whole less amenable to profitable treatment."

Of the Occidental Mine, the same officer wrote:—"The success of this mine is a strong argument in favour of economic handling on a very large scale. When the mine was worked with a small mill, it only paid to search for and treat the rich patches, now that they have a large mill, supplemented by a large cyanide plant, they can treat all the lodestuff and pay dividends, and the success of the mine is now about equally due to cheap mining on a large scale and the saving of the gold by the cyanide process."—(Ann. Rept., 1900, p. 102.)

COBAR MINING DISTRICT—*continued.*

The Cobar Gold-mine, late Fort Bourke, had a successful campaign with free milling stone above the 200-feet level.

Inspector J. Polkinghorne reported—"that about all the free milling ore has now been extracted from the Cobar Gold-mine. At the No. 3, or 250-feet level, the lode has been driven on about 500 feet in length, and a cross-cut put in, which proves the lode to be upwards of 80 feet in width, and of fair gold value, but the presence of copper makes the ore difficult to treat. Pending the erection of a different plant work will be confined to sinking and driving."—(Ann. Rept., 1904, p. 89.)

The following statement of output and yield has been compiled from published reports duly specified. The figures are not to be regarded as complete, but simply as an indication of value and proportional yield from crude ore, tailings, and slimes. The exceedingly fine physical character of the gold in the leached zone doubtless accounts for the high recovery from slimes. The lessening yield from the latter in the latest returns probably indicates the copper influence as well as depreciation.

From the well-known precipitating action of the metallic sulphides, it is reasonable to anticipate secondary gold enrichment about the zone of partial oxidation.

Authority.	Date.	Tonnage of Crude Ore (Amalgamation).	Tonnage of Tailings (Cyanide).	Tonnage of Slimes (Cyanide).	Yield, Gold.
					oz.
Australian Mining Standard.	1902. 6 Feb. (for Dec., 1901).	7,302	.....	.....	539
		.....	1,941		1,258
,,	6 Mar. (for Jan., 1902).	6,514	.....	.....	622
		.....	3,939	.....	1,962
		.....	.....	2,679	
,, ...	1903. 26 Feb.	11,382	.. ...	.....	1,317
		.....	6,985	.....	3,535
		.....	.....	4,932	
,, ...	1904. 5 May	6,473	.....	.....	711
		.....	4,153	.....	1,331
		... ..	.....	2,124	1,002
,, ...	2 June	6,380	.....	.....	561
		.....	3,995	.....	955
		.....	.....	2,187	1,054
,, ...	30 ,,	6,398	.....	.....	720
		.....	4,362	.....	1,172
		.....	.....	2,652	1,353
,, ...	28 July	5,170	.....	.....	646
		.....	3,466	.....	736
		.....	.....	2,262	1,000
,, ...	1 Sept.	4,850	.....	.....	567
		.....	3,196	.....	726
		.....	.....	2,262	1,027

The first record of copper output appears to have been 10 tons raised by tributers, which returned 27 per cent. at Cockle Creek Smelting Works. (*Australian Mining Standard*, 22nd December, 1898.)

In 1899 Inspector Milne reported that, after long suspension, this mine was opened under tribute by the Cobar Mining Syndicate, some rich bunches of carbonate and grey ore being obtained. (Ann. Rept., 1899, p. 100.)

In the following year Inspector Godfrey reported that "twenty men were employed under the tribute with satisfactory results on a small scale, no large bodies of copper ore being discovered, but occasional rich small patches are found." (Ann. Rept., 1900, p. 102.)

In August of the same year an output of 510 tons of ore, yielding 28 tons 15 cwt. of copper, is recorded. (*Australian Mining Standard*, 9th August, 1900.)

In 1901, Inspector Schloesser reported that this mine had been steadily working some rich pockets of carbonates and sulphides. (Ann. Rept., 1901, p. 89.)

In August, 1902, the tributers are reported to have extracted 2,353 tons of ore from Mount Pleasant, for a yield of 150 tons of copper (*Australian Mining Standard*, 7th August, 1902), equivalent to 6·37 per cent.

The Mount Pleasant and Young Australia are now held by the Cobar Copper Company, Limited, which see.

The Phœnix (late Burrabungie) Mine occurs between Mount Pleasant and Cobar-Chesney. So far there has been no output recorded either of gold or copper ore. A shaft was sunk 200 feet, close to the south boundary of the Chesney. A crosscut west at 200 feet undercut a ferric oxide outcrop, passing through about 10 feet of iron pyrites, part solid, part mixed with slate, in which but little copper sulphide occurs. Above the sulphide level stains of copper are visible in the rotten slate country. A crosscut from the Chesney main shaft across the strike of the Burrabungie pyritic band failed to encounter it, pointing to its probable existence as an isolated segregation. A crosscut to the east cut a mullocky lode with films of native copper 30 feet from the main shaft.

The principal developments on this lode have taken place at the extreme north and south ends, viz., in the Cobar-Chesney and Occidental Mines—in the former by underground stoping, in the latter by open cut. The absorption of the Cobar-Chesney by the Proprietary controlling the great copper lode removes it from the sphere of speculation as to future proceedings. Special interest, however, attaches to this portion of the lode as being the site of the first (practical) gold discovery on the field, and the instigation of the great industry subsequently developed.

The presence of gold in the oxidised ores, and in the metallic product of the Great Cobar Copper-mine had long been noted, though, strange to say, no effort was made to realise its value until the Cobar Mining Syndicate began operations in 1893–4, notwithstanding the results of an assay in the Departmental Laboratory being made known in 1881, viz., 2 oz. 12 dwt. 4 grs. gold, and 1 oz. 5 dwt. silver per ton, from borings through several ingots of export copper.

Gold was discovered in the Cobar-Chesney in 1887. Two tons from the outcrop, treated at the Sydney Mint, yielded a little over 4½ oz. per ton. In the following year 28 tons were forwarded to Victoria. Fourteen tons

under ordinary battery treatment yielded 1 oz. 17 dwt. per ton. The other 14 tons, under chlorination, yielded 2 oz. 3 dwt. 15 grs. per ton. A further test of 31½ tons yielded about 2¼ oz. per ton.

In 1889, 2,436 tons yielded 796 oz. 12 dwt. from a lode 4 to 25 feet in width (Ann. Rept., 1889, p. 18), equivalent to about 6½ dwt. per ton.

In 1890, 880 tons for 586 oz. (*Ibid.*, 1890, p. 20).

In 1891 and 1892 no returns.

In 1893, 328 tons for 222 oz. (*Ibid.*, 1893, p. 65.)

In 1894, 1,895 tons for 1,019 oz. (*Ibid.*, 1894, p. 32.)

Disregarding the small parcels of rich stone, the bulk output, so far as recorded, averaged 9·47 dwt. per ton.

The copper value of the enriched portion of the lode may be gauged from the output recorded in 1901, when 4,500 tons treated in the Cobar smelters yielded 135 tons of copper, equivalent to 3 per cent.

Of the concentrates produced during the Cobar-Chesney Company's experiments with concentrating plants, 91 tons 5 cwt. 3 qrs. 16 lb. at the Cockle Creek Works returned £669 5s. 9d., including 26s. 3d. per ton for gold. (*Australian Mining Standard*, 8th March, 1900.)

The outcrop was free from copper. At 150 feet it began to show freely in carbonate form, and as sulphides at about 250 feet. The presence of copper gradually prevented profitable gold extraction by ordinary milling practices. The accumulated cupriferous tailings were eventually leached with sulphuric acid and cyanided.

So far as the lode has been pierced—over 700 feet—it has given no sign of concentrated ore bodies, the copper and iron sulphides being disseminated through the slate and quartz matrix.

The Occidental Mine has had the longest sustained milling career of any on the field. Unfortunately the total output is not obtainable. The following returns, however, give an idea of the value of stone extracted:—

Beginning with a small milling plant, successful headway was not achieved until it was increased to fifty stamps, with the necessary complement of cyanide vats. With the lode about 70 feet in width, in which quarrying was possible to a depth of 150 feet, mining costs were reduced to a minimum. On the large scale on which this mine has been worked, an average extraction of 4·4 dwt. per ton in the upper levels, and 3·19 dwt. in the lower, has been profitable. The copper contamination problem now, however, confronts the near future. Inspector Polkinghorne states that the estimated quantity of ore in sight—presumably free-milling ore—at the end of 1904, was 80,000 tons, and expresses an opinion that the appearance of the lode at 340 feet in the shaft betokens future development into a copper lode. (Annual Report, Department of Mines, 1904, p. 89.) Copper, however, makes its appearance, and will be troublesome below about 250 feet.

The following returns are compiled from the Annual Reports of the Department of Mines, for the years 1889 to 1896, viz.:—29,111 tons for a yield of 6,464½ oz., equivalent to an extraction of 4·4 dwt. of gold per ton.

The gold output recorded in the *Australian Mining Standard* from March, 1900, to February, 1905, totals 14,451 oz., but the tonnage is only given in three issues.

The output for the three years ending December, 1903, is reported as 102,512 tons for a yield of 16,375 oz., equivalent to an extraction of 3·19 dwt. per ton.

COBAR MINING DISTRICT—*continued*.

Of the Peak lode few particulars are available. The discovery of gold at this point followed very closely that of the Chesney. Some rich stone has been extracted, but operations have been of an intermittent character, owing to the irregular and patchy nature of the gold shoots.

The presence of silver in payable proportion in some of the lodestuff is a marked feature, inasmuch as this metal is not prominent in the neighbouring lodes. Some of the rotten slate lodestuff, containing chloride of silver equal to about 30 oz. per ton, was used for fluxing purposes in the Cobar copper smelters.

The gold yield from the Peak, so far as known, averaged a little over 1 oz. per ton for an output of over 8,000 tons.

Cobar District.—In the Central Prospecting Shaft, about 10 miles from Cobar, and 3 from Queen Bee Mine, infinitesimal traces of copper occur in quartz. No value disclosed in over 300 feet of sinking.

Cobar Tharsis, about one mile N. of Cobar, and apparently on the strike of the Fort Bourke (Cobar Gold-mines) and East Cobar lode, viz., N. 10° to N. 15° W. Known also as the Ivanhoe and East Cobar Copper-mine Extended.

Under the latter title aid was granted (P.B. $\frac{1}{0}\frac{7}{5}\frac{4}{3}\frac{a}{a}$) to drive along the lode 100 feet, and to cross-cut east 20 feet, at the 307-feet level.

Later the property was disposed of to the Cobar Tharsis Company, N.L.

Shaft deepened to 350 feet in November, 1906, after which work was suspended. No payable ore was disclosed. The little raised was of a very poor, silicious nature.

Tindary Station.—Raymond and party's prospecting site, 27 miles from Cobar, and 1½ miles east of Cobar-Bourke road, parish Ramsay, county Robinson, Inspector Polkinghorne reported (P.B. $\frac{1}{0}\frac{2}{5}\frac{4}{4}$):—Quartz reef with copper stains at 25 feet. Aided, to sink 52-feet shaft to 202 feet, and to drive 50 feet along reef.

At 163 feet prospects reported as improving. No further record.

Mallee Tank and Conqueror Prospecting Shafts.—Limestone was struck in each of these; a sample from the latter gave the following composition on assay:—

No. 07-7431—Calcium carbonate	97·10	per cent.
Ferric oxide and alumina	·54	„
Gangue	2·12	„
Magnesium carbonate and undetermined	·24	„
	100·00	

Ten miles S.W. from Cobar, and 3 N.W. of Queen Bee Mine, parish Meltie, county Robinson.—Inspector J. Polkinghorne reported (P.B. $\frac{1}{0}\frac{8}{7}\frac{2}{3}\frac{a}{a}$):—Slate with quartz veins carrying strong stains of copper carbonates; country strongly impregnated with iron oxide. Aided to sink a shaft 350 feet, and drive 200 feet north and south from bottom.

At 310 feet heavy water prevented continuation of shaft with prospecting appliances; cross-cutting begun; the first 36 feet of the cross-cut was through a lode of very low grade, a little copper showing in places, and small veins of pyrites.

COBAR MINING DISTRICT—*continued*.

Cobar Gold-mines (formerly Fort Bourke).—Carbonate of copper has been stacked from oxidized zone. Sulphides are being raised from north level at 437 feet.

Experiments were tried with the Elmore Vacuum Concentrator (three units of a capacity of 150 tons per day being installed by the Elmore Proprietary) towards the close of 1907. So far results have not been disclosed, but are believed to have been unsatisfactory.

If these lean sulphides can be successfully concentrated, they will be useful for fluxing the silicious carbonates; but the tailings and slimes will require separate treatment for their gold contents, unless the workable or recoverable proportion be included in the sulphide concentrates.

Nymagee Division.

Cobar-Lyell Mine, about 3 miles north of Shuttleton, and ¾ of a mile from Pine Tank, Priory Run, parish Hume, county Mouramba.—Strike N. 15° W. in slate and sandstone. Inspector H. Hooke reported (P.B. $\frac{1903}{1904}$):—A copper-bearing formation opened to 15 feet. Aided to sink to 65 feet, and to cross-cut 25 feet at bottom. Progress.—At 40 feet, two bunches of copper ore in gossan cut through; at 65 feet, slate intermixed with small veins of carbonates; aided to continue sinking to 115 feet; at 94 feet, same prospects as at 65 feet; no improvement at 100 feet; cross-cut revealed thin veins of ore for 12 feet; nothing beyond.

Examined by the Writer in November, 1907. Work abandoned. Grey sulphide a few inches thick at 80 feet; apparently occurring in bunches. Some tons of dressed ore at surface, consisting of native copper, carbonates, and grey ore, gave the following returns from an average sample:—

No. 07-7433—Copper, 9·98 per cent.
Gold, 1 dwt. 2 grs. } per ton.
Silver, 2 oz. 9 dwt. }

Crowl Creek-Shuttleton Mine, M.Ls. 3, 6, 7, 8, 9, 12, 14, parish Hume, county Mouramba, 17 miles S.W. of Nymagee, 50 miles from Cobar, and 57 miles from Hermidale Railway Station.—Chief Inspector J. B. Jaquet was the first to officially examine the discovery at Crowl Creek. From his report the following extracts are made, illustrative of the surface conditions, now obliterated:—

"Attention was first directed to these deposits by an aboriginal—Jacky Owen—in November, 1900. Remarkable that they remained undiscovered so long, because of occurrence of green stains of copper carbonate on face of slate cliffs in vicinity. Country slate and schist, identical with Cobar formation. Copper ores do not occur in a lode with well-defined walls and a distinctive gangue, but scattered in bunches and pockets throughout the country. Some of the ore consists of slate with a slight impregnation of copper carbonates, and this ore can be seen passing by insensible gradation into one composed almost entirely of copper carbonate, grey ore, and red oxide, with a gangue of quartz and oxide of iron."

"The most promising deposit hitherto discovered is situated upon Osmetti and party's claim. Here a bunch of slate impregnated with copper carbonate has been exposed for a distance of 75 feet. An open cut has been

carried down upon this to 18 feet. At bottom a body of excellent ore, at least 7 feet wide, was exposed. Sixteen tons of ore raised and sent to Cockle Creek. On prospector's claim shaft down 40 feet in decomposed schist, more or less impregnated with copper carbonate.

"In Kerwin and party's claim a little carbonate at surface; at 30 feet a bunch of rich carbonate and cuprite."

The northern, or Crowl Creek, section was originally styled the "Commonwealth." After being taken over by the Crowl Creek Syndicate in March, 1902, it was renamed; the Crowl Creek Copper-mining Company being formed at the end of the year.

Amalgamation was effected with the southern, or Shuttleton, section in December, 1906, under the present name of *Crowl Creek-Shuttleton.*

Progress of development is briefly recorded in the following extracts from official reports:—

Inspector Schloesser, in 1902, reported development continuing satisfactorily. Carbonates, oxides, and glance, followed down in the Crowl Creek section to 200 feet; rich portions stoped and sent away. Chalcopyrite proved at 220 feet, 18 feet wide, grade over 17 per cent. down to 250 feet. (Ann. Rept., 1902, p. 79.)

Smelting began in 1903 with four reverberatory furnaces. 1,300 feet of driving and cross-cutting, and 250 feet of shaft and winze sinking executed. (*Ibid.*, 1903, pp. 45, 46.)

Refinery erected in 1904. Air compressor plant, rock drills, &c., installed. Sinking main shaft to 450 feet, with levels at 350 and 430 feet. Good sulphide ore at each level. Value of copper obtained during year, £34,800. (*Ibid.*, 1904, p. 45.)

Main shaft deepened to 630 feet in 1905. Ten thousand tons of ore treated for 950 tons of copper. (*Ibid.*, 1905, p. 80.)

Concentrating plant in course of erection. Main shaft 680 feet. Amalgamated with Shuttleton Mine in December. (*Ibid.*, 1906, p. 45.)

The following extracts from the Seventh Half-yearly Report, 26th September, 1906, afford an insight into scope and cost of production, when in full running order:—

5,150 tons of lodestuff raised during half-year produced 2,652 tons of dressed ore.

4,400 tons smelted for 268 tons rough copper, 233 tons of which yielded 215 tons refined copper=99·75 grade.

Costs.	£	s.	d.	
Mining crude ore	1	6	6·3	per ton.
„ dressed ore (proportional)	2	9	1	„
Dressing crude ore	2	2	9·3	„
„ clean ore (proportional)	0	5	1·2	„
Clamping (heap roasting)	0	3	1·5	„
Smelting per ton of ore to rough copper	1	17	9·4	„

Costs per ton of Copper produced.			
Mining	22	18	3
Dressing	2	18	8
Clamping (heap roasting)	1	3	8·1
Smelting	31	8	10·8
Average cost per ton of rough copper	£57	19	5·9

Total cost of mining and smelting per ton of ore, £3 9s. 8d.



PHOTO LITHOGRAPHED BY W. A. GULLICK, GOVERNMENT PRINTER, SYDNEY, N.S.W.

The costs at this period were greatly increased owing to difficulty in raising sufficient ore to keep reduction plant running. The evil of the hand-to-mouth policy of establishing a fairly large smelting plant prior to adequate exploration and opening of levels ahead of stoping requirements.

This property was examined by the Writer in October, 1907, immediately after compulsory closing down, owing to financial troubles.

The lodes occur in sandstone and slate close to junction of quartz-felsite, towards which they strike at an acute angle. The main (Crowl Creek) shaft enters the quartz-felsite at 683 feet. The latter occurs on the west side and strikes approximately north and south. The lodes strike north-west, and dip at 58° to 63° south-east.

Three parallel lodes occur in the Crowl Creek section, viz., the "Main," and "East" and "West" lodes. The Main, or Crowl Creek lode, forms a lens which has been worked for a length of 160 feet, and an average width of about 6 feet. A greater width of mineralised rock occurs, but not payable. The ore-lens has been stoped from 630 feet to surface.

Notes on appearance of lodes at time of closing in October, 1907:—

Crowl Creek Section:—

110-*feet level.*—Formation showing good ore in crosscut east.

270-*feet level.*—West, Main, and East lodes opened. Main lode troubled at north end. South end in blank channel rock and quartz—should be driven on.

330-*feet level.*—Mineralised country exposed in crosscut west of West lode. West, Main, and East lodes opened. In West lode at 330-feet level stoped up and followed in winze. Channel rock well defined in face north end. South end not driven on, thin and pinched, but solid pyrites showing; should be driven on.

South end of Main lode at 330-feet level followed for some distance on good ore, ended in strings of quartz with pyrites; should be followed.

North end at 330-feet level, slate with pyrites leanly distributed; traces of copper ore on hanging wall.

530-*feet level.*—Not very productive. Cross-cut west to probably "intermediate" lode, then on to supposed West lode. Small chamber stoped in latter for pyritic flux; fairly solid, reported to contain 1¼ per cent. of copper.

630-*feet level.*—Main lode lens 100 feet long, greatest width 12 feet—of 3 per cent. average. Monkey shaft sunk to 730 feet; greatest depth reached.

730-*feet level.*—Good grade ore at bottom, 90 feet long; greatest width about 18 feet, narrowing to 6 feet. Best grade extends 39 feet north and 16 feet south of Monkey shaft. Hard breaking ground, quartzite. Sump 15 feet deep, half in ore, half in slate on hanging wall. Assay from sump, 7 per cent. copper. Winze 25 feet north of Monkey shaft, depth 7 feet. Assay, 11 per cent. copper from both ends.

On south-west ore dies away in hard quartzite without wall.

The lower developments are decidedly encouraging, there being an improvement at 630-feet level, and still better at 730-feet—where 7 per cent. ore is going underfoot. Following the latter north-west, ore continued for about 90 feet, when a blank was encountered, and further on ore for 60 feet, and still in face.

COBAR MINING DISTRICT—*continued.*

Shuttleton section.—No quantity of payable ore cut in this section above 387 feet. At 150 feet strings of black ore occur in crushed slate, not worked. Thirty-four feet west on this level, junction of quartz-felsite met; no ore, but very pyritous slate at contact. North end of 150 feet level driven only a few feet beyond strings of black ore mentioned.

Crosscut south from 150 feet level for 13 feet, strings of rich yellow sulphide in slate, said to average 3 per cent.

First stope opened at 380 feet on underlay; south of shaft at this level, a good lens of ore made in quartzite, but did not extend up beyond about 15 feet. Closed in south, a little ore showing in continuation of south drive in quartzite, under 1 per cent. grade.

At the 445 feet, or lowest level reached—just above water-level—a lens of ore, stoped about 44 feet by 23 feet, continues south, but of poor quality.

The average yield of the Shuttleton ore, as mined, was about 3 per cent.

Mine Water.—Water-level, 330 feet in Crowl Creek section; just showing at 445 feet in Shuttleton.

From bottom of main Crowl Creek shaft (730 feet) 33,000 gallons per day lifted in dry season (October, 1907). Bulk of water (30,000 gallons) from 450-feet level.

Heavy water struck in diamond drill bore east; pressure forced out five lengths of rod.

Underground supply an important item in this dry tract when concentration is necessary.

Concentration Plant.—This plant had just been installed and run for about one month when the mine was closed down. The progress of the ore was from breaker to ore-bin, thence over grizzly to travelling elevator belt of a capacity of about 60 tons in eight hours, set at a moderate angle. On either side of belt vertical shoots at short intervals (connected with ore-bins), into which boys threw direct smelting ore from belt. An average sample of the picked ore from the bins yielded:—

07-7429—Copper, 9·92 per cent.
Gold, a trace per ton.
Silver, 1 oz. 3 dwt. 23 grs. per ton.

The ore left on the belt passes to a second breaker, then to rolls; from rolls to trommel screens. Over-size material gravitates from inclined trommels to an elevator wheel which returns it to rolls.

Fines passing trommel screens, hoisted to upper floor by endless bucket belt fed from trommel launders. Thence to classifiers; overflow passing to two Wilfley tables, the coarser material to two May Brothers' jigs.

Samples of the concentrates from the Wilfley tables and from May Brothers' jigs yielded the following results:—

Assay No.	Description.	Copper.	Gold.	Silver.
		per cent.	per ton.	per ton.
07·7427	Wilfley concentrates	11·58	a trace	1 oz. 6 dwt. 3 grs.
07·7428	May Brothers' jig concentrates ...	8·84	a trace	1 oz. 7 dwt. 5 grs.

The soft, earthy carbonate impregnations of the surface zone were passed through sluice boxes to get rid of excess earthy or rotten slate fines, partially kaolinised.

COBAR MINING DISTRICT—*continued.*

Smelting Plant.—Consists of four reverberatory reducing furnaces, and one refining, of a capacity of about 100 tons per week each.

Firebrick made from Mount Hope fireclay, which has the following composition :—

No. 07-7432—	Moisture at 100° C.	0·28
	Moisture over 100° C	2·86
	Silica	85·06
	Alumina	8·43
	Ferric oxide	0·70
	Ferrous oxide	0·17
	Manganous oxide	0·04
	Lime	0·32
	Magnesia	0·36
	Soda	0·32
	Potash	0·75
	Titanic dioxide	0·80
	Phosphoric anhydride	0·01
	Vanadic oxide	absent
		100·10

Furnace bottoms formed of crushed quartz which occurs abundantly in barren reefs close at hand.

Ore, sulphides, self-fluxing, clamp roasted.

Output.—The following figures were supplied by Mr. G. Gillimany, late Secretary to the Company :—

	Tons.		Per cent.	
Ore raised and sold prior to March, 1902, when Crowl Creek Syndicate entered into possession	845	...	26	(average)
Ore raised and sold from March, 1902, to December, 1902	3,024	...	23·07	,,
From formation of Crowl Creek Company, December, 1902, to closing down, October, 1907 :—				
Ore sold	900	...	28	,,

Ore smelted, about 40,000 tons for about 2,400 tons of copper, or about 6 per cent.

Mines like Crowl Creek, Nymagee, Mount Hope, &c., are exceptionally handicapped by long team carriage to nearest railway transport, a handicap seriously augmented by frequent droughty conditions imposing almost prohibitive rates on account of fodder scarcity.

Railway communication would unquestionably lead to permanent mining operations on a more extensive scale.

Before the Crowl Creek-Shuttleton lode is reopened, however, it is imperative that adequate prospecting should precede smelting. The furnaces should not be blown in until mining had produced at least six months' supply of smelting ores; development should then be carried on vigorously with continuous augmentation of smelting supply, instead of the previous hand-to-mouth policy of mining under stress of constant smelting demand.

Crowl Creek South Copper Mining Company, N.L., M.L. 17, parish Hume, county Mouramba, formed to prospect adjoining block south of Shuttleton section.

At time of inspection in November, 1907, shaft down 125 feet, a few slight stains of copper carbonate met in a short crosscut about 115 feet from surface. No appearance of lode. Closed.

COBAR MINING DISTRICT—*continued.*

Donnybrook Lode (New Babinda).—14 miles from Nymagee and 1 mile from Hermidale-road. Parish Nymagee, county Mouramba.

Inspector J. R. Godfrey reported (P.B. $\frac{A\,A\,A}{C\,C}$) stains of copper carbonate in schist and slate. Aided to cross-cut at 80 feet on No. 1 Shaft for 50 feet. Also to sink No. 2 Shaft a further 50 feet, and drive 50 feet.

Inspector Schloesser reported (P.B. $\frac{A\,A\,A\,A}{C\,C}$) strong veins of carbonate at 40 feet in No. 1 Shaft, and heavy gossan with carbonate in No. 2. Aided to cross-cut at 80 feet in No. 1 Shaft. No ore over 4 per cent struck; only small veins.

Aided to sink No. 2 Shaft 50 feet deeper and to drive 50 feet.

Inspector J. Polkinghorne reported (P.B. $\frac{A\,A\,A}{C\,C}$) that the Try Again Syndicate sank the 65 feet shaft a few feet deeper and reported 2 feet of ore averaging 3 per cent. Aided to sink 80 feet shaft 150 feet deeper. At 130 feet, a little sulphides. Aided to cross-cut 25 feet west. At 26 feet in crosscut, traces of copper only—not encouraging; at 157 feet in shaft, indications slight; at 182, specks of copper ore only; at 207 feet, prospects reported better—quartz and black slate with sulphides, and some galena—no further record.

Bourke Division.

Doradilla Copper Lode.—Prospecting area on Doradilla Station, parish Mulholland, county Cooper, about 13 miles east of Mooculta railway siding, and 34 miles from Bourke.

Inspector Polkinghorne reported (P.B. $\frac{A\,A}{C\,C}$) a lode containing copper, gold, and silver. Opened by shaft to 132 feet, driven on southerly at bottom for 37 feet. At 17 feet from shaft a winze down 52 feet. Also short drives at higher levels.

The lode in winze reported as promising. Native copper occurring in lode for full width of winze; east wall not exposed; splashes of grey ore in last 10 feet of winze.

Aided to continue winze to 152 feet.

Cobar Division.

East Cobar Mine.—In freehold of Great Cobar, Limited, in P.G.Ls. 46 and 47—on the strike of the Fort Bourke (Cobar Gold-mines) line of lode, and in a direct line with the Cobar Tharsis Mine.

At time of inspection in 1907 the prospecting shaft was down 100 feet, and a drive was being carried north at that level. A second shaft was being sunk a short distance north in P.G.L. 46. Practically little more than traces of copper had so far been discovered. Shaft 130 feet deep in July, 1908. No fresh developments.

East Cobar Freehold Mine, north of, and adjoining the above mine. No outcrop other than ferruginous slates. On direct line of Fort Bourke—Tharsis lode. The strike being N. 10 to 12° W. Copper first struck in the adjoining East Cobar Mine. Closed down.

No sign of lodestuff above 70-foot level, when carbonates and grey ore appeared on west side of shaft, and gradually widened to about 4 feet at 130 feet The actual width of the cupriferous belt had not then been proved; cross-cutting being necessary.

A little gold can be panned off from the rubble. The copper ore occurs as an impregnation in slate country.

COBAR MINING DISTRICT—*continued.*

Water-level, 120 feet, below this could not be kept down with whip. Engine, boiler, and poppet-heads were being installed towards end of 1907. A sample of best selected ore yielded :—

No. 07-7428—Copper	7·75 per cent.	
Gold	a trace	per ton.
Silver	1 oz. 12 dwt. 11 grs.	

Bobadah Division.

Emerald Prospecting Area.—Inspector Schloesser reported (P.B. 03-2338),—Serpentine carrying a little copper ore and chromite for a width of about 14 feet, near Old Bobadah, and 42 miles S.W. of Nymagee. Aided to sink from 20 feet to 70 feet and to cross-cut 50 feet. Apparently not availed of.

Gilgunnia Division.

Gilgunnia.—Copper ore occurs in small quantity about 2 miles N.E. from Gilgunnia, near The Peak, and on the Gilgunnia-Nymagee Road, about 7 miles from Old Gilgunnia.

Northumble Pastoral Holding.—Six miles south of Sandy Creek Government Tank, parish Carlisle, county Mouramba.

Inspector Polkinghorne reported (P.B. $\frac{a}{07}\frac{17}{2}$) a promising formation with quartz and ironstone leaders in slate, proved 9 feet wide, at the 48 foot level, and carrying traces of copper throughout. Aided to sink from 48 to 148 feet.

Nyngan Division.

Girilambone Copper Mine, Great Western Railway-line, 405 miles west of Sydney, parish Gidalambone, county Canbelego, (situated in portions 2 and 3, originally taken up under volunteer land orders).—The actual date of discovery of this mine is in dispute ; but there is no doubt that it was first opened in the beginning of 1880 by Messrs. Hartman, Campbell, and others, the two named being also connected with the discovery and opening of the Great Cobar Mine.

Mr. Hartman's statement, briefly, was that in 1875, whilst proceeding from the Bogan River to Cobar, he camped at some "gilgai" water-holes, close to Girilambone Hill, and, from his experience at Cobar, recognised the characteristic blue and green stainings of copper carbonates at the site of the present South Shaft. As the outcrop was small he did not set much value on it at the time, but contented himself with taking with him to Cobar a sample of the surface ore.

In 1879, accompanied by his brother-in-law, Charles Campbell, and two others, he again visited Girilambone and marked out four 40-acre mineral conditional purchases, and proceeded shortly afterwards to mine the surface ore, which consisted largely of rich red oxide. His title was then disputed by Messrs. W. W. and T. L. Richardson, on whose run (No. 5 West Bogan) the mine was situated, the latter claiming a prior right by volunteer land orders. According to Mr. Hartman, his partners not being sufficiently impressed with the importance of the deposit—as the red oxide was only from 3 to 12 inches thick in flat layers down to 10 feet—relinquished their claim to it rather than enter into litigation. Mr. T. L. Richardson states that his attention was first drawn the outcrop in 1880 by a stockman on the run, who had been attracted by the colour of the rocks. The land was then secured as already stated. It seems unquestionable, nothwithstanding the conflicting

dates, that the site was known to the owners of the run prior to the advent of Hartman and party to begin mining, but the action of the latter practically led to the opening of the mine.

Girilambone, in the aboriginal language, signifies "falling star" or meteorite.

The first official record of Girilambone Mine is that by Mr. L. H. G. Young, Geological Surveyor, who visited it in company with the Writer, in 1880. "The copper deposit is situated on No. 5 West Bogan Block, near the north-west corner, and on the summit of a small hill long known as Copper Hill."[1] The lode has a strike N. 18° W., and dips to the eastward at an angle of 56°. A small trench has been made across the lode, showing it, for a width of 18 feet, to be composed of veins of quartz, including between them bands of slate and occasional bunches of extremely rich red oxide of copper coated with green carbonate. The lode may be again seen 100 yards to the north of the trench, and copper indications also occur about 30 yards to the N.E. of the same place. The strike of the slates is N. 12° E." (Ann. Rept., 1880, p. 262.)

In $\frac{1881}{p.241}$, a company was formed and the mine opened, the lode so far as tested appearing from 6 to 25 feet wide. 650 tons of ore were raised during sinking and driving. Furnaces were in course of erection.

In $\frac{1882}{p.244}$ the deepest level was 198 feet from the surface; the lode at this point being 6 feet wide. 2,000 tons of ore were raised during the year, but only 10 tons of copper were produced. Mr. T. L. Richardson states that after the furnaces were erected the ore was found difficult to treat, and little was done in this line, the output being sent to the English and Australian Smelting Works at Waratah.

In $\frac{1883}{p.117}$ 130 men and boys were employed until the end of April, when twenty-two only were retained sinking a new shaft. The main shaft reached a depth of 252 feet, the lode varying from 2 to 19 feet in width. 450 tons of ore raised during the year yielded 32 tons 4 cwt. 1 qr. of fine copper, valued at £1,655. Value of plant, £7,500. Population, about 500.

In 1884 prospecting by means of a new shaft was carried on. Chief Inspector W. H. J. Slee, reported $\frac{1884}{p.120}$ that bunches of ore were struck at the following levels—86, 122, and 300 feet.

From 1885 to 1893 the mine was not worked.

In 1893 it was let on tribute, and ore extracted to the value of £957.

In 1894 two or more tributes were let, the output being 36½ tons of copper, valued at £1,180.

During 1895-6 the mine was again idle.

In October, 1896, the Girilambone Copper Mining Company, Limited, was formed, and active operations begun, 200 men being employed. The main shaft was deepened to 320 feet. 17,154 tons of ore were raised during 1897; estimated copper contents, 733 tons. Smelting and refining were commenced and 173 tons of copper produced.

The Writer examined developments in 1898.

The country consists of slates and sandstone, with occasional hard bands of quartzite, the latter forming a few low hills in the neighbourhood which are conspicuous features above the general level. Girilambone Hill is of low elevation, with a bare outcrop of rocks, chiefly quartzitic. The copper ores occur as segregations and replacements in the country without the defined limits of ordinary fissure lodes. The matrix consists of silky, schistose, and fine sandy slates, with numerous quartz veins and inclusions

[1] Mr. T. L. Richardson states that this is an error, the name not being known prior to the date mentioned.—J.E.C.

In an open cut—a relic of early operations—at Datson's shaft, the folding and contortion of the country is well defined by infiltration of copper salts —blue and green carbonates—along the lines of folding, imparting to the mass a wavy banded character.

The zone of surface oxidation extends just below the 200 feet level. The oxidised supplies were being drawn from the 140 feet level in the south shaft. In this lode, isolated patches and nodules of red oxide of copper occur in the softer country, following the wavy folds of a hard quartzite band, locally known as the "ironstone lode."

The carbonate ores are seldom homogeneous and solid, but principally earthy and pulverulent; even the apparently pure azurite particles contain little more than half the theoretic value in copper, whilst the malachite rarely approaches even this proportion.

Between the zone of complete oxidation and the unaltered sulphides at 220 feet, there is a gradual transition, the upper extensions of the sulphides being coated, and in places entirely converted partially into loose earthy melaconite—black oxide of copper—and partially into sub-sulphide, which, unfortunately, are difficult to save in concentration.

Serious difficulties at Girilambone are the close association of silica (quartz) with the copper ores, and the absence of solid iron sulphides. Wherever the copper ores occur most concentrated in either the oxidised or sulphide zones, quartz is most abundant; hence, owing to the nature of the ores, and the mode of their occurrence in the matrix, concentration by jigging results in a high percentage of silica being retained with the ore. The clayey material of the earthy ores, and the soft schistose matrix, is mostly removed during the operation. The first concentrates, which are used for fluxing the oxidised ores, contain about 53 per cent. of silica.

Development to 1908.—The main shaft reached 544 feet, but for the last 120 or 130 feet it had passed out of the lode, which had dipped away from the shaft. The deepest working level was 300 feet, but another was being driven at 520 feet. Other working levels were the 200 and 140 feet. The south lode was connected with the main shaft by a cross-cut at 140 feet level, through which all the haulage was done. The south lode strikes about north-west whilst the main lode has an apparent east and west course.

In the fifth half-yearly report—28th February, 1899—Mr. W. Blakemore, mine manager, stated that the main shaft, 544 feet deep, had been securely timbered and divided into compartments. Little work was done at the 360 feet level—insufficient to determine the value of the lode at this depth. At the 300 feet level, the west drive had been extended 70 feet on the course of the lode. Ore stoped, 25 feet wide, 200 feet level. A new stope opened in south-west drive, consisting of malleable copper, grey and carbonate ores. No work performed at the 140 feet level during the half-year beyond completing the cross-cut to the south workings.

A new tank of 6,000 cubic yards excavated; old tank cleaned out.

Treatment of the Ores in 1898.—The oxidised ores from the upper levels were roughly sorted at the surface by hand picking and screening, the richer portions going direct to the smelter's charging bins; poor lumps were discarded, and the balance sent to the ore-breaker for preparation for the jigs. The sulphides on the other hand went direct to the jigs.

The ores raised were divided into three classes, distinguished as "carbonates," which included the red oxide and carbonates from the south lode, "sulphides," which embraced all the sulphides from the 240 and 300 feet levels, and "oxides," from the transitional zone between the former.

The "carbonates," as mined, had an average assay value of 4·6 per cent., according to the half-yearly statement for June 30th, 1898, which is based on weekly average assays. About 40 per cent. of this class of ore was sent direct to the smelters after breaking and picking, and averaged 13 per cent. A small proportion was discarded, and the balance went to the ore-breaker and jigs. The screenings of this class naturally formed a considerable part of the whole, owing to its soft earthy nature. The richer portion, which went direct to the charging bins, consisted chiefly of isolated lumps of red oxide, coated with carbonate and associated with quartz.

The "sulphides" and "oxides" went direct to the concentrating plant, which consists of a Gates rock-breaker, Cornish and Krom rolls, and Handcock's and May Brothers' jigs. Wire-wove ¼-inch mesh trommel screens are used in connection with the rolls.

Each class of ore was treated separately. The crushed material from the breaker was divided between the Cornish and Krom rolls, the coarser material from the former passing to a Handcock's jig[1] (of obsolete pattern), and the finer from the Krom to May Brothers' jig.

The first concentrates went to the charging bins, the seconds were stacked for further possible treatment, the balance passing to the waste heap.

From the detailed statement for the half-year under existing conditions it has only been possible to obtain from the picked ore and the workable concentrates about 66 per cent. of the estimated contents of the output. This percentage is still further reduced by loss in smelting. The actual extraction approximates to about 50 per cent. of the estimated contents of the ore raised.

(*a*) Concentration.—The earthy carbonates and oxides (chiefly screenings), were concentrated to an estimated average assay value of 10·9 per cent. of copper, but a glance at the "seconds" revealed a considerable loss, chiefly in blue carbonate. Attention was given by the Writer to the possibility of mechanically separating these particles after careful sizing, but the difference in specific gravity between the carbonate and the waste was so slight (0·73) as to render mechanical separation impossible. The green carbonate particles, which are also conspicuous on the "second concentrates" heap, need only a glance to establish the fact that their copper contents are more apparent than real. Mostly, the green particles are quartz stained by malachite, the average specific gravity of which is 2·74, whilst that of the slate waste is 2·72. An assay of apparently pure azurite (blue carbonate) yielded only 31 per cent. of copper as against 53·2 per cent. in the pure mineral. In view of these facts, it did not appear that the loss could be averted in mechanical concentration.

The most important question in concentration, however, refers solely to the sulphides, the estimated copper contents of which were increased from 3·1 to 6·5 per cent., and the estimated extraction to about 50 per cent.

It has been demonstrated that there is little hope of better mechanical recovery in the case of the carbonates and oxides; the question, therefore, is whether cleaner concentration is possible in the case of the sulphides. In the first place, the copper and iron sulphides mainly occur sparingly distributed through a greenish schistose slate, and it is specially noticeable that where the sulphides occur most concentrated, that quartz is abundant.

To crush direct to a fineness sufficient to free all the scattered sulphide crystals would, probably, in the absence of an abundant water supply, increase instead of reduce the present loss, owing to the great tendency of the matrix to slime. From a study of the nature of the ore, and the natural

[1]Since replaced by one of Handcock's latest and most complete jigs, having a capacity of 100 tons per day.

Girilambone Copper Mine.

(Main Drive, No. 1 level.)

fficulties of concentration, a few possible improvements in manipulation ggest themselves; the most important being preliminary sorting of the e on the surface in place of crushing everything as it comes from the rking faces. It is unquestionable that a good deal of absolute waste was ing to the jigs at the time of inspection, and adversely affecting the results portionately with the quantity added. If the sulphide ore was screened, d the larger material broken and sorted by cheap boy or elderly labour, a d proportion of waste could be at once discarded, and possibly a percentage smelting ore selected, the balance and the screenings going thence to the ncentrating machinery.

In view of the tendency to slime, the first crushing should not pass a er mesh than at present. If, however, the seconds offer sufficient induce- nt, a further and finer crushing might follow with further jigging, though better results would be obtained by use of buddles or vanners. Both latter are in extensive use in Montana, United States, where fine crushing d concentration are carried out on a large scale. The Anaconda Company understood to have adopted buddles wholly for the fines.

According to Dr. Peters, junior,[1] even with the most approved apparatus, d careful running, it is usually impracticable to concentrate sulphide ores copper with a loss of much less than 25 per cent. With copper glance and rnite, Dr. Peters' experience has been a loss of 33 per cent. in concentration. In large low-grade silicious deposits, it therefore becomes a question for nsideration, after careful testing, whether it would not be more advan- geous to waste a proportion of the ore in the "seconds" than attempt to ave it at an increased cost for further operations.

The following copy of one of the half-yearly returns of the Company's perations will reveal the nature and proportions of the different grades of ore raised, and the results of dressing and concentrating operations :—

THE GIRILAMBONE COPPER-MINING COMPANY (NO-LIABILITY). Half-year ending 30th June, 1898.

Ore raised and jigged—	tons.		per cent.		tons cwt.		*Copper contents.* tons cwt.
Carbonates	2,579	@	4·6	=	118 12	}	
Sulphides.....	3,263	@	3·1	=	101 3		283 12
Oxides	953	@	6·7	=	63 17	}	
	6,795						
Screened Ore—							
Carbonates	1,109	@	13·0	=	144 3	}	145 7
Sulphides.....	44	@	2·8	=	1 4		
	7,948						428 19
Jigged Ore—		*Producing.*					
Carbonates, No. 1 ...	464	@	10·9	=	50 11	}	
Sulphides, No. 1.....	706	@	6·5	=	45 17		139 10
Oxides, No. 1	273	@	15·8	=	43 2	}	
,, No. 2	859	@	3·5	=	30 0	}	
,, No. 3	64	@	4·0	=	2 11		101 8
Tailings	2,994	@	2·3	=	68 17	}	
Slimes and waste ...	1,435		....			(say)	42 14
Screened Ore—							283 12
Carbonates	1,109	@	13·0	=	144 3	}	145 7
Sulphides.....	44	@	1·4	=	1 4		
							428 19

[1] Modern Copper Smelting, 7th edition, 1895, p. 611.

Girilambone Copper Refinery.

(Ladling refined copper into ingot moulds.)

COBAR MINING DISTRICT—*continued.*

Output for the half-year ending 31st December, 1898:—Ore raised, 6,487 tons, averaging 3·85 per cent., equal to 249 tons 14 cwt. 3 qrs. 26 lb. of fine copper; consisting of—

	tons.
Sulphides	4,252
Carbonates	2,153
Oxides	82
	6,487
Ore jigged—Sulphides	4,252
Carbonates	871
Yielding respectively—Sulphide concentrates	958
Carbonates	442
	1,400 tons, of an average value of 8·76 per cent.,

together with 1,281 tons of unjigged 10 per cent. carbonates, making a total of 2,681tons sent to the furnaces for smelting. 2,371 tons smelted yielded 215 tons of fine copper.

The subsequent history corresponds with the earlier in its chequered character. Development has not been continuous, long periods of entire or partial idleness alternating with active work. For a number of years mining operations practically ceased, experimental tests were proceeding for recovery of the large amount of copper locked up in accummulated tailing heaps, with final adoption of a leaching process.

From the records of the Company, the total tonnage of ore extracted from the date of opening in 1881 to the end of 1907, amounted to 58,408 tons, and the total copper produced—1,141 tons 13 cwt. 1 qr. 19 lb.

The process of recovery since the adoption of the leaching process is illustrated in the following extracts from the Company's Half-yearly Reports:—

Leaching of tailings.—The oxidised tailings were treated with sulphuric acid in a vat, the resulting solution with sulphuretted hydrogen gas, and the copper precipitated with scrap-iron. This process was started in April, 1903, but serious leakage of cylinders caused a stoppage. The results achieved to 4th July, 1903, were as follows:—

Half-year ending 30th June, 1903.

Weight of tailings. Tons.	Copper contents. Per cent.	Total copper contents. Tons.	cwt.	qrs.	lb.
1,481	2·5	30	5	1	0
Copper precipitate obtained		19	12	2	0
Residues, 1,451 tons; copper contents, 0·65 %		9	8	2	0
Waste solution (say)		1	4	1	0
		30	5	1	0

Extraction of copper in form of precipitate equal to 64·8 per cent.

Half-year ending 31st December, 1903.

Weight of tailings. Tons.	Copper contents. Per cent.	Total copper contents. Tons.	cwt.	qrs.	lb.
2,626	1·96	51	9	3	0
Copper precipitate obtained		34	5	2	0
Residues, 2,575 tons; copper contents, 0·58 %		14	8	2	0
Waste solution (say)		2	5	3	0
		51	9	3	0

COBAR MINING DISTRICT—*continued.*

Further experiments in leaching resulted in installation of larger plant. Operations began in September with the following results to end of 31st December:—

Half-year ending 30th June, 1904, and 31st December, 1904.

Weight of tailings. Tons.	Copper contents. Per cent.	Total copper contents. Tons.	cwt.	qr.	lb.
2,477	2·46	60	19	1	8
Copper precipitate obtained		35	3	2	15

For the ensuing half-year the following results were recorded:—

Half-year ending 30th June, 1905.

From 7,241 tons of tailings, containing 2·14 per cent. of copper, the extraction was not more than 1·24 per cent., leaving 0·90 in the tailings. The presence of sulphides in the tailings caused this low extraction.

Half-year ending 31st December, 1905.

4,288 tons of tailings, containing 2·13 per cent. of copper, yielded 50 tons 8 cwt. of fine copper.

Half-year ending 30th June, 1906.

854 tons of tailings treated; particulars not given.

Half-year ending 31st December, 1906.

574½ tons of tailings treated for 8 tons 16 cwt. 2 qrs. 5 lb. fine copper.

Half-year ending 30th June, 1997.

1,344 tons of tailings treated for 17 tons 8 cwt. 3 qrs. 20 lb. refined copper.

Half-year ending 31st December, 1907.

1,222½ tons of tailings treated for a recovery of 14 tons 12 cwt. 1 qr. 14 lb. refined copper.

In 1899, 1,288 tons of ore and slag, averaging 3·91 per cent. of copper, were smelted in a small experimental blast furnace, for a return of 50 tons 8 cwt. of copper.

A new furnace (reported to be of the Orford type) of 500 tons capacity was also erected at considerable expense, but proved altogether unsuitable, after an intermittent trial from October to end of December.

Girilambone Company reconstructed February, 1902.

Magnetic separation tried in 1901.

From a quantity of ore sold to public smelters in certain years, it appears that the carbonate concentrates ran to about 12·5 per cent., the sulphides to 9·5 per cent., and Frue vanner fines to 12·8 per cent.

Pulveriser installed in 1904 for reducing coarser tailings.

Mine unwatered in 1905; a little ore won for furnaces. Work proceeding in Nos. 1, 2, and 3 levels in 1906 and 1907. Cobar sulphide supply stopped in 1907.

During the half-year ending December 31st, 1907, all work suspended, with exception of keeping mine unwatered and plant in repair, owing to fall in price of copper.

Girilambone District.—About three-quarters of a mile northerly from Girilambone Mine, Christensen and party took up a mineral conditional purchase of 40 acres, embracing a gossan outcrop, and sank 90 feet in it. A little carbonate of copper was obtained from the bottom of the shaft.

About 3 miles north-westerly, Hartman and party opened another gossan outcrop, under aid from the Prospecting Vote, to a depth of 150 feet, and drove upon it for 200 feet. In the drive, carbonate of copper veins were cut, but were not payable.

COBAR MINING DISTRICT—*continued.*

Day Bros.' Mine.—Portion 11, parish Wilgabone, county Canbelego (A. Leslie's settlement lease). Chlorite schist, with traces of copper ores. Aided to sink (P.B. $\frac{2}{0}\frac{4}{5}\frac{3}{5}$) from 25 feet to 150 feet, and cross-cut 100 feet east and west. No payable ore discovered.

Elletson and Party's prospecting claim, on a line with Day Bros. and Great Western Mine, 8 miles from Girilambone. Sample from a 70 feet shaft in chlorite schist, with stains of copper carbonate, yielded—

No. 07-7488—Copper, 0·8 per cent.
Traces of gold and silver.

Cobar Division.

Gladstone Mine.—Wrightville, Cobar. Inspector Polkinghorne reports shaft 186 feet deep. Cross-cut east from bottom 20 feet (on 2nd July, 1908). At 2 feet, 7 feet, and 10 feet from shaft, rich grey sulphide veins cut, having thickness of 4, 2, and 3 inches. Balance of cross-cut in ferruginous slate and quartz.

Mount Hope Division.

Great Central Copper Mine.—Parish Mount Hope, county Blaxland. This mine was first opened about 1878, under the name of "McDowall's," after the discoverer. South Mount Hope, originally known as "Brown's" and afterwards as the Comet Mine, is now also included in the Great Central property.

The first official record is that by Mr. L. H. G. Young, Geological Surveyor, who visited the site in 1880, accompanied by the Writer. (Ann. Rept. 1880, pp. 260–1). Writing of South Mount Hope (Brown's), Mr. Young states:—"Here copper ore has been found in five or six places, but in my opinion the presence of a well-defined lode has not been established. The veins appear to run in a north and south direction, and are composed of quartz, earthy carbonates, red oxide, and a little grey and yellow sulphides; the rock adjoining the vein is a breccia of the porphyry of which the hill is composed."

Of McDowall's (Great Central) Mine, Mr. Young wrote:—"The mineral deposit on this lease consists of a large mass of porphyry breccia, the pieces of porphyry being cemented together by oxide of iron containing a little copper; thus an assay of some of the cementing matter has been made by Mr. W. A. Dixon, F.C.S., and gave 4·32 per cent. of copper. Two shafts have been sunk, one—I was told—to a depth of 70 feet; but as this was half full of water at the time of my visit, I cannot tell what light it has thrown on the value of the property. Amongst the materials excavated I noticed some earthy carbonates and a little rich red oxide of copper. For a distance of 50 yards round the main shaft the rock is literally seamed with veins of red oxide of iron, varying in thickness from a film to 2 inches."

Inspected by the Writer again in 1898.

The Central and Comet workings are situated on the north and south slopes of the Central Hill—a mass of porphyry of some elevation. A distance of nearly half a mile separates the extreme north and south workings. The principal outcrop occurs at the south end, where the Great Central Company's operations were carried on. Here the porphyry, for a width of about 300 feet, is stained with copper carbonates, and seamed with thin veins of ferruginous oxide of copper. Four shafts had been sunk very close together on a band of lode-stuff on the east side of the spur, and numerous shallow trenches and potholes were sunk on chutes of ore between the eastern and western

workings, but no crosscut has been extended across the intervening formation. The shafts were very rough, and inclined at all angles, making haulage difficult.

The greatest depth attained was only about 240 feet. At this level, sulphides take the place of the oxidised ores. A drive at this depth revealed an improved grade of yellow ore below the hauling shaft. A main shaft, with a proper system of levels and crosscuts, was badly needed. Judging from existing conditions, robbing the rich chutes, without regard to future developments, appeared to have been the method of winning.

The matrix of the oxidised ores is decomposed porphyry, and consequently is soft and earthy, requiring a plentiful water supply for efficient concentration of the leaner grades, which, unfortunately for then existing operations, was not available. One small tank, and a mine-supply equal to about 1,000 gallons per twenty-four hours, constituted the total provision. The surface configurations of the locality are eminently suitable for water conservation. An attempt was being made to turn the mine water to account in concentrating the leaner ores; but a glance at the jigs in operation, with such an inadequate supply, revealed a sludge, from which clean, or even approximately clean, work was an impossibility, in view of the constant re-use of the water. The jigs in use were modifications of the Handcock jig.

Following the strike of the lode northwards, a belt of hard felsitic rock (elvan) crosses the ridge obliquely to the north-west; hereabouts the lode has not been traced by surface prospecting. Over the ridge, however, defined ore channels are encountered, which have been followed some distance south in the Comet workings. The main shaft of the Comet has been sunk, 242 feet, and driven south as stated. Parallel ore veins occur here for a width equalling that of the Central workings. To the north from the shaft the country falls into a low saddle between the Central and a similar hill a short distance north. In this saddle is situated Brown's original discovery, known as South Mount Hope, an eastern lode distinct from that in the Comet.

On the east side of Central Hill, south of Brown's lode, two parallel lodes, one possessing a well-defined outcrop of ferruginous quartz, in which copper ore is visible, and gold, by assay, to the extent of 4 dwt. per ton. It has been opened in one place to a depth of about 50 feet, and the other lode—to the west—to 30 feet. It is reported that ore from these occurrences was sent to the smelters. They are worthy more systematic testing than they have yet received; indeed, the whole cupriferous belt embraced by the Great Central property offers considerable inducement for systematic proving, which should precede any present large outlay for improved plant. The latter could then be laid down on lines commensurate with the developments. The oxidised ores were hand-picked, the firsts going to the smelters, the balance to the breakers and jigs; the sulphides all pass through the latter. The former were concentrated to about 14 per cent., and the latter to 12 per cent. Ironstone flux was obtained from the mine, and fireclay from the New Mount Hope deposit. The smelting plant consisted of three reverberatory furnaces—two reducing and one refining.

In 1900 the mine was taken over by the Option and Development Company, water being conserved and up-to-date machinery installed. Closed down at end of 1902. The shaft not disclosing the ore-bodies expected, the lowest level reached being 500 feet. 400 feet of driving was done at the 300 and 500 feet levels. The treatment plant erected by the

COBAR MINING DISTRICT—*continued.*

new company is reported to have cost about £16,000, but no attempt was made to put the plant in operation, owing to the small quantity of ore obtained. A striking instance of putting the "cart before the horse."

RETURNS of the yearly output and progress of the Great Central Copper Mine, compiled from the Annual Reports of the Department of Mines.

Year.	Ore raised.	Copper produced.	Value.	Deepest Shaft.	Deepest level.	Width of lode.	No. of Furnaces.	Value of plant.	Men employed.	Remarks.
	tons.	tons.	£	ft.	ft.			£		
1881	..	..	..	..	..	..	..	..	..	
1882	..	..	..	..	..	..	..	..	..	
1883	1,139	187	8,700	120	120	3 in. to 11 ft.	..	2,000	102	Total ore raised since starting, 1,551 tons.
1884	2,221	336	14,784	206	150	1 ft. to 13 ft.	..	4,000	150	
1885	..	..	..	..	..	..	..	..	..	Work suspended owing to low price of copper.
1886	..									
1887	..	..	..	..	..	..	..	..	..	
1888	..	142	..	..	..	..	..	..	130	Working eleven months.
1889	2,000	394	15,740	..	..	..	..	..	90	
1890	1,855	228	..	242	192	..	..	..	70	1,667 tons smelted.
1891	..	..	..	..	..	..	..	..	..	Mine closed.
1892	..	..	..	..	..	..	..	..	..	"
1893	..	..	..	..	..	..	..	..	..	"
1894	..	..	..	..	..	..	..	..	..	Ore to the value of £4,000 raised.
1895	900	134	5,093	242	192	..	..	..	..	
1896	454	55	2,195	..	..	..	..	..	..	Six months' work only.
1897	1,200	..	..	..	..	..	..	..	50	Mine let on tribute. Ore raised valued at £4,500. Engaged repairing plant, &c.
1898	1,100	110	5,800	..	..	..	..	..	..	

The late Mr. J. Doust, Managing Trustee for the previous owners of the mine, stated that the total output of the mine, according to the mine books in his possession, amounted to 2,170 tons of refined copper, of an assay value of from 99·15 to 99·65 per cent. The refined metal was free from deleterious impurities.

Cobar Division.

Great Cobar Copper Mine Co.—Parish Cobar, county Robinson, 110 miles south of Bourke, on the Darling River, 80 miles west of Nyngan, on the Bogan River, and 459 miles west by rail from Sydney. The Cobar Company's property consists of 1,100 acres of freehold, on a portion of which the town of Cobar is built.

Historical.—Cobar ("Hopah" in the aboriginal) signifies "raddle" (earthy iron oxide), and from the outcrop of the copper lode the aboriginals formerly obtained it for decorative purposes. In process of time a small circular excavation resulted from scooping out the soft ochreous material, forming a catchment for water and serving as a "native well."

The native name "Hopah" sounds like a corruption of "copper," but the genuineness of the meaning given it by an old Bogan River aboriginal in 1898, has recently been strikingly verified by another native of the district—Jack Torrance—for twenty-two years black-tracker in the Police Force.

In 1869, two Danes—Thomas Hartman and Charles Campbell—engaged boring for water in the district, camped at the "native well," and were attracted by the rusty sediment at the bottom, and the blue and green stains on the sides, and for a limited extent around it. Neither were, at that time, acquainted with copper ores. The story of the facts leading to the discovery of the real nature of the colour which arrested their attention is in dispute. Briefly, the account given by Hartman is that, on raking the ashes of the camp fire made alongside the well, he discovered beads of metallic copper, which he took direct to Bourke and there displayed. The

. Lowell Price. **Great Cobar Copper Mining Company.**

(Main Stack, brick-lined, self-contained. Height 200 feet; inside diameter at top 14 feet.)

conflicting story is that Hartman and Campbell, taking with them specimens of the coloured rock, proceeded on their journey until they fell in with a Cornish woman—Mrs. Kruge,—the wife of a countryman, who at once recognised the true nature of the colouring. On ascertaining its value, Hartman and Campbell returned to Cobar, and subsequently (on the 6th of October, 1870, according to Mr. Russell Barton), at Fort Bourke, secured the land as a mineral conditional purchase of 40 acres, in conjunction with the late Joseph Becker of that place. The latter, in May and June, 1871, also secured 40-acre blocks adjoining the Cobar on the north and south. In January, 1876, the South Cobar Mining Company was amalgamated with the Cobar under the present title of "Great Cobar."

From inspection of the portion of the outcrop and the native well, remaining intact in 1908, it seems improbable that native copper occurred directly on the surface, in which form alone could it have been melted into the beads reported by Hartman, for there is no question that the small camp fire could not have reduced the metal from its ores. Circumstantial evidence, therefore, supports the rival story; but none the less the credit of discovery rests with Hartman and Campbell, whose intelligent curiosity prompted transport of specimens which had drawn their attention. Lack of this valuable trait has frequently led to sources of wealth being undeveloped for years, until the advent of one of greater inquisitiveness or knowledge. In contrast to the action of the Cobar discoverers, the Writer recalls the statement of a shepherd he met at Mount Hope Copper-mine shortly after its discovery. Located within a few hundred yards of the outcrop on Mount Hope, he had often remarked the blue and green colours as he followed his flock over it, but intelligent prompting was wanting in this case.

Prior to the discovery of payable tin ore in New England in 1872, the gold miners were greatly hampered by the heavy black sand (tin oxide) in their sluices, which caused endless trouble in separating the gold. Instances might be multiplied, but sufficient has been written to illustrate the value of intelligent curiosity in regard to Nature's mineral treasures, many of which—unlike copper—she dresses in very unattractive garb, but which, nevertheless, possess distinctive characteristics, either of form or gravity, which compel attention. Notice might here be drawn to the ready means of identification available to even the poorest which the Government of the State has wisely established—a free laboratory and experts to determine the nature and value of any substance discovered, without cost to inquirers, have been provided in connection with the Department of Mines.

Shortly after operations were started at Cobar by Hartman and Campbell, Mr. Russell Barton—since well known in connection with copper-mining in the State—passing the locality, visited the mine, and, being greatly impressed with its possibilities, from the insight he had gained in South Australian copper-mining, purchased an interest. Rich ores were extracted from near the surface and dispatched by team to the Darling River at Bourke, and thence by river steamer to Port Adelaide Smelting Works, South Australia. Some 3,000 tons are reported to have been thus disposed of at a profit.

In January, 1876, the Cobar and Southern Cobar Copper-mining Companies (Limited) were amalgamated under the title of the Great Cobar Copper-mining Company (Limited) of 80,000 shares of £1 each. (For particulars of the Southern Cobar Mine, *see* description under that title, page 245.)

Extraordinary difficulties faced the new company. A mine situated 45 miles (railway measurement) from the sea-board, in an arid tract, destitute o natural drainage channels (the nearest being the Bogan River, 80 mile distant), subject to drought, with an unevenly distributed annual rainfall averaging only 17·21 inches according to the late Government Astronomer and a greedily absorbent sandy soil.

The nearest railway at the beginning of operations was Blayney (opene in November, 1876), distant by the present railway-line 287 miles from Cobar In April, 1877, the Orange extension was opened, which reduced the distanc to 267 miles. The ordinary roadway, however, probably covers a much greate distance between the points mentioned.

That the Company was enabled under such handicaps to pay dividends amounting to more than two and a half times the total capital, is eloquen testimony to the richness of the mine. In 1889 operations had to b suspended owing to the extremely low price of copper and excessive cost o transport. The failure of the Société des Metaux and the collapse of th "copper boom" it had originated were the direct causes of the Company' suspension, as an agreement had been entered into for a term of three year with the Société for the purchase of the entire output from the Cobar Min at £60 per ton on board ship at Sydney. In 1893, however, the mine wa let on tribute to the Great Cobar Mining Syndicate, which began operation when the average value of copper was but £39 per ton, and successfully introduced the cheaper and more rapid blast-furnace method of reduction which revolutionised the copper industry at Cobar. A previous attemp with blast-furnaces (not water-jacketed) was made in 1885, when three wer erected at a cost of £5,000. After a short campaign with charcoal fuel they were discarded, though the Mine Manager, Mr. J. Dunstan, regarded some o the experiments as satisfactory. 325 tons of ore were smelted in thes furnaces. The cost of charcoal alone would have rendered profitable workin impossible at this date. Rapid and certain railway transit has effecte no less complete a revolution in cost of production. Prior to the adven of the railway to Cobar in 1891, the Company was dependent on teamster for freightage to and from the mine, and the latter again were entirely dependent upon the seasons. During a drought in 1882–3, it was found almost impossible to maintain the necessary supply of firewood, whilst th stock of copper in the sheds at the mine increased to over 1,200 tons, owin to the impossibility of transport by team over 300 miles of drought-stricke country to the nearest railway.

The water supply at this period became so restricted that armed patrol guarded the only available tank, and doled out a scanty allowance to th residents. Travellers were allowed but one drink for themselves and horses

Significant of the changed conditions is the fact of continuous operation during subsequent disastrous and protracted droughts.

Cobar, like Broken Hill, affords a striking object lesson of the vita influence which mining exerts on the material progress and prosperity of a country. What other industry can compete with the rapidity of the restless energy with which it overcomes tremendous difficulties and reclaims aric tracts to civilisation?

During the operations of the Company from 1876 to 1893, 213,182 tons o ore were raised, and 23,610¾ tons of copper produced.

COBAR MINING DISTRICT—*continued.*

Geological and Descriptive.—In 1880 the Writer accompanied the late L. H. G. Young, Geological Surveyor, to Cobar. From the report published by the latter (Ann. Rept., 1880, p. 262), the following notes are extracted :—

"The workings are on what is known as the west lode. On the surface there appear the outcrops of two adjacent parallel lodes. It is my opinion, however, that all three form one lode, being only separated by pieces of country known to miners as 'horses.'

"The characteristic point in the Cobar Mine is the great variation in the width of the lode, namely, from a mere film to 100 feet. . . . . .

"The ore from the 50-fathom level is composed of solid yellow sulphide of copper; from the 39-fathom level, of carbonates, metallic copper in films, red oxide, grey sulphide and brown iron ore, the lode being fairly compact.

"At the 26-fathom level the ore is principally carbonate of copper, mixed with iron ore, while the lode is less compact."

The physical features of Cobar may be briefly described as a monotonous stretch of level country, above which a few hills and ridges of low elevation rise conspicuously. Cobar lode forms a low ridge, having a north and south trend. Fort Bourke and the Peak ridges, of greater elevation and length, have parallel trends south and east of the former. The country consists of sandstones and slates of probably Silurian age. On the Geological Map of the State, the elevated peaks have hitherto been coloured as Devonian, but from the Writer's observations, and the identification of Silurian fossils by the Palæontologist, Mr. W. S. Dun, in similar rocks at Bobadah, and also in the limestone between Cobar and Nymagee, as well as the extreme lithological contrast between the highly cleaved and folded rocks, and the outliers of approximately horizontally-bedded sandstones and conglomerates—noted particularly between Mount Hope and Euabalong, and at Mount Boppy—it is more than probable that the Cobar rocks are older than Devonian.

Confirmation of the Devonian age of the upper beds in the Mount Boppy district has recently been obtained through Mr. Johnson, analyst to the Mount Boppy Gold Mining Company, who procured for the Writer a collection of Marine Fossils of that age, from between Mount Boppy and Hermitage Station.

To the north-west of Cobar, on Mount Grenfell Station, Mr. C. A. Chesney, C.E., also obtained undoubted Devonian marine fossils, but the site has not yet been geologically examined. It will probably prove an outlier similar to those already alluded to.

The elevated areas at Cobar are the direct result of mineralisation, the indurating influence of which has rendered them less amenable to subaerial disintegration and degradation than the surrounding country. This feature possibly lessens the prospect of any extensive metalliferous deposits occurring in the level country. The principal indurating agencies in the high metalliferous areas are silica and iron. Infiltrated masses of the former are conspicuous at Fort Bourke Hill, where massive sandstones have been converted into quartzite by the investing silica. The slates of these regions are highly ferruginous.

Outcrop.—Contrary to the general idea, the Cobar copper lode did not make a really strong outcrop. In only one place, near the site of the native

well, did copper ores show at surface. Three small patches of iron oxid were exposed—two near the well, the third at the site chosen for "Renwick Shaft." The outcrop consists chiefly of highly ferruginous slate, which, i the case of the "middle" and "eastern" lodes (2½ and 4½ chains east of th main lode) is highly silicified. The "middle" lode only has been pierce below ground in a crosscut extended 140 feet from the 54-fathom level at th north end of the main workings, and also from the 34-fathom level nea Becker's Shaft. Twenty-one feet of mineralised slate in one instance and 3 feet in the other were passed through, constituting good concentrating loc stuff (yellow copper ore).

In 1885 horizontal drill bores of 330 and 238 feet were also put in ea from the 39-fathom levels, in sections 16 and 19, in search of the paral l eastern lodes, but nothing more than 10 or 11 feet of quartz, at a distance 200 feet east, was encountered in the slate country. Possibly blanks occu as in the main lode.

The comparatively small outcrops of gossan on the main lode afforded litt indication of the immense ore bodies below; neither does the outcrop of th "middle" lode betray the slightest surface evidence of its cupriferou contents beneath. Hence there is reason for anticipating the occurrenc of ore bodies, possibly of considerable extent in both the "middle" an "eastern" lodes, which are as yet practically intact. Both these lode possess strong outcrops of ferruginous slate and quartz. South of the mai shaft a crosscut was driven 90 feet east, but this was insufficient to reach th "middle" lode; cross-cuts at least 330 feet long are necessary to intersect th two eastern lodes.

Development.—The position of the mine, six years after the formation c the Company, is best presented by reproduction of the following extra from a report furnished to the Under Secretary for Mines by the Gener Manager, Mr. George Hardie[1]:—

"Three distinct lodes run through the property known as the 'east lode 'middle lode,' and 'west lode.' Operations thus far have been confine to the 'western lode,' upon which four shafts have been sunk—'Becker's to 324 feet, 'Barton's' to 324 feet, 'Hardie's' to 214 feet, 'Renwick's' 28 feet.

"Becker's Shaft.—Good ores exist from the surface to the bottom. A the 26-fathom level the lode in the shaft is 24 feet wide, composed carbonates and grey ores. At this level drives have been put in north 130 fee and south 270 feet, proving the lode to be on an average 18 feet wide, an worth 14 per cent. At 39-fathom level drives have been put in north 90 fe and south 110 feet, the lode averaging 12 feet throughout of good ores. A the 54-fathom level the lode is proved to be at least 17 feet wide of sulphuret worth 22 per cent.

"Barton's Shaft is 600 feet south of Becker's. At the 15-fathom lev drives have been put in 191 feet, the lode averaging 15 feet of goo carbonates. At the 26-fathom level drives have been put in north 180 fee and south 161 feet—the lode throughout these drives will average 40 fe wide of grey, carbonate, and oxide ores of good quality. At the 39-fatho level drives are in north 136 feet, and south 80 feet, the lode throughou being fully 15 feet wide, with 14 per cent. At the 54-fathom level the sam sulphurets precisely have been cut as in Becker's Shaft at the same level.

[1] Ann. Rept. Dept. Mines for 1878, p. 24.

Great Cobar Copper Mine.

(90-fathom level. **Massive sulphide ore in face.**)

"Hardie's Shaft, 180 feet south of Barton's, is down 214 feet, with good ...e to be found in every winze and drive.

"Renwick's Shaft, 260 feet south of Hardie's, is connected with Hardie's ... the 15 and 26-fathom levels, proving the existence of first-class ores. No ...ork has been done south of Renwick's Shaft.

"Barton's Shaft is the main shaft, and is fitted with skids and cages to ...e 54-fathom level. A 40-horse power engine does all the hauling, works ...e ore breakers, also rollers for crushing fireclay, and saw-mills, etc.; and ... due time will work one of Handcock's patent jiggers specially designed ...r treating poor ores.

"Furnaces.—There are eight furnaces in full work—six reducing, one ...asting, and one refining. The present output is about 40 tons of fine ...opper per week. Additional furnaces are being erected with all speed.

"Tanks.—The Company has expended several thousand pounds in con...erving water, and has just completed a 10,000-yard tank in addition to their ...revious supply.

"Output.—The output of the past year is 1,468 tons of fine copper, valued ...£88,000.

"This mine has been at work three and a half years, during which period 993 tons of ore have been smelted, yielding 2,683 tons of refined copper ...ich assays 99·5 to 99·60 per cent.), valued at £160,980."

The population of Cobar at this time was estimated at 1,000.

Notes by the Writer in 1898.

The deepest shaft was 90 fathoms (540 feet). From this level drill bores were ... down diagonally to a depth of 120 feet, proving a width of lode equal 40 feet, and the ore tenor about 4 per cent. copper. Water was struck at ... feet in the bore. At the north end the Cobar lode splits; the eastern ...nch made into good ore, but the western had not been followed. The ...rking faces at the 74 and 90-fathom levels equalled 50 feet each in width, ...reasing in some places to 70 feet, of solid iron sulphides, containing ...rying proportions of copper pyrites.

The oxidized zone extended to about the 250-foot level. Though a small ...portion of oxidized ores was still being obtained from this zone, the visible ...pply had been practically exhausted.

Winning the Ore. — Wherever possible the Cobar Syndicate adopted ...e contract system in stoping and trucking below ground, with satisfactory ...sults to both parties. Drilling was practically performed by compressed ...ir drills, though a few contract parties were still using hand drills. The ...ontract price for mining was about 4s. per ton. The output amounted to ...bout 2,000 tons per week. Two additional blast furnaces were being erected, ...or which a larger output was necessary. It, however, could not be increased ...eyond a moderate total, because of limited shaft room.

Though electric lighting has been installed above ground, it had not ...een introduced below. The adoption of ordinary coal miners' oil lamps, ...owever, is a considerable advance on candles, both as regards light and ...onvenience, especially for the truckers.

Haulage was necessarily comparatively slow, owing to the very restricted ...imensions of the two working shafts. On reaching the surface, the loaded ...rucks were run to the heap-roasting ground on the east fall of the ridge, ...lose to the shafts, and their contents dumped directly on to the heaps in ...ourse of preparation.

Since the advent of blast-furnaces the old tips had been turned over and carefully sorted, the great bulk of the discarded material being turned to advantage, as it served admirably for fluxing purposes, yielding at the same time its quota of valuable metal. Likewise from the earlier fillings below ground, and from the walls of the lode, much low-grade, yet workable, ore was extracted, which had been discarded whilst following the richer central portions of the lodes.

Composition of the Ores.—The composition of the rich ores from the upper levels may be well studied in the following analyses made by Mr. W. A. Dixon (Ann. Rept., 1878, pp. 25–29). It will be observed that bismuth was present in marked quantity, but apparently the major portion of it was eliminated during smelting operations, as revealed by the analysis of the copper produced from the ores analysed (No. 65). It is noticeable that in a recent analysis of drillings from the 50, 74, and 90-fathom levels (sulphide zone), its presence was not detected. Possibly it may be confined to certain regions of the lode, and in the oxidized zone leaching and re-deposition may have concentrated it in appreciable quantities.

With a view of increasing the malleability of the Cobar copper, about 400 tons of Nymagee regulus were once purchased to mix with it to reduce the effects of the bismuth, Nymagee ore being practically free from this injurious associate.

On the walls of the lode a little zinc-blende and galena make at intervals, which are roughly discarded at the surface.

ANALYSES of Cobar Copper Ores, by W. A. Dixon. (Ann. Rept., 1878, pp. 25-29.)

Assay Numbers.	56	57	58	59	60	61	62	63	64	65
Silica	4·26	2·06	·62	1·92	·90	20·68	·56	10·34	29·28	.....
Copper	22·84	54·06	37·87	54·93	26·47	63·24	57·42	42·79	38·23	99·346
Antimony	·61	Traces	Traces	Traces	·46	·13	Traces	..	..	·029
Bismuth	2·11	1·47	1·96	2·58	2·17	1·16	·95	1·24	·21	·419
Lead	·27	·41	·45	.	..	..	7·72	..	..	·086
Arsenic	Traces	..	..	..	..	..	..	..	..	·011*
Iron	39·20	7·28	30·80	18·26	39·09	1·74	4·99	8·19	·78	·083
Zinc	·35	..	..	..	..	..	..	..	..	.....
Silver	Traces	Traces	..	..	..	..	..	..	..	·026=8 oz. per ton.
Nickel	..	Traces	Traces	..	..	..	..	..	..	.....
Magnesium	..	5·33	..	..	..	..	Traces	..	..	.....
Sulphur	24·11	4·18	18·63	14·48	27·46	5·70	11·67	..	..	.....
Carbonic Acid	..	9·97	..	..	..	Traces	5·87	14·37	17·47	.....
Water	..	3·41	..	..	..	..	4·60	7·04	3·79	.....
Water, oxygen (less water), loss, undermined, &c	6·25	11·83	10·00	7·83	3·39	7·33	6·15	15·43	10·24	
	100·00	100·00	100·00	100·00	100·00	100·00	100·00	100·00	100·00	100·000

* Traces of arsenic, nickel, cobalt, gold, loss, &c.

Sample 56—Copper pyrites and magnetite.
,, 57—Red oxide, copper glance, and ferric oxide.
,, 58—Copper pyrites, red oxide, and ferric oxide.
,, 59—Copper glance with ferric oxide.
,, 60—Copper pyrites and magnetite.
Sample 61—Copper glance and red oxide.
,, 62—Copper glance with malachite.
,, 63—Malachite with ferric oxide.
,, 64—Azurite.
,, 65—Copper from the above.

The nature of the sulphide ores at Cobar is partially revealed by the following analysis made in the Departmental Laboratory from drillings obtained by the Writer through the courtesy of Mr. T. Longworth, of the Cobar Syndicate. The sample was intended to represent an average of two days' drillings at the 50, 74, and 90 fathom levels; the copper contents,

however, may be disregarded, as they do not represent the average value of the ore in these levels, which, according to the smelting returns, ranges between 3·2 and 4·4 per cent. :—

Moisture at 100° C	0·20
Metallic iron	42·65
,, copper	10·15
,, lead	trace
,, zinc	,,
Silica	16·09
Alumina	0·44
Lime	absent
Magnesia	0·34
Sulphur	20·74
Sulphur trioxide (SO_3)	0·23
Oxygen (by difference)	9·16
	100·00

Silver, at the rate of 1 oz. 21 dwt. 21 grs. per ton.
Gold, a trace (under 2 dwt.) ,,

Note—A large amount of magnetite is present in this sample.

The proportion of iron is complicated by the admixture of fragments of metallic iron broken from the drills, which could not be removed without loss of a portion of the magnetic pyrites present.

Preliminary treatment of the Ores.—Though the Cobar sulphides are eminently suitable for partial pyritic smelting, the Syndicate had not deemed the advantage to be gained sufficient to induce it to incur the cost of providing a hot blast, without which it was then considered pyritic smelting could not be efficiently maintained. This process was subsequently adopted; and later (as explained elsewhere) it was accidentally discovered that the costly hot blast was not essential, providing the air-pressure was increased.

As the ore came from the stopes, it was piled on the roast-heaps without extra care. In forming the roast-heaps the V system was roughly followed; sufficient space being left between two adjacent heaps to admit of a third V-shaped filling between, when the former were underway. A rough foundation of wood was laid down, and, in the case of the later-formed central heap, carried up the sides of the adjoining heaps. Apparently little attention was paid to flues for ventilation; doubtless the large size of the ore-blocks afforded sufficient in the cavities between them to obviate the necessity of special preparation to secure it. The heaps took an elongated form from the raised tramway used for stowing, and contained from 2,000 to 4,000 tons. A little ragging was spread on the tops, but scarcely any on the sides. The fines apparently were little used for covering, being mostly roasted separately in a circular kiln excavated in the outcrop.

The absence of sufficient covering accounted for the evidence of too great heating in parts of the roast-heaps, where fusion sometimes took place to a considerable extent. About three weeks were allowed for a roast (according to Mr. T. Longworth, the managing shareholder). The roasting heaps were well situated on sloping ground, which afforded excellent drainage. The natural aridity of the climate disposed of the necessity for provision being made for recovery of copper carried away as soluble salts from roast-heaps during rainy weather.

Owing to the long campaign with reverberatory furnaces at Cobar, the country has been devastated of suitable firewood for a radius of many miles. The wood required for heap-roasting cost 15s. per ton for dry 5-foot lengths, and 12s. 6d. for green. The consumption of firewood in the reverberatory

furnaces averaged about 70,000 tons per annum. In 1889 a trial was made with coal from one of the top seams of the Dubbo Coal-field (Ballimore ?). Mixed with wood, it answered fairly well in a reverberatory furnace, and about equally as well mixed with charcoal in the blacksmith's forge.

(The Great Cobar, Limited, has now decided to use Lithgow coal for firing.)

Smelting.—The furnace charges consisted generally of the following proportions :—

8 cwt. of raw sulphides.
8 ,, of calcined sulphides.
4 ,, of oxidised ores, slate, dry gold and silver ores, &c.[1]
4 ,, of coke.

The first reduction brought the matte up to about 30 to 35 per cent. tenor, in which form it was sent to the Syndicate's roasting and refining plant at Lithgow, where some sixteen reverberatory furnaces are in use.

The smelting-plant at Cobar consisted of four 80-ton water-jacketed blast-furnaces, with a working capacity of about 120 tons per twenty-four hours, but it was announced that two additional furnaces were to be erected.

Gold in Cobar Copper Ores.—Though gold was early known to be present in the Cobar Mine, and in the free state was occasionally noticed in the oxidized ores, no attempt was made to turn it to account until the Cobar Syndicate began operations in 1893–4. In 1882 Mr. Russell Barton secured a specimen of malachite showing coarse gold, and the Company's caretaker (the late Mr. W. Gillard) had in his collection a specimen of slate from near the outcrop containing a rich seam of scaly gold.

In 1881 an assay was made in the Departmental Laboratory of a sample of the Cobar copper obtained by boring through several ingots, with the following results :—

Gold	2 oz. 12 dwt. 4 grs. per ton.
Silver	1 ,, 5 ,, 0 ,, ,,
Copper	92·65 per cent.

As these results were made known at the time it appears strange that no advantage was derived from the knowledge. Cobar copper, for years, must have proved a lucrative investment for metal-buyers in England, who secured it at a lower market rate than Chilian bars, notwithstanding its valuable gold contents. Possibly the difference in market value between the Cobar and Chili metals was sufficient to defray cost of further refining, leaving the precious metal as clear profit. Mr. Russell Barton (at one time Chairman of the Company) attributes the omission to the fluctuating results of tests of the surface ores, portions of which gave fair gold value, others almost negative results, a natural outcome of the leaching and re-precipitating processes to which the upper levels of the lode had been subjected. As gold is less susceptible to natural leaching solutions than copper, it remains to enrich the more gossany ores from which the copper had been wholly or in part removed. The re-precipitated or secondary copper ores would thus become richer and more concentrated, but impoverished in gold, hence the fluctuating returns of assay samples, which appear to have depreciated the importance of the presence of gold, even in small quantities, in the ores, notwithstanding the well-known collective influence of metallic copper on the precious metals in smelting. Mr. Barton states that the gold contents of the copper produced during early operations varied from half an ounce to 3 oz. per ton. Not till the latter half of 1894 did the Company draw

[1] When slag from the forehearths was used—about every second charge—it took the place of this item.

the attention of buyers to the presence of gold and silver in their copper in recoverable quantities. The immediate result was an advance of about £7 per ton over the current quotations for Chili bars.

The sulphides from the working stopes in 1898 were reported to yield from 2¼ to 3 dwt. of gold per ton. Concentration at the present day is extreme compared with past operations, and probably the average proportion of gold in the sulphides, though lower, is more constant and even than was the case in the oxidized ores. In smelting 10 to 20 and even 30 per cent. ores, concentration is very slight compared with smelting ores of a 2 or 3 per cent. tenor, hence the gold and silver contents are considerably higher in the metal produced from the latter. The market value of the Cobar copper is now enhanced some £20 odd per ton by the contained gold and silver. This great enrichment is not due, however, solely to concentration of the indigenous gold of the Cobar Mine, for the quantity is augmented by use of gold and silver ores from other mines as fluxes in the blast-furnaces; and herein lies the great potentiality of the pure iron and copper sulphides of Cobar; their importance as fluxing bases for dry (siliceous) gold and silver ores cannot well be over-estimated. At the Peak, about 5 miles south of the copper-mine, the Cobar Syndicate secured a gold and silver mine (Conly and Barrass'), and worked it in conjunction with the former. The better class of gold ore was treated in a battery locally; the lower grades, which, however, were fairly rich in silver—containing about 30 oz. per ton and 3 dwt. of gold—were carted to the smelting furnaces for fluxing purposes. The Peak lodestuff consisted of soft rotten slate, with harder cherty bands and quartzite; in the ferruginous joints and cavities silver-chloride was freely visible.

The sulphides of Cobar consist largely of pyrrhotite (magnetic pyrites composition Fe_7S_8 = iron = 60·5, sulphur = 39·5), with pyrite, and chalcopyrite (composition Cu_2S, Fe_2S_3 = iron = 30·5, copper = 34·6, sulphur = 34·9) equivalent to a smelting return of about 3¾ to 4½ per cent. of copper. They are comparatively very low in silica—16·09 per cent.—according to the analysis of the drillings already quoted; though not approaching the unique purity of Mount Lyell ore in this respect. The importance to the field of the low percentage of silica in the immense sulphide deposits of the Cobar Mine is very great, as it affords a cheap and efficient means of extracting the gold and silver contents of the ores of some of the neighbouring mines, especially those in which copper occurs too sparingly for separate metallurgical treatment, yet too pronounced for ordinary battery or cyanide processes. Silica is necessary in the furnace charge to combine with the abundant iron of the sulphides to form a fluid silicate of iron slag. The siliceous gold and silver ores of the adjacent mines are just what is requisite for proper fluxing requirements. According to Dr. Peters,[1] Junr., a siliceous schist or slate in itself is preferable to pure silica (quartz) in matte roasting and doubtless also in reducing. The advantage to a smelting company of being able to command siliceous flux having of itself intrinsic value is immense, whilst an equivalent benefit is derived by the owners of such ores. In some public smelting works a mutual gain is derivable from payment of the actual value of the gold and silver contents of dry siliceous ores, without deductions other than freight, in return for the necessary flux thus obtained almost free of expense.

[1] Modern Copper Smelting, 5th ed., 1892, p. 271.

GREAT COBAR COPPER MINE

CROSS SECTION OF LODE

Scale 0 100 200 Feet



(No. 10 cross-cut had penetrated 102 feet of ore up to 8th July, 1902.)

No true walls exist, the ore dying away gradually in the country the blanks between lenses. A marked distinction, however, is n between the channel slate and the west country, the latter being mor and blocky.

Great Cobar Copper Mine.

(90-fathom level. Lode, 70 ft. wide.)

Mr. J. D. Kendall, Consulting Engineer of the Cobar, Limited, estimated the ore *in sight* on the 31st December, 1907, as follows :—

In the Great Cobar Mine	.....	1,400,000 tons.
„ Chesney	„	499,999 „

Accompanying these figures with the following note :—"Although in the above figures the ore in the middle shoot has only been calculated to 75 feet below the 850-foot level, it should be stated the ore body has actually been proved at the 1,000-foot level to fully maintain its width and values."

Description of the New Plant being installed by Great Cobar, Limited.—By G. H. Blakemore.—The alterations and new plant on the Great Cobar Mine have been of an extensive nature. The total cost has exceeded £160,000. A brief description of the alterations is as follows :—

"A new main shaft, 15 feet 5 inches x 8 feet over all dimensions, has been sunk from the surface to the 1,000-feet level. It is divided into three compartments, two of which are for hauling, and one to contain pump-pipes, air-pipes, and ladder-way. The size of the hauling compartments is 7 feet 6 inches x 4 feet 6 inches inside diameter, and the pumping compartment is 7 feet 6 inches x 5 feet 1 inch. The shaft is equipped with a winding engine, made by Andrew Barclay and Sons. It consists of a pair of coupled horizontal non-condensing engines, cylinders 22 inches diameter x 48-inch stroke, governed by Corliss valve gear, Dash-pot release type. The drums are 10 feet diameter, grooved faces, one drum fast and one loose, width 4 feet. The loose drum is fitted with Hall's patent friction clutch, for throwing in or out of gear. The engine is fitted with steam brakes, as well as hand brakes ; its capacity is a winding speed of 2,000 feet per minute, with a load of ore of 2 tons. The ore, as it is delivered at the surface, will be crushed to a 4-inch ring, through an Hadfield rotary crusher, capable of crushing 120 tons of ore per hour. There are two of these crushers, each driven by 100-horse-power electric motors. The crushed ore will deliver from the breakers into a Babcock and Wilcox tray conveyor, which in turn will deliver into a small storage bin. From this storage bin the ore is drawn off into bogie wagons, each of 30 tons capacity, and hauled by electric locomotives to storage bins of, approximately, 2,000 tons capacity. From these large storage bins the ore is dropped into Pooley patent scales, which weigh out the charge required for the blast furnace. There are twenty-four of these scales fitted to the bins. From the scales the ore is dropped into 2-ton wagons, which will be hauled on to the furnace floor in sets of three or six by an electric winch developing about 75 horse-power. The ore will be hand-dumped into the furnaces. The furnaces stand on brick and concrete base 9 feet high from the ground. Each furnace is 56 inches wide by 240 inches long inside at the tuyeres. There are twenty tuyeres on each side, making forty in all. The inside diameter of the tuyere at the nose is 5 inches ; centre to centre of tuyere, 12 inches. The bottom of the furnace is a thick cast-iron base, which stands 3 feet 7 inches above the top of the brick and concrete foundation. The centre of the tuyeres above the brick base is 6 feet 7 inches, and the charging floor is 27 feet 6 inches above the top of the brick base. Each furnace is water-jacketed for a height of 17 feet above the centre of the tuyeres.

"There are ten lower-side jackets, two lower-end jackets, ten upper-side jackets, two upper-end jackets. The end section of the furnace is vertical ; the side section shows a bosh of, approximately, 7 inches in the length of the lower-side jackets, which are 10 feet long. The top jackets are 9 feet 11⅛ inches high.

"There are three such furnaces installed. With the three furnaces are four separators, so arranged that any one furnace can deliver the slag and matte

into two separators. Each separator is 18 feet diameter and 4 feet 6 inches deep, circular in shape, made of ⅝-inch steel plate, having one slag overflow and two matte tap-holes. All the slag and matte from the blast furnace will deliver into these settlers. The slag will overflow into pots of a capacity of 25 tons, which will be hauled to the dump by an electric locomotive, and there emptied of their contents by being turned with an electric motor. The matte is tapped into ladles of a capacity of 10 tons, which will be picked up by a 40-ton electric crane, and poured into 15 tons capacity converters.

"The furnaces are each supplied with a separate blower, of a capacity of 36,000 cubic feet of air per minute, at a pressure of 42 ounces per square inch. These blowers are coupled to separate engines made by Colin Marchent, and Morley. They are compound tandem horizontal engines, fitted with Morley's patent drop valve gear, actuated by a lay shaft and eccentrics. The cylinders are 15 inches and 22 inches diameter by a 36-inch stroke. Each engine is capable of developing 540 indicated horse-power at 100 revolutions per minute, with a steam pressure of 172 lb. per square inch.

"The blowers are arranged in such a fashion that the wind from any blower can be delivered to any furnace. The capacity of each furnace is expected to be about 500 tons per day.

"The converters are blown with air, provided from a single stage blowing engine, made by Walker Bros., of Wigan, England. This engine is a horizontal cross compound of steam, cylinders 18 inches and 38 inches, with 48-inch stroke. The air cylinders are 42 inches diameter. The steam valves are spring Corliss gear, with Walker Bros.' patent air valves on the air end. The capacity of the engine, at about 90 revolutions per minute, is 12,000 cubic feet of free air per minute at 15 lb. pressure.

"All these engines and blowers are contained in one engine-house, together with the following machinery:—Two air compressors, by Walker Bros., of Wigan, each of which are horizontal cross compound two-stage air-compressing engines, fitted with spring Corliss valve gear, with double eccentrics, the air valves being Walker's patent. The steam cylinders are 16 inches and 34 inches, the air cylinders are 19 inches and 31 inches, and the stroke is 42 inches. The approximate capacity of each is 3,000 cubic feet of free air at 80 lb. pressure, with a steam pressure of 170 lb.

"The electric installation in the same building consists of three sets of engines and alternators, together with one direct current converter for transforming alternating current, the transformed current to be used for lighting and part of the power service.

"The alternator engines are made by Browett and Lindley. They are tripple expansion high speed vertical engines, cylinders being 12½ inches and 17½ inches and 26 inches respectively, with a 12-inch stroke; speed, 375 revolutions per minute. These engines are each direct-coupled to a Siemens 300 K.W. 3-phase A.C. generator to operate at a 440-volt circuit. The direct-current converter mentioned above is driven by a Siemens induction motor; the direct-current generator output is 1,040 ampères at 250 volts. This current is used on the Converter Motors, Electric Locomotives, Winding Winch, and for light. The current is transformed down to 110 volts on the lighting circuit, and there are step-up transformers where required, to bring the current up to 3,000 volts.

"The steam for this plant is supplied by six Babcock and Wilcox water-tube boilers, each capable of developing 450 indicated horse-power at 170 lb. of steam, and the boilers are fitted with chain grate stokers, superheaters, and Green's economisers.



H. Lowell Price.

Great Cobar Copper Mining Company.

(Interior View of Smelter Building, showing Furnaces and Settlers nearing completion.)



H. Lowell Price. **Great Cobar Copper Mining Company.**

(Elevation of No. 1 Blast Furnace, showing slag mantle from No. 1 to No. 2

COBAR MINING DISTRICT—*continued*.

"The smoke from the blast furnace delivers out into a flue, the bottom of which is all hoppers. A settling chamber is arranged in the course of the flue, the bottom of which also consists of hoppers. The flue dust will be easily withdrawn in this way. The smoke finally is thrown into the air through a steel chimney, which is approximately 196 feet 6 inches high and 14 feet inside diameter at the top. The boiler smoke is also drawn off by this chimney.

"The installation of this plant will stop the further despatch of matte to Lithgow. Instead of matte being sent, copper in the form of "blister" will be despatched in the shape of cakes weighing about 2 cwt. These will be refined at Lithgow in the anode furnaces, and the gold and silver extracted as before by the electrolytic plant."

OUTPUT of the Cobar Copper Mine (and Cobar-Chesney from 1904).

Half-year ended—	Ore.	Equal to Copper.	Percentage.	
	tons.	tons.		
31 Dec., 1876	1,458	174	11·93	
30 June, 1877	2,350	255	10·85	
31 Dec., 1877	2,530	268	10·59	
30 June, 1878	3,651	600	16·43	
31 Dec., 1878	4,738	857	18·08	
30 June, 1879	5,610	876	15·61	
31 Dec., 1879	7,005	1,015	14·48	
30 June, 1880	8,334	1,181	14·70	
31 Dec., 1880	11,890	1,388	11·67	
30 June, 1881	9,930	1,163	11·71	
31 Dec., 1881	11,622	1,405	1·208	
30 June, 1882	5,882	942	16·00	
31 Dec., 1882	5,820	863	14·82	
30 June, 1883	6,772	955	14·10	Produced by the Great Cobar Copper Mining Company.
31 Dec., 1883	11,324	1,460	12·89	
30 June, 1884	11,876	1,361	11·46	
31 Dec., 1884	12,003	1,403	11·73	
30 June, 1885	11,558	1,064	9·20	
31 Dec., 1885	12,000	1,066	8·88	
30 June, 1886	14,000	1,093	7·80	
31 Dec., 1886	11,887	951	8·04	
30 June, 1887	10,840	888	8·01	
31 Dec., 1888	9,000	705	7·83	
30 June, 1888	5,500	416	7·56	
31 Dec., 1888	7,425	589	7·09	
*3 Aug., 1889	8,177	667¾	8·15	Eight months' output.
1895	38,278	1,694	4·42	
1896	63,185	2,708	4·09	
1897	64,262	2,492	3 87	
1898	111,557	3,424	3·06	
1899	123,834	3,746	3·02	
1900	114,465	3,475	3·03	Produced by the Great Cobar Syndicate.
1901	110,767	3,206	2·89	
1902	89,634	2,415	2·69	
1903	141,781	3,333	2·35	
†1904	143,244	3,580	2·49	
1905	180,538	4,061	2·24	
To 21 Aug., 1906	108,032	3,108	2·87	
From 22 Aug. to 31 Dec., 1907	237,916	5,916	2·48	17,130 oz. gold, 98,769 oz. silver; produced by Great Cobar, Limited.
Total	1,740,675	66,768	3·83	

* Eight months' output. † From 1904, Cobar-Chesney output also included.

Cobar Mining District—*continued.*

Analysis of Great Cobar E.L.C. Copper by Messrs. Dixon and Byrn, Analysts, 97, Pitt-street, Sydney.

Gold	0·0001	per cent.
Silver	0·0013	,,
Antimony	Nil.	
Arsenic	0·0010	,,
Lead	0·0009	,,
Selenium	Trace.	
Telurium	Nil.	
Bismuth	0·0018	,,
Zinc	0·0018	,,
Nickel	0·0031	,,
Oxygen	0·037	= (suboxide of copper, 0·3317.
Copper	99·95462	(by difference).
	100·00000	

Conduction of sample according to Mr. G. H. Blakemore was 100·3 per cent. by Matthiessen's standard.

The following returns of gold and silver from the Great Cobar Mine, from 1898 to 31st December, 1906, including the Chesney Mine output from 1904 to 1906, and presumably the Peaks Gold and Silver Mine whilst working, as well as purchased ores at Lithgow, were kindly supplied by Dr. Richard Read, managing director of the Cobar Syndicate :—

Year.	Gold.	Silver.
	oz.	oz.
1898	16,215·	145,664·753
1899	13,698·004	59,586·517
1900	8,899·815	60,366·378
1901	7,252·815	52,335·655
1902	3,097·0	16,933·5
1903	11,078 055	40,402·501
1904	9,495·0	57,635·15
1905	9,159·875	53,206·599
1906	11,757·48	78,521·823
	90,652·8	564,652·8
Jan. 1 to Aug. 22, 1907*	7,566·	†50,536·
Aug. 23 to Dec. 31	17,130·	‡98,769·
Total production	115,348·8	713,957·8

* Estimated on the rate of the previous year's output.
† To date of transfer. ‡ Produced by Great Cobar, Limited.

Accompanying the above returns was the following note by Dr. Read :—"From 1898 to 1901 the copper was sold as auro-argentiferous material. During 1901 2 the electrolytic works were established at Lithgow, and all the gold and silver separated in them, the copper being shipped as electrolytic copper. The small quantity of gold and silver returned for 1902 is accounted for by an accumulation of untreated auro-argentiferous deposit in the vats during that year."

H. Lowell Price.

Great Cobar Copper Mining Company.

(Nos. 1 and 2 Converter Vessels on blowing stands, with movable hoods, leading to dust chamber at back.)

Cobar Mining District—*continued.*

The southern portion of the Great Cobar lode was originally floated as the Southern Cobar Copper Mine. The following notes are printed as a record:—

Taken up by Joseph Becker in May or June, 1871, adjoining the Cobar Mine on the south. Worked by the Southern Cobar Copper-mining Company Limited, until January, 1876, when the two mines were amalgamated under the title of the Great Cobar Copper Mine.

Renwick's Shaft, frequently mentioned in the reports of the Great Cobar Company, formed the main shaft of the Southern Company. It was sunk within about 40 feet of the south boundary of the Cobar property.

Though this mine became so early incorporated with the main mine, it is interesting to regard it separately up to the time of amalgamation, as the prospecting operations therein have an important bearing on the prospects of the southern continuation of the Cobar lode, in which direction work is not now proceeding.

The Southern Cobar Company was floated with a capital of 80,000 shares of £1 each.

The following particulars have been extracted from the half-yearly reports of the Company:—

Fourth Half-yearly Report, 26th August, 1874.—Main shaft 40½ fathoms, lode 20 feet wide. Preparations for two furnaces being made.

During the half-year 220 tons of good ore raised, and 150 tons despatched from the mine. The quality of the ore can be judged from the following account sales from Adelaide:—

Tons.	Assay per cent.	Net return.		
		£	s.	d.
15	40⅜	294	18	10
58	35¾	1,204	2	4
22	26⅜			
14	27⅜	305	2	4
8	43½			
5	44⅝	109	16	6
12	39¼	243	3	5
4	26⅜			
13	36⅜	231	9	3
15	37⅛	610	4	9
4	26¼			
14	42¼			
3	43	63	5	1
23¼	44	542	7	4
30½	42	671	14	9
6½	43½	150	16	5
18	42⅜	475	3	1
12⅜	39½	264	4	8
		£5,166	8	9

During the half-year ending 31st December, 1874, the main shaft was deepened to 46 fathoms. At 35 fathoms the lode was cut in a cross drive west 122 feet from the shaft, and was found to be only 7 inches thick. A winze sunk, following the lode from the 25-fathom level to the 35-fathom, proved it small and unprofitable.

Cobar Mining District—*continued*.

Operations during the sixth half-year were confined to raising ore from the 15 to 25 fathom levels, and to prospecting. No ore was obtained in either the 35 or 45 fathom levels.

At the 35-fathom level the lode channel was driven on 247 feet north, 24 feet of which alone bore stains of copper. The lode varied in width from 3 inches to 3 feet, consisting principally of slate (in some places quartz), strongly stained with iron.

At the 45-fathom level the lode, intersected in a crosscut west 176 feet in length, was contracted to a mere division in the strata, showing no signs of copper.

During the first half of 1875 two smelting furnaces were completed and a third begun; 316 tons of ore were smelted, yielding about 45 tons of coarse copper; ore at grass valued at £3,945.

Great Cobar North Mine, adjoining the Great Cobar Copper-mine on the north. Prospected by the original North Cobar Company, by three shafts along the strike of the Cobar lode, close to the boundary, without, however, disclosing workable ore, though a little lean ore was struck in No. 3 shaft.

Later, for some unaccountable reason, a shaft was sunk 500 feet west of the strike to a depth of 520 feet, and a crosscut started east from the 500-feet level.

In 1906 the property was reported to have been purchased by the present Great Cobar North Copper-mining Company, Limited, on the strength of surface indications of a strong lode below, discovered (?) by the electric ore-finder.

The West Shaft was thereupon unwatered, and the crosscut extended 605 feet, or 100 feet east of No. 3 shaft on the Cobar strike, without encountering any more favourable indications than previously disclosed by the strike shaft.

The latter was connected by a rise from the tunnel level, and a winze sunk 40 feet below it (at date of inspection in October, 1907).

For a width of 22 feet west, including the shaft, slate, with leaders of quartz, carries copper pyrites very sparingly. The winze was sunk in the best portion, where more copper sulphide was developed for a width of about 2 feet, a sample of which is reported to have assayed 4 per cent. Four feet of similar lodestuff was reported at the bottom of the winze, but water prevented close inspection of the lower part; a little galena is also associated with the copper sulphide. A small sample of picked clean ore from the lode-stuff raised in sinking the winze assayed:—

No. 07-7425—Copper, 8·70 per cent.
Gold, a trace
Silver, 15 dwt. 6 grs. } per ton.

An average sample of all the material raised from the 22-feet crosscut in mineralised lodestuff and the 40-feet winze yielded:—

No. 07-7424—Copper, 0·25 per cent.
Gold, a trace
Silver, 4 dwt. 8 grs. } per ton.

The strike of the orey belt was driven on 62 feet north, without, however, disclosing any metal values. To the south of the shaft, which is 24 feet south of the crosscut from the west shaft, a drive has been extended 31 feet in a blank, no ore showing in face.

It is proposed to deepen the shaft to 1,000 feet. The hope of this venture depends on the continuance of developments of a payable character in the

lower northern extensions of the Great Cobar workings. If these continue to the boundary, there are possibilities about or below 1,000 feet in the North Cobar Mine.

Great Eastern.—Twenty-seven miles by road from Cobar; on Meryula Pastoral Holding; about 8 miles east of homestead, and 14 from Meryula railway siding; parish Rochford, county Robinson.

Inspector Polkinghorne reported (P.B. $\frac{1}{0}\frac{1}{7}\frac{1}{1}$) a large outcrop of ironstone in slate, which at the 100-feet level in the shaft shows some very nice gossan. Aided to sink from 100 to 300 feet level.

At a later date the local Warden's bailiff reported traces of copper.

Nyngan Division.

Great Western Mine.—Portion 189 (?), A. Leslie's settlement lease; parish Wilgabone, county Canbelego.

Copper carbonate in schist. Surface indications first observed by J. McMillan about 1887. About 1901 a shaft was sunk to 75 feet.

In 1906 a Cobar syndicate re-opened it under the above name. A little ore at grass in 1907 was of a very silicious nature, being much mixed with quartz.

Average value, about 5 to 7 per cent. At 75 feet in the old shaft it is reported that the ore dipped away, none being visible in the shaft at that level.

The new proprietors, for some fanciful reason, started a new shaft some 150 feet away to N. 20° E., where there was not the slightest indication, and, instead of following whatever lodestuff there is in the site, proposed to sink 200 feet in blank country and then crosscut to the old shaft. From the indications in the latter the prospects are poor enough, without the dead work in view.

Ten tons of ore from this mine are reported to have yielded a net return of £17 at Lithgow.

Work suspended at end of 1907.

Canbelego Division.

Hermidale District.—The Budgery Copper lode, so far as proving at a considerable expenditure goes, consists of an isolated impregnation, like those of Great Cobar, Nymagee, Mount Hope, &c. Around the boundaries of the Budgery leases prospecting shafts have been sunk to considerable depths, with extensive crosscutting, but all failed to raise even a colour of copper ore. Many of these ventures, unfortunately, were floated on the strength of the one discovery, and the shares boomed and inflated on the market—most unjustifiably, for never at any stage were there any prospects in the majority of them. The following were floated round the Budgery:—

Budgery Reward Mine.
Budgery Reward North.
Budgery Reward South.
Budgery Wattle.
Budgery North Blocks.
North Budgery.
South Budgery.
South Budgery Extended, and others.
Budgeryrogan.
Budgery King.

COBAR MINING DISTRICT—*continued.*

Nyngan Division.

Hunter's Claim.—Four miles north-west of Girilambone. Described by Inspector D. Milne as a strong body of ironstone, with occasional splashes of copper carbonate.

Originally aid granted to Hartman and party to sink from 138 to 150 feet, and crosscut 150 feet. Specimens from 226 feet assayed 8 per cent. of copper. At 240 feet a drive was put in west.

Inspector J. R. Godfrey reported (P.B. $\frac{8}{0}\frac{4}{0}\frac{1}{4}\frac{8}{4}$) that the shaft was 137 feet deep on hanging wall; a crosscut driven west from this level, and from it a winze sunk 103 feet = 240 feet. Lode became more mineralised with depth. No further work recorded.

Judging from the material at surface, pyrites became prominent, but copper value very low.

Bobadah Division.

Long Panel Lode.—Three and a half miles east of Yellow Mountain, in parish Bluff, county Flinders. Outcrop traced for 152 feet, width 9 feet. Discovered by P. Fineren and T. Hart, July, 1908. Carbonates from outcrop assayed 11·8 per cent. copper.

Gilgunnia Division.

May Day Mine.—In this mine a considerable amount of prospecting has been done for gold, but, like the rest of the field, with little success, the gold being disseminated through slate near the junction of porphyry, but not in sufficiently concentrated form to pay for working. Lead carbonate occurs freely in small veins and vugs, and is usually rich in silver. The metalliferous belt at the May Day is upwards of 100 feet in width. It strikes about north-east, with a south-easterly underlay. At 85 feet in the north-east shaft copper carbonate and red oxide made their appearance, and continued to 102 feet. These ores occur in a width of about 3 feet, and at 102 feet dipped out of the shaft. The ore is of good quality, but further testing is necessary to determine quantity. A sample of carbonate of copper and carbonate of lead, assayed $\frac{8}{0}\frac{8}{0}\frac{1}{0}\frac{0}{0}$, yielded copper 7·84 per cent., lead 5·94 per cent., and silver 16 oz. 19 dwt. 17 grs. per ton.

Nyngan Division.

Moondyke Copper Mine.—Nine miles south of Girilambone Railway Station, parish Gidalambone, county Canbelego, 5 miles from railway line.

Inspector R. Schloesser reported (P.B. $\frac{2}{0}\frac{0}{1}\frac{0}{0}\frac{0}{0}$) carbonates and specks of grey ore in chlorite and talc schist.

Aided to sink from 23 feet to 53 feet, and to crosscut 20 feet at bottom.

At 40 feet carbonates in shaly rock assayed 8 per cent. copper.

Inspector J. Polkinghorne reported (P.B. $\frac{3}{0}\frac{8}{0}\frac{8}{0}\frac{0}{0}$), that the previous party sank 43 feet. A new party crosscut west 25 feet, and exposed lode 6 feet wide; then continued shaft to 55 feet; copper showing at that depth.

Further aided to continue to 100 feet. At 85 feet drove north-west. About 5 tons of fair ore on surface, obtained within 30 feet of surface. No further record.

Canbelego Division.

Mount Boppy Copper Mine (*formerly New Burra Burra*).—Portions 50 and 51, parish Buppe, county Mouramba, 6 miles southerly from Boppy Mount Railway Station, and 4 from Canbelego. Discovered by W. Frost.

Strike N.W. in slate and sandstone close to junction of porphyry. Dip slight to N.E. Lodestuff—slate, quartzite, and gossan. Ores—carbonates, black oxide, and yellow sulphide.

Length of proving (in October, 1907) about 150 feet, depth 200 feet. Gross output in recent campaign about 500 tons. 380 tons disposed of during 1907 for £1,800.

History.—First lease taken up in 1886. At 13 feet carbonates and grey ore were struck in the lode, which had a thickness of 5 feet. 30 tons of picked ore assayed 38½ per cent. of copper.

In 1887 little work was done, the lease being sold to a Cobar syndicate.

In 1888 mining was suspended, owing to scarcity of water; a tank, however, was being excavated, and a small reverberatory furnace erected.

In 1889 a quantity of ore was reduced to matte, but the quantity was not stated.

In 1890 500 tons of ore were raised, and about 6 tons of copper produced.

In 1891 stoping and smelting ceased, and Government aid was granted to further explore the lode.

In 1893 the mine was closed.

In 1897 Inspector D. Milne reported that the lode was being prospected; the main shaft had reached the 200-feet level, from which a crosscut 70 feet west exposed bunches of sulphides.

In 1898 compulsory sale of surface gear put an end to operations.

Further aid was granted for sinking in 1901 (P.B. $\frac{£2}{£1}$), and again in 1902 (P.B. $\frac{£2}{£2}$) for testing the east split of lode from 20 to 70 feet, and to crosscut 50 feet; resulting in discovery of a width of 15 feet of carbonate veins and strings of low grade. Aid granted to drive along this line for 50 feet.

Re-opened about 1904. Company formed to work it in November, 1906.

Position in October, 1907:—Principal workings in M.L. 10. Two lodes—east and west—60 feet apart, striking N. 60° W. East lode vertical; west lode dips 12° to 15° to 90 feet, thence vertical. East lode, shaft and winze sunk 259 feet; west lode, 200 feet. Length of proving—east lode, 100 feet; west lode, 120 feet. Levels driven at 90 and 200 feet in both shafts; and crosscuts connecting both lodes at these levels.

The sulphide zone of the *east lode* has been opened for about 100 feet. Lode about 3 feet wide; ore occurs in lenses of pure quality; rest of formation, dredgy quartz and slate. Very little iron pyrites present. Winze 59 feet below 200-feet level, filled with water; ore in it reported to be of good quality; a little still visible in roof above winze.

Channel narrow at north end of level, evidently a blank. To south, channel filled with dredgy material; should be driven on.

The *west lode* has been intersected by crosscut from the north end of 200-feet level in east lode. From this point north-westerly good ore was followed for some distance up to 10 feet in width. At 60 feet from the crosscut, however, it is narrow, but widens underfoot.

To the south-east, beyond crosscut, the lens thins to about 1 foot of rich ore, and to a mere thread at 50 feet. A little ore is, however, showing on east wall. Channel being defined, should be driven on.

A crosscut was driven N. 30° E. for 50 feet to the porphyry contact, which revealed no ore.

Water making freely above 200-feet level; winze below was dry, but filled from upper levels.

The ore raised from the large lens in west lode is of good grade. At surface it is broken, and hand-picked for "firsts." Fines from mining and spalling

is screened. The screened ore is then concentrated in four small handjigs. These two classes are despatched for sale at Customs Smelting Works.

The "seconds" from hand-picking floors are stacked, probably aggregating several hundred tons.

The following assays of carefully selected average samples of the different classes reveal their quality :—

No. of Assay.	Class of Ore.	Copper.	Iron.	Sulphur	Silica.	Gold per ton.	Silver per ton.
		per cent	per cent	per cent	per cent	trace	dwt. grs.
07-7438	Average of "firsts"	18·95	....	....	....	,,	8 17
07-7439	,, "seconds" (stacked)	1·50	....	....	....	,,	trace
07-7437	,, "fines" from screens	8·55	14·42	7·94	49·00	,,	5 10
07-7434	,, "concentrates" from jigs.	16·22	21·42	16·07	28·70	,,	7 15
07-7436	,, "fines" from hutches	7·72	13·23	6·72	46·15	,,	5 10
07-7435	,, refuse from jigs.....	2·70	10·08	2·74	59·25	,,	3 6

Close to the main Mount Boppy copper workings a shaft has been sunk in the north block in soft, rotten slate without sign of ore. Southwards the lode outcrops through M.Ls. 50 and 51, and Mount Boppy South. In places gossany iron and ferruginous slate are prominent in the outcrop. Two shafts were sunk to 100 feet and 180 feet in M.L. 51. In the latter at 12 feet west in a crosscut about 20 feet of impregnated rock is reported to yield an average of about 2 per cent. of copper. A little carbonate and sulphide ore have been raised from it. A greenish pyritic slate on west wall doubtless accounts for the very ferruginous slate at surface.

In the South Mount Boppy shaft adjoining, a 50 feet shaft on the west side reveals decidedly encouraging prospects, 3 to 4 per cent. carbonates being raised in some quantity, which could be picked to higher grade.

From the data secured it appears that the Mount Boppy copper lode is formed of a series of lenses with blanks between. It is worthy of attention; but capital is necessary for proper development, both vertically and horizontally, before establishment of local smelting works.

The latest report, dated 12th March, 1908, records the depth of the winze as 70 feet below the 200-feet level. Driven 6 feet at bottom in solid yellow ore for full width of drive.

The first payment under an option was made about the same date.

During 1907, 380 tons of ore were disposed of for £1,800. (Ann. Rept. 1907, p. 51.)

Mount Hope Division.

Mount Hope Copper Mine (previously New Mount Hope).—Discovered by a miner named McDowell about 1878. In 1880 it was visited by Mr. L. H. G. Young, accompanied by the Writer. A shaft had been sunk, but the mine was practically abandoned at that date. Mr. Young reported ($\frac{1880}{p.\ 201}$) :—"The copper mines at Mount Hope may be divided into three outcrops, more or less in a line with each other, namely, Mount Hope, South Mount Hope, and McDowell's. Of these, Mount Hope is in iron sandstones, having a strike N. 7° E. and dipping 80° to the west, while the other two are in a porphyry formation. The copper at Mount Hope appears to occur in a defined lode, composed largely of quartz, argillaceous matter, and earthy blue and green carbonates of copper, with occasional masses of red and brown iron ore, and also some earthy red oxide of copper and grey sulphide. The main lode is 24 feet wide on the surface, and there are two parallel outcrops. The whole may, however, be looked upon as what is known to miners as a "blow," and affords no idea of what the width of the lode will be lower down. The lode has a strike N. 7° 30′ E.

Mount Hope Copper Mine.

"A shaft has been sunk to a depth of 60 feet on the main outcrop, and some earthy carbonates extracted and dressed. There being no means of descending the shaft, I was unable to ascertain the appearance of the lode at the bottom of it.

"Like most of the copper deposits in this district, the Mount Hope lode crops out on the top of a small hill."

Mr. Young stated the most probable cause of the elevation was mineralisation of the country enclosing the lode during process of mineral deposition.

The Mount Hope outcrop presents features common to both the Cobar and Nymagee lodes, viz., ferruginous slates and sandstones seamed with quartz veinlets, striking about N. 10° E. Mount Hope consists of a long low ridge. The median line, or backbone, consists of a thick bed of sandstone, quartzitic in character, and is flanked east and west by ferruginous slates and alternating bands of sandstone. The quartz veins which seam the rock occur horizontally as well as vertically. Silicification, oxidation, and cementation of iron salts have greatly indurated the strata, destroying the fissility of the slates, and converting the sandstones partly into quartzites. The matrix of the lode as a rule is exceedingly hard, particularly in the sulphide zone, where the ore consists of an impregnated fine-grained sandstone. This induration increases the cost of winning considerably. The ore bodies are not defined within "walls" (which are conspicuous by their absence); in other words, they consist of segregations or replacements in the country itself without definite boundaries.

As at Cobar and Nymagee, some of the surface ores were extracted by open cut at the one place where ores appeared in the outcrop. Below ground the longest longitudinal extension of ore measured about 400 feet, but was solid only for about 150 feet, the principal portion of this deposit having a width of from 60 to 80 feet. Beyond the furthest extension of this body of lodestuff ore has not yet been found, but practically no prospecting has been done beyond 100 feet north and south of the workings. It is regrettable that during the prosperous days of the mine no attempt was made to test the considerable extent of ground lying north and south, which presents favourable indications of mineralisation, though no copper ore appears at surface. Considering the large blanks in the Great Cobar Mine between the main ore bodies, it is possible that similar ones may occur at Mount Hope; at all events, a trial is justified. The occurrence of ore bodies as isolated masses in the country renders it possible to miss them—as happened in the early workings—between ordinary levels and crosscuts.

The oxidised ores consisted chiefly of earthy carbonates, with thin veins of red oxide and grey sulphide. As these ores were raised at date of inspection in 1898, the first grade went from the breaker to the charging bins; the seconds passed from the breaker to Cornish rolls, and thence to Cornish jigs. As raised, the ore averaged from 4 to 5 per cent.; by dressing and jigging it was brought up to 14 or 15 per cent.

Sulphide ore only is now being mined. Unfortunately, the fine sandstone matrix is extremely hard, and, still worse, iron sulphides are almost absent. The change to sulphides began about the 160-feet level, and passed completely into them at 270 feet. The sulphides, owing to the absence of iron pyrites, are high grade when clean, but are leanly distributed through the matrix.

The concentrating plant consisted at the time of six Cornish jigs, which performed very clean work when the ore was crushed to a finer mesh than

formerly, but their capacity was very limited, and considerable time was lo in discharging the hutches twice a week. The absence of a flow of wat prevented the hutchings (fines) from being as free from sludgy slime as wou be possible with a continuous flow and discharge. About 1 ton of ore in was obtained by this method of treatment.

The seconds consisted chiefly of light carbonates, having a reported ass value of from 5 to 6 per cent. of copper, though the later seconds of fin crushings appeared to fall below this estimate. Owing to the earth nature of the carbonates in the large heaps of seconds from the ear workings (7,000 to 8,000 tons, estimated), mechanical separation from th waste did not appear possible; a cheap leaching process alone would l effective.

The smelting-plant formerly consisted of five furnaces, but two only we then in use. Fire-bricks are made from a sandy clay obtained at a depth 60 feet, at a distance of 7 miles from the mine. Its composition may l studied in the section devoted to fireclays and bricks, where an analys appears. It was first discovered in sinking a well for water. Most durab bricks were made from it direct after crushing, being burned in one of the ol reverberatory furnaces. The Great Central and Crowl Creek Mines also dre their supplies from this source.

The furnace charge contained about 23 cwt. of ore, a larger charge not bein possible owing to its composition. It was made up as follows in barrow-load which run about six to the ton in ore and flux :—

4 barrows hutchwork (carb. and oxide fines).
2 ,, raggings (carb. and oxide fines).
1 barrow sulphides (hand-picked).
1 to 2 barrows picked slag (with prills).
1 barrow ironstone flux.
2 barrows charcoal.

Sometimes one of ashes was added. Four charges were reduced in twent four hours. Since adding sulphides, a cleaner slag resulted than formerly.

The ironstone flux was carted from Mount Allen, a distance of 10 miles, a formed a serious item in the expenditure. A large amount of this flux w used by the New Mount Hope Company before its auriferous nature w discovered, which resulted in the Mount Allen Gold-mining Company bei formed. Gold-mining operations were established and successfully mai tained for a time, until the yield fell below payable proportions. Cyanidati was afterwards resorted to for the large amount of ironstone tailings produc by battery treatment. The tailings were purchased by the copper compa at 7s. per ton for fluxing purposes, but the supply was stopped in view of t new treatment. The purchase, mining, and carriage of ironstone flux at t Mount Hope entailed an expenditure of 15s. per ton, which should exped the development of the sulphide resources of Mount Hope. Firewood c 6s. 6d. per ton, and charcoal 37s. 6d.

At the end of March, 1902, the mine was closed on account of copp falling below a figure which was remunerative to the company.

It was decided to meet the lower market by re-equipping the mine w modern appliances, but shareholders failed to respond with necessary capi The company was then wound up and later on the mine was sold by aucti

Mr. R. N. Kirk, Manager of the New Mount Hope Company, stated t the total output of the mine, from the commencement of operations on

Mount Hope Copper Smelting Works.

30th April, 1881, to 31st December, 1898, amounted to 5,070 tons 0 cwt. 3 qrs. 8 lb. of refined copper. After four years' idleness the mine was reopened in February, 1906, under a new proprietary.

RETURN of the yearly outputs and progress of the New Mount Hope Copper Mine, compiled from the Annual Reports of the Department of Mines.

Year.	Ore smelted.	Copper product.	Value.	Deepest shaft.	Deepest level.	Width of lode.	Number of furnaces.	Value of plant.	Men employed.	Remarks.
	tons.	tons.		ft.	ft.	ft.		£		
1881	2,088	431·0	..	268	150	(?)	Four Reverberatories.	7,612	200	Operations started by the New Mount Hope Copper Co. in April, 1881, but no returns are available for that and the following year.
1884	6,194	1258·0	..	340	270	10 to 50	....	..	236	
1885	3,795	635·0	..	..	..	..	....	..	..	Work suspended owing to low price of copper.
1886	..	..	..	..	..	..	....	..	..	A few hands employed at developmental work.
1887	..	..	..	..	..	..	....	..	..	Steps being taken to re-open mine
1888	1,187	137·0	..	..	..	..	....	..	..	Ore to the value of £4,800 raised; 1,187 tons smelted.
1889	1,870	260·0	..	..	..	..	....	..	..	
1890	1,143	218·0	..	340	340	68	....	700	46	Worked on tribute.
1891	1,094	208·2	..	340	340	58	....	700	36	" "
1892	(?)	190·0	..	340	340	..	....	..	40	" "
1893	(?)	(?)	..	340	340	..	....	..	40	" "
1894	892	135·0	..	340	340	..	....	..	36	" "
1895	858	143·5	..	340	340	58	....	..	38	" "
1896	1,092	141·5	..	340	340	..	....	..	36	" "
1897	734	97·3	..	340	340	..	....	..	40	" "
1898	992	131·6	..	360	..	..	....	..	..	" "
1899	662	103·7	..	..	..	..	....	..	..	Worked under tribute until July, 1900—then by the company.
1900	1,560	242·3	..	..	..	..	....	..	..	Produced from 2,212 tons of mine ore and 2,775 tons of tailings, concentrated to 1,560 tons of smelting ore.
1901	3,451	177·2	..	..	..	..	....	..	..	In 1900 the company installed new concentrating and other machinery.
To Mar. 1902	..	47·1	..	..	..	..	....	..	..	
1906	6,950	173	..	..	..	..	....	..	..	Re-opened in February, 1906.
1907	8,500	305	..	..	..	..	....	..	67	Worked continuously in 1907. Handcock jig added to concentrating plant.

Mount Hope District.—At Mount Allen some years since a tunnel on the north-west side was driven some distance in search of copper, but nothing of importance was discovered.

At Coan Peak, on the south-west side, a little copper has been discovered in porphyry. Three shafts were sunk to shallow depths, following a quartz vein. The occurrence is known locally as the Coan Copper Mine, Mineral Lease 33, parish Coan, county Blaxland, but no workable or defined ore body has been found.

Double Peak—locally known as "Dromedary"—consists of porphyry and slate. On the west side, opposite the village of Mount Allen, a rather extensive outcrop of magnetic iron occurs, in parts highly silicious. Stains of copper carbonates are visible in solid pieces of the magnetite. A considerable quantity of the latter was carted to Mount Hope for fluxing purposes. This site was originally opened for gold. In a shaft sunk 50 feet alongside the ironstone, pyrites was met, and in an eastern crosscut copper carbonates; but the latter was not followed, as gold was sought at

the time. On the top of the east peak, copper carbonates cropped out in a claim held by McGuire and party in 1898. A little further south, on the same line, gold was found in ironstone and ferruginous slate, from which various parcels yielded from 4 dwt. to 17 dwt. of gold per ton. The lodestuff closely resembles that of Mount Allen Gold Mine. Aid was granted to Hill and party to tunnel into the mountain at a level about 200 feet below the auriferous outcrop on the slope. At 340 feet the lodestuff was cut, consisting of soft slate with iron and copper pyrites, the latter, however, not in payable quantity.

Seven miles due north of Mount Hope, parish Mount Allen, county Blaxland, on Mount Allen Mountain, 6 miles south of Double Peak; 2½ miles west of main road to Mount Hope.

Inspector R. Schloesser reported (P.B. $\frac{4}{0}\frac{3}{2}\frac{2}{2}$):—Porphyry, with slate and sandstone. Bodies of gossan carrying copper ores extending into the porphyry. A shaft, previously sunk by a Mount Hope syndicate, had disclosed several small pockets of good grey ore. Aided to extend tunnel to 143 feet. Tunnel driven across chloritic slates, a few stains of copper in face at 145 feet. 25 feet further driving granted. Aid also granted to sink 40-feet shaft a further 25 feet. Copper stains showing in full width of shaft. No payable deposit disclosed in these operations.

Inspector Polkinghorne reported (P.B. $\frac{4}{0}\frac{3}{2}\frac{7}{2}$) veins of copper ore 22 miles north of Mount Hope, in parish Killen, county Blaxland.

(MUDGEE MINING DISTRICT.—*Dandaloo Division.**)

Mount Pleasant Copper Mine.—Albert Water Holes, M.L. 4, parish Alberts, county Kennedy. Thirteen miles from Bogan River at Dandaloo; 40 from Trangie Railway Station, and about seven from surveyed Bogan Gate-Bulbodney Railway line.

Discovered by C. J. Keenan, about April, 1898.

Strike N. 20° E., dip westerly 13 feet in 100 feet. Width, 4 to 5 feet; length of proving, 116 feet; depth, 100 feet. No visible outcrop of east lode. Very slight in main lode.

Two parallel lodes occur about 10 feet apart; workings on *west* or main lode. *East lode* reached by crosscut at 100-feet level. Width about 1 ft. 3 in. to 3 feet. Driven on 70 feet. Footwall well defined, polished and coated with flucan; evidencing permanence. Dip slightly east.

Between the lodes contorted schist occurs, with occasional copper stains and quartz.

The ores worked in the main lode occur as bunches and pockets, mostly grey ore and bornite; yellow sulphide zone not yet reached. General character of lodestuff silicious, but capable of dressing up to high grade. Ore lens pitches southerly. Driven on 70 feet at 100-feet level, and stoped up 15 feet, and for a total length of 110 feet, including higher levels. Pinched at north end, but will probably open on strike.

COBAR MINING DISTRICT.

Nymagee Division.

Nangeribone, p. 280.

North Nymagee Copper Mine, portions 4, 5, and 23, freehold, parish Priory Plains, county Mouramba.—Taken up adjoining the Nymagee Mine

* Should appear on page 294.

n 1880, and originally known as the Hartwood Mine. The south boundary f this property is but a short distance from the most northern open workngs of the Nymagee Mine, but notwithstanding a large amount of work, no efined payable ore body has yet been discovered. At the boundary two hafts have been sunk, 200 and 293 feet respectively, and connected by a rosscut at the 200-feet level; the connecting level intersects the strike of he Nymagee lode. At 30 feet west of the 200-feet shaft (No. 1), a channel. 3 feet wide, was cut in the crosscut. The filling consisted of broken ountry, with zinc-blende and a little galena, and very rarely copper pyrites. outherly, a short distance in the Nymagee Company's property, is an utcrop of ferruginous carbonate of lead, which apparently corresponds with he strike of the main lode.

Four hundred feet north from No. 1 shaft, No. 3 has been sunk 112 feet. A little copper ore was found near surface, but none is showing in the haft. The best deposit on this property was located 720 feet N. 55° V. of No. 1 shaft; here a bunch of good ore was stoped out some years go and sold to the Nymagee Company. The chute of ore was stoped 30 feet ong from the 70 to the 130-feet level. The main shaft is 400 feet deep in a ineralised belt about 15-feet wide, carrying a little copper sulphide which ight possibly be concentrated. Some better class ore has been obtained in drive along the ore channel southerly.

Inspector J. R. Godfrey reported deepest shaft in 1900 as 300 feet. Ore ised in 1900, 700 tons. No extensive ore bodies found. Small lenticular atches of rich ore occasionally met. Ore contains copper, lead, zinc, and lver.

Later developments: In No. 1 shaft, lode 4 to 5 feet wide at 300-feet evel; dip west at 15°.

No. 2 shaft, 400 feet: lode, 10 feet wide at 200-feet level; dip east at 5°; length proved, 200 feet; gross output, 2,000 tons.

An option was obtained in 1907 by the present holders of the Nymagee Mine, but was not exercised.

Nymagee Copper Mine, portions 1, 2, 11, 22, 23, parish Priory Plains, county Mouramba.—This mine was opened in 1880, having been floated into a company by Mr. Russell Barton. The earliest geological description dates from within three months of the beginning of mining operations, when Mr. L. H. J. Young, accompanied by the Writer, visited the locality, and reported as follows, $\frac{1}{p.}\frac{8}{2}\frac{8}{6}\frac{0}{1}$:—"The slate rocks adjoining the copper deposits are of a sandy character, and have a strike of N. 24° W., dipping to the south-west at an angle of 68°. At Nymagee Mine there appears to be two lodes. The main lode has a strike of N. 17° 30′ W., and is nearly vertical; three shafts have been sunk upon it, at a distance of 276 feet apart. To the east of the middle shaft (No. 3) may be seen the outcrop of a branch lode, having a strike of N. 9° W., and which as yet remains unexplored. In the three shafts sunk at that date to (1) 120, (2) 55, and (3) 80 feet, respectively, the width and composition of the lode at these levels were—(1) 8 feet wide, composed almost entirely of yellow sulphide mixed with black oxide of copper; at (3) 55 feet, the lode is 8½ feet wide, and is composed of earthy carbonates, grey sulphides,

and red oxide of copper, mixed with decomposed slate and brown iron ore; at (2) the lode is 5½ feet wide as yet, but the whole width has not been exposed; it contains large masses of brown iron ore, and grey sulphide, and red oxide of copper.

"The second lode on this property is called the 'East Lode.' It has a strike N. 18° W., and is composed of argillaceous matter, earthy carbonates, red oxides, and grey and yellow sulphides of copper, the latter only in patches.'

In November, 1898, the Writer visited the mine, but, unfortunately, owing to failure of the water supply—the first time for a number of years—mining operations had practically ceased, and it was not possible to inspect below the 40-fathom level. Nymagee, like Cobar, has to contend with an arid climate and waterless surroundings. During a severe drought in 1882–3, copper to the extent of over 1,300 tons accumulated at the mine, owing to impossibility of transport. The remarks under the head of Great Cobar, touching initial difficulties, apply equally to Nymagee, Great Central, and Mount Hope Mines. The lode at the lowest level is reported to be 30 feet wide, and composed of massive pyrites, containing about 2 per cent. of copper, though a couple of narrow seams of good grade occur. In 1896 the mine was purchased by the Great Cobar Mining Syndicate, who substituted a blast-furnace for reducing, and subsequently established partial pyritic smelting in 1901, heap roasting being discarded. The reverberatory furnaces were retained, however, for matte roasting, the latter being brought up to high grade before despatching to the syndicate's refinery at Lithgow, the distance to the nearest railway station (Hermidale) being 45 miles.

The syndicate did not work below the 600-feet level, operations being largely confined to robbing the old stopes of left and discarded ores.

Fireclay is obtained about 3 miles from the mine, and is mixed with crushed quartz in the manufacture of firebricks. Its composition may be seen under the head of "Fireclays."

The quality of Nymagee copper has always been remarkably pure and free from injurious associates. An assay of the refined copper returned 99·74 per cent., and silver at the rate of 3 dwt. per ton, but no gold.

The main sulphide ore body averaged about 250 feet in length by about 15 to 20 feet in width, and yielded on an average about 10 per cent. of copper.

Several parallel smaller veins have been opened in crosscuts east from the main workings.

The carbonate ores were extracted largely by open cut.

The Nymagee outcrop closely resembles that of Cobar, save that the slates and sandstones stand up more conspicuously above the ordinary surface; they strike N. 30° W. The outcrop of copper ore was comparatively small and confined to one spot, which has since been exploited by open cut. In only two places was iron oxide noticeable on the surface. One of these, at the south-east end, has not yet been extensively prospected. Copper carbonates stain many of the joint and cleavage planes of the strata to the eastward of the main outcrop, but no defined lodes have been exposed.

Cobar Mining District—*continued.*

The extent of the output, and the progress of development, is shown in the following table of returns:—

Return of the Yearly Output and Progress of the Nymagee Copper Mine; compiled from the Half-yearly Reports of the Nymagee Copper-mining Company, Limited, the Annual Reports of the Department of Mines, and from returns supplied by the Great Cobar Mining Syndicate.

Year.	Ore smelted.	Copper produced.	Per-centage.	Deepest level.	Width of ore bodies.	Remarks.
	tons.	tons.		ft.	ft. ft.	
1881.....	6,053	859	13·61	240	15 to 25	Output since starting in 1880.
1882.....	6,618	1,144	17·13	240	2 „ 30	
1883.....	10,236	1,714	16·75	310	3 „ 18	
1884.....	14,743	2,207	14·95	310	4 „ 12	
1885.....	15,773	1,791	11·35	430	4 „ 12	52,000 tons of wood consumed annually.
1886.....	14,449	1,468	10·15	516	4 „ 12	
1887.....	10,739	1,036	9·64	618	10 „ 25	
1888.....	12,826	1,297	10·11	618	8 „ 20	Copper boom year.
1889.....	8,704	836	96·6	720	8 „ 20	Collapse of boom.
1890.....	8,098	792	9·78	720	8 „ 20	
1891.....	9,537	916	9·60	720	8 „ 20	
1892*	6,238	697	11·01	720	8 „ 20	
1893.....	.....	.....	....	....	.....	Mine closed owing to low price of copper.
1894*	1,688	148	8·76	720	.....	
1895*	6,845	485	8·29	720	.....	Mine worked on tribute.
1896*	3,249	380	11·08	720	.....	Purchased by Great Cobar Syndicate.
1897*	11,910	510	4·23	....	.....	
1898.....	17,153	695	4·01	....	.....	
1899.....	14,868	501	3·36	....	.....	
1900.....	16,133	533	3·30	....	.....	Returns supplied by Dr. R. Read, Managing Director, Great Cobar Syndicate.
1901.....	15,521	518	3·33	....	.....	
1902.....	18,636	649	3·48	....	.....	
1903.....	22,036	577	2·61	....	.....	
1904.....	24,150	700	2·89	....	.....	
1905.....	24,251	596	2·45	....	.....	
1906.....	26,649	666	2·49	....	.....	Ann. Rept. Dept. of Mines.
1907.....	14,079	306	2·17	....	.....	„ „ „
Total	341,191	22,021				

* Amounts smelted not specifically stated, but for statistical purposes are assumed to correspond with amounts raised.

Mine purchased by the Nymagee Copper, Limited, in December, 1906. Deepest shaft and level, 680 feet. Large bodies of 3½ per cent. ore opened in No. 6 level south; width, 30 feet. Extensive alterations and additions to plant effected in 1907.

Quartz used for flux; less will be required when new makes of ore at 600-feet level becomes available.

Water Jacket equal to about 220 tons per 24 hours, exclusive of silica flux; 5 per cent. Bulli coke used.

In the early part of 1907, the new company decided to pull out all the old plant, with the exception of the blast furnace, and to instal modern machinery. The dismantling operations involved the suspension of productive work for six months, and entailed an expenditure of some £18,000. The output for the year was, therefore, only 306 tons of copper as against 666 tons for the year 1906.

"The following details of the new plant installed were supplied by the company:—Two Babcock and Wilcox high-pressure boilers of 500 horse-power, with new brick stack for same; a direct high-pressure winding engine, capable of sinking to 2,000 feet and of raising a load of 8,000 lb., with a steam pressure of 125 lb.; a compound steam and air compressor of a capacity of twenty drills; a high-pressure blower, compound engine, capacity 110 cubic feet per revolution, with a pressure of 48 oz. The fitting shop

has been equipped with new lathes, boring and punching machines, and every thing necessary to make it complete. New buildings have been erected over the winding engine, compressor, boilers, blowers, and fitting shop. Poppet heads, about 60 feet high, have also been erected.

"The mine was further opened up, and, by leaving the old drives, large lenses of ore were located which had been previously missed. At the No. 7 level (lowest) one chute has been opened out for a length of about 200 feet, of an average value of over 3 per cent., and for a width of about 15 feet; and judging by appearances at date, there may be still more ore on the eastern side. Another chute is 175 feet long, and the indications point to it continuing further north. As this level is further opened up, the management think the large chute will be located, and what applies to this level may also apply to the upper ones.

"At the smelting furnace no improvement has been made in the size. All that was done was to erect some ore bins, as it has been shown that it would be practically impossible to get in a supply of coke and firewood sufficient to meet the requirements of large treatment works under the present conditions of hauling some 45 miles by teams from the railway. It was also considered advisable to make a test with the present furnace as to the quality of the ore and its smelting qualities, and 8,216 tons were smelted for 213½ tons refined copper. This proved that it is a suitable smelting mixture, and that there is no necessity to go outside the mine for fluxes.

"Unfortunately, with the low price of copper and the high rate of cartage, it was found impossible to make a profit with the present grade of ore, unless a much greater tonnage could be smelted. This was, however, impracticable under the present conditions of road cartage; so the mine has been closed down pending consideration of some method to facilitate transport to and from the mine. The shutting down of this mine means a loss of some £60,000 per annum to the State." (Ann. Rept., 1907, p. 50)

Nymagee, 3½ miles south-south-east, on the Hartwood Pastoral Holding, parish Roset, county Mouramba.—Inspector J. Polkinghorne reported (P.B. $\frac{3\frac{1}{2}}{0}\frac{9}{7}^{0}$): Quartz, gossan, and slate, about 3 feet wide, in porphyry, carrying small values of gold, silver, and copper.

Cobar Division.

Occidental Gold Mine, Cobar.—Two lodes occur—"Big Lode" and "West,' or "Gossan Lode," about 3 feet to 20 feet apart. Big Lode about 70 feet wide, West Lode 15 feet. The Big Lode pinches at both ends, and splits into strings. West Lode traceable to Mount Pleasant Mine on N. 15° W. strike. Worked for gold down to nearly 340 feet. Milling ore difficult below about 250 feet. Sulphides begin about 340 feet. Shaft sunk in country on west side down 540 feet in October, 1907. Water makes at 440 feet; averages about 20,000 gallons per day; practically none in bottom of shaft. Greatest length of Big Lode worked, about 560 feet; greatest length of West Lode proved in No. 1 level, 830 feet; greatest length worked in stopes, about 150 feet.

The East lode, Great Western Section, about 120 feet east of the Big Lode, evidently dies out before reaching Occidental lease, as it was not met in crosscut. Traces of carbonates of copper only in the oxidized zone of Occidental Lode, just above water-level. No. 5 crosscut at 540 feet, shows still less, probably not averaging more than 1 per cent.

Queen Bee Copper Mine.—M.Ls. 33 and 34, parish Narri, county Robinson, about 13 miles south-east of Cobar. Country, slate and sandstone. Strike


PARISH
OF
DEVON
PARISH
Nymagee Copper Ltd
OF
PRIORY PLAINS
To Carbelligo
PARISH
OF
HARTWOOD
TOWN
To Hornsdale
OF
PARISH
NYMAGEE
OF
ROSET
Note The area included in boundaries thus is freehold, and comprises 718 acres
— PLAN OF —
— NYMAGEE COPPER LTD —
— SCALE 0 10 20 Chains

ЗАМЕНА
ЗАМЕНА



N. 40° W.; dip, S. 50° W. at 1 in 12. Prospected for gold prior to discovery of copper. Taken up again early in 1902. Aided from Prospecting Vote. Rich grey sulphide struck in June, 1902, at 85 feet, and followed down to 150 feet. Drives started on rich ore at this level. First ore despatched in September. First copper produced at mine, June, 1904.

Progress of development.—The Queen Bee Copper-mining Company, No Liability, began operations 15th December, 1903. The following notes are extracted from the half-yearly reports:—

First half-year, ending 30th June, 1904.—Greatest depth of proving, 250 feet; length, 300 feet. Reverberatory furnace begun in March; smelting in May. No. 2 furnace in course of erection. Tank, 2,000 yards, excavated.

Second half-year, ending 31st December, 1904.—No. 2 furnace completed in September; No. 3 in December. Main shaft, 336 feet Greatest length of proving, 400 feet; widest part of stopes, 25 feet. Weigh-bridge, rock-breakers, picking-table, hoppers, ore-bins, saw-bench, workshops, brickmaking plant, &c., installed.

Third half-year, ending 30th June, 1905.—Main shaft, 370 feet. No. 3 furnace started in March. Tramway constructed over furnaces for feeding through hoppers. Tank increased to 3,000 square yards. Fire-bricks made at mine.

Fourth half-year, ending 31st December, 1905.—Pumping appliances installed in main shaft, now 425 feet; Babcock boiler set up. No. 4 furnace completed in December. Tank increased to between 6,000 and 7,000 yards. North drive extended to 497 feet from main shaft; no ore in face.

Fifth half-year, ending 30th June, 1906.—Only two furnaces constantly employed, others being closed down alternately for extensive repairs. No. 5 furnace in course of erection. No. 1 furnace being replaced by one of larger type. Winding-engine, air-compressor, rock-drills, &c. installed. Main shaft, 485 feet. North drive at No. 3 level (370 feet) 422 feet; still in ore. Jigging plant, to treat 15 to 20 tons per day of accumulated fines, in course of erection.

Sixth half-year, ending 31st December, 1906.—South shaft, 435 feet south of main, being sunk to prospect southern end of property. New reduction furnace, to replace No. 1, completed. Refinery built. Tram-line and slag trucks installed. Hand-jigging plant completed, but had to be closed, water in shaft failing.

Seventh half-year, ending 30th June, 1907.—Development hampered by industrial troubles. South shaft, 105 feet. Small blast furnace begun in March for experimental purposes. Blast furnace of 100 tons capacity being delivered. Main shaft, 563 feet. Krupp Ball mill added to plant for crushing quartz for brick-making, fettling, &c. Refinery started—copper despatched as refined ingots.

Eighth half-year, ending 31st December, 1907.—No. 1 level (150 feet), length of proving, north 483 feet; No. 2 level (250 feet), length of proving, north 543 feet; No. 3 level (370 feet), length of proving, north 438 feet; No. 4 level (470 feet), length of proving, north 516 feet; total sinking, 1,780 feet; total driving, 2,726 feet; total cross-cutting, 522 feet. No. 2 furnace rebuilt. Small blast furnace run for forty days at 11½ tons per day. 100-ton blast furnace being erected.

No ore stoped south of main shaft. Channel filled with pyritic ore, poor and silicious.

COBAR MINING DISTRICT—*continued*.

No trace of copper was found in the 105 feet shaft, 435 feet south of the main shaft. No stoping south of main shaft.

The lode varies in thickness in the different levels from 1 foot to over 20 feet wide, intermixed with bands of country. In places proved solid for 5 to 10 feet wide. Best ore lens about 120 feet long, width about 3 feet.

At 450 feet level an east lode struck in crosscut about 15 feet from main lode. Width, 2 feet; ore, 4 to 5 per cent.

A large body of slightly impregnated country, 30 feet wide, carrying about ½ per cent. of copper, occurs 70 feet west of main lode.

The general lodestuff at Queen Bee consists of slate with copper and iron pyrites, and an inappreciable quantity of zinc-blende and galena. It is broken and hand-picked over shaking tables before going to furnaces. It carries 1 to 2 oz. of silver per ton, but no gold.

The reverberatory plant embraces four reducing and one refining furnaces of a capacity of about 70 tons per week each, one being occasionally worked to 100. The first run matte averages 40 to 42 per cent. copper.

The small blast furnace, running on the best grade ore, with limestone and ironstone fluxes, averages about 11½ tons per day, producing matte of 31 per cent., at a cost of £2 per ton of ore for smelting, according to the company's eighth half-yearly report; the charge being:—

Coke	100 lb.
Raw sulphide	350 ,,
Slag	120 ,,
Limestone	150 ,,
Ironstone	50 ,,
	770 lb.

The coke and fluxes being slightly increased when slag runs thick.

In view of the above results, with carefully-picked best grade (most pyritic) ore, the erection of a 100-ton blast furnace appears unwise. The best ore only can be treated by this method at excessive cost for coke and fluxes. Limestone and ironstone costing 10s. per ton for cartage. The Queen Bee ore on the average is too silicious for ordinary blast furnace reduction.

The limestone flux is obtained on the Rookery-road, about 11 miles from the mine; its composition is shown in the following partial analysis:—

No. 07-7430—Calcium carbonate	99·03
Gangue	·53
Ferric oxide and alumina	·14
Magnesium carbonate and undetermined	·31
	100·00

OUTPUT from June, 1902, to 31st December, 1907.

Year.	Ore raised.	Ore sold.	Ore smelted.	Rough copper produced.	Remarks.
	Tons.	Tons.	Tons.	Tons.	
1902	383	83*	.....	.....	*Sold for £497.
1904	1,469(?)	319*	1,150	136½	*291 realised £2,292.
1905	7,854	.....	5,383	499¾	
1906	11,556	.....	7,158	573	
1907	10,235	.....	6,422	493¼	
Total	31,497	402	20,118	1,702½	

Dividends Nos. 1 to 13 paid, aggregating £15,625 to end of 1907.

COBAR MINING DISTRICT—*continued.*

Bobadah Division.

y Copper Mine, Top Tank Paddock, Overflow, 18 miles north-Overflow Silver-mine.—Held as a mineral lease of 40 acres. ık 100 feet, and driven east 45 feet. The vein occurs in soft ı slate and sandstone, and consists of ferruginous quartz with a little d lead carbonates, about 12 to 18 inches thick. Assays of picked $\frac{1165\text{-}6 \text{ and } 1824}{97}$) yielded from 15 to 42·5 per cent. of copper. The ported to have pinched out or been lost in sinking. A few dwts. of d, in one instance, 19 dwts. of gold per ton, have been obtained in

in 1906 (P.B. $\frac{1}{0}\frac{2}{6}\frac{1}{4}$) to drive 100 feet north on lode at 100-feet

feet in drive, vein of copper showing 3 to 20 inches wide, country ing stains of copper ore. End of drive not promising. Drive d. Aided to continue shaft to 200 feet.

Canbelego Division.

Budgery.—On south boundary of Budgery Mine. Vertical shaft feet of boundary of latter. Down 213 feet at date of inspection, r, 1907. No ore discovered so far.

Mt. Boppy Copper Mine.—Adjoining M.L. 51 on the south-east. t sunk at junction of porphyry and sedimentary rocks, showing and kaolinized deposit. No ore. West shaft sunk in ferruginous rop. Encouraging results obtained in 50-feet shaft; 3 or 4 per onate ore being raised in some quantity, with bands of richer ore. rospecting below water-level.

adjoining block (M.L. 51) in north shaft, a similar deposit of puggy, ıs, and manganiferous kaolin occurs as in the Restdown Mine, arising from secondary action of leaching and depositing solutions the intrusion of the porphyry.

Cobar Division.

Queen Bee, M.L. 32, parish Narri, county Robinson.—Inspector rne reports that this site was taken up in 1902, after discovery of ning Queen Bee Mine. Two shafts sunk, No. 1, 296 feet, No. 2, about 1,000 feet apart. Traces of copper only discovered.

Nymagee Division.

the West Mine (formerly Wirlong), about 5 miles east of Shuttleton rom Nymagee, parish Hume, county Mouramba.—Discovered in Morris and Kelly, in porphyry near junction of slate. Strike N. 10° . 80° E. Three small veins exposed at intervals of about 150 yards. ne vein to 58 feet. Aid granted to continue sinking and to crosscut. or J. Polkinghorne reported (P.B. $\frac{1}{0}\frac{0}{5}\frac{2}{5}$) ferruginous quartz in porphyry. Aided to sink 30 feet shaft to 100 feet, and to crosscut st and west.

re recorded at 25 feet west in crosscut, carbonates about 1 foot ıl to about 10 per cent.

ne officer reported (P.B. $\frac{1}{0}\frac{5}{7}\frac{4}{1}$) that both crosscuts—in previously pecting—passed through a mineral body, and at 23 feet from the

shaft in the west crosscut some good-looking veins of grey ore and carbonates are exposed, underlying east. Aided to sink from 30 to 200 feet, and crosscut 50 feet at that level—east and west.

At later date prospects were reported as poor, and work ceased.

Bobadah Division.

Walker's Hill, 1 mile north of Walker's Hill Homestead and 16 miles from Bobadah.—Copper ore occurs here in slate and sandstone. Aid was granted from the Prospecting Vote to sink 65 feet and drive 40 feet on a number of leaders from 1 to 4 inches thick, similar to those occurring in an old shaft about 110 feet south. The results obtained under aid were not encouraging, no improvement in the ore veins being manifest.

Geological Surveyor A. J. Watt reported (P.B. $\frac{4}{6}\frac{4}{6}\frac{7}{7}$) copper lode traversing slate. Aided to sink 50 feet from bottom of 15-feet shaft. Leaders of copper ore in bottom of shaft.

Progress.—In drive at 61 feet stains of carbonate in slate. Aided to crosscut 50 feet. Country hard, and mineralised with leaders of copper ore. Aided to continue 68-feet shaft another 30 feet. Vein widening, sulphides more pronounced. Further aided to 128 feet. Ore channel reported wide, with several small leaders of ore. Crosscut 28 feet at bottom. Strings of ore only.

Nyngan Division.

Wilgarbone.—No. 1 Prospecting Area, A. Leslie's Settlement Lease, parish Wilgarbone, county Canbelego, about 8 miles from Girilambone.

Traces of carbonate of copper in chlorite schist. Aided to sink to 150 feet and crosscut. Very poor indications of payable deposit.

Bobadah Division.

Yellow Mountain, M.L. 1, 15 miles southerly from Bobadah.—At the north end of Yellow Mountain, which consists of quartz-felsite, Byrum Bros. discovered three outcrops of ferruginous carbonate of lead of very kindly appearance. In one of these a little copper ore occured—red oxide, and traces of carbonate; but the chief value was in silver and lead. The two principal deposits form bunches on the surface from 18 to 20 feet long, and 6 to 7 feet wide; beyond the bunches the lodes continue, but are thinner. The principal bunch, containing the copper ore, was followed down 40 feet, where it is from 2 feet to 2 ft. 6 in. thick. There is every indication of the lode continuing to form lenticular bunches. Six tons of the ore sent to the Smelting Company, Dapto, yielded 9 per cent. of copper, 45 per cent. of lead, and 33 oz. of silver and a few dwt. of gold per ton. This bunch occurs in slate between quartz porphyry; the other in the porphyry.

Aided in 1903 (P.B. $\frac{2}{0}\frac{5}{3}\frac{2}{2}$) to sink from 62 feet to 112 feet, and to drive 50 feet. No record. Further aid for 100 feet of sinking in winze at 100-feet level. At 150 feet sulphides reported as showing freely. Abandoned.

HUNTER AND MACLEAY MINING DISTRICT.

Port Macquarie Division.

Huntingdon Mines.—In bed of Hastings River, portion 7, parish Koree, county Macquarie, 17 miles from Port Macquarie.

For over twenty years metalliferous ores were known in the remarkable rugged outcrop of quartz-felsite which forms rapids in the river for over 400 feet, and rises like islands above the channel gravel bed.

First opened by Messrs. Cummins and Campbell about 1905. A shaft was sunk in an island of felsite in the centre of the river, to a reported depth of 38 feet, no ore being obtained.

Part of the material pierced consisted of a fine cherty rock, described by Mr. Card as "probably an indurated volcanic ash." The latter contained iron pyrites.

A small engine and pump were employed during operations.

On the opposite side of the river another syndicate sank a shaft 50 feet, but off the quartz-felsite and in the intruded slate. The apparent strike of the former is N. 40° W.

The outcrop in the river is large, but the average percentage of ore is very low.

The ore obtained was all from the one original outcrop of lode matter in the river. It consists of a low-grade refractory mixture of zinc-blende (principally), copper and iron pyrites, and galena, in quartz.

An average sample of picked ore yielded :—

No. 07-451a.—Copper	1·27	per cent.
Zinc	23·23	,,
Lead	2·76	,,
Gold	a trace	per ton.
Silver	1 oz. 5 dwt. 1 gr.	per ton.

An outcrop of Permo-Carboniferous (Lower Marine) limestone occurs at no great distance—in M.L. 2, parish Koree, county Macquarie, about 2 miles from Wauchope. Strike, N. 70 E. Fossils abundant.

Its composition is given in the following analysis :—

No. 07-451a.—Moisture	0·12
Carbonate of lime	93·39
Carbonate of magnesia	4·31
Ferric oxide and alumina	0·65
Gangue	1·70
	100·17

Trace of copper detected.

Kindie.—Hastings and Forbes River district.

Mixed copper, lead, zinc, and silver ore in 6-inch vein, opened by Bethune and party. Assay value :—

Copper	1·5 per cent.
Lead	39·0 ,,
Silver	16 oz. per ton.

Aid recommended by Inspector D. Milne, but not availed of.

Kempsey Division.

Long Flat.—Copper sulphides in quartz have been reported at Long Flat, 63 miles above Kempsey, on the Macleay River. Unopened.

Port Macquarie Division.

Mount Jasper Copper Mine, M.L. 1, parish Jasper, county Macquarie. About 40 miles from navigable water at Beechwood, Hastings River. Discovered by A. Muir in 1887.

Four lines of lode have been discovered, striking from north and south to N. 55° W., and dipping westerly 35° to 55°.

The centre lode received aid for sinking in 1901 (P.B. $\frac{1}{0}\frac{1}{1}\frac{1}{1}$). Work commenced in 1902.

In 1904 the mine was worked by tributers; average width of lode, 3 feet.

In 1905 the shaft reached 100 feet; lode, 4 feet wide. Carbonate ore at 50 feet.

Taken under option by the Mount Jasper Mining Syndicate, which held possession for about fifteen months, but did little towards proving the lodes in depth.

Inspected by the Writer in 1907. The lodes occur in a high range on east side of Jasper Peak, at an elevation of about 1,000 feet above the Forbes River at its base.

The country consists of Permo-Carboniferous Lower Marine beds intruded by dioritic and peridotic rocks, changing to serpentine.

No. 1 or centre lode—opened to 100 feet; driven on south for 25 feet at 90-feet level. Not open to inspection owing to water. Strike N. and S.; dip west at 55°. A little sulphide ore showing at 25 feet; but no workable ore encountered above 60 feet. The ore—quartz and chalcopyrite—pinched to 1 ft. 6 in. wide at end of drive, but varied up to 4 feet wide at best. About 70 tons despatched from this shaft yielded from 10 to 23 per cent. of copper. The first 3 tons yielded also 8 dwt. 19 grs. of gold and 2 oz. of silver per ton. No further payments made for gold.

The composition of the best grade of Jasper ore was found to be:—

Copper	23·4 per cent.
Iron	23·4 ,,
Sulphur	22·9 ,,
Silica	18·9 ,,

No. 2 or "East Lode."—About 9 chains S. 40 E. from No. 1; has been opened by two shafts 50 and 70 feet deep. This lode consists of solid quartz about 3 feet wide, carrying small particles and patches of yellow sulphide of copper. Strike, N. 20° W.; dip, S. 70° W. at 74°. The lode has been driven on 30 feet at the 50-feet level. Of no value as a copper lode.

No. 3 Lode.—Two chains N. 50° W. from No. 1 lode, a 10-feet shaft has been sunk in an outcrop striking N. 40° W., and dipping south-west; 3 feet to 5 feet wide; shows copper carbonates of 3 to 5 per cent. grade.

No. 4 Lode.—Nine and a half chains south-west of No. 1. Strike N. 55° W.; dip S. 55° W. at 35°. Opened by tunnel and shallow shaft. Width of channel, 1 foot to 12 feet; mostly filled with crushed peridotite or serpentine, in which occur bunches and kernels of good yellow sulphide and iron pyrites. Wall rocks hard, forming prominences in places.

Ore good when clean, but silicious as dressed. Twelve tons despatched from this lode averaged 15 per cent. of copper.

Underfoot in the tunnel about 1 foot 3 inches of good ore continues; balance, hornblendic rock with kernels of ore.

Mr. T. McLelland states—10th January, 1908—that little work has been done on these lodes since inspection.

Copper ore is reported in Andrew's block, about 1 mile south of Mount Jasper Mine, but has not been prospected.

Mount Jasper Peak Lode.—W. H. Taylor's prospecting area. About 50 chains S. 80 W. from Mount Jasper Mine. Quartz lode carrying a little carbonate and sulphide of copper. Strike, apparently N. 40° W.; dip, S.W. at 71°. Aided to intersect by tunnel about 170 feet below highest outcrop. From old workings and present operations, apparently no permanent ore body exists.

Singleton Division.

Mount View, Pokolbin.—Messrs. Pepper and party did a good deal of prospecting for copper ores in the inlier of old rocks forming Mount View, but the results were not promising for a payable deposit.

The following samples were received in the Departmental Laboratory for assay:—

Assay No.	Description.	Copper per cent.	Gold per ton.	Silver per ton.
				oz. dwt. grs.
06-3866	Copper ore	10·82	4 dwt. 8 grs.	3 16 8
06-5548	Ferruginous granitic rock with copper carbonates and sulphide—20-feet level.	13·72	a trace	3 16 5
06-5549	do do do ...	1·17	do	1 7 5
07-2230	Copper pyrites, with chlorite	32·45	do	6 10 16
07-4151	Copper pyrites, with chlorite and tourmaline.	7·25	2 dwt. 4 grs.	3 0 23

Inspector D. Milne reported (P.B. $\frac{18}{05}\frac{24}{6}$) that a small bunch of copper ore occurred in granite at this site—4 ft. long, 3 ft. deep, and about 3 inches thick. After this cut out no further sign of copper was met.

Port Macquarie Division.

Port Macquarie, south of Nobbys, the south headland of Port Macquarie.—A lode containing iron and copper sulphides was opened about twenty-six years ago by tunnel from the sea coast, without, however, any satisfactory results being obtained. Assays of the lodestuff in 1880 yielded from 2·13 to 5·05 per cent. of copper, and about 2 dwt. of silver per ton.

Rose Hill Mine, portion 7, parish Koree, county Macquarie On east bank of Hastings River, just above Huntingdon Mine, near Wauchope.—Cummins and party opening lode striking E. and W., dip N. at 73° in quartz-felsite. Opened by tunnel from river bank; traces of copper and iron pyrites and zinc-blende beginning to show at 20 feet.

Kempsey Division.

Willi Willi Copper and Silver Mine, M.Ls. 1 and 2, about 7 chains south of south-west corner of portion 17, parish Panton, county Dudley.—About 37 miles from Kempsey. About 1,300 feet above sea level, and 465 feet below the gap in range between it and Willi Willi Station, the rise to the gap from the latter being about 1,295 feet.

Formation—Permo-Carboniferous dolomitic limestones, altered claystones, and sandstones, with intrusive epidote-quartz rock (6984). Rich bunches of copper carbonates were discovered near the junction of the rocks mentioned with the igneous intrusive rock. Masses of garnet have resulted from the contact of the latter with the limestone; also wollastonite (silicate of lime).

The following section across the strike of the country illustrates the mode of occurrence of the lode in M.L. 1 and its association.



Copper ore was discovered in this locality by H. H. Mansfield about 1891. At the first site—in limestone—aid was granted to sink 80 feet, and drive 50 feet, but the surface ore was found not to extend below 26 feet. Four tons sent to Wallaroo Smelting Works, South Australia, yielded 7 per cent. of copper and 73 oz. of silver per ton.

About 25 chains S. 80° E., a more promising outcrop was discovered at the junction of an intrusive dyke. A number of short tunnels were driven along the junction line, and 57 tons of rich ore extracted from bunches in the lode.

Between the two outcrops a third occurs, which has also been prospected under aid, but not with payable results.

The best results have been obtained, and the most favourable indications occur in the contact lode. The sulphide zone, however, requires effective proving before the real value of the deposit can be ascertained. A considerable amount of leaching has occurred in the oxidised cap. The character of the ore bunches found in the latter can best be judged from the following assay returns, made in 1894; the silver occurs in the form of chloride:—

Copper gossan,	No.	1717	copper,	37·66	per cent.;	silver,	163	oz.	3	dwt.	16	grs. per ton.
Carbonate	,,	1491	,,	29·28	,,	,,	23	,,	3	,,	9	,, ,,
,,	,,	2413	,,	36·94	,,	,,	107	,,	7	,,	8	,, ,,
,,	,,	2414	,,	49·67	,,	,,	118	,,	2	,,	22	,, ,,
,,	,,	2415	,,	16·15	,,	,,	46	,,	1	,,	3	,, ,,
,,	,,	3418	,,	31·71	,,	,,	283	,,	15	,,	6	,, ,,

Mr. Mansfield states that he despatched 50 tons to Harold Bros., Adelaide, between 1893 and 1894, which realised 33 per cent. of copper and 63 oz. of silver per ton. Seven tons sent to Lithgow yielded 18 per cent. of copper and 25 oz. silver per ton.

Baker Bros.—who subsequently held the mine, drove Mansfield's tunnel in M.L. 1 to 75 feet, and struck sulphides as per assays 07–5304 and 5305—are reported to have despatched 33 tons. They abandoned it in 1901 and removed plant. A Kempsey Syndicate afterwards sank a shaft 50 feet higher up the ridge, and struck the lode on the underlay at 79 feet, encountering sulphides as per Assay No. 07–5306.

This lode strikes N. 15° W., and dips S. 75° W. at about 20½°. The following section is exposed at the tunnel mouth, where a cut face has been made along the outcrop between the various tunnels:—

In descending order.

15 feet	Gossan, with pipeclay.
	Garnet.
	Copper ore.
	Garnet.
	Tunnel level.

A lower tunnel was started early in 1907 by the present holder (W. H. Trewenack) 135 feet lower down eastern slope; but as the lode dips flatly in the opposite direction, at least 500 feet will have to be driven to intersect it at not more than 100 feet below the present lowest upper tunnel level. Though the soakage water may be a little troublesome on such a flat underlay, it would be best to continue the upper tunnel or start a straight shaft higher up the ridge to cut the lode further west. The height of the ridge and the dip would not exceed the distance of the present tunnel, and would give a considerable amount of backs, which the latter will not.

Four short tunnels were driven in the outcrop by Mansfield, and these were slightly extended by Baker Bros., the total length opened along the crop between the extreme northern and southern tunnels being about 190 feet.

Mining for the rich argentiferous copper carbonate bunches, which occurred more or less isolated, resulted in excavation of large irregular chambers and erratic drives and cross-levels.

In the southern, or No. 4 tunnel, kaolin is largely developed, in which petaloidal structure has been developed by compression and thrust. A remarkable feature is the occurrence in it of isolated bunches and kernels of pure garnet. The copper carbonates are associated with this mineral to a considerable extent, especially when highly ferruginous.

The sulphide ore struck in the principal tunnel and in the vertical shaft consists largely of magnetic and ordinary pyrites, with chalcopyrite and secondary veins of arseniopyrite, in vitreous altered rock with occasional calcite.

In M.L. 2, on the west, the original site of discovery at Willi Willi, a tunnel was driven 110 feet S. 15° W. towards the middle shaft, two veins of bornite being cut in chalcedonic quartz and limestone, with garnet and wollastonite. An average sample of the ore stacked at the tunnel mouth yielded as per sample No. 07-5307; but the available quantity was too small for profitable extraction. A ton of similar ore raised from the middle shaft some years ago is reported to have yielded 40 per cent. of copper and 35 oz. of silver.

In the adjoining lease (M.L. 4) on the north, on Block and Tackle spur, an opening in a gossany outcrop, with stains of copper carbonate, revealed below the sphere of oxidation a fine greenish garnet rock, with idiogenetic copper ore, the joints of which were covered with a film of shining iron

oxide. An assay of several pieces revealed gold at the rate of 1 oz. 12 dwt. 16 grs. per ton, apparently due to inclusion of a rather coarse unnoticed particle; for several subsequent tests failed to reach above a few dwts.; as it contained, in addition, up to 1·62 per cent. of copper, it may prove a useful flux.

From another large outcrop on the same block a sample was taken, consisting of massive pyrrhotite and a little copper pyrites, which yielded the results shown in Assay No. 07–5308.

Assay No.	Description.	Copper, per cent.	Iron, per cent.	Sulphur per cent.	Silica, per cent.	Gold, per ton.	Silver, per ton.
							oz. dwt. grs.
07–5304 ..	Average sulphides, Old Tunnel, M.L. 1.	1·57	....	....	.. .	trace	2 4 15
07–5305 ..	Enriched sulphides, Old Tunnel, M.L. 1.	13·40	....	....	....	,,	15 19 1
07–5306 ..	Average sample from New Shaft, M.L. 1.	2·55	28·28	21·09	20·79	,,	2 0 20
07–5307 ..	Average sample from New Tunnel, M.L. 2.	11·90	(Lime,	15·19)	31·90	,,	35 14 7
07–5308 ..	Average sample from pyritic outcrop, M.L. 4.	1·05	....	....	....	,,	0 15 6

The composition of the dolomite from M.L. 1 is shown in the following analysis (07–5319):—

Calcium carbonate	57·99	per cent.
Magnesium carbonate	39·98	,,
Ferric oxide and alumina	·60	,,
Gangue	1·18	,,
Strontia	trace	
	99·75	,,

LACHLAN MINING DISTRICT.

Condobolin Division.

Anaconda Mine, about 30 miles northerly from Condobolin Railway Station, parish Melrose, county Cunningham.

Under the name of Boone West, this mine was opened about nineteen years ago, but as far as prospecting then went, a payable lode was not revealed. After being abandoned for a number of years, it was taken up and floated into a no-liability company, active prospecting operations being carried on in October, 1898.

The country consists of ferruginous slate and much crushed conglomerate At the surface, copper carbonates occur sparingly in the latter. A shaft was sunk 100 feet deep on the west of the outcrop, and a cross-cut driven to it. The ore channel at the junction of the conglomerate is filled with soft chlorite with greasy headings. In places a little native copper appears, and thin films of red oxide in the jointings. A thin seam of pyrites occurs, but is almost, if not quite, free from copper sulphide. A little grey sulphide was found in sinking and driving, but not in quantity. Magnetic iron is present in bright micaceous particles, which may be confounded with copper glance. No payable ore was exposed along the southern drive at the 100-feet level.

Recent developments.—Taken up by Mr. G. Eason in 1902 after being idle for two years (Ann. Rept., 1902, p. 50). A little surface prospecting done in 1904 (*ibid.*, 1904, p. 47), and about 150 tons of ore disposed of.

In 1905, sulphides reached at 290 feet reported to yield 3 per cent. copper, 2 dwt. gold and 3 oz. silver per ton. Four hundred tons of ore raised (*ibid.*, 1905, p. 45).

A little desultory work done in 1906 (*ibid.*, p. 47).

Inspector G. Smith reported in the latter year that the depth of proving was 300 feet and the length 200 feet.

About 30 tons raised.

Molong Division.

Armstrong Copper Mine, parish Yetholme, county Bathurst.—In the *Mineral Statistics of New South Wales*, 1875, p. 92, it is recorded that a company was engaged working the above mine, and the following particulars are given:—Strike of lode E. and W.; dip slightly north; thickness at surface, 2 feet, gradually increasing to 4 feet 6 inches at 50 feet. The ores consisted of red and black oxides, carbonates, and sulphides, assays of which yielded from 15 to 36 per cent. of copper; 60 or 70 tons of ore were then at grass. The intention of erecting smelting works on a new American principle was expressed. No further particulars of this mine are recorded, at least not under its original name.

Grenfell Division.

Arramagong.—In 1890 Mr. W. Anderson, Geological Surveyor, recorded the presence of blue and green carbonates of copper in the argentiferous lead lode opened by the Great Southern Silver-mining Company, in C.P. 17, parish Tyagong, county Monteagle, between Young and Grenfell. A small quantity of silver-lead ore was raised, but operations were soon abandoned.

LACHLAN MINING DISTRICT—*continued.*

Gundagai Division.

Back Creek Station, near Kimo.—A copper lode was opened in this locality by Engellen and others, of Gundagai. At surface about 1 foot 6 inches thick of good ore, bornite, occurred. A shaft was sunk 50 feet, but the ore pinched out at that level.

Molong Division.

Bell River.—In April, 1852, Stutchbury mentioned copper lodes close to the Bell River, in the neighbourhood of Molong, having a thickness of 5 to 7 feet, which he regarded as well worthy investigation.

Mandurama Division.

Belmore Copper Mine, Woodstock.—This mine was discovered about 1867. The ore consisted of red oxide at surface from 6 to 12 inches thick. Eighty tons were sent to the Cadia Smelting Works (near Orange), averaging, undressed, 37 per cent., according to report. The mine was afterwards sold for £400. The new proprietors sank three shafts from 60 to 90 feet deep. Fifteen tons of rich red oxide, raised during operations, are reported to have averaged 64 per cent. at the Lithgow Smelting Works. The ore cut out in depth, but was making again, though much mixed with quartz.

No further attempt has been made to re-open this mine.

Condobolin Division.

Big Ben Copper Mine, Melrose, about half a mile west of the Anaconda Mine. As at the latter mine, the geological formation consists of slate and conglomerate, with the addition of quartzite. The mine is situated on the summit of a small hill, where a little copper-staining is visible. It was first discovered about nineteen years ago, and was prospected about the same time as the Anaconda—then the Boone West. Aid from the Prospecting Vote was granted to continue the prospecting shaft to the 120-feet level, and to cross-cut west through the conglomerate. No payable ore was discovered during these operations. In the beginning of 1899 it was announced that a company had been formed to re-open it.

Taken up by G. Eason in 1902—but apparently without effect.

Burrowa Division.

Binalong.—In portion 117, near boundary of portion 118, about 6 miles from Binalong, parish Harden, county Harden, copper carbonate stains occur in a small outcrop of porphyry. Opened for a few feet many years ago, but now mullocked up. Not traceable from this point. Specular iron near by, but unconnected. Unimportant.

Copper ores also occur in the Town Reserve at Binalong, but nothing of a workable nature has been proved. Samples taken from old shafts sunk for gold are reported to have yielded from 7 to 30 per cent. of copper on assay.

Condobolin Division.

Blue Bell Mine.—Portion 11, parish Condobolin, county Cunningham, $2\frac{1}{2}$ miles north of Condobolin.

Inspector G. Smith, in 1906, reported that this lode was discovered by J. Sinclair, about 1898. It strikes E. and W., and dips S. in schist. Maximum length of proving, 50 feet; depth, 96 feet.

Present owners despatched 22 tons of ore, averaging 7½ per cent. of copper and 4 dwt. of gold per ton.

Grenfell Division.

Boori Copper Mine.—Portion 40, parish Bumbaldry, county Monteagle, in James McMahon's private land.

Inspector H. Hooke reported (P.B. $\frac{1}{07}$) a well-defined channel of considerable length, from which small bunches of copper ore are obtainable. Aided to sink from 31 to 81 feet, and to drive 25 feet at bottom.

Cudal Division.

Bowan Park.—Six miles north of Cudal, portion 281, parish Bowan, county Ashburnham. J. Berta sank two shafts in this property, 35 and 40 feet, on a copper-bearing vein from 1 to 3 feet wide. A few tons of ore raised, but none disposed of. Assays gave from 6 to 18 per cent. of copper.

Cowra Division.

Broula, on Cowra-Grenfell road.—The Lyndhurst Railway and Mines, Limited, raised about 300 tons of about 3 per cent. copper ore from the old Broula copper shaft during 1904, for use in their smelters at Junction Reef, but soon abandoned operations, sufficiently solid bodies of ore not being encountered.

Grenfell Division.

Bumbaldry.—Parker, Smith, and McLeod's copper lode at Bumbaldry, about half a mile south of Cowfell Copper Mine. In 1903, O'Brien and party discovered a copper lode on McMahon's private land at Bumbaldry. 30 tons treated at Dapto reported to have yielded satisfactory results.

Bumbaldry.—Between Cowra and Grenfell. Inspector Hooke reported (P.B. $\frac{1}{04}$): Copper-bearing formation of some width (6 tons of ore from which yielded 10 per cent. of copper) near Bumbaldry Battery. Aid subsequently granted for sinking from 75 feet to 125 feet; apparently not availed of.

In the following year it was reported (Ann. Rept., 1904, p. 45) that £188 worth of ore was disposed of, the lode being from 1 foot to 10 feet wide, and the grade running from 8 to 18 per cent.

(*See* Cowfell Mine, with which this is probably identical.)

Cudal Division.

Bumbery Copper Mine, also known as Reedy Creek and Payne's Mine, 9 miles south-easterly from Bumbery Railway Station.—This lode was originally opened as a gold-mine in 1896; the outcrop consists of gossan, from 40 to 50 feet wide. At 30 feet carbonates and grey sulphide of copper were struck. The following parcels of ore were treated during prospecting work:—10 tons sent to Lloyd's Smelting Works, Lithgow, yielded 26⅛ per cent.; 3 tons sent to the Smelting Company of Australia's Works, Dapto, yielded 36⅛ per cent. In February, 1899, the Writer inspected the mine, which was then being worked by the original proprietors—Payne and party—the holders of a purchasing option having forfeited their deposit.

The deepest shaft was then 130 feet, but the oxidised zone had not been penetrated. Rich bunches of secondary ore—copper glance—were struck on resuming operations, from which the following returns were obtained at the Smelting Works, Dapto:—

4 tons	14 cwt.	"Firsts"	yielded	42·6	per cent. of copper.
4 ,,	16 ,,	"Seconds"	,,	27·8	,, ,,
2 ,,	10 ,,	"Thirds"	,,	21·8	,, ,,

In the north shaft (130 feet) a large body of gossan was exposed, in which crystalline native copper occurs in places from redeposition from solution. The rich copper glance occurs in bunches in the gossan at 130 feet. Crosscuts have been driven east and west from 40 to 50 feet, revealing a very large body of oxidised material; but the extension of the eastern drive at the 100-foot level for a considerable distance into the solid country was labour in vain.

The south shaft was sunk 112 feet, and crosscut 40 feet east. Here the outcrop consists of red jasperoid altered rocks, heavily charged with pyrites. Epidote rock is also in proximity. Quartz porphyry predominates.

Prospecting was continued in 1900, the main shaft being carried down to 250 feet. Some rich grey ore in small bunches were encountered, several parcels being sold for £413. The grade reached nearly 50 per cent. in some cases.

In No. 3 shaft quartz and ironstone persisted to 86 feet; then black decomposed slate, with native copper of average low grade. Nothing important struck until 234 feet level, where some rich purple ore was met in a 4-inch vein. Shaft timbered up from 250 feet.

At 240 feet a crosscut was driven west 100 feet through low-grade formation without true walls, and east for 34 feet, the first 4 feet in very hard slate, with splashes of grey ore. The east crosscut is reported to have cut through 14 feet of pyrites containing only traces of copper.

Water encountered at 180 feet level, but none in bottom of 250 feet shaft.

Payne's shaft was driven 50 feet at the 50 feet level in soft gossan, without encountering anything payable; 10 feet south, at the 60 feet level, payable carbonates 1 foot 6 inches wide were met; crosscut driven 24 feet west at the 98 feet level. From this level a winze is reported to have been sunk 12 feet in high-grade black ore; width, 4 feet at top, but pinching to 5 inches at bottom of winze.

Burrowa Division.

Burrowa District.—Inspector James reported (P.B. $\frac{2}{3}\frac{4}{3}\frac{2}{1}$) a copper lode in felspathic rock in portion 129, parish Ware, county King, about 12 miles east of Burrowa.

Opened many years ago to a depth of about 100 feet at a point about 350 feet from present site. Object of operations to prove extension of old Wallah Wallah copper lode. Aided to sink from 34 to 77 feet; progress, at 68 feet, slight copper stains in broken country. At 84 feet small veins showing; further aid granted to crosscut 50 feet; no further record.

Right-hand Creek, west side, on D. Flannery's land, 2 miles from Godfrey's Creek Post-office, parish Warallen, county Monteagle.

Bachelor's Reef, 11 miles south-east of Burrowa, and 6 miles south of Rye Park. Quartz vein with lean copper sulphides; not worked.

Democrat silver-lead mine, on Burrowa River, near Kangiara. A little copper ore present in lode; copper strings in hard quartz-felsite outcrop in river bank and near mine; too thin and separate to be of value.

A few chains down stream thin strings of galena occur under like conditions.

Near the latter a shaft has been sunk by Reynolds and others to a reported depth of 60 feet, from which some tons of ore are reported to have yielded 9 per cent. copper and 25 dwt. of gold per ton. This lode is seen crosing the river bed about 10 chains northerly where it occurs in a bar; a little copper and iron pyrites are visible leanly distributed in quartz-felsite.

Cargo Division.

Cargo.—W. Anderson, Geological Surveyor, pointed out that in the lower levels of the Ironclad Mine, Cargo, solid iron and copper pyrites occurred, and that generally the ore was more freely gold-bearing where the copper was most plentiful. (Ann. Rept., 1890, p. 268.)

In 1888 a copper lease was taken up by Gazzard and party, between the Ironclad and Dolcoath Mines. 10 tons of ore from the Ironclad Mine were sampled and assayed at the Government Metallurgical Works, Clyde, with the following result:—

Copper	2·97 per cent.
Gold	19 dwt. 2 grs. per ton.
Silver	1 oz. 5 dwt. 5 grs. per ton.

Cudal Division.

Cheeseman's Creek.—At Dairy Hill, ½ mile from Orange to Forbes-road, 17 miles west of Orange, parish Boree Nyrang, county Ashburnham. Inspector Smith reported (P.B. $\frac{2}{0}\frac{8}{7}\frac{8}{8}$), copper-bearing felsite at this site, a sample of the rock assaying copper 4·7 per cent., and gold 3 dwt. 16 grs. per ton. Aid granted to sink 50 feet from bottom of 10 feet shaft, following the copper ore. Subsequently abandoned; country hard; prospects not encouraging.

Condobolin Division.

Condobolin Copper and Gold Mine.—Situated about 1½ mile northerly from Condobolin. Opened about 1896 to a depth of 90 feet, under Government aid, in schistose country. The vein has a thickness of from 12 to 15 inches at surface, and 4 inches at 50 feet, and strikes N. 40° E., with a dip S. 50° E. It consists of ferruginous quartz, with a little copper carbonate and grey sulphide. Six tons raised during operations yielded 11 per cent. of copper and a trace of gold at the Australian Smelting Company's Works, Dapto. About a quarter of a mile west copper ore was discovered and followed down 90 feet. Vein reported to have been 2 feet thick at surface, but pinched out at 90 feet.

Traces of copper also occur in Shepherd and party's mine to the north-west on the Melrose-road; it makes its appearance in the schist country.

Cootamundra Division.

Cootamundra.—A sample of carbonate ore from 5 miles from Cootamundra ($\frac{1}{0}\frac{3}{4}\frac{1}{1}$) yielded 12·8 per cent. copper; and another from 8 miles N.W. ($\frac{1}{0}\frac{1}{8}\frac{1}{2}\frac{0}{0}$) yielded 16·80 per cent.

The outcrop is not well defined, being mixed through the granite, forming a thickness of about 2 or 3 feet. A shaft, about 60 feet deep, sunk a few feet from the outcrop, evidently cut the lode, as a good deal of copper-stained ore was brought to the surface. A representative sample proved of very low grade.

LACHLAN MINING DISTRICT—*continued.*

Cootamundra District.—On unused road between portions 235 and 236, parish Dadauman, county Bland (J. Kearns' property). In 1899 a shaft was sunk 60 feet in copper-stained, much crushed quartz-felsite. Quartz veins in faces, and in country alongside. Copper stains not traceable away from shaft. Unfavourable.

(BATHURST MINING DISTRICT.—*Canowindra Division.**)

Copper Mine Creek.—Parish Malongulli, county Bathurst. This creek is a tributary of the Belubula River, and drains from Sugarloaf Mountain, in the same parish, near which the Sugarloaf, Smith and McGuinness's, and Bothery's Mines occur. The cupriferous formation is an andesite, and in one mine—Smith and McGuinness's—copper carbonate and native copper occur in the steam holes of the rock, which are now chiefly represented by calcite amygdules.

LACHLAN MINING DISTRICT.

Grenfell Division.

Cowfell Mine.—Portions 52 and 61, parish Bumbaldry, county Monteagle. M. Morrison, Senior Field Assistant, reports that "the ore—blue and green carbonates, red oxide, and yellow sulphide—occuss in bunches in porphyry. No defined lodes have yet been met with. Five shafts have been sunk close together, the deepest being 75 feet; ore was obtained from each.

Aid was granted some years ago for sinking 75 feet and cross-cutting 45 feet. The output from July, 1905, to end of November, 1907, amounted to 230 tons, for an average of 7 per cent. of copper. The gold contents ranged from a trace to 3 dwt. per ton, averaging under 1 dwt. Silver contents from 1 oz. to 4 oz. per ton.

Molong Division.

Delaney's Dyke.—Mr. C. S. Wilkinson reported that at Delaney's farm altered Silurian limestones and chloritic rocks occur, dipping west at 75 degrees. In these rocks a little grey sulphide and carbonates of copper were noted, but not in payable quantity. (Ann. Rept., 1886, p. 133.)

W. Anderson described Delaney's dyke as a garnetiferous rock containing gold and copper. It traverses Silurian slates near their junction with granite; strikes nearly north and south, and dips east at a high angle. Numerous shafts were sunk in the outcrop, the deepest 65 feet. The lode at 40 feet averages 10 feet; at 55 feet it reaches 23 feet, including a "horse" of dark slickensided slate, stained with carbonates of copper. At the south end of the deepest level the lode was reported rich in copper carbonates. (Ann. Rept. 1888, p. 183.)

Canowindra Division.

Eurow Copper Mine.—About 20 miles east of Eorbes, and 9 miles north-east of Eugowra. This mine, held as a mineral conditional purchase, portion 80, parish Wise, county Ashburnham, is the original site of Sloan's discovery of copper in the locality about 1881. It is reported that 60 tons of ore were extracted in 1884, which yielded, at the Waratah Smelting Works, 18 per cent. of copper. It was again taken up about 1896, and worked by a syndicate. It adjoins the Vychan Copper Mine, about 300 feet separating the workings. The Eurow was formerly known as Payten's Mine.

During a visit of the Writer in 1898, mining operations had ceased pending the result of treatment of a trial parcel of 20 tons of sulphides which, at the bottom of the workings—89-feet level—were very massive, and almost

*Should appear on page 139.

entirely iron pyrite. Apparently the result of the trial was not satisfactory as the property was subsequently advertised for sale under a judgment for wages.

In 1901, Mr. Nicol and party worked for several months, raising ore, valued at £615. (Ann. Rept., 1901, p. 55.)

In 1903 a reverberatory smelting furnace was erected capable of treating 70 tons of ore per week.

Water for domestic purposes is obtained from springs close to the mine, the Lachlan River being about 8 miles distant.

Inspector G. Smith reported in February, 1907, that the lode had been proved by shafts and levels for a length of 800 feet, and a depth of 132 feet. No record of output is obtainable, but the ore is said to have averaged 8 per cent.

(BATHURST MINING DISTRICT.—*Canowindra Division.**)

Fitzroy Mine.—Parish Malongulli, county Bathurst, near the Belubula River, on Licking Hole Creek, a tributary of Liscombe Poole's Creek, about 16 miles from Canowindra. At this and the adjoining Belubula Mine some of the earliest prospecting for copper in the State was done. In 1845 work was also progressing in the Belubula Mine, according to the late Mr. W. M. Rothery, of Cliefden Station, who also stated that no payable ore was discovered in either.

LACHLAN MINING DISTRICT.

Gundagai Division.

Gundagai Mine.—Portion 205, parish Kimo, county Wynyard, 7 miles from Gundagai.

Veins of quartz occur at this site, showing carbonate and sulphide of copper.

The strikes of two being N. 10° W. and N. 15° W.; at least five others strike about N. 20° to 40° E.

The first or north-western lines have been opened by two shallow shafts and a trench; of the others, two only have been opened by shallow shafts.

From the four principal openings, the following average samples of dressed ore were taken:—

Assay No.	Copper.	Gold.	Silver.	—
	per cent.	per ton.	per ton.	
08-433	8·25	1 dwt. 2 grs.	9 dwt. 19 gr.	N. 15° W. vein.
434	1·27	2 ,, 4 ,,	10 ,, 21 ,,	N. 40° E. vein.
435	8·60	2 ,, 4 ,,	8 ,, 16 ,,	N. 10° W. vein.
436	6·47	2 ,, 4 ,,	10 ,, 21 ,,	N. 40° E. vein.

Parkes Division.

Gunningbland Copper Lode.—On Gunningbland Run, near Trundle road, about 18 miles from Parkes. Inspector E. C. Whittell stated in 1898 that the copper ore—grey sulphide—occurs in the form of scattered threads and small bunches in quartzite, which is associated with limestone, sandstone, and conglomerate. A shaft had been sunk in the quartzite to 50 feet, to which depth no payable ore bodies had been discovered. A bold outcrop of ironstone occurs near by, stained in places with green carbonate of copper.

* Should appear on page 143.

LACHLAN MINING DISTRICT—*continued.*

Gundagai Division.

Jones' Creek, near Gundagai.—Copper carbonates occurred in serpentine and talcose slate close, to the old asbestos mine. Width, 2 feet at surface, but pinched out at 20 feet.

The assay value is shown in the following assays :—

No. 07-503—Copper, 4·32 per cent.
Gold, a trace
Silver, 4 dwt. 8 gr. } per ton.

No. 07-504—Copper, 1·82 per cent.
Gold, a trace
Silver, 13 dwt. 1 gr. } per ton.

Kangiara, p. 354.

Cowra Division.

King of England Mine.—On a spur of Illunie Mountains, parish Bang Bang, county Forbes, about 17 miles southerly from Cowra.

Chief Inspector J. B. Jaquet reported on this site soon after discovery (Ann. Rept., 1901, p. 166), and furnished the following particulars of development to that date :—

"Illunie Mountains form a continuation of Broula Range. Small specimens of copper ore were discovered here from time to time. In 1900 Peel and Shearsgold began systematic prospecting, and discovered some narrow veins from which a few tons of 8 to 23 per cent. ore were raised.

"In 1901 H. Newham found by chance a rich outcrop of carbonates, striking N. and S. and dipping W. in felspar-porphyry, and extending for 90 feet. About 20 chains further south, apparently on same strike, rock with carbonates was noted.

"The lode in a 29-feet underlay shaft was 2 ft. 6 in. to 3 feet wide, and very rich. At 29 feet the ore was a mixture of yellow and black sulphides. 17 tons 10 cwt. from 18 feet, mainly carbonate, yielded 15·5 per cent., and 5 tons 9 cwt., carbonates and sulphides, from 18 to 22 feet, yielded 27 per cent."

The ore having become pinched and poor with depth, aid was granted in 1903 (P.B. $\frac{a\,2\,\frac{6}{3}\,1}{c}$) to sink from 112 to 162 feet, and to drive 50 feet at bottom.

The lode had at this time been sunk on 110 feet, and driven on north 70 feet at the 60-feet level and south for 60 feet. Stoping had been carried up for a length of about 70 feet.

Under the grant, sinking was only continued for about 10 feet when operations were suspended owing to water and low grade.

The mine was taken up again in 1906, work being resumed by J. Peel. About 100 tons of ore were raised in 1907, but not treated or despatched.

The total output of ore during operations amounted to 470 tons 4 cwt. 2 qrs. 13 lb., yielding 64 tons 19 cwt. 2 qrs. 19 lb. of copper—equal to 15·2 per cent.

Queen of England Claim.—On same lode, 400 feet from the main mine. Shaft, 85 feet.

Molong Division.

Little Copper Hill Mine.—Three and three-quarter miles from Molong on the Wellington road, about half a mile from the old Copper Hill Mine, parish Copper Hill, county Wellington, on the Larras Lake Estate.

Probably first opened when Copper Hill was in operation; reopened in October, 1906.

The copper occurs as carbonate and a little grey ore in soft, ochreous material, filling vugs or cavities in limestone. Very irregular in occurrence, not forming definite channels. Several shafts have been sunk by the present syndicate from 30 to 60 feet, most, if not all, down to solid limestone.

The ochreous lode material is extremely light, soft, and friable, nineteen large bags (not ore bags) going to the ton. The soft filling of the cavities containing the copper ores has evidently resulted from dissolution and removal of the limestone by acidulated waters, and precipitation of insoluble oxides.

The composition of the ochre is shown in the following partial analysis :—

No. 08–587—Ferric oxide ..... 18·60 per cent.
Manganic oxide..... 18·00 ,,
Copper..... 1·65 ,,
Gold, a trace. } per ton.
Silver, 4 dwt. 14 grs. }

The mass of the small hill is limestone. On east and west of the cupriferous portion large segregated masses of quartz and quartzite occur. A highly altered igneous rock (probably andesitic) also occurs in close proximity.

The total output of ore despatched between October, 1906, and 16th December, 1907, according to the manager, Mr. W. T. Campbell, amounted to 195 tons 3 cwt. 2 qrs. 20 lb., averaging 13·81 per cent. of copper.

Fifield Division.

Mahgalore Lode.—Two miles from Wilmatha Tank, and 12 from Melrose, parish Parkes, county Cunningham. Strike N. 70° E.; dip slight S. 20° E. In felsite. Lode consists of ferruginous quartz, partly chalcedonic; iron oxide abundant. Copper carbonates occur on joint faces of felsite, near surface. At 50 feet, copper ore in gossan met, which continued to 75 feet, 3 feet wide.

Aided (P.B. $\frac{122}{0}$) for sinking from 36 feet to 96 feet. Sulphides showing at the latter level. Aided to continue shaft to 185 feet. At 140 feet pyrites with a little copper sulphide reported. Water heavy. No further record.

Condobolin Division.

Melrose Copper and Silver Mine, about three-quarters of a mile west of the "Melrose Hotel."—Discovered and opened by J. Byrum, who was aided to sink from the Prospecting Vote. The mine is situated on a rugged hill about half a mile north of the Big Ben Mine. Ferruginous slate crops out in cliff-like masses on its summit, having a north and south cleavage. In one spot the slate was stained by copper carbonates, forming films on the cleavage planes. A few feet to the west a flat cross joint carried some massive carbonate of lead, stained with carbonate of copper. It has been followed some distance on the dip to the north-east. The aided vertical shaft is situated between the two outcrops, and a crosscut intersects the cupriferous slates at about 100 feet deep. At this level the cleavage planes of the unweathered slates are coated with films of red oxide, which accounts for the carbonates on the surface. Prospecting operations did not reveal a payable ore deposit.

LACHLAN MINING DISTRICT—*continued*.

Melrose District.—Copper ores occur sparingly over a considerable area in this district, but so far none have been proved in workable quantity. Copper was first discovered hereabouts by J. Byrum about 1884. The chief feature of interest is the association of the copper ores, chiefly with ancient conglomerates, much crushed and indurated. The pebbles consist of quartz, and the cementing argillaceous material has by pressure and shearing assumed a schistose structure. The alternating slates and sandstones are highly ferruginous. In some instances the cleavage planes of the slates are coated with copper carbonate, which, at a lower depth, gives place to a film of red oxide of copper.

From Mount Nobby three samples were assayed in the Departmental Laboratory in 1907—Nos. 5662-4—for yields of 7 to 14·75 per cent. of copper; gold, a trace to 2 dwt. 4 grs.; and silver, from 14 dwt. to 1 oz. 2 dwt. per ton.

Molong Division.

Molong Creek.—S. Stutchbury, in 1851, mentioned finding a green rock, "smaragdite," containing pure native copper, about 1 mile south of Mr. John Smith's house, and 100 yards west of Molong Creek.

In Spring Creek, near its junction with the Bell River, in the parish of Eurimbla, county Gordon, large pieces of native copper were found on the surface. A few thin quartz leaders, with calcite showing carbonates and grey sulphide of copper, and assaying 43 per cent. of copper, were sunk upon, but gave out at a shallow depth, according to W. Anderson (Ann. Rept., 1888, p. 183).

Fifield Division.

Mordialloc Copper Mine.—On Mordialloc Station, 3 miles from Trundle, parish Plevna, county Cunningham Strike N. 70° E.; dip north 10° west at about 9°.

Mr. F. Danvers Power reports that two other lodes on the north have also been prospected. Lodes associated with decomposed andesitic rock. Average channels 4 feet wide, but not all ore-bearing. The productive parts form small lenses. Carbonates above water-level, sulphides below; associated with quartz. Grey ore in north blocks.

South lode developed by three shafts and some trenches for about 4 chains. Carbonate stains noticeable in the material thrown out.

Western and middle shafts old and inaccessible. Recent work confined to eastern shaft. At 47 feet a level has been driven easterly for 27 feet and west 5 feet from the shaft. A sample from 2 ft. 10 in. wide yielded 2·4 per cent. of copper, with traces only of gold and silver.

Geological-Surveyor L. F. Harper reported (15/10/05) that D. Cheshire and party's lode was sunk on 80 feet and driven east 30 feet at the 60 feet level, and west 80 feet. Sulphides in bottom of shaft. One and a half tons yielded 9 per cent. of copper at Lithgow, 3½ dwt. of gold, and 3 oz. of silver per ton. Average width of formation, 3 to 4 feet.

Cootamundra Division.

Mount Felstead Copper and Silver Mine.—Portion 253, parish Yeo Yeo, county Bland, close to Stockinbingal-road, about 7 miles north-westerly from Cootamundra.

Country quartzofelsite, imparts much crushed. Quartz veins and ferruginous jointings numerous, some containing a little gold but not payable. Discovered by G. E. Felstead.

Outcrop betrays no indication of the economic metals other than gold, which began to show at 36 feet. Three shafts (1903), 25, 52, and 70 feet. Payable ore struck in latter at 36, and penetrated 35 feet. Horizontal extension not tested; apparently a short lens.

The Mount Felstead lode appears to have originated from metallic and silicious solutions investing a jumbled mass of rock fragments resulting from shattered fissuring of the country at this point. The ore lens increased in width from 1 to 6 feet, about one-fourth of which is ore. The proportion, however, is variable owing to large blocks of country occasionally curtailing area of deposition.

The metallic ores consist of a mixture of carbonates, red and black oxide, and yellow sulphide, of copper; carbonate and sulphide of lead, and sulphide of zinc.

The composition of the mixed ores is indicated by the following returns of the first parcels despatched:—8 tons 3 cwt. 3 qrs. 6 lb. yielded, copper—13·9 per cent.; lead, 11·8 per cent.; silver, 49 oz. 11 dwt. 4 grs.; gold, 1 dwt. 14 grs. per ton. 7 tons 7 cwt. 3 qrs. 20 lb. yielded—copper, 11·5 per cent.; silver, 48 oz. 10 dwt. 19 grs. per ton.

Seventy tons of ore were raised and 50 sold, netting £150, in 1903. Shaft deepened to 80 feet. Driven 30 feet south, and 8 feet north. (Ann. Rept., 1903, p. 48.)

Re-opened in 1905, under name of Cootamundra Silver and Copper Mine. Main shaft deepened to 145 feet. Steam pump installed. 10 tons of ore despatched; 20 tons at grass. (*Ibid.*, 1905, p. 45.)

Under suspension for greater part of 1906.

During 1907, two winzes sunk from 70-feet level; main shaft deepened to 190 feet; 120 feet of cross-cutting and driving; 85 tons of ore sent to Swansea for treatment.

Cudal Division.

Mt. Keenan (Amaroo Mine).—Portions 252 and 255, parish Boree Nyrang, county Ashburnham; 1½ miles south of Amaroo Railway Station. Labradorite porphyry country. Formation described by Inspector G. Smith (P.B. $\frac{2}{0}\frac{4}{7}\frac{2}{4}$) as apparently 12 to 15 inches thick, showing copper carbonates freely.

Aided to sink to 60-feet level. The copper veins exposed near surface were reported to have dipped east out of shaft at 30 feet.

The output to date 8 or 9 tons, yielding 2 to 4 per cent. of copper; and 1½ tons, yielding 8·5 per cent. Deepest shaft, 90 feet; ore very thin at bottom.

Condobolin Division.

Mount Susannah Copper Lode.—About 1 mile from Melrose Homestead. A cupriferous outcrop in crushed conglomerate close to intrusive porphyry was opened here about twenty-four years ago by J. Byrum. Shafts sunk 30 and 40 feet revealed carbonate of copper impregnating the country for about 6 or 7 feet in width along a north and south strike, but no payable ore bodies were exposed. Aid was granted to continue one of the shafts to 100-feet level, and to drive along the lode.

LACHLAN MINING DISTRICT—*continued.*

(COBAR MINING DISTRICT.—*Nymagee Division.**)

Nangeribone.—The following results have been obtained from samples from J. Brien's aided prospecting shaft :—

No. of Assay.	Description of Sample.	Copper, per cent.	Gold, per ton.	Silver, per ton.		
				oz.	dwt.	grs.
07-4705 ..	Slightly pyritic rock	2·60	a trace.	7	12	10
07-4706 ...	Ferruginous quartz with carbonates ...	6·30	,,	9	13	19
07-4707 ...	Pyritous quartz with carbonates and oxides.	7·17	,,	9	18	4

LACHLAN MINING DISTRICT.

Cudal Divison.

Nangar Range.—Copper ore in small quantity, so far as proved, occurs in two places on the north side of the Nangar Range, about 2 miles southerly from the "Murga Hotel." In Clayton's gold lease, at a depth of 80 feet, in ferruginous quartzite, a small patch of red oxide of copper was cut, but it appeared entirely isolated, as further search failed to reveal any other indications of a copper deposit. This occurrence is close to intrusive quartz felsite. About half a mile distant from this site, and close under the mural cliffs of the range, a little carbonate and sulphide of copper, associated with quartz and talcose material, has been opened for a few feet. The Nangar Range consists of massive conglomerates and sandstones probably of Devonian age.

Cowra Division.

Neila Creek.—In Conditional Purchase 78/75, parish Morongla, county Forbes, about 10 miles south of Cowra, a shaft has been sunk 73 feet in a strong gossan outcrop, in which a little copper is visible. A crosscut has been driven 108 feet. Aid was granted to continue sinking.

Parkes Division.

Parkes District.—Copper ores occur in small quantities in numerous localities in this district. The following have been noted :—

Goobang Station, 5 miles north-west of Parkes.—Copper ore discovered in 1882, and a few tons raised.

Gobandry, 8 miles north-west of homestead.—Copper ore prospected about thirty years ago to 50 feet. Traces only exposed.

Goonumbla Hill, 13 miles north-west of Parkes, on Goonumbla-road, also 4 miles S.S.W. of Goonumbla Hill, on the main range.—Copper ores occur.

Limestone Reserve, 6 miles north-west of Parkes.—In 1883 a shaft was sunk 110 feet in a lode striking north-east and south-west. Twelve tons of ore raised.

Gunningbland Station, 18 miles west of Parkes.—A strong outcrop of ironstone, carrying copper carbonates and galena, occurs here, which was partly opened under prospecting aid in 1898, but unsuccessfully.

Little Mount Currumbla Station, 12 miles west of Parkes.—Native copper occurs here in andesite with quartz and epidote.

Langford's Lease, 12 miles north of Parkes.—Lode traced on surface for about 190 yards by cuttings and trenches, the deepest 18 feet. Lode about 1 foot thick. Assays of samples returned 7 to 30 per cent. of copper.

* Should appear on page 254.

About 1½ miles east, and also west of this lease, copper indications also occur.

Welcome Reef.—Close to this reef, about 2 miles from Parkes, on the Forbes line, Mr. J. Stott reported copper ore. Opened out some years since to a shallow depth.

Trundle.—Four miles south-east and the same distance north-east in the same belt of slate, copper indications occur—in one instance native copper—but nothing payable known, aid was granted one site from the Prospecting Vote.

Cumnock.—Five miles west on Peak Hill and Dilga-road, a patchy copper vein was opened thirty-five years ago to a depth of 30 feet. Taken up again about 1890. Nothing payable or permanent discovered.

Molong Division.

Peabody Copper Mine.—Six miles southerly from Molong, close to the Cudal-road. In J. Black's private land, parish Boree Nyrang, county Ashburnham. Rich bunches of copper ore at surface. Opened by J. Torpy and others about 1872. Copper ores from this mine were exhibited at the Philadelphia Exhibition in 1875.

The prospectors sank two shafts 60 and 100 feet. The following extracts are from a report dated 27th July, 1872, by Captain Reynolds (manager of the Icely Mine, at that date), supplied by J. W. Torpy:—

"Rich veins of red oxide cut at 9 feet and followed down to lowest point reached. Trend north and south. Red oxide and malleable copper broken from shaft. In two places, 50 yards south of main shaft, several rich veins of same class of ore were being uncovered. Outcrop, inconspicuous."

Captain White (of Carangara Mine) at same date described width of lode as 3 to 5 feet. Underlay west at 1 in 6. Traced for about 160 feet by shafts and open cuts.

In 1900, F. Danvers Power described the occurrence of native copper, cuprite, and carbonates in joints of andesite, more especially near the walls of this rock.

Assays of samples of the ore lying at grass yielded—copper, 6 to 9 per cent.; silver, 10 to 17½ dwt., and gold, a trace, per ton.

Condobolin Division.

Phœnix Mine (formerly Shepherd's), G.Ls. 10 and 277, parish Condobolin, county Cunningham, about 2½ miles north of Condobolin.—During 1906 120 tons of ore were reported to have been raised and despatched for a return of £466. (Ann. Rept. 1906, p. 47.)

In 1907 Inspector G. Smith reported the minerals present as gold, silver, and copper, in schist; worked chiefly for gold. Depth of proving, 210 feet.; length, 90 feet. Mine idle.

Six tons of copper ore yielded 5 per cent., and 17 dwt. of gold and 7 oz. of silver per ton. Thirteen hundredweight of lead ore yielded 25 per cent. lead, 17½ dwt. of gold, and 19 oz. of silver.

Molong Division.

Pine Hill Copper Lode, M.L. 1, parish Gumble, county Ashburnham, 13 miles from Molong Railway Station, and 10 from Manildra.

LACHLAN MINING DISTRICT—*continued.*

F. Danvers Power reports a contact lode between granite and limestone, developing garnet. The copper occurs in the latter chiefly as carbonate, with sulphides below water-level.

Shaft sunk about 1880 to 55 feet on hanging wall, but did not cut lode. Copper-bearing portion of garnet apparently 6 to 8 feet wide, but not of uniform richness. Copper stains extend beyond limits mentioned.

First shaft to north sunk in 1903, on underlie to about 20 feet. Next, or middle shaft, sunk 60 feet, part vertical, part underlie. Usual grade of ore. No workings.

North shaft, 120 feet deep, part vertical, part underlie. Crosscut at 80 feet, showing a width of 12 feet of copper-bearing garnet. A short drive to south at bottom of shaft revealed a good deal of magnetite. Crosscut west into limestone. Strike of deposit about N. and S., underlie 60° to West, Most development at southern end. A sample from 8 feet across the third trench, near southern end of block, yielded 2·7 per cent. copper. Sample from heap of selected ore from neighbouring trench, picked as clean as possible, averaged 2·9 per cent. copper, and a trace of gold. Green garnet imparts a deceptive appearance of copper value.

From east crosscut at bottom of northern shaft, a sample from a width of 5 feet assayed 2·28 per cent. copper. Copper contents appear fairly constant, and naturally richer than to be expected below.

Condobolin Division.

Ramping Lion Lode, 2 miles north of Condobolin, parish Condobolin, county Cunningham.—Inspector J. James reported (P.B. $\frac{1}{0}\frac{6}{4}\frac{2}{2}$) a vein 12 to 20 inches wide in schist, good ore being obtained in two shafts to 25 feet. Aided to sink from 25 feet to 100 feet. At 33 feet copper stains; at 50 feet, slate and ironstone; at 75 feet, no ore.

Molong Division.

Reedy Creek.—On the 12th April, 1852, S. Stutchbury reported: "At 300 yards from Reedy Creek, and half a mile from the station hut, which bears E. 10° S., is a mound of porphyry, composed of a red paste with crystals of felspar, traversed by veins of prehnite. Masses of ore have been found with native copper, several large lumps of which have been found. One, weighing 102 lb., is now in the possession of Mr. Smith." Probably this lump is identical with the exhibit at the London Exhibition of 1851, consisting of 1 cwt. of native copper from Reedy Spring, the property of the late Mr. Smith, of Gamboola Station, near Molong. A similar block, weighing $\frac{3}{4}$ cwt., from the same locality, is at the station homestead.

Gundagai Division.

Reno, about 3 miles south J. Robinson's private land.—Inspector E. C. Whittell reported (P.B. $\frac{2}{0}\frac{6}{0}\frac{3}{0}\frac{2}{0}$): "Copper-bearing quartz vein in slate, carrying 1 to 4 inches of yellow copper ore." Aided to sink to 65 feet.

Condobolin Division.

Rifle Butt Claim, 3 miles N.W. of Condobolin, parish Condobolin, county Cunningham.—Inspector Smith reported (P.B. $\frac{2}{0}\frac{7}{7}\frac{2}{0}$): "A small vein of copper ore of good quality (15 to 20 per cent.), but too small for profitable working. Bismuth also present." Aided to sink to 100 feet.

LACHLAN MINING DISTRICT—*continued.*

Junee Division.

Rockdale Gold and Copper Mine.—P.G.L. 1, parish Warri Warral, county Clarendon, Junee Reefs.—Baker and party reported that in sinking their main shaft, at a depth of 60 or 70 feet, a band of blue and green carbonates of copper was struck, having an average width of 1 ft. 6 in. This ore continued in the shaft for about 8 feet with a northerly dip. At 100 feet, the reef consists of ferruginous quartz, stained with copper carbonates. Samples of the blue carbonates assayed 24·96 per cent., and the green about 12 per cent. In the former, a return of 6 oz. 9 dwt. of silver was also obtained. From this mine it was also reported that samples of the auriferous portions of the reef treated at Wyalong, Footscray, and Ballarat (Victoria), yielded from 3 to 7 oz. of gold per ton. Ordinary battery treatment reported unsuitable for extraction.

Condobolin Division.

Sultan Copper and Lead Mine, portion 1, parish Condobolin, county Cunningham.—Discovered by B. Roberts, about 1876. Three miles N.W. of Condobolin. Inspector G. Smith reported (29/10/06) copper ores in schist. Worked to 90 feet, stopes filled. Said to have been 2 feet thick. New shaft 18 feet.

During previous five months 17 tons 17 cwt. despatched yielded about 13 per cent. of copper, 14 oz. of silver, and 1 dwt. of gold per ton.

Two previous parcels treated at Dapto during the previous year yielded: 7 tons, 11 per cent.; 10 tons, 17 per cent.

T. W. Copper Lode (late Byrum and Sinclair's), portion 9, parish Melrose, county Cunningham, 31 miles from Condobolin Railway Station.—Discovered by James Byrum in 1882. Ores: copper, lead, and silver. No output. Prospecting company formed. Old shaft 45 feet sunk under aid.

Described by Inspector G. Smith (3/11/06) as impregnated schist. Strike N. 20 W.; dip N.; 70 E., shaft, 67 feet.

Cudal Division.

United Empire Mine, 2½ miles east of Murga, and 17 miles from Moura Railway Station.—Inspector G. Smith reported (P.B. $\frac{4}{5}\frac{1}{7}\frac{2}{2}$): "A strong quartz vein in quartz-porphyry, said to average from 4 to 6 feet wide. Copper carbonates and sulphate showing freely, and a little copper pyrites in lower portion of shaft."

Aided to sink from 100 to 150 feet, and to drive 100 feet on vein at bottom. Originally worked for gold.

Canowindra Division.

Vychan Copper Mine, portion 81, parish Wise, county Ashburnham, 20 miles east of Forbes, 8 miles from the Lachlan River, and 14 miles from Cookamidgera Railway Station.—Copper was discovered in the adjoining Eurow Mine—300 feet distant—by a member of D. Sloan's family, about 1881. The site was secured by mineral conditional purchase, but was abandoned after three shafts had been sunk. In 1889, 56 tons 9 cwt. from this lode, forwarded by Mr. A. Lockart to the English and Australian Smelting Works, Waratah, yielded 17⅛ per cent. of copper.

LACHLAN MINING DISTRICT—*continued.*

The country consists of highly-crushed and altered rocks. The lode strikes N. 30° W., and dips west.

The Vychan Mine was taken up by F. Clayton as a mineral lease of 40 acres in September, 1897. The main shaft was continued to the 150-feet level, and the north to 120 feet. Levels connect the shafts at 30, 109, and 150 feet. The sulphide ores began to appear at about 120 feet from surface. Above this level oxidised ores occurred in bunches. The lode varied from 1 to 8 feet in thickness, averaging about 2 feet. Both the oxidised and sulphide ores were of excellent quality. To 1899, about 50 tons of ore had been despatched to the Smelting Company of Australia, Limited, Dapto, the copper contents of which ranged from 17·7 to 25·3 per cent; silver, from 4 to 10 oz.; and gold, 2 to 5 dwt. 14 grs. per ton.

Since the date mentioned, the following consignments were treated at the above works for yields shown in the accompanying table, which reveal the character of the ores:—

Weight.	Copper.	Silica.	Gold, per ton.	Silver, per ton.	Nature of the Ore.
	per cent.	per cent.	dwt. gr.	oz. dwt. gr.	
53 bags (?)	20·5	20·2	1 19	3 2 9	1st carbonates.
22 ,, (?)	12·5	20·6	4 14	1 19 14	2nd ,,
10 ,, (?)	12·4	26·8	4 4	2 3 14	2nd ,,
tons cwt.					
4 17	21·7	.....	3 0	.....	1st ,,
1 1	16·1	.....	3 4	.....	2nd ,, (screenings).
2 16	16·3	.....	1 19	.....	Fines ,, ,,
2 4	23·3	.....	4 0	.....	1st ,,
5 10	8·5	.....	3 19	.....	4th ,,
6 17	9·6	.....	2 14	.....	Sulphides from 150-foot level.
2 6	23·9	.....	2 4	.....	Carbonates.
1 7	17·5	.....	2 19	.....	Fines ,,
8 5	11·0	.....	2 14	.....	Sulphides.
6 0	13·0	.....	3 0	.....	1st sulphides.

In driving between the north and south shafts at the 150-feet level, the main body of sulphides was struck near the north shaft, at an angle which carried it about 7 feet west of the south shaft, from which the level started, and accounted for the blank country in the latter. The sulphides were solid and 6 feet wide at the point of intersection.

Prospecting northerly from the 120-feet level in the north shaft. After 50 feet of blank country, copper stains and a little copper glance made in the drive. (For particulars of the adjoining mine, on the same lode, *see* Eurow Mine.)

Worked for five months in 1901, value of output, £720—ore averaging 15 to 19 per cent. (Ann. Rept. 1901, p. 55.)

Worked on tribute in 1902—ore 18 to 22 per cent. Lode irregular; in bunches.

MUDGEE MINING DISTRICT.

Dandaloo Division.

Ace Mine, M.Ls. 24 and 31, parish Beaconsfield, county Kennedy.—Lode outcrops for about 350 yards in bunches of porous iron oxide after pyrites. Strike N. 30° W.; dip N. 60° E., varies from 45° near surface, to 32°, and then 35° at 250 feet.

The main—or underlay—shaft has been sunk 321 feet, water being struck at 275 feet.

Development.—Lode driven on 25–30 feet at the 170-feet level, 140 feet at the 220-feet level, and 80 feet at the 270-feet level. From the latter a crosscut has been driven 240 feet north-easterly to connect with No. 2 (vertical) shaft.

The ores consist of oxides, carbonates, and grey ore at 170-feet level; native copper and enriched sulphides at 220-feet level. At 270 feet, enriched sulphide (black) and pyrites occur south of shaft, also making north. The width of channel at each level being 4 feet, 6 inches to 6 feet, and 3 to 5 feet respectively.

At 321 feet the owner (Mr. A. H. Dight) reports about 1 ft. 6 in. of lode-stuff, carrying 6 inches to 8 inches of good ore, the remainder being pyrites.

No ore has been despatched, the work carried on being purely developmental; a smelter being contemplated when a safe margin of ore is in sight.

It is estimated by the owner that on the 10th January, 1908, there were in hand about 40 tons of firsts and 150 tons of seconds. The gossan is also estimated by him to contain from 1 to 2½ per cent. of copper, and the pyrites 1½ per cent.

A sample of the massive sulphides at 220 feet, taken by the Writer, yielded the following results:—

No. 07-2374—Copper	5·42	per cent.
Iron	36·26	,,
Sulphur	24·60	,,
Silica	6·98	,,
Gold	a trace	per ton.
Silver	16 dwt. 8 grs.	per ton.

A sample of the screenings from 250-feet level yielded:—

No. 07-2373—Copper	3·10	per cent.
Iron	37·94	,,
Sulphur	39·52	,,
Silica	10·02	,,
Gold	a trace	per ton.
Silver	17 dwt. 10 grs.	per ton.

The composition of the sulphides in this mine (also those of Mount Royal, Orange Plains, and Bogan River mines, so far as proved), illustrated in partial analyses, reveals most kindly smelting ore, the low silica rendering it eminently suitable for fluxing the silicious surface ores of the district.

Wellington Division.

Backes' Copper Mine.—Leases for copper were taken up about 1873 by John Backes, at Sugarloaf, parish Galwadgery, east of Wellington. In 1883, the Warden described the mine as situated east of The Springs Railway

Station, near the Burrandong-road. At this time it was designated the Great Burril Mining Company's Lease. One of the proprietors, C. Barton, supplied the Warden with the following information:—Three shafts, over 100 feet each, have been sunk, also a number of shallower ones. The first shaft was on a vein rather inconstant in thickness, sometimes pinching out, the maximum thickness being 2 feet; about 25 tons of ore were taken from it, averaging about 12 per cent. copper. Another shaft, sunk at the north end of a large gossan outcrop, reached a deposit of copper and iron pyrites. A drive to the eastward, at 60 feet, discovered a small quantity of decomposed lodestuff, containing native copper. Assays of ore then at grass were reported to yield 8 to 14 oz. of silver per ton, and from 4 to 7 per cent. of copper. The principal feature of the property was reported to be an immense gossan "blow," or outcrop.

Gulgong Division.

Belara Copper Mine, about 25 miles from the Wellington Railway Station, alongside the main Mudgee road. Locality also known as Goolma. Portions 27, and 31 (100 acres), parish Worobil, county Bligh.

The Belara Mine, according to the Warden's report of 1880, p. 98, was discovered by G. McDonald on freehold land. In the "Mineral Statistics of New South Wales," 1875, p. 90, the lode is recorded as 2 feet thick. Strike N. and S.; dip 1 in 3. One hundred and fifty tons of ore were then at grass, but no tests had been made.

The next official record is that of the Under Secretary for Mines in 1885, in which it is stated that 1,000 tons of ore had been raised during the year, producing 640 (?) tons of regulus, which is evidently an error. Depth of shaft, 160 feet; deepest level, 140 feet. Width of lode, 8 inches to 8 feet.

In 1886 there was no record; in 1887, 100 tons of ore were raised, but no smelting was done; during 1888, 1,400 tons of ore were raised, 840 of which were smelted for 70 tons of copper, valued at £5,250.

In 1889 little work was done. Three hundred tons of ore raised yielded 16 tons of copper, valued at £800. The smelting furnaces were only worked for three months, mostly experimenting with gossany gold and silver ores.

In 1890 the only work performed was the deepening of the engine shaft to 55 feet. The mine apparently remained idle from this date until October, 1893, when twenty men were employed until May, 1894. Two hundred tons of ore raised during this period yielded 9 tons of copper. So far as official returns are recorded from this mine, the output amounted to about 260 tons of copper to the end of 1907.

D. H. Thomas and others had the mine on tribute in 1893 for about six months, during which about 20 tons of copper were produced (9 in the official return). To Mr. Thomas the Writer is indebted for the following particulars, which represent the mine as it then stood:—Shaft, 200 feet deep; levels at 112 feet and 155 feet (lowest); lode, 3 feet wide at 112 feet, 6 feet at 155 feet. Value of ore—5 per cent. copper; gold, 3 dwt., and silver, 3 oz., per ton. The lode traceable on the surface for a considerable distance by a gossan cap from 1 ft. 6 in. to 12 feet wide, in which gold and silver are

E. R. Cocks. **Belara Smelting Works.**

E. R. Cocks. **Belara Copper Mine.**

PLAN AND SECTIONS OF THE BELARA COPPER MINE



present. Carbonates of copper showing in lode 300 yards north of shaft. Gangue silicious at surface. Sulphides from lowest level solid. Country consists of slate.

The smelting plant at this time consisted of two reducing, one calcining, and one refining furnace. Firebrick made from clay, obtained about 9 miles distant.

The Belara Mine was examined by the Writer in December, 1907, and January, 1908. The lode strikes about N. 20° W. in slate country, about 90 feet west of an intrusive dyke of quartz-felsite, to the occurrence of which it doubtless owes its origin.

The channel, in which the ore makes in lenses, is persistent for a considerable distance, as shown in the accompanying longitudinal section of Belara provings supplied by Messrs. Cock Bros.

The Native Bee Mine, recently discovered, about 80 chains southerly, is also on the same strike.

The Belara section has been superficially proved by shafts and shallow openings for about 1,540 feet northerly from the main shaft, and about 120 southerly. Though these shafts are not now available for inspection, it is evident that ore has been raised from them. At the extreme north end, ore has evidently been removed from an open excavation where two outcrops of gossany lodestuff occur, separated by a horse of country in part igneous. These superficial workings probably afforded oxidised ore for fluxing during early smelting operations. It is highly probable that lenses of sulphides occur beneath.

The width of ore exposed in the main shaft varies from a few inches at the pinched northern end of the lens up to 10 or 12 feet. The lens averages from 3 feet to 8 or 10 feet in width.

At 100 feet pyrites occurs massive but poor in copper, zinc-blende also being prominent. At the lower levels the latter averages about 4 or 5 per cent, in places, however, making solid on the hanging wall up to a foot in thickness and to 40 per cent. metallic zinc. This band was usually discarded in working.

Recent developments.—Leased to Captain H. Cock in 1899, under a purchasing option. Main shaft unwatered, depth 200 feet. Opened out at 150-feet level, and stoped up to 100-feet level on south side of shaft, for a length of about 70 feet.

Seven hundred and eighty tons of ore (including some from surface) smelted for 36 tons of copper, equal to an extraction of 4·6 per cent. The copper product contained gold to the value of £9, and silver £7, per ton.

Operations ceased after two years' continuance, not proving remunerative with the plant available.

In March, 1907, the same shaft was unwatered and repaired by Messrs. Cock Bros.; and the lode driven on 25 feet each way at the 200-feet level; and underhand stoped 60 feet long and 12 feet deep on south side of shaft.

During operations—which ceased in December, 1907—807 tons of ore were treated in the local reverberatories for an average return of 3·33 per cent. of copper; and gold at the rate of 1·47 dwt., and silver 2·21 oz., per ton.

Solid ore remains between the 200 and 150-feet level stopes. The south face at the former level at present reveals 3 to 5 feet of sulphide ore, zinc-blende making on the hanging wall. An average sample from a width of 3 ft. 6 in. in face yielded the following composition:—

No. 08-160—Copper	2·40	per cent.
Iron	34·25	„
Zinc	11·34	„
Sulphur	48·28	„
Silica	28·48	„
Gold	2 dwt. 4 grs.	per ton.
Silver	2 oz. 18 dwt. 19 grs.	per ton.

From the south face at 150-feet level the following average sample was taken from a width of about 7 feet:—

No. 08-161—Copper	1·20	per cent.
Iron	22·12	„
Zinc	19·74	„
Sulphur	29·49	„
Silica	10·60	„
Gold	2 dwt. 4 grs.	per ton.
Silver	2 oz. 18 dwt. 19 grs.	per ton.

The local smelting plant consists of two reducing and one roasting and refining reverberatories. The sulphide ore was roasted in clamps—reduced to 12 per cent. matte in first, and 40 per cent. matte in second smelt; in which form it was recently despatched. This ore is described by Mr. E. R. Cock as free-smelting and self-fluxing; and would be most suitable for blast furnace treatment.

The shallow development—200 feet—in one site only, cannot be regarded as an efficient test of the possibilities of the Belara lode. It is highly probable that other lenses will be proved below the shallow oxidised zone on the northern strike. Development of other sulphide bodies on the course of the lode, even of the moderate grade exposed in the main shaft, should give a new life to the mine under blast furnace treatment, and lead to further discoveries along the strike towards the Native Bee Mine.

Dandaloo Division.

Bogan River Copper Mine (formerly Royal Sweep), M.L. 1, parish Beaconsfield, county Kennedy.—About 20 miles from Dandaloo, on the Bogan River, and 48 miles from Trangie Railway Station. The Bogan Gate–Bulbodney Railway, however, has been surveyed within 8 miles.

Discovered by W. Shallalla in 1905. Supposed to be on faulted continuation of Mount Royal lode about half a mile distant; connection not proved.

Work under Bogan River Company began in February, 1906.

Strike of lode, N. 62° W.; dip S. 28° W. at 47°. Width from 1 foot to 3 feet, in places 4 feet or more. Opened by three shafts, 65 feet, 100 feet, and 150 feet. At 60-feet level 150 feet driven on ore, and 65 feet at 140 feet, when examined, August, 1907. Sulphides at 150-feet level of low grade.

Strike of lode N. 62° W.; dip S. 28° W. at 47°. Width 1 ft. 6 in. to 4 feet.

Country—micaceous schist. Outcrop ill-defined.

The following particulars of subsequent developments to 19th May, 1908, have been supplied by the manager, Mr. D. Jones:—

"Depth of shaft, 125 feet; a level driven at 60 feet, and one at 120 feet; length of No. 1 level, 340 feet; stoping in oxidised ore from 18 inches to 6 feet in width; value 9 per cent.

"No. 2 level driven 324 feet in decomposing sulphide the whole distance, varying in width from 2 feet to 12 feet; average value, 5 per cent.

"Poppet legs and winding engine have been erected; also 600 feet overhead tramway from shaft to furnace and burning floors, respectively.

"Preparatory to smelting, the sulphides are roasted in heaps; and, after roasting, are practically self-fluxing.

"Ore raised to date, approximately, 2,500 tons, representing the amount mined from No. 1 level and stopes therein, and from drive at No. 2 level; no stoping yet done at No. 2 level.

"Generally speaking, the lode seems of a permanent character, as ore is showing underfoot in the whole length of No. 2 level.

"Ore disposed of as follows:—

Sold	627	tons firsts.
,,	80	,, seconds.
Smelted	560	,, all classes.
On surface	1,000	,, ,,

"From the 560 tons smelted, 28 tons blister copper have been obtained.

"(1) Reverberatory furnace—Dimensions of hearth 23 feet x 12 feet, underground culvert 50 feet, to stack 60 feet high.

"Smelting commenced in February (1908), and is proceeding satisfactorily, taking the present price of copper into consideration.

"There is an abundance of wood for furnace fuel close at hand.

"Two tanks have been excavated by the Company of a capacity of 5,000 and 1,000 yards respectively."

Wellington Division.

Bungiebomar (or Copper Hill) ***Mine.***—J. Crick's land, parish Bungiebomar, county Lincoln, about 25 miles from Wellington.

Mr. F. Danvers Power informs the Writer that copper carbonates occur here in joints of andesite, with cuprite and native copper in small irregular bodies, not along any defined lines. Best show of the kind in Smith and Stewart's shaft, where carbonates are exposed for its length and breadth at the lowest level. Occurrence similar to Delaney's Dyke near Molong, but does not offer much inducement for development.

Leadville Division.

Bowenbang Creek, 4 miles from Hannah's Bridge, Leadville to Coolah road.—Dawson's prospecting shafts, 40 feet and 70 feet, sunk on different veins in which rich grey copper ore occurs in prills up to 40 per cent. grade, but not in quantity.

Dandaloo Division.

Christmas Gift Mine, Albert Water Holes, M.L. 1, parish Albert, county Kennedy, 13 miles from Dandaloo, 43 miles from Trangie Railway Station, and about 7 miles from Bulbodney line, in course of construction.—Discovered by C. J. Keenan, Christmas, 1897. Strike N. 75° E.; dip S. 15° E. at 60° in contorted schist. Position in March, 1907: Opened to 233 feet in depth, driven 13 feet south-westerly, stoped where payable upwards for a

length of 100 feet or more in oxidised ores. Probably 200 tons of ore despatched. Discoverer sending 96 tons of a reported yield of 13 to 36 per cent. of copper.

Work stopped for some time. Two men now raising ore on tribute. A few bunches left in higher levels.

Silicious sulphides at 233 feet, good grade when dressed. Lode about 2 feet wide at this level.

Two parcels despatched in June, 1907, reported to have yielded—carbonates 26 per cent.; sulphides, 10 per cent. Quantities not stated.

Chris. Watson Mine, M.L. 16, parish Beaconsfield, county Kennedy—Adjoining Mount Royal Mine on east end. No outcrop. Small bunch o ore cut in drive from 80-feet level in shaft. Eight tons yielded 18·5 per cent copper.

In February, 1908, 22 tons of ore from this mine are reported to hav assayed 23 per cent. copper.

Leadville Division.

Denison Town, Talbragar River.—In 1888 a copper lode in slate country was opened by Messrs. Wall and Lynch during the copper boom of the year, near the south-west boundary of Pine Ridge Station. Outcrop traceable for about 20 chains, but very narrow, striking about north and south. Opened to about 18 feet. Twenty-eight tons of carbonate and grey ore sent to the Waratah Smelting Works reported to have yielded nearly 15 per cent. copper. The site has recently been taken up by Mace and others, of Leadville. (*See* Mount Laut.)

Wellington Division.

Dripstone.—The Blayney Mining and Smelting Company in March, 1907, secured an option over a copper lode on the Camelford Park Estate, near Dripstone, and a start was made to prospect it.

Great Wheal Burril Consols Copper Mine, Burril Ranges, 9 miles from Wellington.—This property formed the subject of a dispute brought before Parliament in 1873. The matter being disputed mineral selections by Burn, Philp, & Co., embracing Mylecharane's Lode, Muddy Creek, on Burril and Booral Run. Copper ores in the Australian Museum, purporting to have come from a depth of 45 feet in a 30-feet lode, are labelled with this name, but nothing authentic is known of the deposit. (*See* also Backe's Mine.)

Gulgong Division.

Gulgong.—Within 3 miles of Gulgong (probably Isbester's Paddock, 2 miles east, where a broken lode was opened to 70 or 80 feet). Copper ores were sent for assay in 1895, Nos. 2531-2 yielding from 25 to 32·67 per cent. of copper, and 13 oz. 12 dwt. 4 grs. of silver per ton. In 1896 a sample purporting to come from a hill near the Canadian Lead, No. $\frac{2402}{06}$, yielded 35·67 per cent. of copper, and 3 oz. 11 dwt. 20 grs. of silver per ton. Shaft sunk 40 feet. Fifteen hundredweight yielded 22 per cent. of copper at Waratah. (*See* Invicta Mine.)

MUDGEE MINING DISTRICT—*continued.*

Dandaloo Division.

ybugle, about 16 miles west of the Bogan River at Dandaloo.—cal Surveyor Young (Ann. Rept., 1880, p. 262) recorded the occurrence artz reef stained with carbonates of copper in hornblende porphyry, ieybugle. Thickness of reef, about 14 inches; strike, N. 6° W.; dip, to the W. Since that date a shaft was sunk about 80 feet, the r being hard and the reef small. Gold is present in the veinstone.

Gulgong Division.

ta Gold and Copper Mine, 3 miles easterly from Gulgong.—Copper and ere occur in an altered igneous rock. The following samples have sted:—

Carbonate ore ...	No. 07–661—Copper	39·25
	No. 07–662—Copper	31·55
	No. 07–663—Copper	37·60

tons raised during 1907 disposed of for £96.
rted to be of irregular occurrence and not persistent.

Dandaloo Division.

Duke Lode, Albert Water Holes, M.L. 2, parish Tabratong, county ly.—Opened by C. J. Keenan about 1899, to a depth of 25 feet, and t 30 feet.
ong silicious outcrop, with stains of copper carbonates visible in the ig schist.
e N. 35° E.
; developed in 1907 by the Iron Duke Copper-mining Co., Limited.

Wellington Division.

r Mine, 11 miles by road from Wellington, and 3 from Bodangora.—l for gold for widths varying from 9 to 20 feet, and to a depth of at different points, for a length of about 500 feet. Costeens further ; the outcrop for another 100 feet.
er carbonates manifest below the first outcrop, and sulphides at the evels attained.
Writer is indebted to Mr. J. Carey for the following notes from his atic sampling tests, recently made:—
m an open cut, 90 feet x 15 feet x 60 feet (C), six samples from the level (where the sulphides begin) averaged, copper, 2·78 per cent. d sample gave 7·5 per cent. An average of the oxidised ore at south cut—16 feet wide—yielded 4·04 per cent. Fine gold being also in panning tests.
hundred feet east of (C), 12 feet of auriferous stone, in a 50-feet shaft, d 2·0 per cent. of copper.
ve feet south of this shaft is another open cut (D), 50 feet x 20 feet x deep. A sample from 9 feet wide, in west end of cut, gave 4·83 per copper; and one from the east, 4·26. Free gold in panning tests.
of cut covered with débris.
y-six feet south of (D), the most southern workings (E) occur. The orm a long costeen, 120 feet x 15 feet x 6 feet deep. Copper average to 1·2 per cent. Colours of gold only.

The sulphides at the Kaiser Mine exposed at 60 feet do not essay well for gold; and, regarding the ascertained copper value as excessive owing to partial enrichment, the latter, in the permanent or unaltered zone, is likely to be insufficient for independent treatment, unless richer lenses are disclosed for sweetening.

Dandaloo Division.

Lady Elwyn Mine, portion 7, parish Beaconsfield, county Kennedy; 5 miles S.E. of Orange Plains, and 16 miles westerly from Dandaloo.

Inspector J. James reported (P.B. $\frac{aaaa}{0}$) an ironstone formation with copper ore, striking east and west, and dipping south. One hundred and seventy-five feet sunk, partly on underlay. Good patches of ore met in sinking, also in drives at 166 feet.

Fifty tons treated at Waratah at a profit. Picked sulphides assayed 20 to 22 per cent. Aided to sink from 175 to 200 feet.

"*Monarch*," *Elizabeth; or, No.* 3 *Copper Mine*, M.L. 3, parish Albert, county Kennedy; Albert Water Holes; about 300 yards from Mount Pleasant Mine. Discovered by C. J. Keenan, in 1898.—Strike N. 50° E.; dip N. 40° W. at 66°. Five shafts, ranging in depth from 40 to 150 feet, have been sunk along the lode, covering a length of 520 feet, the quartz outcrop being well exposed.

Width varies from a few inches to 3 feet in places. Stoped above 60-feet level wherever payable between Nos. 1 and 2 shafts—a distance of 300 feet.

Ninety tons of ore extracted are reported to have yielded from 16 to 36 per cent. of copper. The ore mined was evidently picked clean below, there being comparatively no seconds at grass.

A little sulphide was showing at 150 feet, lean and silicious. Water also struck at this level.

In the worked area, bunches of carbonates and grey ore were extracted, the lean silicious ore being left unstoped.

Mount Keenan, Albert Water Holes, M.L. 1, parish Tabratong, county Kennedy.—Discovered by C. J. Keenan in 1897. Strike N. 50° E.; dip N. 40° W.; channel 4 to 5 feet wide, quartz filling, good walls. Schist country. Opened to 150-feet level, driven 25 feet south-westerly. Prospector reported 30 oz. of gold dollied from surface stone; also, that 30 tons of copper ore, obtained at 50-feet level, yielded 18 per cent. of copper at Lithgow and 11 dwt. of gold per ton. Fifteen hundredweight treated separately yielded 1 oz. of gold.

A little sulphide of copper struck at 150 feet; no further work. Not opened to inspection.

Leadville Division.

Mount Laut (formerly Mount Hope), portion 136, parish Bullinda, county Lincoln, on W. Davis' private land.—Strike N.E. in slate; dip S.W. at 68 to 78°. Channel of impregnated slate, with a little quartz, from 1 ft. 6 in. to 4 feet wide. No solid ore. Carbonates in cleavage of slates in oxidised zone; bands of sulphides below. Evidently copper solutions followed line of fissuring or jointing, and impregnated country for a few inches or feet.

Reported to have been discovered by J. Cohen, about 1890.

MUDGEE MINING DISTRICT—*continued*.

In 1902 Inspector Polkinghorne reported two shafts, 60 and 69 feet, with veins of good ore. Formation at bottom, 3 ft. 6 in. wide. (A second lode reported outcropping south-west.) Seven and a half tons despatched yielded 1 per cent. of copper.

Aided to sink to 200-feet level (P.B. $\frac{1}{0}\frac{6}{2}\frac{9}{2}\frac{7}{}$).

Inspector James reported (P.B. $\frac{4}{0}\frac{6}{4}\frac{4}{}$) that the shaft had reached 68 feet, and the channel had been driven on 35 feet at bottom, without disclosing anything of an encouraging nature. A little scattered sulphides through the slates. Nothing to warrant further aid.

Re-opened by Laut Bros. in 1906, who confined their operations above the 90-feet level. The output, so far as can be obtained, works out 31¾ tons, yielding 14·3 per cent. of copper, about 2 oz. of silver, and a trace of gold per ton.

Parallel quartz reefs occur; the western, distant about 50 feet, the eastern, 120 feet—unopened.

At the date of the Writer's inspection in January, 1907, the main shaft was sollared at 150 feet, preventing inspection below. At 150 feet a crosscut given west should have cut the lode, but no trace of it is seen. At 91-feet level a stope was carried north-east for a short distance, and up about 10 feet. About 4 or 5 feet of channel slate at north-east end, but greater part carrying only strings of pyrites and a little copper sulphide. About 1 foot of more solid ore on footwall.

From 23-feet level stoped up to surface on both sides of shaft. Ore also obtained in shallow trenches, mostly to the north-east from shaft. Ore has been won from three shafts, and three open trenches aggregating 150 feet, at intervals along a length of about 400 or 500 feet.

The nature of the Mount Laut ores is shown in the following partial analyses:—

No. of analysis.	Nature of Ore.	Copper, per cent.	Iron, per cent.	Sulphur, per cent	Silica, per cent.	Gold, per ton.	Silver, per ton.
							oz. dwt. gr.
8-162 ..	Carbonate from surface	0·10	....	....	50·23	trace.	3 5 8
8-163 ..	Sulphides from 91-feet level	4·40	5·04	6·16	65·45	,,	1 7 5
8-164 ..	Enriched sulphides from higher level (?) (from heap at shaft).	7·12	14·56	12·17	51·35	,,	1 1 19

Unfortunately for the prospect of local treatment—if quantities warranted its contemplation—Mount Laut lode does not promise solid sulphides in the permanent zone, such as would flux the silicious superficial ores. The leafy occurrence of carbonates and oxides in the cleavage of the slates in the upper levels, is represented below by leanly distributed sulphides in a vast proportion of gangue. The absence of any iron oxide, or gossan, in the cap is also indicative of lack of solid pyritic lenses in the lode. The Mount Laut ores would, however, prove a useful flux for the massive pyritic lodes at Mount Stewart, about 9 miles distant (which see).

Mount Laut South.—About 15½ chains from the nearest point of the Mount Laut workings; to the south-west a shaft has been sunk 100 feet (?), but beyond a few stains of carbonate in a crosscut, nothing of value has so far been disclosed.

MUDGEE MINING DISTRICT—*continued*.

Mount Laut, Dawson's Mine.—A recent discovery near the Mount Laut Mine, consisting of slate slightly impregnated with copper carbonates, without defined boundaries or walls.

Strike N. 60° E.; dip N. 30° W. at 80°. Shaft about 50 feet deep, showing about 1 ft. 6 in. of copper-stained slate of very low grade. An open cut on S.W. strike reveals similar carbonate stains in slate 140 feet from shaft. At 35 feet on N.E. strike a shallow cut exposes a similar occurrence.

Dandaloo Division.

Mount Pleasant Copper Mine.—See p. 254.

Mount Royal Copper Mine, M.L. 59, parish Beaconsfield, county Kennedy, 48 miles from Trangie Railway Station, and 8 miles from the surveyed Bulbodney Railway line.—Discovered by H. Fishpool, October, 1903.

Strike N. 80° E.; dip S. 10° E. at 45°. The dip flattens to 25° between the 110 and 150 feet levels, then steepens to 45°. Schist country.

Opened by three shafts—No. 1, "main," 240 feet on underlay; No. 2 (150 feet easterly) cuts the lode at 75 feet; No. 3, 18 chains westerly, 38 feet. Outcrop strong at west end, not discernible at east. Here in the main shaft a small rich vein, 4 to 6 inches thick, was followed down to 80 feet, when it began to widen gradually until it attained 6 feet at 110 feet.

Sulphides begin at 170 feet, and become massive at 200 and 240 feet.

At 110 feet the lode has been driven on for 120 feet westerly, and 130 feet easterly, to connect with No. 2 (vertical) shaft. The lode at this level has been moved slightly by a fault near No. 2 shaft. A sample of the partially enriched sulphides at 200 feet yielded:—

No. 07-2371—Copper	5·55	per cent.
Iron	37·66	,,
Sulphur	39·14	,,
Silica	13·58	,,
Gold	4 dwt. 8 grs.	per ton.
Silver	1 oz. 19 dwt. 14 grs.	per ton.

An excellent smelting composition; but very urgent that the copper value of the unaltered zone be proved.

Stopes 120 feet long and 15 feet high at the 110-feet level, and 10 feet high at the 150-feet level, east of No. 1 shaft, yielded, between 1904 and 11th May, 1907, 220 tons 16 cwt. 2 qrs. of ore, realising £2,785 3s. 2d. Two and a half tons of the enriched sulphides from the 200-feet level yielded 7½ per cent. of copper.

At the west end, where outcrop is strong, silicious, and gossany, 7 tons from the 39-feet underlay shaft, yielded 21 per cent. of copper.

Southerly from the west shaft, a vertical shaft cut copper ore at 77 feet, apparently a parallel lode, unless the dip of the Mount Royal lode suddenly changes.

In March, 1907, the mine was sold to Sydney investors, who erected a reverberatory furnace, which was started at the end of October. From 1st November to 27th February, 1908, 780 tons of ore were smelted for 65 tons of 66 per cent. matte.

The Writer is indebted to Mr. G. A. Pechey, manager and metallurgist, for the following particulars of developments since last inspection:—

"*Mount Royal Mine*, 18th April, 1908.—No. 1 shaft has been sunk 240 feet on the underlay. From this shaft, *No. 1 level* (150 feet from the surface) has been driven 180 feet *east* along the lode, which along this level has an

average width of 4 feet. Stoping has been done all along this level. The *west* level has been driven 150 feet, the lode being an average width of 4 feet. The face of this drive is now in very good red oxide and carbonate ore. Stoping has been done all along this level up to the intermediate level, and also underhand.

"*No.* 2 *level* (200 feet) has been driven 30 feet east and 28 feet west, the lode at both ends having an average width of 5 feet, the ore being solid sulphides, very suitable for pyritic smelting.

"*No.* 2 *shaft*, situated 1,200 feet west of No. 1 shaft, has been sunk 100 feet vertical, but where the lode underlays through the shaft at a depth of 70 feet, it has been converted into an underlay shaft for an additional depth of 67 feet, making a total depth of 137 feet. From the bottom a level is being driven *east and west* in good sulphide ore of an average width of 3 feet. The east drive is in 40 feet, and the west, 30 feet, and stoping has been done from this level up to the line of demarcation between the sulphides and oxidised ore. The latter ore from this section of the mine is mostly solid grey ore. The sulphide ore from this shaft is heap roasted before being smelted. The drives west from No. 1 shaft, and east from No. 2 shaft, are now being extended with the intention of connecting the shafts. The faces are both in good ore, and the lode can be traced on the surface from shaft to shaft.

"*Plant.*—At No. 1 shaft, poppet legs, winding winch, and boiler have been installed. A reverberatory furnace, 24 feet x 14 feet, inside measurement, has been erected, and is now smelting about 77 tons of ore weekly.

"*Men employed.*—A total of fifty-two hands are at present employed in the mine, on the surface, and at the smelter.

"*Smelting return from 1st November, 1907, to 18th April, 1908* (stopped nine weeks, holidays, repairs, &c.) :—

Ore Smelted.	*Product obtained.*
1,154 tons oxidised and sulphide ore, average assay value 7·01 per cent. copper.	111 tons 6 cwt. of matte, of average assay value of 61·6 per cent., containing 69 tons of copper. Equal to 6 per cent. of copper from the ore.

Average slag assays—	Copper	0·78 per cent.
	Oxide of iron (Fe O)	43·70 "
	Insoluble	55·80 "
	Lime	trace.

No flux used.

"An economical and effective method of producing a high grade matte is used. During ordinary ore smelting a matte of 40 to 45 per cent. is produced, the matte being retained in the furnace till the fourth day, when a charge of the higher grade oxidised ore (without any sulphide ore) is given. This is smelted in eight hours, and the matte brought up to over 60 per cent. By this means the usual delay in roasting the matte is avoided, and the furnace is kept continuously smelting ore, and at the same time producing comparatively low slag loss."

The sulphides from No. 2 shaft are clamp roasted. The recent smelting proportions being:—

Oxidised ore	38 tons.
Roasted sulphides	24 "
Raw sulphides	14 "

Smelting ceased early in June, 1908. Developmental work only being carried on. No. 1 shaft being deepened to 400 feet.

MUDGEE MINING DISTRICT—*continued.*

Leadville Division.

Mount Scott, near Leadville.—Strike N. and S.; dip west at 45°. Opened by two shafts. Lode channel 5 to 6 feet wide. Vertical shafts to 140 feet. Winze below to 170 feet, following underlay on a dip of 42°. Footwall not showing at bottom. A little galena and zinc-blende making on hanging wall. Channel filling mixed with country.

An average sample of lodestuff yielded:—

No. 08–172—	Zinc	12·79 per cent.
	Silica	25·38 „
	Lead	1·00 „ (about).
	Copper	none detected.
	Gold	a trace per ton.
	Silver	16 dwt. 8 grs. per ton.

A sample picked for supposed copper ore also gave negative results on assay.

Mount Stewart Mine, M.Ls. 1, 2, 3, parish Talbragar, county Bligh.—Leadville, 3½ miles from nearest point of Mudgee–Dunedoo Railway line in course of construction. Opened in 1888 as a silver-lead mine. A water-jacketted blast furnace was erected in 1892.

During the smelting campaign—lasting for fourteen months—6,464 tons of ore were smelted for 1,539 tons of lead and 292,093 oz. of silver (according to Mr. C. L. Garland), a yield equivalent to 23·8 per cent. of lead and 45 oz. of silver per ton.

In July, 1898, the mine was purchased by Messrs. Garland and Channon, who have since carried out a considerable amount of development.

Several large parallel lenses, with strong gossan outcrops, occur in quartz-felsite, quartzite, granulite, and limestone. Striking from N. 25° to N. 75° E., and dipping westerly at 60 to 75°.

The provings extend for about 2,000 feet along the strikes, but are not continuous, the principal workings being at the north-east and south-west ends.

The Western Lode (north-west end), which is the site of the original discovery, lies about 170 feet west of the "Main," or central lode, with the engine shaft of which it is connected at the 200-feet level.

The "East," or Paddock Lode, lies east of the "Main," but has not been connected.

At the south-west, or Extended Block, end, two lodes have been opened; a strong gossan outcrop to the west is practically unopened.

From surface indications it is probable that extended connection between the extreme end workings will reveal a series of large, more or less disconnected lenses, of kindly gossany nature in the oxidised zone, and strongly pyritic below it. The outcrop of this metalliferous belt is traceable some distance south-westerly beyond the Extended Block.

The "Main" lode has been driven on for about 600 feet at the north-east end—at the 157-feet level, the oxidised ore being stoped to surface in parts for lead and silver. Below 157 feet sulphides begin; principally solid pyrites, with appreciable quantities of silver in limited areas, though the general average is unfortunately low. Lead sulphide, however, is not prominent for the most part. The width averages from 15 to 40 feet. The composition of the pyritic ore is shown approximately in Assays Nos. 08–165, 168, and 171.

Offices
Shaft to 50'

the connecting crosscut at the 200-feet level from the engine shaft to West lode, the following rocks were cut through:—

7147—Quartz-felsite.
7148—Quartzite.

stone occurs on south-west side of the West lode, and beyond this a cut exposed a coarse porphyritic rock, determined as granulite—ably crushed granite (7149, 7150). The quality of the limestone—which used for flux during smelting operations—is shown in Assay No. 08–174. stone of a similar character occurs also about 2 miles north-easterly from it Stewart.

e West lode has been sunk on to 260 feet. It strikes N. 75° E., and N. 15° W. This lode is composed largely of zinc-blende and pyrites; t 40 feet wide. Made into limestone; zinc making again below 150.

e East, or Paddock, lode, at the north-east end, strikes N. 25° E., and N. 65° W. at 56°. Width of lode about 40 feet. Composed largely nc-blende, pyrites, and carbonate of lead. Opened by underlay shaft depth of 170 feet.

incipal attention was given to the south-west end in the Extended Block—e copper ores become appreciable; for the future of the mine entirely nds upon developing, or securing elsewhere, sufficient copper to form e and collect the silver and gold of the kindly pyritic ore in the northern on, which is so eminently suitable for partial pyritic smelting.

pper ores in this section were first encountered in the West lode in the copper shaft—145 feet deep. This lode strikes N. 75° E., and dips 5° W. at 76°.

om 100 to 145 feet levels copper sulphate coats the exposed kindly ny lodestuff; the width at 145 feet is about 20 feet, but part of the ue is kaolin. The metallic values of this ore from the width mentioned, a length of 45 feet, are shown in Assay No. 08–166. This lens has not tested below about 155 feet. The ore here is partly decomposed es and chalcopyrite, which gives rise to the sulphates on exposed. ces.

om the 145-feet level connection is made with the East lode. A shaft been sunk in the latter 200 feet. A lens of copper-bearing lodestuff nds up about 30 feet above this level, forming a shoot of about similar meter; its quality is shown in Assay No. 08–170. The thickness of the t lode ranges up to 70 feet.

opper ore is also exposed in No. 2 winze, the quality of which is shown Assay No. 08–167. Also in No. 3 winze from the intermediate level, t lode, 60 feet below the 145-feet level, where it begins at 190 feet from face, and extends down as far as the winze goes, viz., to 210 feet. Here phides with sulphate efflorescence are exposed. This lens of cupriferous has an apparent width of 30 feet.

Zinc-blende makes strongly on hanging wall of the East lode at 200-feet el, averaging 4 to 5 feet in width, and assaying 41·32 per cent. of zinc ay No. 08–169).

Zinc also makes strongly in a crosscut under the West lode; it is, however, low grade, being mixed in part with limestone. An average of 16 feet de in the crosscut, without excluding anything, shows the composition picted in Assay No. 08–168.

Zinc also makes prominently, as before stated, in the Western and Paddock workings at the north-east end.

If it were not for the vast zinc by-product of the Broken Hill lode, those of Mount Stewart would probably be worked for their zinc contents as a primary product. In any future operations it must be reckoned as an essential item. Even if—as is hopeful—sufficient copper be obtainable in the mine or district, to enable partial pyritic smelting to be established, separation of the zinc in commercial form will be a necessity, both for revenue and for effective furnace work. Doubtless much clean pyritic ore could be selected comparatively free from zinc; but the only adequate and economic method, in a low-grade deposit, is to work it all on a large scale. Mount Stewart ore is suitable for magnetic concentration, and the mine product could probably be roughly classified into concentrating and direct smelting ore.

In the event of re-establishment of smelting at Mount Stewart, the question of fuel will become prominent. Though the Upper Coal Measures extend into the district of the Talbragar, it is doubtful whether the coal seams in them are of sufficiently good quality for coking or firing purposes. So far as proved, in Ballimore Bores and in several wells, the quality has been inferior.

In the event of being forced to seek further afield, the advent of the railway within about 3 miles of the mine will largely reduce the disabilities previous smelting laboured under. Excellent coal for all purposes is procurable alongside the railway at Cumber Melon, near Rylstone, or even from Cox's Siding, distant about 76 miles by rail from Mount Stewart.

Mount Stewart pyritic ores would form a valuable flux for silicious copper ores such as the Mount Laut, or *vice versâ*.

Assay No.	Description.	Copper, per cent.	Zinc, per cent.	Iron, per cent.	Lead, per cent.	Sulphur, per cent.	Silica, per cent.	Gold, per ton.	Silver, per ton.
								oz. dwt. gr.	oz. dwt. gr.
08-165..	Average of 30 feet of solid pyrites, Main lode, 200-feet level.	..	0·65	40·04	..	45·37	9·00	trace.	3 2 1
08-264..	Average from 2 tons of large blocks sent to Franco-British Exhibition from same lode, upper level.	0·35	2·22	..	1·30	..	..	0 6 13	59 11 5
08-171..	Average from Main lode, 217-feet level, 300 feet south of No. 08-165.	0·20	..	..	0·20	..	..	0 4 8	14 19 18
08-166..	Copper gossan, West lode (south end), Extended Block, 145-feet level.	4·05	0·76	..	1·00	..	39·00	trace.	0 12 15
08-167..	Gossan from East lode (south end), Extended Block, over No. 2 winze.	0·50	0·56	..	2·00	..	16·75	0 1 2	38 7 7
08-168..	Zinc-blende, West lode, Extended Block, 200-feet level.	..	12·95	..	..	..	..	trace.	0 13 1
08-169..	Average of zinc lode, hanging wall, East lode, Extended Block, 4-5 feet wide.	..	41·32	..	..	..	..	trace.	6 12 2
08-170..	Copper ore from lens in East lode, Extended Block.	3·72	5·26	17·78	..	21·68	35·12	trace.	1 6 16

08-174—Limestone from West lode, north end.	Calcium carbonate	97·67
	Ferric oxide and alumina	·18
	Gangue*	2·20
		100·05

* Contains a small amount of carbonate of magnesia—less than 0·1 per cent.

MUDGEE MINING DISTRICT—*continued.*

During the smelting campaign the enterprise had to contend with the following transit charges:—

Coke from Rix's Creek, Singleton (rail to Mudgee), 17s. 6d. per ton.
Coke from Mudgee to mine (50 miles), from £1 to £3 per ton.
Bullion from mine to Mudgee (50 miles), from £1 to £3 per ton.
Bullion, rail (Mudgee to Sydney), £1 10s. per ton.

Gulgong Division.

Native Bee Mine, on S.E. strike of Belara Lode, portion 131, parish Worobil, county Bligh.—Discovered by W. Spicer and L. Davis, October, 1906, in W. Harvey's private land. Occurs under similar conditions to the Belara, in slate country near intrusive quartz-felsite. Strike N. 30° W., dip N. 60° E. at 65°.

Opened by four shafts. Proved for a length of about 450 feet, and to depths ranging from 76 to 90 feet.

Development.—No. 1 shaft, 90 feet deep, driven north-westerly at 60 feet level for 30 feet, and south-easterly for 25 feet; lode 9 inches to 2 feet wide.

No. 2 shaft (78 feet south-easterly from No. 1), 76 feet deep, driven north-westerly for 30 feet at 56-feet level, and south 20 feet. Winze from north drive down 20 feet. Lode thin—6 inches quartz with carbonates.

No. 3 shaft (78 feet north-westerly from No. 1), 90 feet deep, driven north-westerly for 30 feet at 70-feet level, and 30 feet south-easterly.

No. 4 shaft (270 feet north-westerly from No. 3), 70 feet deep, driven south 20 feet at 60-feet level.

Output.—Eighty-eight and half tons of rich oxidised ores sold to Great Cobar, Ltd., at Lithgow, yielded from 25 to 28 per cent. of copper. Thirty-six and a half tons were treated locally by Messrs. Cock Bros., in the Belara furnaces; 34 tons of which yielded only 4·6 per cent Thus reducing the average yield to 16·78 per cent. of copper, 8·6 oz. of silver, and a trace of gold per ton. Aided from the Prospecting Vote (P.B. $\frac{1}{0}\frac{3}{*}\frac{2}{*}\frac{A}{*}$) to sink to 200-feet level.

Dandaloo Division.

Orange Plains Copper Mine (also known as "Ironstone"), M.Ls. 11, 19, 23, parish Beaconsfield, county Kennedy, near the Mount Royal Mine.—Solid outcrop of ferruginous quartzite, and iron oxide. Strike apparently east and west; dip south at 45°. Opened by 150-feet shaft (to March, 1907), following underlay. Sulphides at this level enriched; an average sample assayed:—

No. 2376—Copper	11·7	per cent.
Iron	35·70	,,
Sulphur	38·99	,,
Silica	8·48	,,
Gold	2 dwt. 4 grs.	per ton.
Silver	8 ,, 17 ,,	,,

A level 50 feet west, and 18 feet east, at 108-feet level. Ore stoped from east end. Crosscut north through schist with copper stains.

Reported output, 24 tons, averaging about 18 per cent.

Peak Hill Division.

Peak Hill Gold Mine.—In 1900 about 11 tons of copper were obtained during gold-mining operations. The sulphides (pyrites) from lower levels treated in a small experimental blast furnace, yielded from 1 to 1½ per cent. of copper, and 7 to 12 dwt. of gold per ton.

MUDGEE MINING DISTRICT—*continued.*

Rylstone Division.

Queen of the Stream Lode, Running Stream, about 4½ miles westerly from Capertee, parish Rylstone, county Roxburgh.—Discovered by Frank and party, June, 1897. Inspector H. Hooke reported (P.B. 4½¹¹) "Slate traversed by quartz veins carrying copper sulphides. Aided to sink 50 feet."

Inspector J. Polkinghorne reported (P.B. 99–5,885): "Several openings showing a series of veins of copper and lead ores, but nothing defined. Aided to continue to 100 feet. At 25 feet struck small vein of grey ore. At 4[illegible] feet copper pyrites. Rate increased at 52 feet. No further record."

Wellington Division.

Rose Hill Copper Mine, about 4 miles south of Geurie Railway Station, parish Mickety Mulga, county Lincoln.—The Warden in 1888, p. 70, reported that three shafts had been sunk on a lode about 2 ft. 6 in. thick, and well defined, the depths of proving being 25, 40, and 90 feet. The ore consisted chiefly of yellow sulphide. A trial parcel of 4 tons was sent to the Waratah Smelting Works; but as work ceased in 1889, it is presumed that the result of the trial was not satisfactory.

Dandaloo Division.

Sydney-Wallaroo Copper Mine (late Caroline), M.Ls. 1 and 17, parish Caroline, county Kennedy, about 15 miles from Dandaloo, 45 from Trangie Railway Station, and 13 from Bogan Gate–Bulbodney surveyed line.—Opened about 1888 to a depth of 140 feet; taken up again in 1898 by a Cobar syndicate, which supplied the following particulars through the late MR. W. Gillard, of Cobar, under date of 7th September, 1898:—

"We thoroughly overhauled the surface of the mine, and found that there are three shafts—one supposed to be 140 feet deep; this shaft is 8 feet x 4 feet. The next shaft is supposed to be 50 feet deep. The other shaft is 14 feet deep. The 140-feet shaft is on the eastern side of the lode. The 50 feet is on the lode, which is 3 feet wide at the bottom of the shaft, containing very good carbonate ore. The lode strikes north-westerly in a 40-acre block. The net profit on 6 tons 14 cwt. of ore, sold in March, was £36 7s. 6d. The next parcel, of 6 tons, treated in May, returned a net profit of £27 4s. (sold to the Great Cobar Syndicate). The ore will average above 14 per cent. of copper. The amount expended on the mine was about £200. Mineral lease granted on 11th May, 1898, to W. Meriel and W. Rowe."

Position in March, 1907.—Strike N. 20° W.; dip N. 70° E., at about 50°. Outcrop well defined, but not prominent. Proved for about 12 chains, by shafts. Principal workings close to boundary of M.Ls. 1 and 17. Greatest depth, 140 feet.

Lode consists of impregnated contorted schists, resembling those of Girilambone. Greatest proved width of impregnated country, 20 to 30 feet.

Seven chains south of main shaft, Keenan Bros., who secured the property in 1905, cut the lode at a depth of 35 feet, and raised about 4 tons of fair grade ore.

A belt of hard ferruginous quartzite occurs a little east of the lode; further south it has been opened by shaft and open cut without disclosing any value. Its highly ferruginous outcrop simulates a lode.

The early workings have not been deepened or extended. Pockets and veins of carbonates and grey ore have been more or less exploited in the oxidised zone, but not to any great extent. Keenan Bros. raised 10 tons from a shallow level for a reported yield of 12 to 17 per cent. copper.

At the deepest level—140 feet—the transition to sulphides is revealed, though not completely; if anything there is slight enrichment at this level. An average sample chipped from a width of 28 feet of pyritic schist yielded:—

No. 07-2372—Copper	2·55	per cent.
Iron	20·72	,,
Sulphur	13·00	,,
Silica	35·08	,,
Gold	3 dwt.	6 grs. per ton.
Silver	7 ,,	15 ,, ,,

Further prospecting in the sulphide zone is necessary to determine the value of the deposit. At the level mentioned the sulphides are not sufficiently solid and homogeneous for partial pyritic smelting.

In June, 1907, an Adelaide syndicate was reported to have taken over the mine.

Inspector J. Polkinghorne reported that 60 tons of ore were raised during 1907, and disposed of for £960. (Ann. Rept., 1907, p. 91.)

Underlay Mine, M.Ls. 4, 5, 6, 7, 22, parish Beaconsfield, county Kennedy, 16 miles from Dandaloo.—Discovered by J. Dunwell in 1903. Strike N. 55° E.; dip S. 35° E., at about 45°.

Ore lens opened by two shafts 130 feet apart to depths of 150 and 200 feet. Copper ore struck at 104 feet, followed down to 165 feet; driven on 130 feet at this level. Stoped up to 100 feet. Shaft passed into country below 165-feet level.

At south-west end of drive at 128-feet level in new shaft, the lode believed to have been faulted to the south. The fault plane being smoothed and slickensided, search not made directly opposite junction. Fault plane driven on south 40 feet, when ferruginous quartzite was cut. Drove from this point to old shaft (150 feet). Country disturbed. The ore gave out at 200 feet in main or new shaft—the schist being wonderfully contorted; hard intercalated bands of quartzite presenting complete corrugations; at this point the ore ceased.

At the 163-feet level, rich thin veins of copper and iron pyrites occurred, yielding by assay—

No. 07-2376—Copper	13·52	per cent.
Iron	34·58	,,
Sulphur	36·82	,,
Silica	11·02	,,
Gold	trace	per ton.
Silver	2 dwt. 4 grs.	per ton.

From the lowest level where granular pyrites are developed, a sample yielded:—

No. 07-2375—Copper	2·17	per cent.
Iron	32·90	,,
Sulphur	32·88	,,
Silica	23·84	,,
Gold	trace	per ton.
Silver	16 dwt. 8 grs.	per ton.

150 feet from the old shaft, on underlay side, a large formation has been exposed in a trench, which deserves attention at lower levels.

MUDGEE MINING DISTRICT—*continued.*

The output to end of 1906 is stated by the owner to have realised £1,87[illegible] net; which, at the average rate of local yield, would equal about 104 tons A considerable quantity of seconds are at grass, very silicious, but workabl locally with massive sulphides, such as occur in other neighbouring lode at Orange Plains.

The following particulars of development and output since inspection i 1907 were supplied by Mr. Dunwell, under date 11th January, 1908:—

Drove 52 feet easterly in No. 2 shaft at 137 feet level. At 12 feet struc a fault, drove through it, and struck lode 8 feet wide, consisting of ironston and pyrites, with a little grey and black ore. At 52 feet the lode turned an is now going north, about 4 feet wide; vertical, with clean walls.

A western drive from same level for 32 feet through gossany ironston with a little copper. No walls showing.

Additional output—46 tons 19 cwt. 3 qrs., averaging 17½ per cent. o copper.

Wellington Division.

Wellington District.—C. S. Wilkinson, Government Geologist, in 1876 reported that the formations at Wellington consist of a thick series o sandstones, shales, conglomerates, and limestones, provisionally classed a Upper Silurian, traversed in places by greenstone dykes. The dykes ar in some places traversed by quartz reefs containing grey sulphide and car bonates of copper.

In 1886 the Mining Registrar reported that 300 tons of ore had bee smelted for a yield of 40 tons of copper, but no particulars of localities ar given.

Copper ores were reported in the following localities:—

Fittes' Mine, about 12 miles from Wellington; working in 1876. A assay of copper glance and pyrites yielded 10·04 per cent. of copper, and 7 oz. 14 dwt. 10 grs. of silver per ton.

Weandre Creek, parish Three Brothers. Copper reported present in most of the reefs of this locality.

Wellbank—

The Springs railway station.

Lindberg's Mine, Wellington Common.

Apsley Mine, Wellington Common.

In 1882 a small smelting furnace was erected near Wellington at a cost o £450, and ores from the Apsley and Lindberg's Mines were tested, with poor results.

In 1898 the Warden reported that applications had been lodged for coppe lands at the following places in his district, but that little real work ha resulted:—

Wellington Common.

Galwadgery Creek.

Ponto, near Wellington.

Garry Owen—carbonate ore assaying 3 to 6 per cent.

Newrea.

Three Mile Flat—assaying 13 per cent.

Goolma Creek. (Belara ?)

Kadumble Range.

Kaiser Mine.

MUDGEE MINING DISTRICT—*continued.*

Apsley Mine, close to Apsley platform, about 2 miles east of Wellington.—Ore taken from this mine (in andesite) was dressed and despatched to Lloyd's Lithgow Smelting Works by W. P. Mitchell, the returns from 4 tons 17 cwt. being—copper, 7·9 per cent.; silver, 2 oz.; and gold, 7 dwt. 13 grs. per ton.

Aid granted (P.B.$\frac{a}{5}\frac{1}{1}\frac{a}{}$) to sink from 25 to 75 feet. At 50 feet traces of copper in gossan. Fruitless.

Tremayne Bros. Black Rock property, 9 miles from Wellington.—Copper reported in September, 1907; ¼ mile from Bell River, between it and Molong-road. Cuprite in andesite close to junction of limestone. Several shallow openings showing copper ore.

Commonwealth Mine, Yarragol, about 9 miles from Wellington.—Originally profitably worked for gold in oxidized zone, but became very refractory below water-level. The ore being a complex mixture of zinc, lead, iron, and copper, with a little gold and silver. The copper runs to about 1½ per cent.

Wellington Champion Hill Lode.—Reported that a furnace was erected here twenty years ago.

In the andesitic rocks of Wellington, Blayney, and Carcoar, native copper is frequently found in small isolated pellets and in thin veins. The weathering and decomposition of the metal in the exposed outcrops of the andesite has stained it in many places, inducing prospecting for lodes—but none have eventuated in the solid rock.

Mudgee Division.

Wilbetree.—In the latter part of 1896, a newly-discovered copper lode in R. Atkinson's land at Wilbetree, 9 miles north-west of Mudgee, was opened up. A shaft was sunk 60 feet, which cut through the lode at 13 feet. The outcrop reported from 12 to 15 feet wide, showing carbonates. Work soon abandoned without any tangible results being obtained.

Wellington Division.

Yarragol Copper Mine, portion 40, parish Yarragol, county Bligh, about 4 miles from Dripstone Railway Station.—Originally opened about 1878. Taken up again by Aaron and party about five years later. About 3½ tons carbonates, and 2½ tons sulphides, raised during the operations of the Woolaman Mining Syndicate, realised at Lloyd's Smelting Works, Lithgow, 9 and 6 per cent. of copper. The developments consist of a 30-feet shaft sunk by the first prospectors, and a 60-feet shaft sunk by the last at some distance from the former. A crosscut from the latter, however, failed to reach the lode. This caused some of the shareholders to abandon their interests, and the closing of the mine.

Re-opened during 1906. Second shaft deepened to 110 feet; 4½ tons of ore reported to have been treated with good results.

NEW ENGLAND MINING DISTRICT.

Kookabookra Division.

Aberfoyle Copper Lodes, M.L. 5, parish Allingham, county Clarke.—In June, 1907, a syndicate was formed to develop several outcrops of copper ore at Aberfoyle River, about 45 miles from Armidale.

Later it was reported that a lode had been cut in several places about 800 feet below the plateau level on the steep falls therefrom. Other outcrop occur about half a mile south. The following assays were made:—

07-1741—Quartz with sooty copper pyrites, yielding:—

Copper	6·60 per cent.
Silver	9 oz. 16 dwt. per ton.
Gold	a trace per ton.

07-1742—Quartz with sooty copper pyrites, yielding:—

Copper	8·07 per cent.
Silver	5 oz. 2 dwt. 8 grs. per ton.
Gold	a trace per ton.

Reported abandoned on the 18th January, 1908.

Adjoining the above lease P. Meehan was prospecting for continuation of above lode. Aid refused.

Drake Division.

Adeline Mine, Drake, parish West Fairfield, county Drake.—E. C. Andrews, Geological Surveyor, states (Ann. Rept., 1903, p. 132), that at least three distinct lines of reef occur in this property.

The "Main lode" had then been driven 150 feet at the 100-feet level and 500 tons of ore extracted, of a value of 5 per cent. copper and 5 dwt. of gold per ton, from a width of 4 feet of lodestuff.

The main shaft was down 310 feet and intercepted the main lode at 15 feet. The lode dips west at 45°. A crosscut from the 300-feet level was being driven to cut it.

The "Second" lode, lying to the south, had been driven on 240 feet, smelting ore being extracted from a length of 200 feet, and an average thickness of 2 feet.

The deepest shaft on the "Second" lode being 120 feet. Ore stoped between the 50 and 80-feet levels, yielded 600 tons of firsts, averaging 3 oz. of gold per ton, and 9½ per cent. of copper.

Nine hundred tons of seconds averaged 12 dwt. of gold per ton, and 3 to 4 per cent. of copper.

The ore consists of chalcopyrite in quartz, with a little pyrite.

According to the Annual Report for 1906 (p. 48), this mine had been idle for the previous two years. During the latter, 39 tons, picked from old dumps, realised £250 for copper and £121 for gold.

According to Mr. Gunlach (13/9/05) the surface ores were solely auriferous but changed at a shallow depth to silicious copper ores. Strike of veins, N. and S.; dip, westerly, at an average of 45°. Country, andesite

rhyolite, and breccia. The two veins at present developed occur about 2 chains apart. The early output is not known, but since the Adeline Company had possession, the following output has been won, according to Mr. Gunlach:—

About 2,000 tons ore raised, which yielded 1,600 tons, comprising—650 tons of firsts, realising 3 oz. of gold per ton, and 8 per cent. of copper; 105 tons of concentrates, realising 15 dwt. of gold per ton, and 12 per cent. copper; 850 tons seconds (at mine), valued at 14 dwt. gold, and 5 per cent. copper.

(See also returns under *Drake*.)

Emmaville Division.

Bald Nob Mine, about 5 miles north of Emmaville.—Native copper occurs in fluorspar at the 90-feet level in the Bald Nob Tin Mine. The most interesting feature of the occurrence is the association of tin and copper, other instances noted in the State being at Gumble near Molong, Ottery, Royal George Mine (Tingha), and other New England tin lodes. Chief Inspector J. B. Jaquet, who visited the mine, states that the same conditions obtain at Bald Nob as in the Dolcoath Mine in Cornwall, where copper gave place to tin in the lower levels. At Bald Nob, for 30 feet from the surface, good copper ore was obtained; below this the lode became poor. At 70 feet, apparently where the diorite was entered in the shaft, tin ore came in in limited quantity in the form of a rich bunch. At 90 feet, in a drive easterly, native copper occurs in fluorspar, also a bunchy deposit, probably an impregnation along the junction of the sedimentary and intrusive rocks of which the country consists. The diorite in the vicinity of the shaft is impregnated with copper pyrites. A few tons of very rich copper ore were obtained, but the tin ore was not sufficient to pay.

This mine was opened, about 1873, to a shallow depth. A shaft was sunk 90 feet at the junction of diorite and claystone.

Drake Division.

Bates' Lode, about 40 chains north-west of Minnie Copper Mine, parish Ewingar, county Drake.—Strike N. 20° E., in trachytic tuff, brecciated in part, resembling Drake rocks.

Discovered and superficially tested by H. M. Bates in 1907. Opened by trench. Veinstone about 14 inches at widest, mostly on footwall. South end in hard country, with a little pyrites. Of no importance.

Border Chief Mine, 2 miles west of Drake.—Inspector Carthew reported (P.B. $\frac{8}{0}\frac{8}{0}\frac{4}{0}\frac{4}{0}$) a quartz reef in slate, striking N.E.

Shafts, 30 and 70 feet. Aided to continue 70-feet shaft to 100 feet.

Progress.—At 80 feet, veins of copper about 4 inches wide. At 90 feet, lode formation 18 inches wide, with small bunches of copper and arsenical pyrites. At 100 feet, vein only 6 inches wide—prospects not encouraging.

Deepwater Division.

Castle Hill Copper Mine, about 5 miles from Deepwater.—Opened by a Newcastle Syndicate.

NEW ENGLAND MINING DISTRICT—*continued.*

The following parcels of ore from this mine were treated at the English and Australian Copper-smelting Works, Waratah:—

			oz.	dwt.	grs.	
2 tons 10 cwt., yielded	6½	per cent. copper and silver...	9	12	8	per ton.
15 „ „	4.	„ „	32	0	0	„
6 „ 0 „ „	9¼	„ „	35	11	11	„
6 „ 14 „ „	6	„ „	35	0	0	„

Castlerag, near Deepwater.—A Newcastle Syndicate opened a copper lod a few hundred yards north from the Old Castlerag Silver-lead Min probably identical with Castle Hill Mine. 4 tons 2 cwt. treated at th Waratah Smelting Works yielded 2½ per cent. of copper, and 22 oz. 8 dw 8 grs. of silver per ton.

Drake Division.

Cullen's Creek, near Rivertree.—Argentiferous copper ore occurs at Cullen Creek. At surface the ore consists of gossan, which passes below int a mixture of copper and iron pyrites, galena, and blende. No particula of the size of the lode have come to hand, but it is understood to be smal An assay of a sample, forwarded through Chief Inspector J. B. Jaquet, yielde 19·23 per cent. of copper, and 37 oz. 13 dwt. 12 grs. of silver, and a trace gold per ton. Later samples yielded—$\frac{1}{9}\frac{5}{4}\frac{1}{1}$, and $\frac{1}{9}\frac{2}{6}\frac{1}{1}$, copper, 23 to 30·7 pe cent.; silver, 98 to 134 oz. per ton.

Deepwater Division.

Deepwater District.—In 1885 samples from near Deepwater, consisting iron and copper pyrites, yielded from 12 to 14·35 per cent. of copper, an 10 to 31 oz. of silver per ton. Ore from 5 miles north, probably nea Castlerag ($\frac{4}{9}\frac{4}{8}\frac{6}{2}$) yielded 8·49 per cent. copper, and 20 oz. 15 dwt. 22 gr silver per ton; $\frac{4}{9}\frac{1}{7}\frac{2}{4}$ yielded 17·87 per cent. copper, and 32 oz. 1 dwt. 8 gr silver per ton; $\frac{2}{9}\frac{9}{8}\frac{6}{6}$ yielded 16·60 per cent. copper, and 18 oz. 1 dwt. 12 gr silver per ton.

The "Iron Lode" near Castlerag Silver-lead lode, was opened in earl days of silver-mining. It is reported to be 12 inches thick, carrying coppe ore. A shaft was sunk upon it about 60 or 80 feet, and a tunnel drive 400 feet; a little sulphide and carbonate ore being still at grass. Leas applied for by F. Thompson, Deepwater, in 1907.

Emmaville Division.

Copper ore associated with wolfram and mispickel has been noted in smal quantity by Geological-Surveyor Andrews about 1¼ miles N.N.W. o Emmaville, the copper occurring as chalcopyrite in granite; a pipe-lik occurrence near the junction of sedimentaries.

Drake Division.

Mr. J. P. Curran, Warden's Clerk, Drake, kindly furnished the followin report on the copper output of the Drake Mining Division during 1907:—

"The output for 1907 has been very small, as the miners have to sen their mineral to distant smelting works for realisation, consequently, nothin lower than 20 per cent. ore will pay for shipment, which means that a larg quantity of lower-grade mineral must be temporarily discarded. Presen indications, however, point to a much larger output of copper ore durin 1908. Messrs. Baker Bros. are erecting concentrating and smelting work in a central part of the field. If their system of treatment is successful, th

miners will have the opportunity of disposing of their ore locally; and several mines which have been closed down will resume work, and others may spring into existence.

PRODUCTION of Copper Ore in the Drake Mining Division (J. P. Curran).

1899	.....			
1900	.....	230	tons, value	£1,660.
1901	.....	1,197	,, ,,	£5,930.
1902	.....	1,666	,, ,,	£7,523.
1903	.....	975	,, ,,	£2,361.
1904	.....	111	,, ,,	£635.
1905	.....	24	,, ,,	£289 (Australian Smelting Co., closed).
1906	....	157	,, ,,	£1,594.
1907	.....	559	,, ,,	not disclosed.

"*Return of production for* 1907.—P. Donnellan & Co., 'Baal Gammon Mine,' 47 tons ore, yield 7½ tons copper. McCrossin & Co., 'Lady Mary Extended Mine,' 29 tons ore, yield 4½ tons copper. Pioneer Co., 'Pioneer Mine,' 425 tons ore, yield 14½ tons copper. McAuley & Co., 'Lady Mary Mine,' 14 tons ore. J. Parker, 'Rainbow Mine,' 44 tons ore."

Drake.—The Drake, or Fairfield mining centre, began with gold and silver mining, but at the sulphide zone, copper gradually became prominent. Geological-Surveyor Andrews (Ann. Rept., 1903, p. 132) described the metalliferous occurrences as follows:—"The ore bodies contain gold, copper, silver, lead, and zinc. Certain reefs contain gold and copper alone; others, again, have these metals intimately associated with lead and zinc, also small quantities of silver. The ordinary vein material has the appearance of auriferous quartz with mixed sulphides—averaging from 15 to 20 per cent. of the whole. Extreme cases (Pioneer No. 1) contain 40 per cent. sulphides, mostly as iron. The gangue is thus seen to be highly silicious in character, with a minor percentage only of mixed sulphides. The reefs were originally worked for gold, but free milling soon became impossible, and at present the copper is the most valuable product. This metal, which rarely makes its appearance above the 100-feet level, is present to the extent of from 4 to 5 per cent. of the vein material."

Several of the principal lodes have been noted herein under their specific names. Other occurrences of copper-bearing veins are:—

McAuley and party's, on north slope of Mount Carrington, on which six shafts have been sunk to various depths, and connected by a main drive. The principal operations lie between No. 1 shaft (100 feet) and No. 2 (80 feet). In a level from the 80-feet shaft, a drive for 120 feet reveals a width of 3 inches to 1 foot of veinstone; 11¾ tons ore obtained, yielded 2·3 per cent. copper (*ibid.*, 1907, p. 54).

Rainbow Mine, on south slopes of Mount Carrington, and adjoining Pioneer Mine. In 1907 Parker and party drove along the lode 70 feet, and stoped along back of lode for 80 feet; 44 tons copper ore raised, valued at £220 (*ibid.*).

About 3 miles south of Drake a formation is reported by J. P. Curran, Warden's Clerk, with indications of copper lode; bunches of carbonate 2½ inches wide occurring, but at 18 feet are reported to have pinched, with less encouraging prospects.

NEW ENGLAND MINING DISTRICT—*continued*.

Donnellan and party, at Sawpit Gully, sank two shafts of 50 feet each, in their lease, and connected them by a drive 200 feet long. The lode averages about 3 feet wide. Two men won 47 tons of ore, yielding 7½ per cent. of copper (*ibid.*).

No. 9, *Drake*.—Geological-Surveyor Andrews reported: shaft over 100 feet deep on well-defined lode. Gangue quartz with abundant zinc (*ibid.*, 1903, p. 132).

M.L. 10, *Drake*, parishes Gerard and West Fairfield, county Drake.—At Sawpit Gully. J. P. Curran reports (P.B. $\frac{1}{9}\frac{8}{9}\frac{2}{2}$): Shaft 26 feet, lode formation 7 feet wide. Three veins in shaft—western, 1 foot thick; centre vein, 1 foot; and east vein, on hanging wall, 2 feet wide. Lodestuff quartz with small bunches of black and yellow ore—average low.

Strike N.N.E., traceable 4 or 5 chains. Aid granted for 50 feet of sinking. No record.

Geological-Surveyor Andrews states that the Straus, Watson's Block, the Lead Block, Nil Desperandum, Hogg's Line, Lone Hand, Hot Scone, and other reefs in the neighbourhood of Drake, are more or less well defined, and contain, approximately, the same amounts of copper and impurities as in others enumerated (*ibid.*, 1903, p. 132).

Emmaville Division.

Emmaville.—Copper ores have been reported from several localities in the Emmaville District, but no lodes have yet been worked to any extent. At Hall's Grampians, portion 600, parish Strathbogie North, Professor T. W. E. David reported "Reid's copper lode" as the principal copper vein seen by him in the district. The lode, a breccia vein, resembling the Little Plant silver lode, is from 1 to 3 feet wide, strikes 16° N. of E., dips S.E. The vein stuff is chiefly chlorite with a little quartz containing blue and green carbonate of copper. The country is dark thickly-cleaved claystone.

Copper occurrences are also reported at Little Plant Creek, Pye's Creek, Glen Creek, and the Ottery lode. In portion 85, parish Strathbogie North, a vein of cellular quartz about 2 feet (?) wide strikes N. 40° E. The veinstuff shows streaks of blue carbonate and a little black oxide of copper.

In portion 2, parish Paradise North, county Gough, the same authority mentions the occurrence of a vein of fluorspar, copper carbonate, and iron oxide striking 20° N. of E., and dipping northerly. The portion containing the copper carbonate is 4½ inches wide.

Grey copper ore, Tetrahedrite, containing from 400 to 1,100 oz. of silver per ton, occurred in the silver lodes at Little Plant Creek and Pye's Creek.

The following analysis by the Government Analyst shows the composition of the argentiferous grey copper:—

In 100,000 parts.	
Metallic copper	31·500
„ antimony	18·130
„ zinc	6·140
„ iron	6·440
„ lead	·680
„ silver	1·635
Sulphur	26·180
Insoluble in acids (silica)	7·200
Traces of arsenic, gold, undetermined	2·095
	100·000

Kookabookra Division.

Guy Fawkes River, 15 miles N.W. of Hernani; also, 38 miles on road Armidale to Guy Fawkes, and 1½ miles S.E. of 38-mile road peg.—Copper ore in small vein, striking north and south, dip west. Formation, about 2 feet; copper sulphide veins 2 to 3 inches thick. Opened in creek, 9 miles from Guy Fawkes.

Drake Division.

Lady Mary, and Lady Mary Extended Mines, Drake.—Geological-Surveyor E. C. Andrews reported a dyke and quartz reef associated in these claims. The quartz reef strong, but of poor quality; width about 4 feet. The dyke, in places, exceeds 22 feet in width. Small veins of enriched black copper sulphide occur throughout the mass. Two shafts, about 140 feet deep, have been sunk in the dyke. (Ann. Rept., 1903, p. 132.)

In 1907 the main shaft was 170 feet deep, the principal mining being at 120-feet level, where the lode is reported to have a width of 9 feet, and an average value of 4 to 5 per cent. of copper, with rich bunches up to 18 and 20 per cent.

Gross output during 1907, 29 tons; 25½ tons smelted gave 4½ tons of copper at Customs Smelting Works (*ibid.*, 1907).

Of the Lady Mary Extended, portion 180, parish West Fairfield, county Drake, Inspector G. Smith reported in 1905: The strike N. 20° E.; dip easterly. Width, 9 feet. Maximum length of proving, about 100 feet. Depth, 170 feet.

Output—about 20 tons copper ore averaging 27 per cent., 1,200 tons copper ore averaging 3 per cent. The latter concentrated in a local battery to 80 tons, yielding 32 per cent. copper. One hundred and thirty tons from a quartz vein also yielded 230 oz. of gold.

In 1906 a 20-feet eastern crosscut proved a 2-feet vein, worth 5 to 6 per cent. of copper. At 120-feet level a crosscut east for 40 feet, proved a formation, 6 feet wide, containing a 4-inch copper vein, worth 20 per cent.

Value of output for year, £263.

Mount Carrington Mine.—Geological-Surveyor Andrews reported (Ann. Rept., 1903, p. 132) that this lode is similar to the Pioneer, near by, but amount of sulphides less. Deepest shaft, 340 feet, following underlay. Vertical shaft, 200 feet, to intersect reef on east. Average width, from 3 to 4 feet. Worked for copper.

Mount Carrington.—A little copper ore has always been a feature of the auriferous veins and lodes of the Drake District (*see* Drake), and with depth payable copper veins have been opened. Under date 14th, July 1898, Mr. J. P. Curran, Warden's Clerk, Drake, supplied the following particulars of the aspect of the copper-mining industry in his district at that date:—

"Three distinct copper lodes, striking north and south, occur on the north side of Mount Carrington. The ore at surface is of good quality, but operations so far are too shallow to allow of definite determination as to permanency of lodes. The indications, however, are favourable.

"The lode in Mineral Lease 5, of 40 acres, held by J. Staunton and party, appears well defined, and about 3 feet thick. It has been opened in several places for a distance of about 10 chains, disclosing carbonates of good quality near the surface, and native copper and red oxide just beneath."

In 1893 the following parcels were treated at the English and Australian Smelting Works, Waratah:—

	Yield.
19 tons 9 cwt.	20 per cent. copper.
7 „ 0 „	18 „ „
5 „ 5 „	25 „ „
3 „ 5 „	21 „ „
12 „ 10 „	18¼ „ „
5 „ 17 „	19 „ „
3 „ 16 „	21 „ „

In addition, Mr. Curran reports that a large quantity of this ore was treated by the Adeline Company in 1891 at its local works, with very satisfactory results.

A short distance west of Staunton and party's mine, is another parallel lode worked by D. Creed and party in a mineral lease of 20 acres. A shaft had been sunk to 35 feet, at which level a large bunch of red oxide was met. The lode, so far as opened, varies from 9 inches to 3 feet in thickness.

About 12 chains south of Creed and party, and apparently on the same line, Handcock and party are working at a depth of 140 feet on a 6-inch copper vein, composed chiefly of black oxide, assaying from 20 to 40 per cent. of copper. A parcel of 5 tons treated at the English and Australian Smelting Works, Waratah, yielded 25 per cent. of copper and 1 oz. gold per ton.

A short distance further west, D. Mickle and party were working the Great American Barber Mine.

In the adjoining block, on the same line, Hawkins and Tubman, at a depth of 40 feet, were working on a small but rich vein of black oxide, assaying from 30 to 40 per cent. of copper. Considerable improvement in the width of the vein was manifest at the 60-feet level at a later date, the lode being well defined, the matrix quartz, with about 2 feet of clean ore over 30 per cent. grade.

Still further west, Kay and Peacock had opened a promising copper lode on what is regarded as a new line, and at a depth of 15 feet obtained a quantity of black and yellow ore. Two veins occur in the shaft, 9 and 12 inches thick.

The Adeline Mine, which was originally worked for gold, may now be classed as a copper mine, as copper is the predominant metal. At the 100-feet level the lode for a considerable distance along its course varies from 3 to 5 feet in thickness. 16 tons 10 cwt. treated at the Smelting Company of Australia's Works, Dapto, yielded 1 ton 4 cwt. of copper—equivalent to about 7½ per cent.

M.L. 5, parish W. Fairfield, county Drake, about 1 mile north of village of Fairfield.—Inspector G. Smith reported (P.B. $\frac{22}{05}$) copper lode in igneous (?) rock. Said to have averaged 5 per cent. of copper, and 2 dwt. of gold per ton. Average thickness, 2 ft. 6 in.

Aided to sink a further depth of 60 feet.

Pioneer Mine, Drake.—Geological-Surveyor E. C. Andrews describes three shafts on this lode, deepest 240 feet, following underlay. Lode well

defined, averaging 18 to 24 inches in width. Ores copper and gold; copper ore as black oxides, and yellow sulphide. Reported to average 4 to 5 per cent. of the vein. Gangue-quartz, with sulphides of iron, varying from 20 to 40 per cent. Underlay, 1 in 1. (Ann. Rept., 1903, p. 132.)

In 1907 a tunnel had been driven 800 feet. Lode formation, 3½ feet wide, from which 425 tons crude ore were obtained, which produced 14½ tons of copper (*ibid.*, 1907).

Poor Man's Friend Mine, Drake.—Two shafts on line of lode, 30 and 40 feet, connected by level 140 feet long. Width, 6 to 12 inches. About 34 tons smelted at Customs Works for 4 tons 17 cwt. of copper.

Deepwater Division.

Pye's Creek, 14 miles N.N.W. of Deepwater, and 1 mile from Cadell's out station on Pye's Creek.—A lode about 4 feet thick is reported to occur at the above locality, consisting of copper and iron pyrites, galena, and zinc-blende. Bunches of rich copper ores occur at intervals. Opened about 40 feet by shaft, and driven on for 20 feet. About 40 tons of mixed ore at grass. No bulk tests made. Assays yielded up to 20 per cent. of copper from best bunches. Numerous indications are reported to occur in neighbouring veins and lodes.

Drake Division.

Rainbow Mine, portion 188, parish West Fairfield, county Drake.—Inspector G. Smith reported (1/7/05): Quartz vein with gold and copper ores, striking N.E., and dipping S.E. Proved to 140 feet, and for a length of 150 feet.

Gross output, 300 tons of ore, valued at £3,000.

In 1906 Parker and party put in tunnel to unwater old workings, and intersect lode at 180 feet. Cut another lode at 150 feet, striking at an acute angle to the Rainbow. New lode, 2 feet wide, containing low grade concentrating ore, and bunches of native copper.

Thirty-one tons ore sent to smelting works realised £105. (Ann. Rept. 1906, p. 48.)

Hillgrove Division.

Sunnyside Copper and Silver Mine.—See p. 330.

Styx River, 35 miles from Armidale, and 9 from George's Creek.—Formation 2 feet wide, with poor copper ore. Showing also in river about 2 chains above bridge. Tunnel driven 60 feet.

Ward's Mistake, C. E. Brazier's claim, parish Blythe, county Clarke.—Inspector J. James reported (P.B. $\frac{21\frac{1}{2}}{0}$) a copper lode in sandstone and slate. Carbonates discovered at surface, and traced for upwards of 100 feet in length. About 6 inches of sulphides showing at bottom of shaft. Aided to sink to 72 feet.

Progress.—At 47 feet a small bunch of ore encountered, not payable. At 64 feet progress slow on account of water. A fair deposit of copper ore visible, but insufficient to pay for working. Aid for tunnel refused.

McKinley's Claim, 9 miles east of Ward's Mistake, same parish, about quarter mile east of Brazier's claim.—Inspector J. James reported (P.B. $\frac{21\frac{1}{2}}{0}$) gossany formation in sandstone and slate. Formation, 20 to 40 feet wide, with gossan outcropping in several places. Aid granted to sink to 50 feet.

NEW ENGLAND MINING DISTRICT—*continued.*

Progress.—At 35 feet, occasional pieces of quartz with copper ore. At 50 feet, ironstone bands.

Re-examined by Inspector James (P.B. $\frac{A}{0}\frac{A}{8}\frac{1}{1}$), who reported that lode had been passed through. Aid granted to crosscut.

Emmaville Division.

Willow's Mine, north side of Glen Creek, 4 miles from Tent Hill, 6 miles from Emmaville, and 18 from the Deepwater Railway Station.—This mine occurs between the Little Plant Silver Mine and the Emerald Mine. The lode in it varies from 8 inches to 3 ft. 6 in. in thickness, and is about 12 inches at the lowest level reached—70 feet.

5¼ tons yielded about 5½ per cent. of copper at the Smelting Company of Australia's Works, Dapto.

PEEL AND URALLA MINING DISTRICT.

Tamworth Division.

Attunga Copper Mine, P.M.Ls. 1 and 2, and P.G.L. 1; areas, 10, 5; and 14 acres; within portions 225 and 226, parish Attunga, county Inglis, in T. Bryan's land; 9 miles easterly from Attunga Railway Station.— Discovered and taken up by J. Brogan in 1902, but probably known to the owner of the land prior to that date.

The Attunga lodes strikes about north and south at contact of limestone and sedimentary rocks with igneous. The outcrop for the greater part of its length has determined a small gully owing to its greater susceptibility to weathering. The latter falls into Willow Tree Creek, one of the heads of Attunga Creek. At no great distance below the mine is a permanent water supply. Within half a mile an excellent dam site is obtainable.

In the accompanying longitudinal section of the workings it will be observed that the southern termination of the outcrop rises to the top of a saddle 400 feet above the lowest tunnel (F); on either side of the latter, ranges rise above it 1,000 to 1,200 feet.

South of the saddle the main lode has not yet been proved to extend, though a cross lode striking N. 85° W. has been discovered on the southern fall. It



occurs in an igneous rock (andesite), has no true walls, being fast o "frozen" in the solid country. Small nodules of rich sulphide (bornite occur, but are not persistent, the greatest width of ore being about 1 inches. The average quality is shown in Assay No. 08–1196.

Though the main lode is traceable by workings and open cuts for abou 900 feet, actual mining is confined to a length of about 220 feet, and a dept of 258 feet, though little actual stoping has taken place. Sulphides begi about 30 feet above the lowest or G level—which marks the water-level their quality is shown in Assays 08–1194 and 1195.

As might be expected in a contact deposit, where partial alteration o one rock (limestone) has given rise to the secondary mineral garnet, th width of mineralisation is variable, ranging from a couple of feet to ove 20 feet; in some bunches to 60 feet; though these greater measurement include barren bands.

Assay No.	Description.	Copper, per cent.	Iron,‡ per cent.	Silica, per cent.	Sulphur, per cent.	Alumina,§ per cent.	Bismuth, per cent.	Gold, per ton.			Silver, per ton.		
								oz.	dwt.	grs.	oz.	dwt.	grs.
08–1190	Average of paddocks of "firsts" from A and B levels.	6·20	6·23	38·01	..	8·26	less than 0·25	0	4	8	4	15	19
08–1191	Average of paddocks of "seconds" from A and B levels.	5·22	5·32	38·70	..	9·50	0·25	0	3	6	3	2	1
08–1192	Average of "firsts" from 2-feet wide E. level.	9·85	5·81	36·03	..	1·86*	0·25	0	6	13	6	4	3
08–1193	Average of "seconds" from 2-feet wide E. level.	1·87	5·88	41·16	..	2·86	0·25	0	2	4	0	13	1
08–1194	Average of ore from G level, 5 feet wide.	3·28	5·46	39·77	0·06	1·56	0·25	0	10	21	3	18	9
08–1195	†Average of ore from G level, south end, 3 feet wide.	0·56	2·59	38·53	2·38	8·04	Nil....	0	4	8	0	8	17
08–1196	Average of cross lode, south end of lease.	14·02						0	10	21	10	13	10

* Phosphoric acid, 0·70 per cent. † Contains a fair quantity of Molybdenite. ‡ Soluble in acid.
§ Including a little phosphoric acid.

NOTE.—In each case the gangue—in addition to the silica and alumina determined—contains large quantities of lime, some magnesia, and a little iron which was not deter mined. All the samples contain more or less carbon dioxide and water. The coppe is present as oxide or carbonate. The iron (soluble in acid) is present as oxide or carbonate The percentage of alumina represents the total alumina.

Taking sample No. 08–1190 for example, the assay results can be stated thus:—

Copper	6·20 per cent.
Iron	6·23 „
Sulphur	nil.
Silica	38·01 „
Bismuth.....less than	0·25 „
Alumina and a little phosphoric acid	8·26 „
Oxygen, carbon dioxide, lime, magnesia, water, &c.	41·30 „
	100·00

The non-metallic gangue, therefore, works out in each case as follows :—

No. 1190, 63·43 per cent.; No. 1191, 56·21 per cent.; No. 1194, 44·47 per cent. No. 1193, 65·9 per cent.; No. 1194, 70·49 per cent.; No. 1195, 77·91 per cent.

An earlier sample of the carbonate ore yielded:—

No. 05-3128—	Silica (SiO_2)	34·32
	Alumina (Al_2O_3)	12·64
	Ferric oxide (Fe_2O_3)	9·50
	Copper oxide (CuO)	8·45
	Bismuth (Bi)	0·17
	Lime (CaO)	7·92
	Magnesia (MgO)	1·44
	Manganese (Mn)	0·25
	Ferrous oxide (FeO)	trace

A sample of the limestone from lowest tunnel (F level), which occurs on the western wall of the lode, yielded the following composition on partial analysis, the impurity of which is doubtless due to secondary silicic infiltration from the ore channel:—

No. 08-1204—	Calcium carbonate ($CaCO_3$)	75·77
	Lime (CaO)	2·65
	Ferric oxide and alumina ($Fe_2O_3+Al_2O_3$)	3·74
	Magnesium carbonate ($MgCO_3$) and undetermined	0·14
	Gangue	17·70
		100·00

NOTE.—Gangue mainly silica with some earthy matter. A few specks of pyrites visible. A portion of lime is combined as silicate, as there is not sufficient carbon dioxide present to combine with the total lime.

Abundance of excellent limestone is, however, procurable within a few chains.

A yellowish-green silicate of iron is conspicuous in parts of the lode channel, the composition of which is shown in the following analysis:—

No. 05-2175—	Moisture at 100° C.	4·50
	Water above 100° C.	4·84
	Silica	73·26
	Alumina	0·50
	Ferric oxide	14·90
	Ferrous oxide	0·27
	Manganous oxide	0·01
	Lime	1·22
	Magnesia	0·24
	Barium oxide	absent.
	Strontium oxide	trace.
	Soda	0·28
	Potash	0·13
	Lithia	absent.
	Phosphoric acid	trace.
	Titanic acid	absent.
	Vanadic oxide	,,
	Chlorine	,,
	Copper oxide	0·12
		100·27

Specific gravity, 2·243.

PEEL AND URALLA MINING DISTRICT—*continued.*

Output.—The output for which account sales have been received is shown in the following table. About 946 tons were sent from the mine, some of which remains unsold. Remarkable discrepancies, however, occur between the mine weights and actual returns.

Location.	Quantity (21 cwt. tons).	Copper, per cent.		Gold, per ton.		Silver, per ton.	
		From	To	From	To	From	To
	tons cwt. qr.			dwt.	dwt.	oz. dwt. gr.	oz. dwt. gr.
Open cut, mouth of A tunnel....	404 0 0	5·5	6·78	3·1	9·14	4 18 5	6 0 0
Open cut and B tunnel	152 13 0	5·2	6·7	¼	4·9	4 0 0	5 6 0
C level and stopes	118 5 3	5·6	8·78	3½	4	4 0 0	4 3 14

Total, 674 tons 18 cwt. 3 qrs., or 708·6 ordinary tons.

The total amount despatched from the mine, according to the manager's estimates, was 946 tons 2 cwt. 2 qrs., without allowance for moisture.

The appreciable quantities of gold and silver revealed in the above returns from Customs Smelting Works, and in the assays of very carefully taken samples of many tons of ore at grass, made in the Departmental Laboratory, are of special importance in the economics of this mine, especially when it is known that the noble metals are not confined to the copper ores. Probably a proportion of the non-cupriferous lodestuff may prove payably amenable to cyanidation.

Dr. R. L. Jack, who made a prolonged and exhaustive examination of the mine just prior to the Writer's visit, estimates the ore at grass—by measurement—at 1,628 tons.

The following assay returns, from average samples, personally selected by Dr. Jack from ore faces in different portions of the workings, are taken from his report:—

Portion of Mine.	Width of Ore.	Nature of Ore.	Copper, per cent.
	ft. in.		
A Level	3 0	Carbonate	13·4
,, ...	1 0	,, in garnet	8·6
B Level	3 5	Carbonate	12·5
,, (below)	5 0	,, ...	7·5
,, ,, ...	2 0	,, ...	21·0
C Level	3 2	,, ...	2·4
,, ...	5 10	,, ...	2·4
,, ...	1 3	,, ...	1·8
,, ...	6 0	,, ...	4·3
,, ...	3 0	,, ...	2·8
,, ...	4 0	,, ...	5·4
,, ...	1 0	,, ...	2·8
,, ...	10 0	,, ...	5·3
D Level	2 0	,, ...	5·2
,, ...	4 3	,, ...	4·3
,, ...	3 6	,, ...	3·2
G Level, winze	0 3	Sulphides	1·5
,, ,, ...	1 0	,, (west side).....	11·9
O Shaft, near top of saddle	0 9	Carbonates	·4
South side (cross lode)	1 3	.....	7·8

"G" level, which marks approximately water-level, is 75 feet below the lowest feasible tunnel-level (F), which is now being driven for the purpose of reducing the water lift, and thus facilitating deeper sinking to prove the sulphide zone below water-level. On the extent and quality of the latter, the future prospects of the mine—as a copper producer—depend. From the absence of solid pyritic masses, so far as proved, concentration will probably have to be faced.

Here a note of warning is offered in reference to contemplated establishment of blast furnace reduction for the oxidised ores (which applies with equal force to ordinary reverberatory furnacing). Attempting to smelt silicious oxidised ores in the absence of sulphides would result in too rapid reduction, and unclean slags. Moreover, the productive furnace capacity would be proportionally lessened by the large necessary admixture of probably valueless fluxes.

The wisdom, therefore, of proving the sulphide resources of the lode before devising, or even contemplating a reduction plant, is unquestionable.

Barraba Division.

Barraba District, 12 miles N.E. of Barraba, and 7 miles S.W. of Gulf Creek Copper Mine, parish Tiabundie, county Darling.—Inspector Carthew reported quartz reef in sandstone. Strike E. and W.; dip S.; shaft, 46 feet.

Aided to 146-feet level. At 81 feet serpentine rock met, carrying copper and iron, reef 6 inches thick. Country hard; water making. Similar conditions at 102 feet. Abandoned.

Bingara Division.

Bingara District.—Inspector Carthew, in 1901, reported—A quartz reef containing copper ore 7 miles south-easterly from Bingara, near Gwydir River, towards Keira Station. About 30 chains south of M.L. 11, parish Bingara, county Murchison. Strike of reef N. and S. Aided to sink 100 feet; aid not availed of.

Also a quartz reef with copper and gold in altered slates at Spring Creek, 3½ miles south-east of Bingara. Strike N. and S.; dip E. Shafts, 15 feet and 35 feet. Aided to sink to 135 feet. (P.B. $\frac{1}{0}\frac{8}{0}\frac{8}{0}$.)

Progress.—At 53 feet, serpentine rock with indications of copper. At 68 feet, several small veins showing in shaft. No further record.

Bobby Whitlow Mine, M.L. 3, parish Myall, county Murchison; about 7 miles from Bingara, and 27 by road from Warialda Railway Station.—Discovered by R. Bennett and F. Clusterman about 1875. Worked intermittently. Ore raised and despatched to end of 1906—about 802 tons, averaging from 8 to 16 per cent. of copper. No seconds.

Examined August, 1907. Lode strikes N. 10° E.; dips east slightly. Country slate with quartzite bands.

Opened by two shafts 30 feet apart, to depths of 82 feet and 142 feet respectively. Water-level at 120 feet. Oxidised ores to about 85 feet; enriched sulphides stoped to 95 feet, little stoping below this level. Not open to inspection below 120 feet. Unaltered sulphide apparently too low grade for despatch.

Greatest length of lens in oxidised zone about 85 feet; 55 feet in enriched sulphide, apparently contracting with depth. Width, 1 to 7 feet.

PEEL AND URALLA MINING DISTRICT—*continued.*

No prospecting beyond ends of ore body though channel persists. At 82-feet level a 19-feet lens proved after blank of 10 feet. No crosscutting, though a flat vein enters footwall at about 70 feet. Parallel vein splitting from main lens on east side at 82-feet level followed down until pinched; 70 tons ore extracted from it; channel still persistent.

Option secured by Messrs. Brandeis, Goldschmidt, & Co. in 1907. After cleaning out the shaft the prospects were not considered encouraging enough for further development; the option was therefore abandoned.

Bora Creek Copper Mine, M.L. 5, parish Bingara, county Murchison; about 7 miles from Bingara, on south side of Gwydir River, near Bundarra road.—Strike N.W. in slate; dip S.W. at 71°. Shaft sunk many years ago, to about 40 feet, and a few tons of copper ore extracted.

Aided (P.B. $\frac{11}{0}\frac{0}{6}$) to sink from 40 to 100 feet.

At 80 feet shaft following veins of copper ore. At 86 feet water making, with thin veins of enriched (black) sulphide showing.

Position in August, 1907.—At 40-feet level in underlay shaft, driven 20 feet south-east. Winze from this point 30 feet deep; reported on ore.

Channel 2 ft. 6 in. to 3 feet wide, filled with gossan. Vertical shaft 20 feet south-west of underlay shaft—cut reef at 80 feet. Driven 40 feet south-east on sulphide ore, which pinched at end of drive, but passed under foot. Country slate and jasperoid quartzite.

Thirty tons of sulphides from vertical shaft and south-east drive yielded 6¾ to 8 per cent. of copper. Seven tons bagged at surface; close picking should bring grade to at least 10 per cent.

Nundle Division.

Bowling Alley Point, 3 miles from and 1 mile east of road to Nundle, parish Dungowan, county Parry.—Inspector James reported (P.B. $\frac{2}{0}\frac{1}{7}\frac{2}{1}$) lode formation carrying copper in diorite and slate. Sunk on to 30 feet; showing a small vein 4 to 6 inches wide, carrying blue and green carbonates. Sinking expensive, owing to water making.

Aided to tunnel from 63 feet to 104 feet along the lode.

Armidale Division.

Bundarra Mine, parish Darby, county Hardinge; 3 miles south of Bundarra, 1 mile from Gwydir River, and 32 from Inverell Railway Station.—Discovered by H. Shand about 1877. Opened by J. Russell and party about 1897, and proved to 150 feet. Rich patches of ore obtained, but no defined or continuous lode. Seventy-two tons of ore despatched to August, 1898, averaging about 17 per cent. copper.

Three hundred feet level reached in 1900; thence until 1906 practically idle. Passed into possession of Messrs. Brandeis, Goldschmidt, & Co., London, at end of 1905. Small reverberatory furnace erected.

Examined March, 1907.—Strike N. and S.; dip west at 45°. Country altered slate (chloritic) and jasperoid quartzite. Main ore-body proved 18 feet to 22 feet long. The 124-feet, 200-feet, and 270-feet levels extended from 40 feet to 140 feet north and south beyond the ore shoot in blank

PEEL AND UBALLA MINING DISTRICT—*continued.*

channel rock. Payable ore exhausted above 270-feet level; below it, winze sunk in low grade ore to 360-feet level. Average sample from it gave the following results:—

No. 07-6436—Copper	0·90	per cent.	
Zinc	11·04	,,	
Iron	34·74	,,	chiefly magnetic and arsenical pyrites.
Sulphur	9·87	,,	
Silica	14·44	,,	
Gold	A trace (under 2 dwt.) per ton.		
Silver	5 dwt. 10 grs. per ton.		

From surface to 50 feet earthy carbonates occurred, worth about 2½ per cent. copper; from 50 feet to 90 feet, ferruginous carbonates and grey ore, worth about 15 per cent. Average value of ore extracted, about 6 per cent. Zinc-blende prominent in part; also arsenic at lowest level. Calcite, in bands and seams, aids reduction.

Smelting.—In small reverberatory, capacity about 120 tons of ore per week, charging every four hours:—

2½ tons roasted and raw ore, 6 cwt. silica (jasperoid quartzite from mine), ½ to 1 barrow slag (from first three pigs) = 6 cwt. carbonates, ferruginous, 6 cwt. carbonates, earthy, 1 ton 18 cwt. roasted sulphides.

Matte previously shipped at 45 per cent. Recently run to 60 per cent. in finishing up prior to closing down. A barrowful each of charcoal and wood chips added to charge for higher grade.

About 200 tons of heap-roasted ore at grass to finish; absence of compact sulphides renders reduction of oxidised ores too rapid. No flux other than silica used.

The recent mining and smelting campaign has been profitable, but outlook not encouraging enough to induce further effort. Ore at bottom of proved area too poor for extraction. None in sight above water-level. Prospecting has been extended some little distance beyond the ore lens at different levels on north and south strike without avail. Other lenses may occur in crushed channel, but prospecting may be costly. The latter pinches very thin in places, and is thrown to the west. Greatest width in ore lens about 7 feet.

Owners relinquishing mine and dismantling plant.

The total output during the last smelting campaign—between 12th February, 1906, and 10th September, 1907—amounted to 3,732 tons of ore, producing 418 tons of matte.

Towards the end of the latter year, preparations for re-opening were being made by others.

Copeland Division.

Comstock Copper Mine (formerly Wet Creek); on F. Williams' C.L., parish Dewitt, county Hawes; about 25 miles from Copeland.—Inspector D. Milne reported (P.B. $\frac{22\frac{1}{4}1}{0}$) a lode formation heavily stained with copper carbonates, also containing small nodules of cuprite in porphyry.

Aid granted for tunnelling 50 feet in the formation.

Progress.—At 24 feet the lode was reported to be 2 ft. 6 in. wide; ore from it reported to assay 11 per cent. copper. Lode later reported to have pinched or dipped. Transfer of aid to shaft refused; balance cancelled on account of work ceasing.

Property secured by a Newcastle syndicate. Re-inspected by Mr. Milne (P.B. $\frac{22\frac{1}{4}4}{0}$).

PEEL AND URALLA MINING DISTRICT—*continued.*

Aid granted to continue tunnel on north side of creek from 40 feet to 190 feet, following the formation. Inspector Milne reported:—"On the site where the tunnel is started immense blocks of gossan are lying on the surface, and the tunnel is driven (40 feet) in ore. All the surface indications point to the hill being the strongest portion of the lode." In the shaft for which aid was refused, on the opposite side of the creek, the formation is described as very broken, and assay results very erratic, and not so favourable as in tunnel.

Tingha Division.

Conrad Stannite Mines, Ltd., Borah Creek, parish Mayo, county Hardinge.—In granite country. The feature of this lode is its great horizontal persistence in undiminished strength; the provings extending over 6,000 feet, and worked continuously for 4,611 feet. To quote the manager—Mr. B. C. Besley—"We have worked, at a depth, 4,611 feet continuously, and during that length of lode we have only had one fault—these workings run from 400 to 500 feet deep on the average. The fault was at the 400-feet level, and was a complete cut off in the lode for 30 feet, and is very interesting as it was so clean and complete, and was taken up at exactly the same width as where it first left the lode.

"With reference to the proved distance of the lode, a shaft has been sunk over 6,000 feet south of this again, for over 130 feet in the same lode; which is easily traced along the surface.

"Another peculiar point about this lode is that exactly the same ore is found on the surface as at a depth of 900 feet underground. Under the Big Hill it is now 900 feet to our bottom workings."

The composition of the ore is best judged from the following returns, furnished by the manager, from January to September, 1907:—

1,970 tons lead concentrates; average assay value,—lead 45 per cent., silver 80 oz. per ton.
570 tons prill ore, assaying about 60 per cent. lead and 120 oz. silver per ton.
260 tons copper matte, averaging about 40 per cent. copper and 250 to 400 oz. silver per ton.
A tin-lead bullion is also being turned out, containing about 45 per cent. of tin, the balance being lead.

Method of treatment.—Concentrating in mill producing lead concentrates as above, and tin sulphide concentrates, the latter being treated on the mine.

Process.—Calcination in a Merton calciner down to about 6 per cent. sulphur, roasted ore smelted in reverberatory, precipitating tin into slag and producing matte of about 40 per cent. copper in one operation.

Slag, containing about 10 per cent. tin, is melted, and tin precipitated by using green poles and metallic iron, leaving about 2 per cent. of tin in slag. (Process discovered by Mr. J. Howell.)

Walcha Division.

Cooperacurripa Copper Mine, near Nowendoc.—Lode in main shaft reported to be 4 ft. 6 in. thick at 45 feet, and the ore improving from 8 to 14 per cent. Another shaft on a reported 14-feet lode of promising character.

Tingha Division.

Cope's Creek.—Near the junction of the Gwydir River and Cope's Creek a sample of lodestuff carrying galena, malachite, and sulphides of iron and copper yielded ($\frac{28}{33}$) 7·08 per cent. of copper, and 59·69 per cent. of lead.

PEEL AND URALLA MINING DISTRICT—*continued.*

In the *Australian Mining Standard* of the 6th May, 1897, it was announced that a copper lode was discovered near Boggy Camp Diamond Mines, showing carbonates at surface.

Nundle Division.

Dungowan.—Inspector G. Smith reported (P.B. $\frac{20}{6}\frac{1}{2}\frac{2}{2}$) a quartz and ironstone formation 1 to 2 feet thick, with a little copper ore. A sample assaying 3 per cent. of copper, 3 oz. silver, and 2 dwt. gold.

Aided to sink to 60-feet level—at 15 feet reported that copper pinched out.

Walcha Division.

Europambella Lode, near Walcha.—J. Notley and party reported disposing of 110 tons of ore for a gross return of £600, in 1902. Ore reported to average 10 per cent. Deepest shaft, 96 feet. Lode faulted at this level. (Ann. Rept. 1902, p. 49.)

In 1906 Inspector D. Milne reported that the mine had been re-opened. Some tons of ore gathered from surface had yielded about 5 per cent. copper. Lode about 2 feet wide, of an average grade of 2½ per cent. The flow of underground water is heavy (*ibid.*, 1906).

Nundle Division.

Fisher's Copper Mine, Dungowan Creek, about 16 miles from Tamworth, in county Parry; discovered in 1881.

In 1885, Mr. C. S. Wilkinson reported that "lower down Dungowan Creek, on Mr. Fisher's land, some copper-bearing lodes have been opened in places for a length of about 8 chains, striking N. 10° W., and dipping westerly at 70°. These consist of several masses—of irregular size up to 10 feet long and 4 feet wide, and thinning out—of gossan and quartz, containing pyrites, native copper, red oxide, and carbonate of copper. They occur in greenish schists and jasperoid rocks. At the present low price of copper these small bunchy lodes could not be profitably worked."

Under date 19th July, 1898, Mr. Warden Jones writes that this mine, consisting of two mineral purchases of 40 and 50 acres, in 1882 was leased to the Hon. P. G. King, M.L.C., and others, for a period of fourteen years, but little work was done during the tenure of the lease, which expired in 1896. In that year Dr. Pratt secured the right to lease or purchase for a period of two years, which has just expired without labour being expended on the property.

The following assay was made in 1897 of a sample of green carbonate in ferruginous silicious gangue:—Copper, 42·20 per cent; silver, 2 oz. 19 dwt. 21 grs. per ton; gold, a trace (under 2 dwt.). Another sample of carbonate ore, selected by the Warden and forwarded with his letter of the date quoted, yielded copper, 34·23 per cent.; gold, 2 dwt. 4 grs.; and silver, 1 oz. 8 dwt. 7 grs. per ton.

According to the *Australian Mining Standard*, 23rd March, 1899, Mr. Fisher had just received returns of 5 tons 13 cwt. 2 qrs. of copper ore from the lode, which he was opening on his own account, viz., 1 ton 3 cwt. 2 qrs. 1 lb. of copper; value, £83 14s. 4d. A further consignment of 6 tons yielded 1 ton 2 cwt. 25 lb. of copper, which realised £107 13s. 3d.

PEEL AND URALLA MINING DISTRICT—*continued.*

Barraba Division.

Four-mile Lode, 4 miles from Gulf Creek, along Wood's Reef road.—Pro pecting area. Shaft, 50 feet. Carbonate ore showing on surface, none i shaft. Samples assay about 3 per cent. of copper.

Gulf Creek Copper Mine (originally the *Cornish* Mine), M.Ls. 6 and parish Capel, county Murchison, about 22 miles from Barraba Railway Statio 234 miles by rail from the coast at Newcastle, and 338 from Sydney.

In 1896 the Cornish Company received aid from the Prospecting Vot by means of which they succeeded in opening up payable ore, which realise sufficient to cover costs of development.

In the beginning of 1898 the mine was let on tribute, and later in the ye passed into the possession of the Mining and Financial Trust Syndicat Limited.

From the report of the Secretary of the Cornish Company, it appea that the first campaign only lasted until October, 1896, during which reverberatory and a small blast furnace were erected. In the former 80 tons of ore were smelted, and about 200 in the latter, with, howeve unsatisfactory results.

Three parallel lodes are now known, but the first company was only awar of one—the East lode.

In 1899 the mine was secured by W. H. Trewenack, who ran it on his ow account for a few months, and then on behalf of an English company (Th Gulf Creek), this campaign lasting until 1905. Smelting was carried o for a part of the time (1903 to 1905) in two reverberatories, and a sma blast furnace. Later on a 40-ton blast furnace was added to the plant.

According to Mr. Trewenack, about 1,200 tons of ore per month we smelted for an average yield of about 5 per cent. of copper, the resultin matte being shipped to Swansea.

On depreciation of ore tenor the mine was abandoned by the Gulf Cree Company in 1895, but was immediately secured by some of the la employees, under the title of the Gulf Creek Syndicate, who ran it unt February, 1907, when it was purchased by the present owners, Messr Brandeis, Goldschmidt & Co., London.

During the Gulf Syndicate's campaign about 200 tons of ore per mont were reduced in one reverberatory furnace, for an average yield of abo 6 per cent., and a matte grade of 40.

From a "burnt" stope, about 500 tons of naturally reduced matte w disposed of by the Syndicate for yields averaging from 12 to 20 per cen copper. About 20 tons of washed material yielding from 45 to 60 per cen

Messrs. Brandeis, Goldschmidt & Co. began operations on 1st May, 190 renovating and rebuilding plant, developing and prospecting the lodes.

According to Mr. R. Schloesser, Supervising Engineer, whilst high met values prevailed, about 2,500 tons of ore were smelted in the two reverber tories for 269 tons of matte of about 35 to 36 grade; which was shipped England.

This amount brings the total output of ore from the mine, so far as recor can be obtained, to between 34,000 and 37,000 tons to the end of 1907.

H. Stewart.

Gulf Creek Copper Mine, near Barraba.

The fire started during Trewenack's campaign, at a crosscut end from main shaft, and extended 250 feet along the south-east strike, and burned upwards to the gossan, and downwards for about 20 feet below the level.

Attempts were made to smother and extinguish by water and steam, and sealing, but unavailingly. Shafts were also sunk from surface to get at seat of firing.

The fire burned out after abandonment, ceasing about 1905, after the Gulf Syndicate assumed possession. The latter opened up the workings to allow free access of air and accelerate combustion.

In working the burnt stope—from which 500 tons of naturally reduced matte were obtained—spraying and respirators were used for protection against fine acidic ash.

The fire evidently ceased just below the zone of enrichment, for the unburned pyritic lodestuff has an average value of under 3 per cent.

The present proprietary used a proportion of the remaining burnt ore (averaging about 4½ per cent.) in their furnace charges.

The composition of Gulf Creek sulphide ore may be studied in the following average analysis of 1,330 tons from No. 2 level (100 feet), 1,000 from the big lode, and the balance from the Cornish and Middle lodes:—

Copper	2·7	per cent.
Iron	31·85	,,
Zinc	4·65	,,
Silica	18·93	,,
Alumina	4·84	,,
Lime	2·95	,,
Sulphur	31·70	,,
	97·62	

Gold and silver inappreciable.

The composition of this ore renders it very suitable for partial pyritic smelting, and affords a means of reducing more silicious ores.

Smelting plant.—The original plant of the Gulf Creek Company embraced a calciner furnace, blast furnace, and two reverberatories. The calciner and blast furnace were removed; the calciner stack remaining is 45 feet high, and the reverberatory stack, 120 feet. The flue connections remaining of the blast furnace equipment, measure 450 feet, part on piers, part under ground, the section being 6 feet x 8 feet.

Pending erection of a 100-ton blast furnace, the present owners have utilised the existing reverberatory. The furnace charge being:—

19,124 lb. roasted (heap) sulphide ore.
11,760 ,, burnt stope ore and raw ore (as required).
2,000 ,, old bricks from bottoms, re-treated slags, and quartzite.

32,884 lb. charged every four hours.

As ore is basic, one-fifteenth of silica is added in the form of quartzite.

The composition of the resultant slag is shown in the following analysis by Mr. Gurney:—

Copper	0·67
Iron	52·37
Zinc	2·4
Silica	32·2
Alumina	7·5
Lime	4·39
	99·53

H. Stewart. **Gulf Creek Smelting Works, Offices, &c., near Barraba.**

Limestone used for fluxing is obtained from portion 16, parish Capel, about 140 chains N.W. of the mine. Its composition is revealed in the following partial analysis:—

No. 07-6434—Carbonate of lime	92·35	per cent.
Carbonate of magnesia and undetermined	0·37	,,
Ferric oxide and alumina	1·60	,,
Gangue	5·68	,,
	100·00	

The composition of the local clay, which is used with a percentage of sand from Macintyre Creek for fettling is:—

No. 07-6437—Water (at 100° C.)	0·67	per cent.
Water (above 100° C.)	7·33	,,
Silica	64·35	,,
Alumina	16·58	,,
Ferric oxide	7·40	,,
Ferrous oxide	0·27	,,
Lime	0·50	,,
Magnesia	0·21	,,
Potash	0·80	,,
Soda	0·83	,,
Titanic acid (TiO_2)	0·70	,,
Phosphoric acid (P_2O_5)	0·07	,,
	99·71	

A trace of chlorine (soluble) and sulphuric anhydride detected.

Macintyre Creek sand—distant about 6 to 8 miles—used also for moulding, contains 83·7 per cent. of silica.

Newcastle beach sand is used for furnace bottoms.

The sulphides are roasted in clamps of about 250 tons—about eight weeks being occupied in the process.

The "burnt stope" ore has been reduced to about 18 per cent. of sulphur.

Copper in Mine Water.—During baling operations about 20,000 gallons per day were lifted. From the rate of reduction it is probable that the permanent daily make of water does not exceed 8,000 or 10,000 gallons.

The accumulated water in the workings was found by frequent tests to hold 0·09 per cent. of copper in solution; and after passage through the precipitating vats, 0·03 per cent.: an extraction of 66 per cent., which is good considering the rapidity of the flow and the solidity of the scrap iron in use.

About 3½ tons of cement copper obtained in partial clean-ups to September, 1907, contained about 73 per cent. of copper, the balance being ferric oxide.

An interesting fact, noted by the principal vat boy—E. Kenny—was that coke, or raw pyritic ore, acted as a cathode in the solution when in contact with iron, but remained inert without it. Mr. Schloesser, writing in January, 1908, stated that precipitation is now effected by layers of coke and heavy iron as more economical. The copper being precipitated in the presence of iron on the surface of the coke, which is broken to about 3-inch gauge. Fresh coke being introduced from time to time, and the copper-bearing coke stacked for use as fuel in the blast furnace.

PEEL AND URALLA MINING DISTRICT—*continued*.

Gulf Creek, 1½ miles S.E. of the Gulf Creek Mine, in parish Capel, county Murchison.—Aid was granted to sink 50 feet. Carbonate of copper stains occurred at 20 feet, but no defined lode had been proved to 24 feet (P.B. $\frac{1\,8\,9\,0}{0\,7}$).

Bingara Division.

Harrison's Mine, Copper Gully, Upper Bingara.—Discovered and opened by W. H. Harrison in 1895, in slate and diorite (?) country near serpentine. Lode cut in shaft at 9 feet; thickness, 4 feet; assay value, (2½ per cent. Shaft sunk 35 feet, partly under aid; lode widened to 6 ft. 6 in., and increased in value.

Hilda May Copper Lode, Spring Creek, 3 miles from Bingara.—Originally worked for gold. Shaft 37 feet, following peridotite, containing copper carbonates as films on joint faces.

At 37 feet, at end of drive dipping north-west, gossan is making with seams of copper sulphide; here there is probability of about 1 foot of fair sulphide ore.

Strike N. 40° W.; dip slight, north-easterly.

Close by in Spring Creek and Spring Gully, near old cinnabar leases, stains of copper carbonate are lightly distributed. Dunbar, Bailey, and party are in receipt of aid for sinking in slightly impregnated serpentine of very unpromising character.

Further down Spring Gully, in Twyford's claim, copper ore associated with chromite and calcite occurs, but is of no importance.

Tingha Division.

Hoy's Reef, Sandy Creek.—Inspector J. Carthew, reports that this reef consists of quartz with galena, zinc-blende, and copper pyrites, and has a thickness of 2 feet. Several other veins occur S.E. of it, one apparently larger. Strike N. 70° E., dip S. 20° E.

Barraba Division.

Ironbarks Lode, Wood's Reef, parish Tiabundie, county Darling.—First opened by C. Orchard, 1887; a small parcel of ore sent away.

Held by present owners—E. Jeffray and party—since February, 1907. Country hard, red jasperoid quartzite. Lode occurs in bank of Ironbark Creek and strikes N. 20° W.

Proved by four openings and a short tunnel for a length of 260 feet, and a depth of 26 feet. The oxidised ore consists of gossan, with carbonates in cliff face. In the lowest levels, sulphides of very low copper grade are making 6 inches to 8 inches wide.

From the evidence of the creek-bed openings the lode, or patchy impregnation, makes into low grade iron sulphide of discouraging composition. A little good-grade ore was obtained from a bunch in the 26-feet shaft.

An assay of material from the west end of the tunnel, made at Gulf Creek, yielded:—

Copper	0·8 per cent.
Gold	3·2 dwt. per ton.
Silver	4·2 „ „

PEEL AND URALLA MINING DISTRICT—*continued.*

Tingha Division.

Lady Mary Mine, 3 miles from Copeton, towards Inverell, parish Copeton, county Hardinge, on north side of Cope's Creek.—Inspector J. Carthew reported (P.B. $\frac{4\,4\,8\,2}{0\,0}$) quartz showing copper ore in decomposed slate.

Aided to sink to 100 feet. At 61½ feet country hard; vein, 1 ft. 6 in. to 2 feet wide. At 75 feet prospects not improving. Abandoned.

Bingara Division.

Mandourie Paddock, 20 miles from Ashford, parish Warialda, county Arrawatta.—Inspector J. James reported (P.B. $\frac{2\,2\,4\,8}{0\,7}$) a lode 1 foot wide carrying black copper ore and silver; said to assay up to 27 per cent. of copper and 20 oz. of silver per ton. Exposed for a length of 12 feet in an open trench.

Aided to sink 25 feet.

Mona Copper Lode, M.L. 6, parish Gouron, county Murchison, Top Bingara.—Discovered by D. McCarthy and W. Madden, May, 1907.

Two lodes about 30 feet apart. Strikes N. 55° W., dip slight to the north-east.

East lode opened by shaft to 45 feet. Ore struck at 25 feet. Gossan at surface. Channel 1 to 3 feet wide. Ore in lenses from an inch or two to 12 inches thick, of good quality. Country chloritic slate, with bands of red jasperoid quartzite with strings of quartz.

West lode opened by shaft to 29 feet. Ore struck at 18 feet, low grade and refractory; consisting of copper pyrites leanly distributed in hard quartzite. Channel 2 to 3 feet wide.

Mount Everest Copper Mine, M.L. 2, parishes Gouron, Dinoga, and Macintyre, county Murchison, about 1½ miles from Top Bingara Post Office.—Strike N. 75° W. Discovered by W. Power about 1894. In 1900, aid was granted to prospect. Power, Smith, and Carey sank 150 feet, then sold to W. H. Trewenack, who drove a crosscut tunnel 270 feet to cut the lode at 130 feet. Lease afterwards secured by W. Smith, of Newcastle, who let on tribute to Hoskins, Akerman, and Daly, for about two years. The tributers despatched between 600 and 700 tons of ore to Waratah, for a reported average of 14 per cent. copper.

A winze was sunk 14 feet below the tunnel (130-feet) level—not open to inspection. Partly enriched sulphides at 130 feet. Bunches of rich grey sulphide extracted from oxidised zone. Kindly gossan in outcrop. Country chloritic slate and red jasperoid quartzite with quartz veinlets.

Length of ore lens, 100 feet, by a width of 16 feet, at 130 feet level. Blanks at both ends beyond ore body. Very desirable that the lower sulphide zone should be tested below sphere of enrichment.

In 1907, Messrs. Greenway and others erected a small blast furnace of about 40 tons daily capacity to treat the ore in sight about the 130-feet level. First trial of smelter began 18th December, ran intermittently until 8th January, 1908. During this campaign 500 tons were mined from the tunnel stopes, of which about 200 tons were smelted for about 45 tons of matte.

Mount Lauff Copper Lode, in W. Morris' C.P. Lease, parish Goorin, county Murchison, about 3 miles easterly from 7-mile peg on Bingara-Barraba road.—Opened by shaft to 90 feet; crosscut west 14 feet at 50-feet level; driven north 20 feet at 60-feet level.

The section of outcrop at shaft exposes 16 to 17 feet of alternating crushed clay stones and ferruginous quartzites with copper stains in places. At bottom of shaft a few small kernels of rich sulphide occurred (a few pounds only). Aid received for sinking 50 feet deeper.

Nundle Division.

Mount Pleasant Copper Mine, Dungowan, about 28 miles from Tamworth, county Parry.—Mr. C. S. Wilkinson in 1885 reported that "at Mount Pleasant, on Dungowan Creek, Mr. T. Hole has had a shaft 50 feet deep sunk in prospecting for a copper lode, where the altered red jasperoid slates are traversed by a small irregular vein a few inches thick of gossan, quartz, and serpentinous clay containing carbonates of copper. It is evidently a decomposed vein of copper and iron pyrites, and of no value as a copper lode; but in one specimen I detected free gold, and I would advise further prospecting to ascertain if gold does not exist in payable quantity. Jasperoid rocks appear at the surface for about 10 chains in a north-easterly and south-westerly direction, and in places are stained with carbonates of copper."

Three mines are known in this locality—the Dungowan, the Kurrajong, and the Mount Pleasant.

In 1886, several tons of ore from the Mount Pleasant Mine were tested and found auriferous but not payable.

Mr. Warden Jones, writing under date 19th July, 1898, stated that the mine occurs on a conditional lease, and that a permit was granted to G. Hyde in 1897, but no work was done under this authority.

Inverell Division.

Mundowie Copper Lode, Fraser's Creek, parish Mandoe, county Arrawatta.—Discovered by E. Devlin. Copper, silver, and lead ores reported. Striking N. and S. in slate; dip east. Opened to 20 feet; width, 2 feet.

Barraba Division.

Murchison Lode, 1½ miles north of Gulf Creek Mine, M.L. 5, parish Capel, county Murchison.—Lode 1 to 4 feet wide, bunchy, opened to 50 feet.

Fifteen hundredweight of ore purchased by Gulf Creek Company at 11 per cent. copper; 1¾ tons, at 3·35 per cent.; 10 tons of 3 per cent. at grass.

Tamworth Division.

Namoi Copper Mine, M.L. 4, parish Attunga, county Inglis, about 9 miles from Attunga Railway Station.—Discovered by J. J. Wade in 1903.

Inspector D. Milne reported (P.B. $\frac{1}{0}\frac{0}{4}\frac{2}{4}\frac{2}{4}$) lode well defined, about 10 inches wide, carrying veins of copper ore.

Aided to continue tunnel from 33 feet to 100 feet.

Progress.—At 100 feet in tunnel, hard rock; at 130 feet, no prospects. Two ore bodies reported. Aid allowed for 50 feet driving along shoot passed in tunnel.

Aided to sink winze 50 feet on formation 3 ft. 6 in. wide at 9 feet from tunnel entrance. (P.B. $\frac{2}{0}\frac{0}{4}\frac{7}{4}\frac{6}{4}$.)

PEEL AND URALLA MINING DISTRICT—*continued.*

Inspector J. James reported (P.B. $\frac{1}{0}\frac{8}{8}\frac{9}{}$) a short shoot of sulphides of fair quality at 56 feet in winze, 2 to 4 inches thick, apparently passing into footwall.

Aided to continue winze to 100 feet. Ore vein passed through at 83 feet. Sinking discontinued. Driven S.W. for 50 feet at 83-feet level, passing through ore shoot at 25 feet from shaft; remainder of drive in country. Vein reported to average from 1 ft. 6 in. to 2 feet in drive, but low grade.

The following samples were selected by the Writer from bagged and stacked ore at the mine:—

Assay No.	Description.	Copper, per cent.	Silica, per cent.	Gold, per ton.			Silver, per ton.		
				oz.	dwt.	grs.	oz.	dwt.	grs.
08-1187 ...	Dressed ore in bags from tunnel and winze.	10·80	48·70	0	2	4	0	15	6
08-1188 ...	Fine screenings from tunnel and winze.	9·55	53·10	0	1	2	0	14	3
08-1189 ...	Coarse screenings from tunnel and winze.	6·45	65·94	0	1	2	0	9	19

Bingara Division.

Prince of Wales Copper Mine, Bobby Whitlow Creek, Bingara District.—In 1878, Geological Surveyor L. H. G. Young reported that the results of exploration in the outcrop, though encouraging, were not sufficient to warrant an opinion of the extent or value of the lode. The lower levels were then under water. In 1878, 8 tons 6 cwt. and 1 ton 17 cwt. of ore from this lode were treated at the English and Australian Company's Works, Waratah, for yields of 18¾ and 6¾ per cent. of copper respectively.

Later reports state that the mine was idle after No. 1 shaft had been sunk 100 feet and No. 2, 24 feet. Two hundred tons of ore were reported to have been raised. In 1883, the mine was again taken up, but apparently nothing has been done since that date.

Spring Creek, 3½ miles S.E. of Bingara.—Inspector J. James reported (P.B. $\frac{2}{6}\frac{4}{7}\frac{4}{}\frac{2}{}$) a copper-stained formation in diorite and slate, 3 to 4 feet wide, carrying copper stains throughout. Aided to continue sinking to 50 feet.

Tingha Division.

Royal George Mine, 1½ mile E.N.E. of Tingha.—Small veins, 1½ inch thick, striking N.E., in granite, opened to a depth of 19 feet, and for a distance of about half a mile along the strike. Originally opened for tin ore to 8 or 10 feet. Copper ore (bornite) appeared at lower levels, associated with tinstone and mispickel.

Barraba Division.

Spring Creek Copper Mine, M.L. 1, parish Wood's Reef, county Darling, about 4 miles east of Wood's Reef, and 1 mile south of Barraba-Dundarra road.—Discovered by W. Browning. Inspector Carthew reported (P.B. $\frac{1}{0}\frac{4}{0}\frac{4}{}\frac{1}{}$):

PEEL AND URALLA MINING DISTRICT—*continued.*

"Shafts 15 feet and 25 feet; 16 per cent. copper obtained from some of the ore." Aided to 125 feet. At 40 feet very hard rock carrying small copper lode of good grade.

In 1901 Trewenack and party raised 40 tons of ore, realising £250 (*ibid.* 55–1901).

No further record until 1906, when two small parcels of ore reported to have been despatched with satisfactory results. (Ann. Rept. 56–1900).

In 1905 Inspector G. Smith reported ($\frac{1}{5}\frac{8}{4}\frac{2}{2}$) two shallow shafts, about 36 feet, in strong copper and iron formation, in places 8 feet wide. Proved for about 60 feet in length. Formation uncertain and irregular. Aided to sink main shaft to 86 feet. At 49 feet sulphide ore, 15 inches wide, in slate formation, reported. No further record.

Output stated to have been about 118 tons, believed to have averaged 16 to 25 per cent. copper.

Inspected by Writer, September, 1907. Country red quartzite, jasper, and slate. Five shafts on line in a distance of about 63 feet, all shallow. Kindly gossan and carbonate ores of good grade. Ore channel lies very flat in its westerly dip. Apparent strike of outcrop, N. 10° W.; dip 56° S. 80 W.

In southernmost shaft (30 feet) gossan with carbonate of copper—low grade; 120 feet west, shaft started in hard quartzite and slate—to cut lode—down 40 feet at time of inspection; 13 tons 10 cwt. sold at Gulf Creek Mine recently, yielded an assay value of 16·5 per cent. copper.

(NEW ENGLAND MINING DISTRICT.—*Hillgrove Division.**)

Sunnyside Copper and Silver Mine, Hall's Peak, Chandler River, parish Tiara, county Sandon, about 22 miles by road from Hillgrove.—An aided prospecting party discovered loose specimens of argentiferous copper ore at this site, but failed to locate their source. Later, Messrs. Keys Bros., of Hillgrove, after a systematic search, were successful in doing so. In 1896, shortly after discovery, Chief Inspector J. B. Jaquet visited the mine, and sampled about 3 tons of ore which had been collected, the outcrop being at the time covered with loose shingle and débris, owing to the steepness of the slope on which it occurs. The assay results ranged from 39·38 to 47·51 per cent. of copper, and 10 to 13 oz. 13 dwt. 6 grs. of silver per ton. In March, 1898, the Writer visited the scene of operations in connection with an application for prospecting aid, which was subsequently granted. The copper lodes occur as contact deposits at the junction of massive intrusive quartz-felsite with slate and quartzite. Since Mr. Jaquet's inspection, two additional outcrops had been discovered on the river bank about 150 yards north of the first discovery. These average from 6 inches to 2 feet in thickness so far as exposed. Strike N. 80° W.; dip N. 10° E. at 65°. The two latter occur about 15 feet apart.

The ore in the first lode consists of rich yellow sulphides, superficially coated with carbonates. In the second and third lodes the quality is depreciated by the presence of zinc in considerable proportion. At the surface the ore consists of blue and green carbonates, red oxide, and native copper; a few feet below at the river level, yellow sulphides appear, mixed with zinc and lead sulphides. Under aid the shaft was deepened to 50 feet, and a drive into the ridge extended from that level, the prospects being reported good.

* Should appear on page 311.

PEEL AND URALLA MINING DISTRICT—*continued.*

The following assays were made of samples selected by the Writer:—

No. 2 lode—(Carbonate and oxide, chalcopyrites, &c.).

$\frac{1}{10}$	Metallic copper	22·59 per cent.
	„ zinc	4·57 „
	„ lead	7·48 „
	„ silver	5 oz. 1 dwt. 6 grs. per ton.
	„ gold	nil.

No. 3 lode—(Mixed sulphide ore).

$\frac{1}{10}$	Metallic copper	14·32 per cent.
	„ zinc	16·04 „
	„ lead	10·07 „
	„ silver	2 oz. 3 dwt. 13 grs. per ton.
	„ gold	nil.

No. 3 lode was been opened by tunnel for 70 feet under aid; prospects reported good.

The Sunnyside lodes are situated in the southern bank of the Chandler River; which runs in a precipitous valley—over 2,000 feet in depth. If payable ore is proved to occur in workable quantity, a cable tramway, after the style of those in use at Hillgrove, would be necessary for transport in and out of the valley.

PEEL AND URALLA MINING DISTRICT.

Bingara Division.

Sweet Nell Copper Lode, ¾ mile east of Mount Everest Mine, M.L. 6, parish Gouron, county Murchison.—J. Miller's shaft 50 feet, driven 10 feet; 4 tons yielded 6 per cent. In jasperoid quartzite.

Three miles south of Top Bingara, same prospector sank 40 feet, and drove 30 feet on carbonate stains at junction of serpentine.

Tamworth Division.

Trough Gully North Mine, portion P.M.L. 1, parish Piallamore, county Parry; about 17 miles east of Tamworth.—Inspector J. Carthew reported (P.B. $\frac{14}{18}$) a copper lode striking N. 10° E., dip nearly vertical. Aided to sink a winze 50 feet below tunnel level. Also to continue tunnel 50 feet, and 25 feet of crosscutting. Reported fruitless.

From Trough Gully it is recorded that Bregenzer and party forwarded 350 tons of ore for treatment in 1901, which yielded 7½ per cent. of copper. (Ann. Rept., 1901, p. 55.)

In 1906 about 30 tons forwarded for treatment, with reported satisfactory results (*ibid.*, 1906, p. 48). In 1907 W. J. J. Wade raised about 200 tons of ore from his mine at Trough Gully, valued at £300 (*ibid.*, 1907, p. 55).

Inspector J. James reported that the Trough Gully Mine, about 12 miles in an easterly direction from Nemingha Railway Station, Tamworth District, was taken over by a company in 1907. (Ann. Rept., 1907, p. 92.)

Greatest width, 12 feet; greatest depth of proving in August, 1908, 123 feet; greatest length of ore proved, 120 feet. Reverberatory furnace erected. Smelting started end of July, 1908, 161 tons treated.

Bingara Division.

Upper Bingara 3 miles N.E. from Upper Bingara, and ¾ mile from Mount Everest Mine, parish Gouron, county Murchison.—Copper lode in slate; strike, N.W. Aided to sink from 44 to 94 feet (P.B. $\frac{A^{0}\frac{1}{2}^{6}}{0}$). No development.

Inspector J. James reported good patches of ore taken from this lode. Aided to drive 50 feet from 50-feet level (P.B. $\frac{1\,1\,1}{0\,\text{w}}$).

Miller and party took up land previously held by R. Bennett, M.L. parish Dinoga, county Murchison; on same strike of country as Mou Everest lode. Outcrop discovered in 1887—copper sulphide in quartzit Strike N.W. Two lodes about 50 feet apart. Copper ores, 6 to 15 inch wide, occurring in bunches. Maximum depth of proving, 90 feet; crosscu 50 feet to 60 feet; shaft on second lode. Driven on 25 feet at 65-feet lev

Gross output 13 tons, averaging about 19 per cent. at Waratah.

Victory Lode, M.L. 4, parish Dinoga, county Murchison; adjoining Mo lode on N.W.—Originally prospected for gold in a wide bed of ferrugino jasperoid quartzite. R. Bennett struck copper about 1903. Two lodes occu striking N. 40° W., and dipping N. 50° E. at 75° (about). Shaft 86 fe deep on east line. Crosscut to west line at 60-feet level. A small vein good sulphide, about 1 ft. 6 in. wide at greatest, cut in west reef. Ea lode apparently not productive. Nineteen tons of ore despatched, most from West lode, yielded from 11·6 to 21 per cent. of copper at Waratah.

Walcha Division.

Walcha District.—Copper ores are reported at the following localities i this division:—

Walcha Creek, near Nowendoc.

Blue Mountain Creek, 19 miles north-east of Walcha.

Jones's Reef.—From here a sample ($\frac{5}{6}\frac{0}{7}$) yielded—copper 10·97 per cen and silver 13 oz. per ton.

In May, 1873, the English and Australian Smelting Company, Warata received two consignments of ore from this district, probably from one these localities, which yielded as follows:—

9 tons 11 cwt., 21¾ per cent. of copper.
,, 5 ,, 22¼ ,, ,,

Bingara Division.

Warialda.—Traces of copper occur on G. Hamilton's Improvement Leas parish Adams, county Burnett, near Warialda-Bingara road. Limestor and chromic iron also occur in this lease in the serpentine belt. The form is burned for local requirements. A little chrome has been mined for th Conrad Mines at Howell, for use in the new furnace bottom. Evidentl occurs in small bunches only.

Limestone alongside railway line about 1 mile east of Warialda railwa station, is also mined for flux at the same mines, and burned for local pu poses. It occurs in altered Carboniferous or Devonian claystones and re jasperoid quartzites, striking about N. and S., with isolated patches Mesozoic conglomerates and sandstones capping highest points of ridge Width of limestone, about 2 chains at greatest.

The quality of the limestone is shown in the following partial analysis:-

	No. 07-6407—1 mile east of Warialda.	No. 07-6408—Hamilton's
Calcium carbonate ($CaCO_3$)	98·28	98·07
Magnesium carbonate ($MgCO_3$) and undetermined	·08	·43
Ferric oxide and alumina Fe_2O_3 + Al_2O_3	·22	·28
Gangue	1·42	1·22
	100·00	100·00

Peel and Uralla Mining District—*continued.*

Barraba Division.

Wilpina Copper Lode, M.L. 6, parish Wood's Reef, county Darling.—Discovered by V. Salter about 1899. Two lodes; strike of east lode, N. 18° W.; west lode—18 feet distant—N.W. Dips S. 72° and 45° W. Shaft sunk on east lode to 36 feet; lode dipped to west out of shaft; crosscut west from 36 feet level, cut west lode in 18 feet. Followed latter down 35 feet from intersection at time of inspection (September, 1907).

East lode worked for carbonates down to about 30 feet; pinched to about 4 inches at 33 feet of shaft, about 7 inches showing in crosscut west. Opened along its length for about 140 feet by four shafts, ranging in depth from 12 to 36 feet. Driven northerly from latter for 33 feet to next shaft.

The west lode shows about 7 inches wide in roof of winze at south-east end; stronger to north-west. At 23 feet in winze, ore channel 4 ft. 6 in. wide, between well-defined walls; 3 ft. 6 in. of solid sulphides showing for a few feet. The mode of occurrence in lenses is illustrated in the following section, at north end of winze, at 23 feet.



An average sample of the ore raised from this lode yielded:—

No. 07-6447—Copper	7·45	per cent.
Iron	31·22	,,
Sulphur	27·02	,,
Silica	12·52	,,
Gold	a trace	per ton.
Silver	8 dwt. 18 grs.	per ton.

Wood's Reef, 2 miles south of the village of Wood's Reef. Parish Wood's Reef, county Darling.—Inspector J. R. Godfrey (P.B.$\frac{a\,a\,2\,1}{0\,0}$) reported that the lode strikes N. 30° W., and dips south-westerly in quartzite. Its thickness is about 6 feet. The ironstone and gossany cap is more or less stained with copper carbonates, and rich carbonate ore occurs at the south end.

A parcel of 2 tons 13 cwt. of ore from this lode, treated at the English and Australian Smelting Works, Waratah, yielded 14⅛ per cent. of copper.

Aided to sink 50 feet.

Progress.—At 22 feet, some fair copper ore, lode about 7 feet wide. No further sinking at this site. Aided to sink another shaft, from 22 to 72 feet. At 44 feet, lode reported to be opening well, ore good. Tunnel being driven to intersect. Aid allowed for 200 feet of tunnelling from site, about 300 feet south of shafts, to cut lode at 200 feet. No further record.

Inspector J. Carthew reported (P.B. $\frac{4}{0}\frac{4}{1}\frac{4}{1}\frac{4}{1}$) a copper lode, 4 feet wide, 4 miles N. E. of Wood's Reef Post Office. Ore sent to market yielded 22 per cent.

SOUTHERN MINING DISTRICT.

Burrowa Division.

Bachelor's Reef, portion 229, parish Olney, county King. Aided from Prospecting Vote (P.B. $\frac{4}{98}\frac{2}{1}\frac{1}{7}$) on report of Inspector Pelkinghorne, to depth of 100 feet. Lode described as copper-stained porphyry.

Progress.—At 57 feet, lode 2 ft. 6 in. wide, showing fairly well in copper. Assay sample from 90 feet reported to have yielded 3·15 per cent. copper, 1 oz. 14 dwt. silver, and a trace of gold.

Further aided to 170 feet, and cross cutting 20 feet at 118 feet. Lode in crosscut reported 3 feet wide, and showing good ore to south-east, but patchy. Shaft sunk to 187 feet, country hard. Balance of aid not utilised.

Braidwood Division.

Boro Copper Mine, about half a mile south of the Mulloon Copper Mine.—Discovered by George Scott, about 1878, in which year it was sunk 80 feet and driven 50 feet south. The country consists of slates and sandstone, with limestone in close proximity. The lode strikes N. and S., and dips west, and has a thickness of 2 to 6 feet, but is much broken and mixed with country.

Thomas and party entered into possession about October, 1898, and stoped up from the 50-feet level for a length of 50 feet, bunches of good carbonates being obtained.

The following returns were obtained from the Smelting Company of Australia, Dapto:—

7 tons copper carbonates.....	Copper, 18·7 per cent. Gold, 6 dwt. 6 grs. per ton.
4 „ „	Copper, 22·6 per cent. Gold, 1 oz. 1 dwt. 19 grs. per ton. Silver, 2 oz. 16 dwt. 19 grs. per ton. Silica, 31·1 per cent.
2 „	Copper, 12·5 per cent. Silica, 38·3 per cent. Gold, 1 oz. 12 dwt. 9 grs. per ton. Silver, 2 oz. 9 grs. per ton.
9 „	Copper, 15·9 per cent. Gold, 8 dwt. 11 grs. per ton. Silver, 2 oz. 2 dwt. 11 grs. per ton.
6 „	Copper, 19·7 per cent.

Sulphides of copper and iron with a little zinc sulphide appeared at the 80-feet level. A cwt. sample sent to Dapto yielded 9 per cent. of copper and 7 dwt. of gold per ton.

Copper ores have been reported and tested from the following localities in this Division:—

Thames Gully, ($\frac{2}{0}\frac{1}{6}\frac{2}{2}$); yield, 6·5 per cent. copper.

Endrick River, ($\frac{2}{0}\frac{2}{6}\frac{2}{2}$); yield, 13·6 per cent. copper.

Green Creek; in 1885 a sample yielded 42·45 per cent. of copper a 29 oz. of silver per ton.

Mulloon Creek; ore yielding 22·45 per cent. copper.

Currowan Creek, about 12 miles E. of Braidwood, Inspector E. C. Whitt stated that McGuinness's lode occurs in a belt of andesite traversing Carb iferous rocks at the head of the above creek. Large bunches of epidote a small irregular veins and bunches of quartz occur in the andesite. T quartz veins vary from a few inches to a foot in thickness, but are not cc tinuous for more than a few feet in length or depth. Native copper a yellow and grey sulphides are present in the quartz. In 1898 two mine prospecting areas were applied for for copper-mining at Sugar-loaf, on t Braidwood Mountains, but little work was done.

Braidwood District, 17 miles S.W. from Braidwood, on west slope of Maj Mountain, east bank of Little Bombay Creek, parish Palerang, county Murra —Inspector Milne reported (P.B. $\frac{3}{0}\frac{6}{7}\frac{2}{2}$) a gossan lode in granite. Stri N.W., dip S.W.; well defined and apparently 20 feet wide, carrying yell ore in blotches; centre of lode of softer material, carrying galena.

Aided to sink 60 feet in the lode, and to crosscut 20 feet at that level.

Braidwood District, 10 miles from Braidwood on Nelligen Road, and abo 3 miles east of latter.—H. I. Jensen, D.Sc., reports native copper with cupri glance, and gold, in basalt; native copper and carbonate visible in ha specimens; also epidote and limestone inclusions. Prospected superficia some years ago to depths of 10 to 15 feet.

Picton Division.

Bullio.—In 1906, attention was directed to this locality in the Wollondil Valley, owing to a number of applications for authorities to enter priva land for copper mining.

The following assays reveal the character of the occurrence:—

07-3404—Slightly pyritous copper-stained limestone—from authority 1 yielded:—

Copper	under 25 per cent.
Gold	a trace.
Silver	do

07-3405—From authority 17; yielded:—

Copper	4·90 per cent.
Gold	a trace.
Silver	6 dwt. 13 grs. per ton.

07-3406 Pyritous greisen, from authority 42—Copper, under 0·45 per cent.

The locality was subsequently examined by Chief Inspector Jaquet, w advised abandonment.

SOUTHERN MINING DISTRICT—*continued.*

Nowra Division.

Bundundah.—In 1883, the Warden reported that Captain Reynolds had started a copper mine in a gully of Bundundah Creek. Shaft sunk 90 feet; driven north 40 feet, and south 30 feet, at 50-foot level. Eight to 10 tons of ore raised, estimated to yield 25 per cent. copper. Strike of lode, north and south.

In the same year Mr. E. F. Pittman reported on copper at Bundundah Creek—probably the above—and stated that a lode from 18 inches to 2 feet thick, consisting of hematite, galena, and a little metallic copper occurred here in granite. An assay gave a return of 20·8 per cent. lead, 3 per cent. copper, and 60 oz. of silver per ton.

Goulburn Division.

Bungonia District.—The Jacqua Copper Company, on Jacqua Creek, about 12 miles from Bungonia (parish Inverary, county Argyle), drove 60 feet into side of range, and then abandoned the site. From Jacqua Reef ore assaying ($\frac{1}{3}\frac{6}{3}\frac{2}{2}$) 8·18 per cent. copper, and ($\frac{2}{3}\frac{1}{7}\frac{5}{1}$) 12·4 per cent. copper was obtained.

Doctor's Copper Lode, Jacqua Creek (probably identical with Jacqua Copper Mine) was examined by Inspector E. C. Whittell, who regarded it as very unpromising: the copper ores occurring only in small veins, some mere threads, in a formation from 3 feet to 4 feet thick.

Copper ores also occur at Cryer's Arm and Spring Creeks; in the latter near its junction with the Shoalhaven River. The ore here consists of copper pyrites, galena, blende, and mispickel. The deposit was opened under aid from the Prospecting Vote, but did not prove extensive enough to work. Its assay value, determined in 1892, ranged from 13 to 22 per cent. of copper.

Captain's Flat Division.

Canning and Gibson's Mine.—This property, M.L. 86, situated 1 mile from Captain's Flat, was examined in 1890 by Mr. Harrie Wood, late Under Secretary for Mines. At that time three shafts had been sunk, 25, 50, and 60 feet respectively. (*a*) 25-feet shaft sunk through broken veins, no defined lode. (*b*) 60-feet shaft sunk on a well-defined lode, with black shaly ore, about 4 feet wide; the eastern side of the black lode-stuff contained native copper. (*c*) 50-feet shaft sunk in an irregular deposit of grey ore at surface. At 50 feet the lode was reached by crosscut, ore veins up to 1 foot thick occurring in it.

The following parcels of ore from the mine were treated by direction of the Prospecting Board:—

No. 1.—15 cwt. 2 qrs. 14 lb., consisting of carbonates of lead and copper in clayslate, with a little quartz, yielded—

Copper	6·65 per cent.
Lead	6·95 „
Gold	2 dwt. per ton.
Silver	5 oz. 7 dwt. 2 grs. per ton.

No. 2.—2 tons 19 cwt. 3 qrs. 18 lb. carbonate of lead, with a little carbonate of copper, in ferruginous claylate, yielded—

Copper	1·42 per cent.
Lead	9·97 „
Silver	3 oz. 6 dwt. 23 grs. per ton.
Gold	Nil.

No. 3.—17 cwt. 3 qrs. 18 lb. carbonates of copper and lead, with a little chalcopyrite, in claylate, yielded—

Copper	13·40 per cent.
Lead	4·85 „
Silver	4 oz. 3 dwt. 7 grs. per ton.
Gold	Nil.

No. 4.—1 ton 0 cwt. 1 qr. 8 lb. carbonates of copper and lead, with a little chalcopyrite, in claylate, yielded—

Copper	12·45 per cent.
Lead	10·45 „
Silver	4 oz. 16 dwt. 10 grs. per ton.
Gold	Nil.

Goulburn Division.

Chisholm's Freehold, Merrilla, adjoining Gillett's Lucky Hit Mine, parish Gurrunda, county Argyle.—A cross lode, strike N.E., dip N.W.. crossing Lucky Hit lode on S.W. strike; slate country; contorted. Two shafts 45 feet apart, and open cut where Lucky Hit line crosses. Deepest shaft 65 feet, showing lean sulphide ore at bottom; bouldery and silicious. Ores occur as impregnations in slate—irregular owing to contortion. Nothing payable yet disclosed.

Ulladulla Division.

Conjola Creek, parish Little Forest, county St. Vincent.—Copper ores occurs in highly-altered rocks in the bank of Conjola Creek, near its head. The outcrop of original discovery was but a few feet in length, and dipped under the bed of the Creek, which is a permanent stream. The ore consisted of refractory iron and arsenical pyrites, with chalcopyrite. At the outcrop a little carbonate stainings occured, but were merely superficial. Assays of selected samples returned very little copper, and but traces of gold and silver.

Inspector D. Milne (Ann. Rept., 1907, p. 81) stated that the copper lode being prospected at Conjola Creek, follows " the trend of the latter, and is, therefore, difficult to test. Some very good bunches of ore are showing along the creek bed, and it is intended to cut the lode with a vertical shaft at a depth of 100 feet.

SOUTHERN MINING DISTRICT—*continued.*

On a parallel lode, about 1 mile north-west, Shoebridge and party are prospecting a lode from 4 feet to 10 feet wide, consisting of yellow ore impregnated through the country rock.

Goulburn Division.

Cullerin Copper Mine, portion 12, parish Milbang, county Argyle.—Taken up by C. H. Wakefield in 1906, under authority to enter. Originally opened by S. Murray in 1895. Close to railway line about 3 miles from Breadalbane railway station.

Wakefield received aid from the Prospecting Vote to sink 75 feet and drive 50 feet in No. 2 shaft. Has sunk 103 feet on underlay, which is to the east at 1 in 6. The strike being about N. 10° W.

From the 100-feet level a crosscut was driven west towards a massive outcrop of brown and specular iron oxide, having a length of 500 feet by a maximum width of 100 feet. This iron lode continues on a N. 10° W. course to the Lal Lal, or Hannam's Iron Mine, about 18 chains distant. At the latter a considerable amount of flux was at one time quarried for the Cockle Creek Smelting Works.

The Cullerin lode consists of iron oxide and chlorite, with a little copper carbonate. At the 100-feet level the transition to pyrite and chalcopyrite is manifest.

About 50 feet of rotten quartz-felsite intervenes between the lode and the big iron mass on the west. On the footwall of the former about 8 feet of rotten chlorite occurs. The Cullerin lode originated from decomposition of an intrusive hornblendic dyke, from which iron oxide has segregated. It is highly probable that the large ironstone mass on the west has had a similar origin. Chlorite has also been developed.

At the 100-feet level in No. 2 shaft, the ironstone is passing into pyrites, and in its joints stains of copper carbonate are visible. The future of this prospecting venture depends on the cupriferous contents of the unaltered pyrites; if 2½ or 3 per cent. is present in a massive body of pyrites, it will be profitably worked. The thickness exposed at 100 feet, where the hanging wall had not been reached, was about 8 ft. 4 in. of chlorite and iron ore. An average sample chipped from the full width gave the following returns:—

No. 07-3462—	Copper	2·70 per cent.
	Silver	a trace per ton.
	Gold	2 dwt. 4 grs. per ton.

From 3 feet of copper-stained chlorite and iron on the hanging wall side 0·60 per cent. of copper only was obtained. From 1 ft. 10 in. on the footwall, where the transition to sulphides was manifest, better results were obtained:—

No. 07-3463—	Copper	5·70 per cent.
	Sulphur	11·33 „
	Silica	36·90 „
	Gold	a trace per ton.
	Silver	2 dwt. 4 grs. per ton.

The following transverse section reveals the mode of occurrence and loc of assay test samples.



1. Iron ore deposit.
2. Quartz-felsite.
3. Bleached chlorite schist.
4. Iron and chlorite with carbonate of copper stains, Sample No. 07-3463.
5. Chlorite (soft).
6. Chlorite and iron.
7. Chlorite and iron with copper carbonate, Sample No. 07-3461.
8. Chlorite and iron ore.

A sample from the Lal Lal end of the iron lode, where the ironston was quarried, was tested for the presence of copper:—

No. 07-3465—	Copper.....	under 0·1 per cent.
	Gold.....	a trace per ton.
	Silver.....	2 dwt. 4 grs. per ton.

SOUTHERN MINING DISTRICT—*continued.*

Curra Creek Mine, 11 miles from Tarago.—Opened in 1905; a few tons of rich ore raised.

Mr. E. B. Barber states that he has been following a pipe down to a depth of 105 feet on underlay, from which ore was raised realising about £400; the expenditure, however, exceeding the value. The underlay proving too costly, a syndicate was formed for the purpose of sinking a straight shaft in the hope of striking a main lode.

Collector Division.

Currowong Copper Mine (afterwards the *Phœnix*), about 3 miles from Lake George, 22 miles from Goulburn, and 13 from Bangalore Railway Station.—The copper lode worked in this mine was discovered by the presence of characteristic ores in the outcrop, samples from which assayed at the Sydney Mint at the rate of 27·90 per cent. of copper, 10·79 per cent. of lead, and 9 oz. 16 dwt. of silver per ton. The first shaft was sunk through gossan, various assays of which yielded from 11 to 14 dwt. of gold, and 5 oz. of silver per ton.

Mr. W. O. Cooper, on whose property the mine is situated, states that it was originally in the possession of Thos. Clark, who, about 1862, brought specimens of carbonate ore to Mr. Joseph Bull, of Goulburn, who eventually purchased the property, and in turn sold to Manton for £1,000, who formed a company to mine for copper.

Two lodes occur in slates and sandstones, associated with a highly altered igneous rock, now consisting largely of epidote—probably originally a diorite.

In 1865 a company was formed to work the deposit, under the title of the Currowong Copper-mining Company, capital £60,000, in £1 shares, having obtained the mine by purchase from the prospectors.

The first report of the company was issued on the 31st December, 1866. From it it appears that a well-defined lode was discovered soon after the company entered into possession, but it had to be followed down some depth before ore was obtained of sufficiently good quality to justify transit to Sydney.

During the last four months of the period mentioned, about 1,000 tons of 14 per cent. ore were forwarded to Sydney. This amount—less a small parcel sent to England—was delivered to the Newcastle Smelting Works for treatment, from a part of which 44 tons of refined copper were produced. A large sum was expended in machinery for the mine. The carriage of ores and machinery formed a heavy item in the expenditure, as the railway had not then reached Mittagong. A dividend of 10 per cent. was announced after writing off £7,218 for preliminary expenses, and carrying to profit and loss account £2,245.

In the third half-yearly report, ending 31st December, 1867, it is stated that the first smelting operations had not, so far, proved satisfactory, chiefly—according to the manager—on account of the "refractory nature of the ores and the inferior quality of the imported firebricks."

Local firebricks, manufactured on the property, however, answered every test.

The lode at 90 feet was reported to be 26 feet wide. At 162 feet, 15 feet of lode-matter had been exposed without revealing the hanging-wall. The length of proving along the lode was 325 feet.

The following shafts had been sunk:—

Mitchell's shaft, depth	168 feet	.....	135 feet through lodestuff.
Wolfskehl's	„	„	77 „	.....	Average width of lode in these workings reported fully 15 feet.
Bell's	„	„	66 „	.....	
Engine	„	„	76 „	.....	

During the half-year 1,100 tons of ore were raised.

In the fourth half-yearly report six furnaces were stated to be in full work, reducing the ore to regulus, in which form it was found more profitable to despatch it than to attempt refining at the mine. Contracts were entered into with the smelters to convert 5,000 tons of ore into regulus by the end of October ensuing, and to erect additional furnaces. About 2,500 tons of ore were handed over to the smelters during the half year.

In 1869 the company was wound up, and in 1872 reformed as the Phœnix Copper-mining Company.

A progress report of the latter, dated 30th January, 1872, states that the mine had fallen into the hands of the Mortgagees of the Currowong Company, who leased it to some of the former employees working co-operatively. The operations of the latter are reported to have yielded about 450 tons of copper or its equivalent, which gave a net dividend of £18,000. Mr. Holman, reporting for the Phœnix Company, stated that during the previous eleven months a party of six miners (shareholders), in conjunction with Deer & Co., had extracted, in round numbers, about 4,000 tons of ore, from which 298 tons of copper had been smelted, 560 tons of regulus and ore sent to Newcastle, leaving about 700 tons at grass. The ores sent to Newcastle are stated to have averaged 12 per cent.

In the second half-yearly report of the Phœnix Company 82 tons 12 cwt. 1 qr. 14 lb. of fine copper are stated to have been produced, as compared with 135 tons for the previous half-year. In mining all the ore was being taken out, for it was found that during the operations of the working shareholders after suspension of the Currowong Company only the best ore was picked out—an evil only too likely to occur under such conditions in the absence of supervision; temporarily rich returns may thus be made at the expense of systematic mining—in fact, at the ruin of the mine.

No further particulars are available of the operations of the Phœnix Company, but Mr. D. H. Thomas stated that he and others worked on tribute in the "new lode," a short distance west from the first discovered deposit, when the Phœnix Company held possession, this being the last work carried on under its ownership. The ore raised during the tribute averaged about 4½ per cent. copper. In the bottom of the workings the lode was 30 feet wide and of an average value of about 3 per cent. The matrix was stated to be solid pyrites, which is an important feature in view of the possibilities of pyritic smelting.

In 1896 a company under the title of the Currowong Copper and Gold Mining Company (Limited) was formed to open up the mine. The earliest workings were unwatered and cleaned out and prospecting drives put in, but the results were not encouraging, and the enterprise was abandoned when the limited capital was expended. The "new lode" referred to by Mr. Thomas was not reopened.

In 1880, three samples of water from the Currowong Mine were analysed by W. A. Dixon, with special reference to their poisonous action on the fish in Lake George, and were therefore only examined with regard to the metals in solution. The metals were present as sulphates, and are stated below as anhydrous salts:—

	From Currowong Creek.	From Working Shaft.	From Old Shaft.
	Grains per gallon.	Grains per gallon.	Grains per gallon.
97. Sulphate of copper ...	1·12	17·67	6·42
,, zinc	16·98	53·54	7·20
,, iron	·43	1·42	·98

In May, 1907, a new Currowong Copper Company was formed to unwater and test the mine, but on reaching the bottom of the old workings in the western lode, prospects were not considered good enough to encourage continuance, and the enterprise was abandoned in January, 1908.

The most recent shaft in the eastern lode proved to be 132 feet deep, with a crosscut extending 280 feet towards the West lode. At the end of the crosscut a thin vein of quartz and pyrites was opened for a few feet. An average sample yielded on assay:—

No. 08-368—	Copper.....	5·07 per cent.
	Gold.....	a trace per ton.
	Silver.....	10 dwt. 21 grs. per ton.

The earliest and most extensive workings in this lode were not opened.

The main shaft in the West lode proved to be 186 feet deep in country on the west side of lode. The lode worked in open cut at surface appears to have been stoped down to 180 feet, where it had a width of 12 feet, the maximum width of stoping being at the 120-feet level, where it reached 20 feet.

Strange to say, the recent company was unable to find any ore by trenching the floors of the lowest level and stoped areas; a little pyritous schist or slate, however, occurred in places. A thin skin of pyritic ore, left on the wall at 120 feet, showed the following quality on assay:—

No. 08-367—	Copper.....	2·40 per cent.
	Gold.....	a trace per ton.
	Silver.....	13 dwt. 1 gr. per ton.

Below the lowest stopes a winze at the south end was cleaned out to a depth of 68 feet without reaching its bottom. This was reported to be through a

solid pyritic mass worth 3 per cent. of copper, but recent inspectic this report. From some of the material extracted during cleanin sample of the most pyritic was selected for assay. It yielded:—

No. 08-366—Copper	.....	0·67 per cent.
Gold	.....	a trace per ton.
Silver	.....	13 dwt. 1 gr. per ton.

It is not improbable that better results would be obtained furth under the main stopes, for it is inconceivable that the latter should n abrupt termination of the lode.

Provision was made for precipitating the copper in solution wl watering, but, contrary to expectations, the results were infinitesimal 1 ton of cement copper was obtained as scale from old iron rails and left in early workings. That these were not entirely destroyed is of the weakness of the solution. The water from the eastern shaft in a dam apparently contains no appreciable copper salts, for stock with impunity.

Bailing in both shafts was effected simultaneously by same power, b chains of wire cable connecting both pumping beams.

Judging by the size of the slag dump, a large amount of ore must h smelted. A sample of the slag taken from broken-up material at number of test openings, yielded (07-3454)—Copper, 0·1 per cent.; trace; silver, 6 dwt. 13 grs. per ton. An attempt to gauge the tenc sulphides smelted was made by selecting samples from the east a shafts, and from the site of the roast stalls, the results being as fo

07-3451—Sulphide ore from surface heap alongside shaft in open cut, West

Copper	.....	2·95 per cent.
Silica	.....	8·65 ,,
Iron	.....	41·02 ,,
Gold	.....	a trace per ton.
Silver	.....	19 dwt. 14 grs. per ton.

07-3452—Sulphides at grass from East Shafts:—

Copper	.....	0·10 per cent.
Silica	.....	57·90 ,,
Iron	.....	14·88 ,,
Lead	.....	4·78 ,,
Gold	.....	a trace per ton.
Silver	.....	3 oz. 0 dwt. 23 grs. per t

07-3543—Sulphides from old Roast Stalls:—

Copper	.....	1·30 per cent.
Iron	.....	36·40 ,,
Lead	.....	0·25 ,,
Silica	.....	7·13 ,,
Gold	.....	a trace per ton.
Silver	.....	9 dwt. 19 grs. per ton.

The sulphides from the West Lode and roast stalls (samples 3451 a are ideal pyritic fluxes, and probably account for the absence material at these workings.

SOUTHERN MINING DISTRICT—*continued.*

Donnelly and party's Mine, M.L. 4, parish Gurrunda, county Argyle.—Shaft 25 feet, passing through soft, kindly-looking gossan into sulphide zone, where bands of more or less massive iron pyrites occur in slate and dolomitic rock. A little copper sulphide also visible. In the gossan a little carbonate and red oxide, and possibly native copper, occur.

On the east, about 50 feet distant, a large lode of barytes occurs, but ferruginous and of bad colour. Gossan occurs more or less through it, and at 38 feet, in a shaft, has been intersected. No metallic ores, however, were met.

Solid barytes also occurs a little further on, near Nosworthy and party's shaft.

The carbonate and cuprite ore from Donnelly's shaft assayed 12 to 15 per cent. of copper, the sulphides, 6·5 per cent. and 11 oz. of silver per ton. Sufficient work had not been done to expose the lode either horizontally or vertically.

The dolomite gave the following results on partial analysis:—

	07-3499	07-5302
Carbonate of lime ($CaCO_3$)	46·85	46·17
Carbonate of magnesia ($MgCO_3$)	35·41	36·29
Ferric oxide and alumina ($Fe_2O_3 + Al_2O_3$)	1·70	2·38
Gangue	16·36	15·24
	100·32	100·08

Nowra Division.

Ettrema Lodes, Ettrema Creek, M.Ls. 7 to 11, parish St. George, county St. Vincent. Discovered by J. McKane and Sons and J. R. Chaffey in September, 1907. Eight miles north-westerly from Sassafras, and 28 west of Jervis Bay. The lodes outcrop in a precipitous gorge cut by Ettrema Creek, about 1,000 feet below the Upper Marine sandstone plateau, and about 1,400 feet above sea level.

The plateau sandstones and conglomerates overlie Devonian—and probably Silurian—highly-folded quartzites, slates, and silicious limestones, in which the lodes occur, with one exception, as bedded deposits, impregnations, or replacements. The pitch of the strata brings the upper metalliferous beds to the creek level as it is followed down.

The lodes consist of a complex mixture of zinc-blende (principally) mispickel, chalcopyrite, and galena.

(For further particulars see page 413.)

Frogmore Division.

Federal Copper Mine, on J. B. Cassidy's land, about 7 miles north of Frogmore.—Strike N. 10° W. vertical. Shaft sunk 80 feet, and crosscut east 40 feet at 78-feet level, in a large ferruginous outcrop. Sulphides struck

at 30 feet, where a little decomposition had taken place. The sulphides taken out below this took fire on exposure at surface, and burnt to a loose powdery mass, a sample of which assayed:—

No. 07-6706—Copper	.....	0·30 per cent.
Gold	.....	a trace per ton.
Silver	.....	„ „

Solid iron pyrites occur in shaft and east crosscut for about 30 feet.

On east side of pyritic mass, native copper and red oxide coat jointings of country (averaging about 2½ per cent.) as the result of precipitation along a soakage channel; not likely to continue to any depth.

To the west of the shaft pyrites still showing. Probably a little enriched ore on back of lode might be obtained at the 30-feet level.

Judging by the cindered ore caused by natural decomposition, the pyritic mass disclosed is of too low grade for smelting purposes.

Captain's Flat Division.

Federal Mine, Captain's Flat, about half a mile east of the Lake George Mine, and 100 yards east of cutting on Braidwood road, parish Bealibi, county Murray.—Inspector J. R. Godfrey reported (P.B. $\frac{22}{11}$) hard quartzose and schistose country carrying iron pyrites and a little copper pyrites; striking north and south, and dipping west at a slight angle.

Aided to continue 36-feet shaft to 86 feet. A seam of sulphides passed through at about 43 feet, underlying west. At 50 feet a 1-foot vein cut, assaying 5 per cent. copper. Also dipping west.

Aided to crosscut west at 80 feet, apparently without profitable results. No further record.

Frogmore Division.

Frogmore Copper Mine (formerly *Frogmoor*), about 17 miles north of Burrowa, in parish Bala, county King; discovered in 1870, and taken up by J. Sheedy as a mineral lease.

In 1873 the English and Australian Smelting Company, Waratah, treated 4 tons 19 cwt. of ore from Frogmore for a yield of 9½ per cent. of copper.

In the "New South Wales Mining Statistics," 1875, p. 99, this mine first receives official notice. Seventy tons of ore are reported to have been raised at this date from a lode averaging 3 ft. 6 in. in thickness at 75 feet from surface, and striking N.W. (dip, 1 in 6 westerly). The ore was estimated at 12 per cent. copper.

In 1880 work was suspended after about 50 tons of copper were produced. In 1881 the mine was floated into the Frogmoor Copper-mining Company, having previously been worked by Messrs. Deer Bros. At the end of the half-year ending 31st December, about 50 tons of copper had been produced.

In 1882 1,050 tons of ore raised yielded 118 tons of copper, 12 of which were produced by a wet process, which was not, however, in complete working order. The company was about erecting concentrating machinery to treat a large amount of lean ore at surface. Main (No. 1) shaft, 373 feet deep; No. 4 shaft, 360 feet.

Frogmore Copper Mine.

FROGMORE COPPER MINE.—Mining Statistical Table.

Half-yearly Report ending—	Tons of Ore Raised.	Tons of Ore Smelted.	Tons of Copper Produced.	Average Yield per cent.	Deepest Shaft.	Deepest Level.	Remarks.
			tons cwt. qrs. lb.		feet.	feet.	
1st report—1 Jan., 1882	500 (?)	500 (?)	50 9 1 0	9·6	317	317	One furnace at work; ore raised from No. 1 and No. 4 shafts; underhand stope in No. 4 shaft, 50 feet long; quantity of "seconds" and "smalls" reserved for further treatment; sulphuric acid chamber being erected in connection with leaching process.
2nd ,, 31 July, 1882	550	520	55 2 3 0	10·6	354	354	Lode at bottom of No. 1 (deepest shaft) yielding about 6 tons of 10 per cent. ore per fathom, in addition to dredgy ore reserved for future treatment. No. 4 shaft yielding about 7 tons of 10 per cent. ore per fathom; about 3 tons of precipitate obtained from recently-started leaching process.
3rd ,, 30 Jan., 1883	500	500	63 14 1 9	12·74	373	373	Sinking discontinued; ore chute in No. 4, 60 feet long; principal part of ore smelted from this shaft; lode about 4 feet wide; 10 tons of copper obtained from precipitates in wet process.
4th ,, 31 July, 1883	500	450	45 5 0 0	10·05	373	373	Operations retarded by drought; Handcock jig being erected; dam completed; two furnaces at work; north end of No. 4 shaft improving; large quantity of "seconds" and "smalls" raised in addition to ore smelted; little done with wet process.
5th ,, 29 Jan., 1884	800 (?)	800	82 5 0 0	10·31	373	373	New lode discovered at 288-feet level in No. 4 shaft, 17 feet wide at its junction with the main lode; average width of new lode 6 feet, yielding 8 tons of 10 per cent. ore per fathom; two furnaces at work; jigging plant started.
6th ,, 22 July, 1884	535 (?)	535	53 9 2 0	10·00	373	373	New lode not up to expectation, small, and producing about 4 tons of 10 per cent. ore per fathom; concentrating plant idle for four months owing to want of water.
7th ,, 17 Jan., 1885	... (?)	460	48 0 0 0	10·43	373	373	Copper market low; operations unsatisfactory; concentration intermittent; one furnace only at work; treatment of carbonates by wet process abandoned; ore raised by tribute from branch vein in west wall of No. 4 shaft yielded 15 per cent. dressed.
	...	3,765	388 5 3 9 = 10·53% extraction.		.....		

It will be noted that the yield of the ore smelted during the company's operations averages 10·31 per cent. of copper, and, further, that as soon as the copper market became depressed operations ceased, and have practically never been renewed. The spasmodic attempt during the copper boom of 1888–9 was as brief as the boom itself. This mine certainly offers sufficient inducement for renewed effort.

A few hundred feet west of the main lode Mr. S. L. Bensusan opened another (*Pride of Frogmore*) in Mr. J. Sheedy's property, and erected a reverberatory furnace. A good deal of work was done, but the results were not satisfactory. The two properties could, perhaps, be worked together in any new venture. Samples of the sulphides from both mines were selected from heaps at surface for assay, with the following results:—

No. 99–830—Silicious copper pyrites from Frogmore Mine:—

Copper	10·35 per cent.
Iron	13·54 ,,
Silica	54·60 ,,
Silver	1 oz. 14 dwt. 20 grs. per ton.
Gold	nil.

No. 99–831—Quartz with iron and copper pyrites from Bensusan's Lode:—

Copper	3·69 per cent.
Iron	16·32 ,,
Silica	58·00 ,,
Silver	13 dwt. 1 gr. per ton.
Gold	nil.

In 1898 McInnes and Cook were working a copper-vein on the north boundary of M.C.P. 51, parish Alton, county King, belonging to the Frogmore Proprietary. A shaft had been sunk 50 feet on the vein, which traverses crushed porphyry and schist. Three tons of ore extracted down to water-level yielded 14½ per cent. of copper, and silver 6 oz., and gold 3½ dwt. per ton.

On the south boundary of the Frogmore property the same party were working a 5-acre lease under private agreement on portion 74, parish Bala, county King. Country crushed porphyry and schist, with copper carbonates in the laminæ for a distance of 17 feet in a crosscut; in fact, copper carbonate colourings are discernible through a wide belt of these rocks at Frogmore. From a more concentrated deposit in a new shaft, about 6 tons of good ore were treated at the Dapto Smelting Works for a yield of 17·6 per cent. of copper, and 5 dwt. 14 grs. of gold per ton.

On the 10th June, 1907, Mr. Francis Drake started to unwater the mine, under a purchase option. The latest, or New Shaft, sunk in 1890, being selected for the purpose, being about 100 feet lower down the hill than the Top shaft. The water stood within 30 feet of the surface; lowering it had no influence on the water in the higher level shafts south of New Shaft, the only one affected being May's, about 40 feet north ; thus proving the "May" ore-lens unconnected with the southern, either naturally, by the same lode channel, or artificially by mining.

The depth of the New Shaft proved to be 360 feet, and May's 290 feet. Above the 290-feet level stoping has been carried up between the shafts to near the surface; the stopes extending for a few feet north of May's shaft, and south of the New Shaft, for a distance varying from 45 feet, at 355 feet, to a few feet near the surface.

In the southern face of this section from 1 ft. 6 in. to 2 feet of sulphide ore is exposed from the bottom up to the 302-feet level, having an average assay value of 10·34 per cent. of copper. A sample taken from this end (not average) for the purpose of ascertaining approximate composition, yielded:—

No. 07-6716—Copper	.....	12·75 per cent.
Iron	.....	17·36 „
Sulphur	.....	15·53 „
Silica	.....	44·15 „
Gold	.....	a trace per ton.
Silver	.....	4 oz. 12 dwt. 15 grs. per ton.

The northern face exposed an average of about 2 feet of ore, assaying, according to Mr. J. F. Carey, 5½ per cent. copper.

The average width of the "May" lens must have been considerable, judging by the width of extraction; the widest portion, however, resulted from junction of a western lens with the "May."

Judging by the surface workings, the Frogmore lode, or lodes, has been opened by six shafts for a length of about 660 feet between the Top and May shafts. The unopened shafts are reported to range from 65 to 240 feet in depth.

The general strike of the workings is N. 20° W. The dip of the ore in the New Shaft is S. 70° W. at 83° in the upper levels, and 69° at 333 feet.

The New Shaft was an illadvised expenditure, being practically in worked ground, and proving nothing more than the existing May shaft, 40 feet away.

The only drive from it was to the south, which, instead of following the strike of the channel after losing the lens, turned south-easterly for a considerable distance, and then south-westerly, following throughout a most erratic course for 197 feet. The lens pinched about 18 feet south of the shaft.

From the results of the unwatering recorded, it is evident that a further test must follow in connection with the southern shafts before any criterion of the value of the lower ore reserves can be obtained. The surface dumps bear testimony to considerable ore extraction from the upper levels; and there is, therefore, reason to infer supplies of probably comparatively low grade, yet workable, ore beneath the early stopes.

Contrary to expectation—which induced provision for recovery—the water baled from the New Shaft, below a few feet, was practically non-cupriferous. This poverty was doubtless due to the complete extraction of the lode within the sphere of oxidation; thus preventing decomposition into soluble copper salts in the old stopes above the permanent water-level. For it is in the damp airways of the stopes and shafts, that the change takes place wherever poor sulphides remain exposed on the walls, or in left pillars, before the surface waters fill the workings. Below the permanent water-level the chemical change is comparatively insignificant.

The ore at grass has been estimated by Mr. Carey, acting for Mr. Drake, at 125 tons—of an average value determined by sampling, of 3·8 per cent.

The slag dump has been similarly estimated and tested—at 12,216 tons of an average assay value of 1·13 per cent. copper.

Frogmore District.—Inspector Hooke reported (P.B. $\frac{40}{1}$) a copper-bearing formation in schist rock, about 3 miles north of Kenyu Station, alongside, and north of Right Hand Creek.

SOUTHERN MINING DISTRICT—*continued.*

Lode recently opened, of large dimensions, showing copper stains freely.

Aided to sink from 12 feet to 62 feet.

Progress.—At 36 feet prospects not good, country hard. No further record.

Bell View Mine, portion 112, parish Yundoo, county Monteagle.—Discovered by T. Carmody in 1907. Shaft 30 feet, on thin erratic veins of gossan, containing copper carbonates and rich kernels of grey sulphide. No defined channel nor persistent veins. Bottom of shaft in slate. A few tons of ore at grass averaging 7 or 8 per cent.

Conjuror Mine.—Stevenson's land, Goba Creek. Discovered about 1877. Taken up by J. Williams and party in 1907. Strike N. 33° W.; dip N. 57° E. at 53°. Shaft 55 feet; channel 5 inches to 18 inches. No true vein. Small prills of grey ore near surface. Bottom of shaft in country. No lodestuff.

Mount Kenyu, on Kenyu Estate. Williams and party sank 80 feet in gossan outcrop; a little carbonate and grey ore reported at 80 feet.

Right Hand Creek, 13 miles north-westerly from Frogmore, portions 21 and 41, parish Yundoo, county Monteagle.—Vein 18–24 inches wide (not solid), with yellow sulphide. Small parcel of 11 per cent. ore sent to Waratah.

Stewart and party, Flannery's land, portion 14, parish Narralla, county Monteagle, 2 miles from Godfrey's post office.—Good-looking gossan outcrop on west of shaft; but a crosscut under it, at the 73-feet level, proved only a leanly pyritic rock with calcite, iron pyrites, and a little copper pyrites and blende.

Aid was granted (P.B. $\frac{4}{5}\frac{1}{5}\frac{2}{4}$) to sink to 130 feet, and for cross-cutting 50 feet at the 85-feet level.

At 95 feet cut gossan with carbonate and black oxide, without defined walls.

An examination of the workings in 1907 revealed massive limestone in the west crosscut at 73-feet level, which does not appear at surface. An analysis revealed its composition as:—

No. 07-6710—Carbonate of calcium	73·67
*Carbonate of magnesium	3·25
†Ferric oxide and alumina	4·92
Gangue (silicate of alumina and iron, and trace of lime	18·16
	100·00

* Including water and undetermined.
† Including any phosphoric and titanic oxides present.

A little pyrites was showing in face of crosscut at 70 feet from shaft.

An eastern crosscut at 83 feet, extending for 30 feet, exposed very kindly-looking gossan with traces of carbonate of copper, but undercutting at 120 feet revealed no trace of it. The disappointing results obtained at the latter level caused the aid to cease.

Right Hand Creek, in portion 106, parish Narralla, county Monteagle.—J. P. Adams received aid to sink on vein in slate and breccia; striking N. 15° E. A little ore at grass, of poor, silicious character. At the bottom of shaft traces of copper only are visible alongside a wall striking N. 40° W., and underlying N.E.

Petty and Son were prospecting on Goba Creek between the Conjuror and Carmody's Mines, in a gossany ontcrop in which no true vein had been disclosed. Odd prills of grey ore were, however, reported.

O'Malley and Peel's shafts are distant about 6½ chains north of Adams' shaft. This was the site of the original discovery at Right Hand Creek (abandoned at time of inspection). Two shafts have been sunk about 90 feet apart. It is reported that 6 tons of dressed ore from them yielded 17 per cent. of copper.

South Frogmore, 750 feet south of Frogmore engine-shaft. Shaft 95 feet, driven south for 78 feet, and crosscut west 22 feet. Seven tons of ore extracted from south drive are reported to have yielded 13·2 per cent., and 6 tons from 66 feet to 95 feet in shaft, 12·5 per cent. Another shaft, 320 feet east of the 95-feet, sunk to 90 feet, and driven north 27 feet, yielded 5 tons of carbonate ore, returning 9 per cent. of copper.

Yundoo Lode, portions 43 and 44, parish Yundoo, county Monteagle.—Discovered by J. Carmody, July, 1906. Striking N. 15° W., in slate. Thin gossany veins with slight traces of copper carbonates, not persistent in depth; opened for 20 feet. Traceable by gossan outcrop in places for a short distance south. Not promising for permanence or size.

Watson and party, No. 437 (Yass), parish Congera, county Monteagle.—Prospecting alongside old shafts sunk many years ago for copper. Carbonate stains in crushed porphyry.

Yass Division.

Good Hope Copper Mine, situated on the north side of the Yass River, about 17 miles from Yass, in portion 1, parish Woolgarlo, county Harden.—This was probably one of the earliest-opened copper mines in the Colony. In a despatch from Governor Sir Charles Fitzroy to the Right Honorable Earl Grey, dated 1st March, 1849, mention is made of copper mines in operation in the neighbourhood of Yass and at Molong (Copper Hill).

The ore consists of copper carbonates, sparingly distributed through a quartzitic matrix.

Mr. Argyle McCallum (whose father originally owned the land), under date 7th August, 1898, supplied the following particulars:—Several rich patches of ore have been found, but the main body of the lode is of low grade, the ore being too disseminated through the large mass of matrix. About forty-seven years ago the Scottish-Australian Mining Company expended a considerable sum prospecting the Good Hope lode, and it was reported that at a depth of 180 feet a lode of sulphide ore was cut, about three-quarters of a mile from the main outcrop, which lies about 55 chains from the Yass River, at an elevation of about 300 feet above it.

About 1896, 100 tons of silicious ore, dressed from the outcrop, were forwarded by Thomas Rowe and party, to W. H. Trewenack, for fluxing low grade copper matte of high silver value. It averaged 11 to 12 per cent. copper, and consisted of cuprite and native copper.

Examined by Writer in 1898 and 1908.

The main lode presents a strong outcrop for about 20 chains; beyond this it thins out, and apparently disappears. Numerous shafts have been sunk along its course, as well as open cuts. The former are all fallen in; hence inspection is entirely confined to the outcrop, which consists of a rugged mass of ferruginous quartzite and quartz, with traces of copper carbonates, and, in places, cuprite and native copper. Some of the shafts have cut into a very carbonaceous slate.

On the bank of the Yass River, near the north-east corner of portion 2, a bluff of fine-grained sandstone (quartzitic) and slates with thin quartz leaders, forms the bank of the river channel. Copper carbonates stain joint

and bedding planes; and a little copper pyrites is discernible, sparingly distributed. The principal dip at the shaft level is S. 50 W. at 27°; but folding is conspicuous.

About 1 chain from the river a shallow shaft has been sunk to the copper level—a few bags of dressed ore at surface being of very low grade.

About 13½ chains N. 60° W. from the S.E. corner of portion 1 is the site of the sulphide lode referred to by Mr. McCallum.

This lode was intersected in an eastern crosscut from a vertical shaft, at a depth of 169 feet. The workings being recently unwatered, the strike of the lode was found to be N. 20 W., and the dip of the hanging wall about S. 70° W. at 65°. Thickness, 7 feet.

The average value of the ore exposed is: copper, 3·43 per cent.; iron, 7·03 per cent.; silica, 73·75 per cent.; sulphur, 4·40 per cent.; silver, 1 oz. 5 dwts. 14 grs. per ton; and a trace of gold. It is uncertain whether it is a continuation of the Good Hope lode.

At Goodna Creek J. B. Jaquet reported (Ann. Rept. 1896, p. 138) that gold occurs in thin veins ⅛ to ½ inch thick, composed of quartz, limonite, and copper carbonates. For 1 or 2 inches on either side of the veins the country rock is impregnated with gold.

Goulburn Division.

Goulburn.—(*See* Currowong, Merrilla, Cullerin).

Copper ore is also reported from Baw Baw, and at Lockyersleigh, where a copper lode of low grade was opened by shaft prior to 1863, but proved then unworkable.

Captain's Flat Division.

Grogan and Singleton's Copper Mine.—This property consists of a 40-acre lease adjoining the Old Commodore Vanderbilt Mine. Mr. H. Wood, late Under Secretary for Mines, who inspected the mine in 1890 in connection with the Prospecting Vote, reported the lode to have a thickness of from 4 inches to 18 inches, a meridional strike, and well-defined walls. Three tons of ore raised during sinking operations to 75 feet, and driving 20 feet from the 45-feet level, were tested at the Clyde Smelting and Chlorination Works, with the following results:—

Smelters assay—Metallic copper	29·59 per cent.
Chemical „ „	31·19 „
Silica	22·17 „
Silver	10 dwt. 21 grs. per ton.
Gold	a trace (under 2 dwt.)

Heffron's Creek, parish Gurrunda, county Argyle.—Messrs. Heffron, Nosworthy, and Le Champ, tunnelled into very graphitic slates outcropping in the bank of the creek. Small blebs and veins of quartz occur rarely, and still more rarely specks of copper sulphide and pyrites, which are confined to the quartz. Native copper occurs in thin plates, and specimens have been washed from the crushed outcrop. This occurrence is unlikely to improve.

A shaft was started higher up the bank in a ferruginous slate breccia simulating gossan. These breccias represent the cemented detritus of an earlier channel level lying uncomformably on the edges of the slates, here, and at other points of the creek course through a rugged gorge of some length.

Goulburn Division.

Jasper's Gully, 60 chains north of Manton's Reef, and 22 miles from Bungonia, parish Narramungar, county Argyle.—Inspector H. Hooke reported

(P.B. $\frac{2}{0}\frac{9}{7}$[1]) a formation about 12 feet wide carrying copper, lead, g silver, &c., in a remote gorge of the Shoalhaven River. Country sla opened in various places by J. Mackie and D. Hockey. Other ve exposed in proximity.

Jerralong.[1]

(LACHLAN MINING DISTRICT.—*Yass Division.**)

Kangiara Mine, G.Ls. 1,158 and 1,159, parish Taunton, county King, Burrowa-Yass Road, and about half a mile from Burrowa River, 12 m from Binalong railway station.—Discovered by J. Alder in 1899. Ope in July, 1902. Strike N. 10° W., dip (slight) easterly.

Deepest proving—to September 30th, 1907—83 feet; Greatest leng 235 feet. Ore strong at both ends. Two shafts to 60-feet level; two win from latter to 83 feet.

In the oxidised zone two lodes occur about 10 feet apart, with flat lead between. The eastern lode had not then been proved from the 83-feet le in the main lode.

The width of ore exposed in the winzes in the main lode varied from 4 t feet, averaging about 4 feet; mostly solid sulphides. Copper sulphide ma on footwall in higher levels, on hanging wall at lower.

The ore consists chiefly of galena, with chalcopyrite and zincblende, latter reported not to exceed 3 per cent.

The total output to 20th September, 1907, was 1,500 tons, 1,400 of wh were despatched for sale at Cockle Creek.

One thousand two hundred tons sold to 1st June, 1907, averaged about:

Lead	30 per cent.
Silver	30 oz. per ton.
Gold	5 dwt. ,,

The composition and value of the ore in the lower levels is illustrated the following table of the latest returns:—

Quantity.	Lead, per cent.	Copper, per cent.	Gold, per ton.			Silver, per ton.			Remarks.
Tons.			oz.	dwt.	grs.	oz.	dwt.	grs.	
37	31	11	0	4	0	25	13	0	
30	23	8	0	6	0	28	0	0	
11	5	18	0	10	12	33	9	0	Picked for copper valu
10	3	19	1	15	0	48	0	0	,, ,,
38	20	16	0	4	0	21	0	0	
20	28	14·3	0	8	0	26	0	0	

In 1907 the mine was held for some time by Messrs. Horton and Freen under a purchase option, during which the two winzes were deepened ab 20 feet each, making a depth proved about 100 feet; a little driving done from this level. The lode persisted to the depth mentioned; but a considering a second option, the purchase was not effected.

SOUTHERN MINING DISTRICT.

Captain's Flat Division.

Lake George Copper Mines.—Situated at Captain's Flat, 25 miles so of Bungendore Railway Station. Elevation about 2,700 feet above sea-le District well-wooded, with good rainfall.

[1] *Goulburn Division.*—Jerralong Creek, near junction of Shoalhaven River, copper vein about 1 foot Unopened. Taken up in 40-acre lease by J. Mackie, parish Jerralong, county Argyle, January, 1907.

* Should appear on page 276.

Captain's Flat, with Lake George Copper Mines and Smelting Works.

Mr. J. E. Wright, about 1874, when engaged on Foxlow station, near Captain's Flat, first noticed copper ores in the vicinity, but mining did not start until 1882, when the discovery of a promising copper lode was announced by the Under Secretary for Mines.

In 1884, Warden Woore reported that 2,380 tons of gossan ore had been crushed for 360 oz. of gold (about 3 dwt. per ton). Another parcel of 800 tons yielded 6 dwt. per ton. He further stated that "the character of the reef is an auriferous gossan, overlying a large copper lode of low percentage."

In 1885, blast-furnace treatment superseded the battery, and the two furnaces erected were run intermittently until 1889, when three additional, and a 20-head stamper battery and Huntingdon Mill, were added to the plant.

In 1890, heap roasting of the sulphides was in operation at the Koh-i-noor Mine, whilst at the Commodore a revolving calciner was erected for the fines.

In 1894, the two mining companies—Koh-i-noor and Commodore Vanderbilt—were amalgamated under the name of the Lake George United Mining and Smelting Company.

The Lake George Mines, Limited, came into existence in August, 1896, when English capital was introduced.

In 1897, J. B. Jaquet and J. A. Watt, Geological Surveyors, made an examination of the deposits, and from their joint report the following extracts are taken:—

"The dominant formations at Captain's Flat are Silurian slates, breccias, &c., which have a meridional strike, and for the most part nearly vertical dip. Upon the western side of the township flat there is a slight western dip, and at the Vanderbilt Mine, which is situated upon the eastern side of the flat, we found an eastern dip; so an anticline would seem to have stretched across the flat at one time, and the Vanderbilt lode upon one hand and the Koh-i-noor and Commodore lode on the other would seem to be on the same geological horizon.

"The lodes, wherever observed by us, are closely comformable with the bedding planes of the country rock. . . . Portions of the lode exhibit a perfect bedded structure, and without doubt represent country rock, which has been slowly replaced by ore *in situ*. In many places no distinct walls occur, and compact ore may be seen, passing by insensible gradations into country rock slightly impregnated with iron pyrites.

"The Commodore shaft—now called Keating's section—is distant 3,300 feet from the Koh-i-noor shaft—now Elliott's section—and between the two there is 1,500 feet of unproved ground. The lode in Elliott's section to the 400-feet level varies from 22 to 30 feet in thickness. In Keating's section it reached a thickness of 40 feet.

"The unaltered sulphide ore consists essentially of a compact, fine-grained mixture of iron pyrites, galena, and zinc blende, with a small quantity of copper pyrites, and a quartzose aluminous gangue. Upon the footwall side of the pyrites lode in Elliott's section, a considerable quantity of barytes is in places associated with the ore. Between the unaltered primary ore and the gossan which caps the lode, there is present a zone of partially oxidised and enriched sulphides, which differ noticeably from these below in containing black oxide of copper (tenorite), and in being on the whole slightly more friable. The upper portions of the gossan have been almost entirely robbed of their copper, lead, and zinc contents by percolating waters, and the enrichment in copper of the unaltered sulphides is probably due to a portion of the metal having been redeposited as black oxide below."

The chemical composition of an average sample of the ore from the various exposed faces in the great pyritic lode at the 400-feet level in Elliott's section, taken by Messrs. Jaquet and Watt, is revealed in the following analysis by Mr. H. P. White, Assistant Analyst. (Ann. Rept., 1897, p. 21):—

Moisture at 100° C.	0·10
Combined water	0·65
Insol. in acids (gangue)	23·70*
Metallic iron	17·75
„ zinc	14·50
„ lead	8·04
„ copper	1·11
Sulphate of lead ($PbSO_4$)	0·32
Alumina (Al_2O_3)	1·38
Lime (CaO)	0·40
Magnesia (MgO)	0·65
Sulphur trioxide (SO_3)	0·25
Carbonic acid (CO_2)	2·08
Phosphoric acid (P_2O_5)	0·57
Sulphur (S)	27·97
Oxygen and undetermined	0·53
	100·00

* NOTE.—91·35 per cent. of the gangue consists of silica, the remainder containing alumina, magnesia, and alkalies. The silver contents averaged 2 oz. 8 dwt. 14 grs., and the gold 1 dwt. 12 grs. per ton.

The new plant consisted of three blast furnaces of a daily capacity of about 180 tons, and a smaller furnace previously used for concentrating the matte from the above, but since converted into a reducing furnace. Partial pyritic smelting had been adopted after some initial difficulties. In the furnace charge, about 5 per cent. each of flux and fuel only was required.

The following return of the output of Captain's Flat Mines is compiled from the Annual Reports of the Department of Mines and Agriculture:—

Mine.	Year.	Tons of ore.	Silver.		Gold.		Lead.		Copper.	
			oz.	per ton.	oz.	per ton.	tons.	per cent.	tons.	per cent.
				oz.		dwt.				
Koh-i-noor	1887	2,106	45,705	21·3	377	3·5	125	5·9	21	1
„	1888	Value of product, £6,880—No particulars given.								
„	1889	4,732	54,511	11·5	660	2·8	215	4·5	70	1·5
Commodore-Vanderbilt	1890	3,986	33,857	9·0	602	3·0	80	2·0	...*	...
Koh-i-noor	1890	4,860	.....	...	823	3·0	(Smelting returns not given)			
Commodore-Vanderbilt	1891	5,657	(Smelting returns not given).							
Lake George S. & G. M. Co. (Late Commodore-Vanderbilt.	1892	7,322	8,824	1·2	156	0·4	...	...	671	9
New Koh-i-noor	1892	11,900	83,050	7·0	783	1·3	...	...	556	5
Lake George S. & G. M. Co.	1893	7,710	60,000	7·8	...	...	...	...	238	3
New Kohinoor	1893	4,264	58,002	13·6	784	3·7	...	...	137	3·2
„	1894	2,247	17,797	8·0	320	2·8	...	...	94	4·0
„ (gossan)	1894	3,946	.....	...	391	2·0	...	...	...	...†
Lake George United M. & S. Co.	1894	2,871	14,667	5·0	106	0·7	...	...	55	2
D ‹ do	1895	18,563	137,951	7·0	2,164	2·3	64	0·3	350	1·9
Do do	1896	12,783	69,600	5·4	1,251	1·9	36	0·2	205	1·6

* Gossan. † Battery.

Lake George Mines (Limited).

Date.	Ore smelted.	Matte produced.	Gold in Matte.	Silver in Matte.	Copper in Matte.	Gold per ton of Ore.	Silver per ton of Ore.	Copper, per cent.	Cost of Production per ton of ore.	Remarks.
	tons.	tons.	oz.	oz.	tons.	oz.	oz.	per cent.	shillings.	
From commencement of operations to stoppage in September, 1898.	79,010·4	2,673·62	5,158·12	190,505·08	885·69	0·065	2·411	1·12	...	The gold and silver contents are included in 16·4 tons of bullion and 6·59 tons of dross, in addition to the matte.
From recommencement of work on 26th November, to 31st December, 1898.	6,351·5	295·56	575·67	15,954·58	92·60	0·099	2·511	1·457	...	
January, 1899	5,312·56	274·20	452·68	13,761·86	76·86	0·085	2·590	1·446	14·78	Total cost of mining, handling, smelting (inclusive of all fluxes and fuels), and general mine expenses.
February, 1899	5,420·18	291·18	369·63	14,712·55	86·93	0·068	2·714	1·603	14·65	,, ,, ,,
March, 1899.....	5,840·44	326·96	466·95	15,844·88	97·74	0·0799	2·713	1·674	15·55	,, ,, ,, (of which 1s. 2d. is development.)
April, 1899	5,494·05	278·48	370·48	14,453·04	82·66	0·0674	2·63	1·545	15·58	,, ,, ,, (of which 1s. 6d. is development.)
May, 1899	*5,339·67	232·81	330·0	11,606·	61·71	0·0618	2·17	1·55	16·	Including total cost of mining; handling, smelting, development, and general expenses at the mine. Development equalled 2s. per ton.

* In addition, 7·94 tons of precipitates, containing 83·87 per cent. of copper, were produced, valued at £522 16s., at present price of copper. Estimated cost of transport and realisation for the month was 6s. 8d. per ton. The sterling value of the ore, at present price of metals, is £1 8s. 1d. per ton.

In March, 1899, the Writer inspected the smelting plant and the working levels of the mine for the purpose of recording developments.

The success of operations had been publicly attributed to free use of accumulated stocks of ore, fuel, and fluxes charged to former accounts, also to robbing the richer portions of the lode.

A visit to Captain's Flat was sufficient to dispel the above illusions. Fuel and fluxes were constantly arriving at the smelters, and ore from all levels being continuously delivered from the mine.

The rate of winning (by contract) was too rapid and economical, and the output too great (nearly 2,000 tons per week) to allow of "picking." Stoping was being carried on at the 150, 200, 300, 400, 500, and 600 feet levels in the Koh-i-noor section. Certainly a higher-grade copper ore occurred at 150 feet, and a richer, but refractory, zinciferous silver ore on the east wall of the lode at all levels. The output from these portions of the lode were naturally delivered separately at the ore bins, and judicious blending took place in charging.

LAKE GEORGE MINES.

TRANSVERSE SECTION.

SCALE 0 50 100 FEET



The whole operations of Lake George Mines were, perforce, run on such extremely fine lines, owing to the natural poverty of the lode, that no recoverable element of value could be disregarded. Hence, robbing the mine of an undue portion of the richer copper-bearing ore would tend to the exclusion of the richer silver ore, and *vice versâ*. The latter, again, is so refractory, on account of the associated zinc and lead sulphides, as to prohibit profitable separate treatment.

It is impossible for anyone to pass through the working levels of the Koh-i-noor and Commodore sections of the Lake George Mines without a feeling of profound regret for the poverty of a lode which, for size, solidity, and permanence, is rarely equalled.

It was at the time probably the lowest-grade smelting problem ever attacked, the difficulties of which were aggravated by the presence of zinc. Too much credit cannot be given to those who, for a time, skilfully turned it to profitable account without the aid of by-products, and in doing so established a record for treatment and economy, though successful working was to a large extent dependent upon a favourable copper market.

The two classes of lodestuff in the Koh-i-noor workings, designated "copper" or "bulk ore" and "silver ore," owe their classification to the relative

quantities of copper and silver, which, as will be seen from the following analyses by the Mine Analyst, in either case is exceedingly small:—

	Bulk Ore.	Silver Ore.
Silica	21·55	26·48
Iron	22·26	15·19
Zinc	13·26	14·28
Lead	9·70	8·05
Lime	1·60	...
Sulphur	29·50	27·50
Copper	1·25	·94
Gold	·04 oz. per ton.	·06 oz. per ton.
Silver	1·15 „	3·03 „

The ores were graded into firsts, seconds, and thirds, according to the proportions of zinc in them. Carbonate of lime and a little barytes are also present.

An excellent porous oxide of iron flux was obtained from the gossan outcrop in the Commodore Mine, and copper ore from the Vanderbilt Lode, on tribute.

Special interest naturally attached to the smelting plant, which, like the mining equipment generally, was admirably planned and housed.

Four furnaces were continuously in operation, the blast (hot) being maintained by four Root's Acme Blowers.

Under the method of reduction, the matte was brought up to a marketable grade—30 to 35 per cent. copper—in one operation, thus avoiding the previous extra cost of roasting in attaining this grade.

The composition of a consignment can be judged from the following partial analysis:—

Copper	34·01 per cent.	
Iron	20·85 „	Gold, 1·63 oz. per ton.
Zinc	9·90 „	Silver, 60.00 „
Lead	11·75 „	
Sulphur	22·00 „	

Naturally the proportions of the furnace charges (which were varied to suit the idiosyncrasy of each furnace) were matters of commercial secrecy. The constituents, however, were about 12 cwt. of sulphide ore, with variable quantities of limestone, ironstone (from the Commodore Mine), and slag from the fore-hearths. About 3¾ to 4½ per cent. of carbonaceous fuel (coke) was added to each charge.

Limestone was procured about 3 miles from Captain's Flat, alongside the Bungendore Road.

The silica in the ore is just about sufficient for fluxing requirements.

The composition of the slag discharged over the dump is indicated by the following analyses:—

	(i.)	(ii.)
Silica	34·43 per cent.	37·65 per cent.
Ferric oxide	35·73 „	33·17 „
Calcic oxide	10·86 „	10·40 „
Zinc	12·16 „	14·97 „
Copper	·30 „	·40 „

The discharge from the furnaces was continuous through fore-hearth separators into slag pots.

"Barring down" was performed about every fifth day to remove the crust formed chiefly of oxide of zinc. The operation required about three hours to complete.

The flue-dust was moulded into bricks, cement being the binding medium used.

Unanderra (South Coast) coke was used in the furnaces.

The plant was lighted by electricity, and telephonic communication was established with all parts of the works, offices, and mine.

At the time of inspection, the old Commodore shaft was being pumped out. The water being charged with copper salts, a primitive attempt was made to precipitate the copper with scrap iron.

A cyanide plant had recently been erected to treat the auriferous gossan capping the southern extension of the lode, which was estimated to average from 2½ to 3 dwt. of gold per ton.

The Lake George Mines furnished an instructive and valuable object lesson on the possibilities of partial pyritic smelting.

Unfortunately the campaign above described did not continue long, the lower levels became too poor for profitable work; copper values depreciated below 1 per cent. with depth, and the better grades at higher levels became exhausted.

In 1900, about 9 tons of precipitate were obtained from the water bailed from one of the old shafts in the oxidised zone.

In 1904 the mineral leases and machinery were purchased by Mr. Channon.

In 1905 a little prospecting was done, mine unwatered, about 4 tons of precipitate obtained with scrap iron.

In 1906 Messrs. Channon and Plumb (owners) employed about ten men for a time prospecting the lode.

In 1907 prospecting operations were continued for a time without favourable results.

Burrowa Division.

Lang's Creek Mine, portion 77, parish Taunton, county King; 5 miles S.E. of Burrowa.—Opened many years ago. Again in 1905; and in 1907 by Messrs. Walker, Garvan, and party.

Strike N. 55° W., dip N. 35° E. at 50°, in quartz-felsite. Length of lode proving about 70 feet, depth 75 feet. Hanging wall well defined. Prospectors two years previously drove a considerable distance south just above water-level, without discovering any further payable ore. Northerly the lode is cut off by a cross joint, and may possibly have been faulted.

Oxidised ore has been stoped out. Winze started in sulphide zone below 70 feet; ore very poor.

The output in 1905 was:—74 tons 14 cwt. 3 qrs., yielding 8 tons 10 cwt. 1 qr. 19 lb. of copper, equal to 11·4 per cent.

Goulburn Division.

Lucky Hit Mine, Merrilla, M.L. 1, parish Gurrunda, county Argyle, about 8 miles from Breadalbane Railway Station, and 20 from Goulburn. Discovered by H. Gillett, August, 1905.

Main lode.—Strike N. 50° W., dip S. 40° W., 39° to 59°—wavy.

East lode.—Similar strike, dipping at 75°. Distant 78 feet from Main lode. Country slate. Lodestuff—impregnated crushed country along a well-defined and persistent fissure, traceable for a considerable distance north-westerly; but not south-easterly, where it apparently is cut off by a cross joint at the Lucky Hit boundary. (For description of the latter see Merrilla Freehold.)

The Lucky Hit, or Main lode, has been opened by two shafts 100 feet apart, to depths of 93 and 115 feet; and to the south-east by an open cut 64 feet further along the strike.

The East lode was opened by two shafts 30 feet deep and 16 feet apart; and costeens to the south-east.

About 50 feet west of the Main lode an outcrop of carbonate stains in slate had not been opened at time of inspection in May, 1907.

A tunnel from the south-west has since been driven about 400 feet, which will intersect the Main reef at about the level of the bottom of the Main shaft, at an estimated distance of 600 feet. The west lode was cut at about 450 feet, carrying chalcopyrite for a considerable width.

The output to May 3rd, 1907, reached about 130 tons, which realised from 7·8 to 25·9 per cent. of copper at Waratah and Lithgow.

During 1907—95 tons were dispatched for 10 tons 16 cwt. of copper, equal to 11·36 per cent.

Since the beginning of 1908 to the 27th March—the following parcels have been dispatched:—

20 tons, yielding 12·5 per cent. copper, silver 3 oz. 1 dwt., and gold 1 dwt. per ton.

23 tons, yielding 13 per cent. copper, and similar amounts of gold and silver.

These consignments have all been from the carbonate or oxidised zone in both lodes. A little very-sparsely distributed copper sulphide occurs in the Main shaft at 115 feet.

In the 93-feet, or Underlay shaft, a vug was encountered (30 feet x 30 feet x 2 feet), below which to 93 feet no ore occurred.

Channel at bottom reddened, upper part of vug filled with pug.

The workable lens proved in the East shaft was 35 feet long and 5 feet in the widest part.

Major's Creek Division.

Major's Creek.—Copper ore occurs in Rigby's Reef, about 1½ miles north-west of Major's Creek township; but gold is the chief element of value. Two and a half hundredweight of stone from the 64-feet level, sampled and assayed at the Australian Smelting Company's Works, Dapto, yielded:—

Gold	19 dwt. per ton.
Silver	26 oz. „
Copper	14½ per cent.
Antimony	5 „

Thirty tons subsequently forwarded yielded only 4 dwt. of gold and 9 oz. of silver per ton, and 3 per cent. of copper. The unoxidised ore consists of iron and copper pyrites and fahlerz.

SOUTHERN MINING DISTRICT—*continued.*

Burrowa Division.

Mayfield Copper Mine, Rye Park, about 17 miles east of Burrowa.—This mine was opened in 1895. Fifty tons of ore raised yielded 9 tons of copper, valued at £360. Shaft, 125 feet deep; lode, 2 ft. 6 in. thick. In 1896 the mine was being developed; no output recorded. In 1897 worked by a party of four; output valued at £1,605. The following parcels of ore were treated at the English and Australian Smelting Works, Waratah:—

Tons	cwt.	Yield.	Tons	cwt.	Yield.
13	13	12½ per cent. copper.	4	10	10½ per cent copper.
2	10	23 „ „	3	18	15½ „ „
5	1	9⅝ „ „	10	8	15½ „ „
9	18	15½ „ „	5	0	32 „ „

Goulburn Division.

Merrilla.—Costley and party's prospecting area, 40 acres, adjoining M.L. 4, on the south, parish Gurrunda, county Argyle.—Shaft 115 feet, sunk in pug and breccia, made ground; water heavy, standing at 75 feet from surface. Evidently old valley filled in with alluvial and detritus from bounding ridges. Similar breccia seen on banks of Heffron's Creek, lying flat on cleavage of slate. In the pug—which swells up in bottom of shaft—nodules of secondary pyrites occur; also fine-grained granular pyrites.

In crosscut east at 50-feet level, about 4 feet of soft granular gossan occurs, carrying crystals of carbonate of lead, and in a lesser degree carbonate of copper. A similar bunch seen in west end of shaft. The ferruginous breccia occurs on both sides of the gossan. The lead and copper carbonates appear to be of secondary origin, probably from solution, unless representative of altered boulders of lodestuff.

A sample of the breccia and ore exposed for 17 feet in shaft and crosscut yielded:—

No. 07-3459—Gold	.....	a trace per ton.
Silver	.....	11 dwt. 23 grs. per ton.
Copper	.....	less than 0·25 per cent.
Lead	.....	1·85 „

Sample 07-3460 (representing the metalliferous portion only) yielded:—

Gold	.....	a trace per ton.
Silver	.....	1 oz. 8 dwt. 7 grs. per ton.
Copper	.....	0·35 per cent.
Lead	.....	2·88 „

Merrilla Copper Mine, parish Gurrunda, county Argyle, adjoining the Lucky Hit Mine on the north-west.—The Lucky Hit Main lode has been traced for a mile or more, though no important discoveries have yet been made in it outside of the two mentioned.

The Merrilla mine was opened by W. Hanley in May, 1906, taken over by a syndicate, and subsequently by the Merrilla Copper Mining Company.

The lode, as in the Lucky Hit, consists of an impregnated belt of crushed slate without defined walls. It has been opened up by three shafts and a tunnel. The shafts being 30 feet, 40 feet, and 86 feet deep; and the tunnel 80 feet long. The Main—86 feet—shaft is sunk in a valley 130 feet below

the surface level of the furthest north-western shaft. These openings extend for a distance of about 20 chains along the outcrop, copper carbonate being visible in the shallow levels, sulphides below.

The Main (86 feet) shaft has been sunk mostly on the underlay of the lode—which is to S. 40° W. at 55°. Levels have been driven 20 feet south-easterly at 55 feet, and 20 feet north-westerly at 60 feet.

About 10 feet wide of impregnated country is exposed in this shaft, carrying native copper, cuprite, and probably melacconite, down to about 50 feet. Then sulphides, consisting of pyrite and chalcocite (subsulphide of copper) from enrichment. At the lowest level the sulphides are fairly solid.

A greasy joint occurs near footwall simulating a true wall, but ore occurs about 1 foot behind it; the joint probably being more recent than the metallic sulphides. The impregnated slate is more or less corrugated on a minor scale. Quartz strings and lenses occur but rarely in the lodestuff; but a large defined quartz reef outcrops a few feet west on a persistent south-east strike.

The nature of the enriched ore at 86 feet is shown in the following partial analysis:—

No. 07-3464—	Copper	1·90 per cent.
	Lead	2·81 „
	Silica	22·85 „
	Gold	a trace
	Silver	6 oz. 3 dwt. 1 gr. per ton

At 40 feet in No. 2 shaft similar enriched (subsulphide) ore occurs, but not so solid as in No. 1.

The crosscut tunnel is of little importance as it intersects the lode only a few feet below the crop.

According to the Annual Report of the Department of Mines, 1907, p. 54, about 100 tons of ore were sent to market which yielded a profit of £120.

The mine was disposed of to a Melbourne syndicate, which, however, failed to fulfil engagements.

Taralga Division.

Mount Bannaby Copper Mine, portion 177, parish Bannaby, county Argyle, 12 miles from Taralga; discovered by A. Potter.—Depth of proving, 40 feet. Lodestuff quartz with a little copper and iron pyrites.

Braidwood Division.

Mount Fisher Copper Lode, about ¼ mile from old Mulloon Copper Mine, Bungendore district.—Shaft, 170 feet at beginning of 1907. Lode reported to be 7 feet wide at 140 feet, thin at 170 feet.

Major's Creek Division.

Mount Hope Mine (known also as Eureka and Snobs), P.M.L. 94, parish Elrington, county St. Vincent, near Major's Creek, Braidwood.—Inspector G. Smith reported in 1903:—Quartz reef containing pyrites with small quantities of chalcopyrite and fahlerz. Thickness averages about 4 inches. Strike E. and W., slight dip N.; depth proved 375 feet, length 600 feet.

The picked ore yields about 3 oz. of gold per ton, 2 oz. of silver, and 2 per cent. copper. The seconds—about 3 dwt. of gold and the same percentage of copper.

Braidwood Division.

Mulloon Copper Mine, 30 miles north-west of Braidwood, and 10 miles south-west of Boro.—Mr. James McDonald, of Braidwood, supplied the following particulars (1898) of the above mine, which is situated on the property of Messrs. Scott:—"This mine was worked some twenty-five years ago, and a furnace was erected for smelting purposes, but prematurely, as little prospecting had been done. The shaft was down 100 feet. The ore consisted of grey sulphide, assaying very high, but occurring only in bunches. Both gold and silver were associated with the copper. By the time the above work had been completed the capital was understood to be exhausted, and the enterprise was abandoned."

A trial parcel of copper ore from Boro, treated by the English and Australian Smelting Co. at Newcastle in 1873, doubtless came from this mine, viz., 1 ton 11 cwt.; yield, 12⅞ per cent. of copper.

Inspection by the Writer in 1898 disclosed a considerable amount of work, but all very close together. The furnace, for some unaccountable reason, was erected some miles from the mine. The timbering of the shafts had all been destroyed by fire, so that inspection was not possible. Limestone is adjacent to the mine.

Opposite the Mulloon mine, on the south side of Mulloon Creek, McLaughlin and party were working the adjoining property, which was opened at the same time as the Mulloon. Country, slate; lode-strike, east and west, but wavy, following bedding of country. In an open cut close to the creek a wide body of copper ore is exposed without defined walls. A little good ore is visible in the old stopes. No particulars are available of the results of the early workings.

The Mulloon mine was taken on tribute by two miners in 1906, who despatched 5½ tons of ore to Lithgow. Veins very narrow. Ore reported to have yielded 25 per cent. of copper.

Also worked on tribute in 1907. Shaft 175 feet deep. Vein 4 inches thick; 10 tons averaged 20 per cent. of copper.

Goulburn Division.

Mummell Copper Mine.—In the *Australian Mining Standard*, December 17th, 1896, it was reported that a lode had been struck in this mine at a depth of 100 feet, having a thickness of 1 foot, according to a previous issue. Assays $\frac{100 \text{ to } 120}{60}$ from this locality yielded from 28 to 35 per cent. of copper, the ore being glance.

Under date of December 8th, 1898, J. B. Jaquet reported that the Mummell Copper Mine occurs in R. Lamb's property, about 10 miles west of Goulburn, in slate country. The lode, from 2 to 13 feet wide, dips west at an angle of about 45°. The lode material consists of country rock, silicified and otherwise altered, with veins and nests of copper and iron pyrites, with a little galena and blende. The ore, on the whole, is very silicious. Some rich carbonate ore was obtained near the surface. About 70 tons have been sent away to various smelting works for treatment, yielding, according

to Mr. Lamb, about 17 per cent. of copper. The lode has been proved to a depth of 70 feet by a shaft, and short drives have been driven along its course at that level.

A shaft to cut the lode on the underlay has been sunk 100 feet, at a distance of about 60 yards from the outcrop, naturally without cutting the lode at that level.

Murrumbidgee River Basin.—The Rev. W. B. Clarke, in a report[1] dated June 1st, 1852, wrote as follows of portion of this area:—

"The whole basin of the Murrumbidgee, from near Bullanamang to the junction of the Queanbeyan River, and even as far as the junction of the Yass and Goodradigbee Rivers (as, for instance, at Good Hope), exhibit not only metalliferous formations, but in some places lodes of lead, copper, and iron; and there can be no question that in some of these localities metallurgical operations may be profitably conducted. The association of abundance of limestone with these deposits is quite in accordance with similar associations in the mining countries of the European and American continents. The quartz porphyry, which occupies so large an area in the Murrumbidgee basin, is in Europe one of the most important and prolific sources of mineral wealth.

"Judging from what I have seen of the ores and vein-stuff of the copper lodes of Pudman Creek, on the Burrowa branch of the Lachlan, I presume that the Murrumbidgee deposits are continuous to the north, probably branching at intervals along the 149th meridian, to a junction with the copper and lead districts of the Belubula and Macquarie.

"A further confirmation of the metalliferous nature of the region along the 149th meridian is shown by the lodes of copper and lead about Quidong and the traces of similar ores on the McLaughlin.

"Near the junction of the Queanbeyan and Murrumbidgee Rivers the copper is found occasionally in the native state—*i.e.*, pure—in flakes adhering to the laminæ of the granite rock, which is traversed by the lodes. Near Yarralumla I saw somewhat similar examples."

Binalong Division.

Murrumbidgee Copper Mine, mineral lease, 40 acres, parish of Birrama, county Harden.—Geological Surveyor W. Anderson, who examined this mine in connection with the Prospecting Vote (P.B. $\frac{81}{92}\frac{82}{4}$) reported that an underlay shaft had been sunk 125 feet in a well-defined lode in granite, and several levels driven. The lodestuff was reported to consist chiefly of copper pyrites; but, judging from samples shown the Writer, the bulk of it was magnetic iron oxide. Aid was granted to continue prospecting, but without satisfactory results.

Reopened in 1907, and shaft unwatered for a brief period.

Frogmore Division.

Pride of Frogmore Mine.—In Sheedy's land, adjoining Frogmore Mine on west side. Worked at same date as the latter, by Mr. S. L. Bensusan. Smelters erected—no particulars as to output. About 2,500 tons of slag in

[1] Southern Goldfields, pp. 236-7.

dump, reported by Mr. J. F. Carey to assay 1·75 per cent. of copper. Also about 400 tons of ore at grass from early operations; averaging 3·72 per cent. of copper, and 10 per cent. iron, according to the same authority.

Mine not now open to inspection. Reported that the old main shaft was in a lens of ore which dipped south from the shaft at 210 feet. Average size of lens, 66 feet long by 4 feet wide. Oxidised ores to about 85 feet, then sulphides. Apparently no prospecting beyond stopes. Ore reported to have been left at south end from 90 feet up—18 inches to 24 inches wide. Strike of lode, N. and S.

Country, slate and crushed quartzite. Water standing at about 30 feet from surface in old workings.

Taken under option by Mr. F. Drake, in 1907, who sank a shaft 340 feet south to a depth of 100 feet and crosscut west 5 feet, east 26 feet. The latter cut 12 to 18 inches of gossan without trace of copper.

Yass Division.

Red Hill Mine, about 14 miles from Yass, near the head of the Burrowa River.—According to Mr. A. McCallum, of Yass, this mine was being worked in 1906 for gold and copper. In sinking the main shaft (110 feet), ironstone was passed through for 40 feet, then copper carbonates to 75 feet. At 110 feet sulphide ore was being tested. An east and west crosscut for 30 feet reveals no walls.

Frogmore Division.

Sapling Gully, about 6 chains south of Water Reserve on Narraba Creek, D. Flannery's land, 25 miles north of Burrowa, parish Yundas, county Monteagle.—Inspector J. James reported (P.B. $\frac{25}{7}$°) a lode striking N. 20° W., dip N. 70° E., Patches of good ore have been discovered along this line for a distance of 1½ miles; the lode being 2 feet wide in places.

Aided to sink from 23 to 75 feet.

Later the Warden's Clerk reported a good deal of water to contend with. Good ore decreasing; pyrites with splashes of yellow ore coming in shaft.

Yass Division.

Sapling Point Creek, near north-west corner, portion 131, parish Borambola, county Murray, about 12 miles south of Yass.—Geological Surveyor L. F. Harper reports that two leases for copper were taken up at this site in 1887, but little work was done. Several small veins of quartz carrying copper and iron pyrites are visible, and oxidation gave rise to carbonate stainings on the surface of the porphyry country. Indications unfavourable.

Goulburn Division.

Sassafras.—Inspector D. Milne reported—" On the Shoalhaven River, about 15 miles from Sassafras, Sievewright and party discovered a copper lode showing on the south side of a deep gorge. The formation can be seen for a distance of about 500 feet, cutting diagonally across the face of a gorge, varying in thickness from 1 to 10 feet, consisting of bands of ore composed of copper pyrites, galena, zincblende, iron pyrites, and slate rock. Owing to the almost inaccessible position, it will require a very heavy outlay to remove the ore to a suitable site for treatment." (Ann. Rept., 1907, p. 81).

Talwong Mine, Shoalhaven River, near Bungonia.

SOUTHERN MINING DISTRICT—*continued.*

Binalong Division.

on Kop Lode, 2 miles N., 20° E. from Goondah Railway Station, and
a Bowning; portion 640, parish Illalong, county Harden. Discovered
Cotter about 1905.—Strike N. 32° W., dip S. 58° W., at 78°, in quartz
lspar porphyry.
lth of ore channel, 2 ft. 6 in.; walls well-defined. Ore mostly on walls,
onally in centre, greatest thickness about 1 foot, usually a few inches;
r in mode of occurrence. Length of lens, 50 to 60 feet. Ore consists
ena with a little copper and iron pyrites. Proved for a length of
et by three shafts, ranging in depth at time of inspection in 1907,
13 to 55 feet. Main shaft since deepened to 80 feet, and aided from
cting Vote.
lve tons of gossan from 10-feet level yielded 16 dwts. of gold, and
of silver per ton. Copper and lead not ascertained
rage samples of the "firsts," stacked at surface, and the "seconds,"
d from the former, yielded the following results:—

No.	Description.	Copper per cent.	Lead per cent.	Gold per ton.	Silver per ton.
					oz. dwt. grs.
r ...	"Firsts" from heap at grass ..	2·35	20·20	Trace.....	5 8 21
..	"Seconds" from heap at grass...	2·00	.....	3 dwt. ...	7 0 0

Nowra Division.

ong Mine, M.Ls 1 to 4, parish Borimbodal, county St. Vincent.—
rered by John Sivewright about 1904, in a precipitous gorge of the
aven River Valley, about 9 miles S.S.E. of Marulan Railway
n. The river channel has been excavated from 1,500 to 1,600 feet
n quartzites and slates of Ordovician age, at least in part. The
ng lode is strong and well-defined, cutting across the stratification.
res are a complex mixture of mispickel, stannine, chalcopyrite, and
. (For further particulars, see page 413.)

Yalwal Division.

ga Copper Mine, parish Touga, county St. Vincent, about 10 miles
Nerriga, in a northerly direction.—The first record of copper-ore in
cality appears in the Parliamentary Votes and Proceedings, 1872,
p. 1021, in the form of a petition *re* a copper lode on the west side of
?) Creek, Braidwood district, north and south of the crossing-place at
a Station, which, petitioners averred, had been wrongfully taken up
ers who had learned of its existence from one of the discoverers.

1896 J. B. Jaquet visited the locality, and reported as follows:—
geological formations represented are horizontally bedded sandstone
ing to the Devonian or Upper Marine Series, and much indurated
and quartzites of Silurian age. The copper lodes are confined to
ates, &c. The outcrop of a copper lode has been exposed for a
ce of 36 feet, at a point distant about 100 yards below the junction

of Touga and Quera Creeks. The lode is about 2 ft. 6 in. thick. It does not appear to have defined walls, but, like many other deposits of this metal, seems to consist of country more or less impregnated with quartz and copper pyrites.

"About 200 yards north of the lode last described, another one has been discovered, and traced for several chains upon the surface. It is about 1 foot wide A picked sample yielded 13/16 per cent. of copper, and silver at the rate of 1 oz. 12 dwt. per ton.

"A little south of the junction of the two creeks the outcrop of a copper lode can be seen running up the precipitous bank of Touga Creek."

Mr. J. Donohue, who worked in the mine, stated that the prospecting shaft was sunk 40 feet vertical and 40 feet on the underlay, and a level driven 80 feet on the course of the lode. No stoping was done. The only ore raised was from the sinking and driving. The copper deposits were very patchy. The ore was chiefly grey ore. A little native copper was obtained from the shaft.

Major's Creek Division.

United Miners', Major's Creek, parish Elrington, county St. Vincent, in private land.—Quartz vein containing pyrites, worked for gold; containing about 2½ per cent. of copper.

Burrowa Division.

Wallah Wallah Copper Mine, parish Rugby, county King.—Opened about 1846, according to the late Mr. J. K. Hume. W. Anderson, in 1891, reported that this mine was opened over forty years prior to his visit to the locality, some good ore being obtained from it. J. B. Jaquet states that the lode occurs in granite about 1½ mile from the junction with slates in the parish of Ware. It has a general north and south strike. The outcrop can be traced for a considerable distance, its width being about 4 feet. A good deal of carbonate ore can be seen where the lode is exposed.

Mr. I. Stevenson, of Burrowa, stated that no ore was smelted or sent from the mine during the early workings, but that it was stacked on the surface. Many years after, it was despatched to smelting works, but the result is not known.

Yass Division.

Woolgarlo Mine, Yass River, 17 miles from Yass.—This mine is situated directly opposite the Good Hope Mine. Several lodes occur on the Woolgarlo property, but none have yet been proved workable. Some contain a little copper ore. The main lead (galena) lode has no defined walls. In 1870 a concentrating and smelting plant for lead was erected on this property; but being placed too close to the river bank, was washed away in the first flood. The prospectus of the Woolgarlo Lead-mining Company (Limited) was issued on 16th March, 1867.

Fluor-spar forms the gangue of lead ore, and is evidently in considerable quantity.

TAMBAROORA AND TURON MINING DISTRICT.

Stuart Town Division.

Al Mine, Tinby, near Yeoval, south-east corner portion 35, parish Obley, county Gordon.—Held under authority to enter. Discovered by W. Blatch in 1903. Work started April, 1907. Strike of lode N. 25° W., dip S. 65° W. at 83°. Development to 12th December, 1907:—Shaft 90 feet, sulphide of copper struck at 60 feet. Lode formation, 2 to 4 feet wide. About 2 feet of ore at bottom on north end of shaft; traces only in south. Not solid or defined; irregular, in granite country. Apparent walls at 90 feet, but may not be true. Ore at higher level passing into footwall, gossan into hanging wall.

Ore consists of chalcopyrite and magnetite, the latter somewhat specular in appearance.

An average sample of dressed ore at surface yielded:—

No. 07-8009—Copper			12·37 per cent.
Zinc		less than	0·1 „
Gold			a few grains per ton.
Silver			17 dwt. 10 grs. „

An average of the "fines" from the above, yielded:—

No. 07-8010—Copper			4·05 per cent.
Zinc		less than	0·1 „
Gold			1 dwt. 2 grs. per ton.
Silver			16 dwt. 8 grs. „

Rylstone Division.

Cheshire Copper Mine, 3 miles south of Cudgegong.—The first mention of copper ore in this locality occurs in a report by the Rev. W. B. Clarke, dated 1st October, 1852. "Indications of lead (galena) and copper occur in the quartz lodes of the ranges upon the upper portion of Lawson's Creek" (15 miles from Cudgegong).

In 1882, prospecting operations were carried on by C. Knoblanche (about 6 miles from the Ilford Station on the Mudgee railway), the shaft being about 75 feet in depth. Carbonates of copper occur at surface, sulphides at 40 feet or 50 feet. The lode has a thickness of about 2 feet, N. and S. strike, and westerly dip.

In 1883, the Mining Registrar reported that a large staff of men were employed, the shaft being down 120 feet, at which depth levels were being driven, the lode being 6 feet wide.

In 1885 the company in possession suspended work, and subsequently let the mine on tribute, but work ceased entirely in 1886.

In 1897 the mine, under the name of the Rhobodah, was bailed out by I. Wall, but no work was done, as the lode was not deemed equal to represen-tations. It does not appear that any ore was ever despatched.

Cyclops Copper Mine, Lower Tinby, near Yeoval, portion 93, parish Obley, county Gordon.—Opened about thirty years ago to a slight extent. One hundred acres now held under option from trustees of Thos. McCulloch's estate.

Several ore bodies occur, two of which have received most attention.

No. 1 shaft has been sunk 70 feet on a vein, striking N. 30° W., and dipping S. 60° W. at 71°, carrying copper pyrites. Width about 1 ft. to 1 ft. 6 in. at bottom, in very hard country. Greatest reported width about 3 feet.

About 10½ chains S. 70° W. No. 2 shaft has been sunk 60 feet on a vein, striking N. 10° W. Between the shafts a shallow shaft and trench expose other veins showing copper stains.

No. 2 shaft has been driven 40 feet south at the 50-feet level, at the end of the drive the ore is being followed down on a southern pitch. Underhand stoping was proceeding from this level. A sample of the dressed ore from the stope yielded the following results:—

No. 07-8011—Copper	.....	6·52 per cent.
Gold	.....	a few grains per ton.
Silver	.....	10 dwt. 21 grs. „

The total output from May, 1907, to January 17th, 1908, was 40 tons, averaging 11 per cent. of copper and 1 dwt. of gold and 3 oz. of silver per ton.

Dolcoath Lode, on J. Whittaker's private land, parish Obley, county Gordon, near Yeoval.—A new discovery of copper ore in granite; opened about 8 feet at time of inspection in 1907. Lodestuff carries a little carbonate and sulphide of copper, with magnetic iron of a character resembling specular ore. A width of lodestuff 6 inches to 18 inches showing in 8-feet shaft just started. Strike N. 25° W.

An average sample yielded:—

No. 07-8008—Copper	.....	3·55 per cent.
Gold	.....	a few grains per ton.
Silver	.....	6 dwt. 13 grs. „

About 5 chains south-east similar copper stains show at surface.

Goodrich Copper Mine, formerly known as Buckenbah, Gordon, and Yeoval.—The Goodrich Mine is situated about 4½ miles from the village of Yeoval. The ore occurs in quartz veins in granite, and consists of chalcopyrite, magnetite, and a little molybdenite and gold and silver. The mine was worked as an open quarry to a depth of 120 feet by a width of about 70 feet.

According to the late Mr. Gibson, of Yeoval, the lode was discovered about 1868, and was shortly afterwards taken up by Messrs. Wynne, Gibson, and party, who worked it as a gold mine for twelve or fourteen months, extracting in that period 800 tons of stone, which yielded by battery treatment 1,504 oz. of gold, of the value of 58s. 9d. per ounce only, on account of the large admixture of silver.

At surface the deposit presented the appearance of a small cone of brown iron ore in granite. From this point the gold-bearing quartz veins dipped away in annular form, so that as the excavation proceeded the central cone was left standing. The party worked the auriferous ring about 16 feet wide to a depth of 28 feet, when copper pyrites were encountered, which rendered their battery treatment ineffective and influenced them to dispose of the property to a syndicate, who erected furnaces under the direction of Mr. Lewis Lloyd, to treat the copper ore. The syndicate, in blasting away the central cone, are reported to have obtained a good bunch of workable ore.

Mr. Gibson stated that smelting was continued for about seven years. The furnaces—two reducing and one refining—were erected on the Little River, about three-quarters of a mile from the mine. The ore was cobbed and

picked by hand, the fines being jigged. The refined copper is reported to have realised a high price, because as subsequent assays proved, of the quantity of gold concentrated in it—equal to 3 oz. 17 dwt. 10 grs. per ton by assay. It is, however, probable, judging from the experience of Cobar, that the quality of the copper alone affected the sales.

After Mr. Lloyd's supervision terminated, mining was carried on for a further period of two years under Mr. Gibson's management, who stated that the output averaged about 8½ tons of copper and 130 oz. of gold per month. Later the mine was purchased by Mr. J. Veitch, who worked it for gold only, but afterwards attempted, unsuccessfully, to smelt the cupriferous concentrates and tailings.

The quarry-like opening during the above operations assumed its present dimensions—about 75 feet by 60 feet by 150 feet, though the centre was not removed lower than 70 feet.

In 1886, Chief Inspector Slee reported that the monthly crushings under Mr. Veitch's management amounted to about 150 tons, yielding from 3 to 7 dwt. of gold per ton. The crushing plant consisted of a 20-head stamper battery, with grinders and concentrators constructed by the owner; a tramway of about three-quarters of a mile in length connected the mine and the crushing machinery. After extraction of the free gold by battery treatment, the copper ore was roughly concentrated, over 1,000 tons of the latter being stacked at the date of inspection, which the owner estimated by assay to contain 9 per cent. of copper, and 10 dwt. of gold, and 2 oz. of silver per ton.

After a fatal accident to a miner the open quarry workings were abandoned, and work ceased so far as winning ore was concerned. Subsequently a syndicate secured the property, on a purchasing option, and sank a shaft 80 feet in the country about 50 feet from the side of the quarry, and then abandoned operations before anything definite had been accomplished.

A large amount of lean ore was at grass, but the presence of copper precluded advantage being taken of cheap extraction of the gold by cyanidation. At the bottom, 4 per cent. concentrating ore was reported. Pillars of ore had been left in the workings, and veins—hard and firmly attached to the country—were to be seen in the sides of the open quarry, dipping flatly away from the opening.

The mine was again held in 1898, and the workings unwatered; but little development work was done.

About 1903 it was reopened by the present Goodrich Proprietary Company from the main or new shaft—then 80 feet deep—in country about 200 feet from the open quarry workings. At time of inspection by the Writer in 1908, strong poppet heads had been erected and the shaft deepened to 300 feet. At 200 feet a crosscut south-south-east for 70 feet cut the lode under the quarry, apparently at its strongest point—about 10 feet wide. A level was driven for about 200 feet along its strike in both directions; the ore lens tapered to mere blotches and strings in the granite.

A rise from the crosscut in the ore body connects with the bottom of the open workings at about 120 feet from surface.

It is intended to again crosscut at 300 feet. Its slight eastern dip is expected to bring the lode nearer the shaft at that depth.

So far the country has not been crosscut west, and as ore occurs east of the lode, it may also extend in the opposite direction.

It is unlikely, owing to extreme hardness of the country, that any but the solid ore makes will pay for extraction.

From the crosscut and the rise considerable paddocks of firsts and seconds are at grass. Segregated masses of pure chalcopyrite occasionally occur; a 10-ton parcel of picked ore of this class yielded 23 per cent. of copper.

The ore contains a considerable proportion of magnetic iron oxide, which at first glance might readily be mistaken for zinc blende, from which the ore is very free. Quartz is also freely associated with the ore.

An interesting feature of the deposit is the occurrence of isolated patches of quartz and copper ore in the solid granite, apparently unconnected with the lode.

An average sample of firsts, paddocked at surface, yielded:—

No. 07-8007—Copper	.....	3·35 per cent.
Zinc	.....	0·10 „
Iron	.....	11·90 „
Silica	.....	61·58 „
Gold	.....	3 dwt. 6 grs. per ton.
Silver	.....	9 „ 19 „ „

In the treatment of this ore concentration will be needful, and should prove clean and effective.

One mile south of Goodrich Mine, the Buckenbar Copper-mining Syndicate sank 120 feet in a copper lode, the ore being disposed of to the Goodrich smelters, but the quantity was not large.

At Dilga Creek, 6 miles south of Goodrich, poor copper ore occurs, much mixed with other sulphides. (For other occurrences in the neighbourhood, *see* Tinby Hill.)

Lady Lizzie Mine, about 1 mile north of Yeoval, parish Obley, county Gordon, in Reserve 28,321.—Strike N. 20° W. in granite with diorite intrusions. Several outcrops superficially opened, revealing a little copper carbonates and sulphides in granite associated with quartz.

Aided to sink from 56 feet to 106 feet.

At 54 feet the vein material varies from 8 inches to 18 inches wide in hard country. An average sample of the dressed ore gave:—

No. 07-8005—Copper	.....	6·07 per cent.
Gold	.....	a few grains per ton.
Silver	.....	6 dwt. 13 grs. „

Three tons previously despatched to Lithgow yielded 3½ per cent. copper. Not promising.

Mount Rose (late Frog's Hollow), reserve 45, parish Bolderogery, county Gordon, near N.W. corner of portion 23, near Goodrich Mine.—Opened originally by P. Brown, about 1872. Several parallel lines striking about N. 55° W., dip S. 35° W. at 45° in granite. Consisting chiefly of copper-stained garnet rock. Two lines, about 145 feet apart, opened by shafts 75 feet and 45 feet; recently the latter received attention, being deepened to its present depth. Matrix mostly garnet, with a little copper carbonate and sulphides of the following grade:—

No. 07-8006—Copper	.....	5·47 per cent.
Gold	.....	1 dwt. 2 grs. per ton.
Silver	.....	1 oz. 6 dwt. 3 grs. per ton.

TAMBAROORA AND TURON MINING DISTRICT—*continued.*

Sofala Division.

Sofala, G.L. 8, parish Dulabree, county Roxburgh, Tobin's Oaky Creek 8 miles east of Sofala.—Geological Surveyor Harper reported (11th March, 1908) a quartz reef with copper pyrites near junction of intrusive diorite, with Devonian quartzites and conglomerates. Several shafts were sunk some years ago, prospecting for gold. Present prospectors, in a 12-feet shaft, had 2 feet of quartz containing 5 to 6 per cent. of copper.

Stuart Town Division.

Tinby Hill, about 1 mile northerly from Yeoval, and about 4 from the Goodrich Copper Mine.—In the same belt of granite country as the latter, copper ore of poor quality has been prospected at Tinby Hill. On the hill and on its slopes stains of copper carbonates occur freely distributed, but rarely forming more than mere colourations in the joints and cracks of the granite. Under Government aid a shaft was sunk about 60 feet in a large body of quartz, stained with carbonates, in which a little gold occurs, but not in payable quantity. More recently a syndicate prospected on the top of the low hill, along a small joint which carries copper pyrites, concentrated in ¼ to ½ inch skins on the faces of the joint. Little quartz shows at this point, but farther south at the end of the hill, old workings reveal a quartz reef about 10 inches thick, lightly copper-stained. A short distance west, another line of jointing shows faint stains of copper. The strike of both joints is about N. 10° W. A shaft has been sunk 28 feet on the first mentioned with hard country at bottom. As copper lodes, these are of no value, and the gold contents are not in payable quantities.

Viles' Lode, portion 29, parish Bolderogery, county Gordon.—Worked when Goodrich Smelting Works were running; ore from it sent to latter. Strike approximately N. and S. in granite. Opened by three shafts (not open to inspection). "Seconds" rejected at surface—very silicious. Length of proving about 4 chains; depth, 28 to 80 feet.(?) Lode apparently of fair size—judging by refuse. A little sulphides present in quartz.

Yeoval, portion 23A, parish Obley, county Gordon. Copper carbonates staining granite and quartz in several places in this portion. Several shafts and open cuts, all revealing stained country, but nothing defined. On principal outcrop, aid granted to Williams and Taylor to sink to 80 feet level; not fully worked out. Site abandoned.

North Buckinbar Prospecting Claim, portion 99, parish Obley.—Opened in April, 1907. From surface to 40 feet a few leaders showing slight stains of copper carbonates only. Shaft 72 feet; crosscut at 50 feet for 31 feet west, in country.

Copper stains also occur about 10 chains southerly.

TUMUT AND ADELONG MINING DISTRICT.

Tumut Division.

Adjungbilly Creek.—Copper ores occur sparingly in the serpentine belt which trends from Muttama south-easterly to Lac-ma-lac and beyond. Adjungbilly Creek crosses this belt just south of Mount Lightning, near the Murrumbidgee River. In Tea-tree Gully, about three-quarters of a mile south of the creek, native copper has been found. On the north fall of Mount Lightning copper ores outcropped; but a few feet of sinking revealed the superficial character of the carbonate stainings. At Brungle, Wyangle, and near Kangaroo Mount, in the same belt, copper ores occur.

Queanbeyan Division.

Balconnel Gold Mine, parish Weetangra, county Murray, close to junction of Molonglo and Murrumbidgee Rivers.

Inspector Godfrey reported (P.B. $\frac{22}{1.0}\frac{1}{1}\frac{2}{2}$) a quartz lode containing sulphides of lead and copper. Strike, S. 40° E.; dip, S. 50° W. at about 75°.

Opened by tunnel under bluff 14 feet high. Veins of galena worked here previously. Quartz reef 1 foot 6 in. thick, cut at 14 feet in tunnel, carrying galena and chalcopyrite.

Aid granted to sink a winze 50 feet. Tunnel continued to 55 feet. A leader 4 in. wide carrying pyrites and galena cut at 36 feet. Aided to continue 100 feet in tunnel. Nothing of value disclosed.

Delegate Division.

Belmore Copper Mine, Quidong, Monaro.—In an official report, dated 6th February, 1852, the Rev. W. B. Clarke wrote as follows of the site of this subsequently-opened mine:—

"As the extent of the limestone country is considerable, and its aspect is such as to lead to the belief that it is metalliferous, being bare of grass and extremely ferruginous in hue, occasioned by the presence of cupriferous iron-stone. I think it is not improbable that more than an insignificant amount of gold may be discovered hereafter, but the value of the locality appears to me to rest upon other considerations.

"Exactly where the largest auriferous hollows occur, veins of copper and lead, several feet in width, make their appearance in the limestone, and pass through to the face of the cliff in a south-east direction. The veinstone is chiefly barytes, and the ores are chiefly fibrous and earthy green carbonates, and yellow and iridescent sulphurets of copper, with interspersed crystallised sulphurets of lead. The latter stands out of the face of the limestone in independent crystals.

"As copper and lead exist in various parts of this tract of country, it is extremely probable that a mining field may be here profitably worked."

In Mr. Clarke's collection at the Paris Exhibition of 1855 were specimens of copper and lead ores in limestone, from "Merinoo, Deleget River," which, doubtless, corresponds with the above locality.

In December, 1868, the prospectus of the Belmore Freehold Silver and Lead Mining Company, Bombala, was issued. Judging from the appearance of the locality when visited by the Writer in 1897, a considerable amount of prospecting for copper must have followed the formation of the company. A large amount of work was done in sinking and driving on the east side of

the Quidong River, in country revealing surface indications of copper, and abundant oxide of iron, the latter resulting from oxidation of pyrites, which, in its unaltered condition, is very plentiful in the spoil from the deepest shafts. Another source of the prevalent iron oxide which colours the rocks and soil of the neighbourhood, is the original precipitation of iron salts by the abundant organic remains (Upper Silurian) in the strata, which consist of mudstone, sandstones, and limestone. The precipitates have been converted into oxides, as weathering and denudation exposed the fossiliferous layers to atmospheric influences. In some instances—Clarke's Rock, for example—the cellular, gossany appearance imparted to certain strata by the decomposition of the original organic remains, and the subsequent alteration of the investing salts into powdery oxides, has given rise to an erroneous impression that the "gossan"-like outcrops are caps of metallic lodes.

Evidently these early prospecting operations failed to reveal any workable copper lodes. Later a stamp battery and smelting furnace were established on the opposite side of the river in connection with the lead ores, but apparently were little used; it cannot, however, be said that the prospects of the field have been exhausted.

In 1907, a little prospecting was done in this locality in a gossany outcrop.

Cooma Division.

Berridale District.—Copper ore occurs in G. Rogers' conditional purchase, about 7 miles from Berridale, alongside Jindabyne-road.

In 1906, a shaft was sunk 30 feet on a 1-foot quartz vein, showing a little carbonate of copper; reef thins to 6 inches in sinking and in face of drive east for 34 feet; no sulphides yet visible; picked ore, probably 5 to 7 per cent. copper.

Three and a half chains along the strike, N. 85° W., traces of copper carbonates are exposed in a shallow opening.

One hundred and thirty feet along the south-eastern strike another quartz reef cuts the former on a N. 30° W. strike; this has not been tested.

On J. Constance's portion 40, parish Cootralanta, county Wallace, T. Hooper and party in 1906 sank about 25 feet in granite, with quartz veins or strings irregular and inconstant; specks of copper sulphide and traces of green carbonate are associated with the quartz and occasionally present in the country; no defined channel visible.

Kiandra Division.

Blue Creek Reefs—Bradley's, about half a mile above junction with Yarrangobilly River, parish Yarrangobilly, county Buccleuch.

First opened by H. Bradley in a 12-foot tunnel, and open cut about 20 feet higher.

Strike, N. 60° E.; dip, nearly vertical; thickness, 4 to 5 feet; veinstone quartz with bands and angular fragments of slate, with copper and iron pyrites very sparingly distributed; stains of carbonate in surface stone; occurs in altered slate; elevation about 300 feet above river; no value as a copper lode.

Blue Creek Reef, about half a mile from Yarrangobilly River, below Yarrangobilly Caves Reserve.

Situated about a quarter of a mile up Blue Creek from Bradley's Reef, and about 235 feet higher.

TUMUT AND ADELONG MINING DISTRICT—*continued.*

Several thin quartz reefs exposed in a bluff of altered slate, ranging from 3 inches to 14 inches in thickness.

The quartz veins carry small particles of chalcopyrite, mostly in small vugs; not promising.

Tumut Division.

Bogong Copper Mine, parish Banoo, county Buccleuch, 15 miles east of Tumut.—Inspector Hooke reported (P.B. $\frac{21}{04}\frac{2}{21}$) copper-bearing formation in serpentine. Aided for 100 feet of sinking.

Further report. Shaft, 80 feet; driven north 25 feet and south 10 feet, at 50-foot level; channel mainly crushed country, with isolated ore bodies; ore—principally bornite, with a little carbonate; about 14 chains north an outcrop occurs, seamed with thin films of bornite.

Thirty tons of ore despatched, averaging 25 per cent. of copper.

Cooma Division.

Bredbo Copper, Silver, and Lead Mine (late Baalgammon), portion 5, parish Bransby, county Beresford, about 4 miles east of Bredbo Railway Station. Private land.

Prospected about 1880. No details available. Country—Limestone, between slate and quartz-felsite. Early workings consisted of a shallow shaft and tunnel, the latter cross-cutting towards, but not reaching, the principal ore body.

Recent developments to March, 1907, deepening shaft to 64 feet, and starting drive on strike south-easterly.

Workings disclose neither walls nor defined ore channel. Ore consists of copper pyrites and galena sparingly distributed in quartz, and of irregular occurrence.

Nature of occurrence well exposed in small drainage channel crossing strike of limestone. Between the quartz-felsite on the west and banded slate and limestone on the east, numerous thin quartz strings carrying galena, and in places copper, occur parallel in a width of about 270 feet of limestone and slates. In the only one of importance—from 1 ft. 6 in. to 2 ft. 6 in. thick—the shaft has been sunk; the others are mostly from ¼ to 1 inch thick, the widest being 5 inches.

About 6 chains north-westerly a shallow opening shows quartz, with stains of copper carbonate and a little pyrites, in slate. Here the lode cuts across the bedding of the country. Further along the strike is an old shaft in banded limestone and slate, with carbonate of copper stains and galena, the latter more prominent.

From recent developments in the shaft about 4 tons of dressed ore were obtained, an average sample of which yielded :—

No. 07-3457—Copper	11·07 per cent.	
Gold	a trace (under 2 dwt.)	per ton.
Silver	2 oz. 3 dwt. 13 grs.	,,

A sample of the better grade limestone revealed the following composition on partial analysis :—

No. 07-3455—Calcium carbonate	88·75
Ferric oxide and alumina	1·60
Gangue	8·10
Magnesium carbonate and undetermined	1·55
	100·00

TUMUT AND ADELONG MINING DISTRICT—*continued.*

Bredbo District.—Reed and party's copper lode about half a mile south of the Bredbo Mine. Portion 179, parish Bransby, county Beresford. Country, crushed quartz-felsite; two quartz reefs carrying copper. Striking N. 10° E. about 15 feet apart. Copper carbonates, and sulphides very leanly distributed through the quartz. One shaft on west reef down 21 feet in April, 1907. Vein from 12 inches to 20 inches thick, dipping easterly at about 65°.

East reef opened for a considerable distance by small cuts; reef 5 to 18 inches thick.

An average sample from the 21 feet shaft yielded :—

No. 07-3456—Copper	.....	3·75 per cent.
Gold	.....	a trace, per ton.
Silver	.....	14 dwt. 3 grs. per ton.

An average from south end of provings on east reef, yielded :—

No. 07-3458—Copper	.....	3·72 per cent.
Gold	.....	a trace per ton.
Silver	.....	17 dwt. 10 grs. per ton.

Tumut Division.

Brungle (Upper).—Inspector Godfrey reported (P.B. $\frac{A\,2\,0\,A}{2\,9}$) an outcrop heavily charged with copper carbonates on P. Kiley's C.P. 112, parish Brungle, county Buccleuch. Aided to sink 50 feet. Results poor.

Queanbeyan Division.

Congwarra, or Cowley Copper Lode, at the junction of the Cotter and Paddy's Rivers, in portion 20, parish Congwarra, county Cowley, about 27 miles from Queanbeyan.—Copper ores occur in this locality in a bed of limestone, in granite country. The limestone has an apparent N.E. and S.W. strike. The deposit on portion 20 has been prospected to a small extent by open cuts and a tunnel. Sulphides associated with a hornblendic rock are exposed in the tunnel, but not in payable proportion. The outcrop shows abundance of iron oxide from alteration of pyrites, and stainings of copper carbonates. This deposit is being further prospected by the Cowley Copper Development Syndicate, Limited.

Other deposits occur higher up Paddy's River. The Under Secretary for Mines in 1895, states that from Coyle's Mine 60 tons of ore were raised, yielding copper to the value of £150 and silver to £105 (Ann. Rept., 1895, p. 61); but it is not certain whether it is identical with the lode under description.

Cooma Division.

Cooma Copper Mine, Middle Flat, portion 25, parish Montague, county Beresford.—Large gossan outcrop in quartz-felsite, stained with carbonates of copper.

Position in 1898.—Shaft 50 feet deep. Traces of carbonates in several places near shaft on west side. Shaft started on about 15 inches of good carbonate ore which, however, gave out at 23 feet, the length of the ore shoot being about the same. Shaft passed into pyritous stone at about 50 feet (the water-level), containing little more than traces of copper.

Aided for 50 feet of cross-cutting to intersect western outcrops; not availed of.

Inspector Polkinghorne reported subsequently (P.B. $\frac{4.4.2}{9.9}$) that layers of black oxide and sulphide were cut at 67 feet. Probably enriched zone of subsulphide.

At 63 feet a cross-cut extended east 10 feet, apparently to hanging wall. A drive along the wall south 21 feet, and north 12½ feet on a nice vein of copper mineral.

Aided to sink to 200 feet level. At 100 feet porphyry reported with copper, iron, and arsenical pyrites. Water making at rate of 2,500 gallons per hour.

At 129 feet water heavy, and no change in mineral conditions. Apparently end of test, though in 1900 £50 worth of ore was reported to have been raised (Ann. Rept., 1900, page 55).

Apparently western portion of outcrop has not been tested by cross-cut from shaft. At surface the best indications are to the west.

Mr. G. T. Litchfield stated that near Buckley's Crossing, on the right-hand side of the Snowy River, between the junctions of the Boloco and Bobundra Creeks with the River, the granite country is traversed by several large quartz reefs, heavily charged with pyrites and oxide of iron. In several places the reefs are stained with malachite, and good specimens of both malachite and chalcopyrite are obtainable. These reefs strike E. and W., and can be traced for several miles.

About 30 miles further down the river, between the entrances of the Matong and Paupong Creeks, in slate country, a large quartz lode occurs on the right-hand side of the river, carrying fluorspar, baryta, copper pyrites, and malachite, and about 4 dwt. of gold per ton. The outcrop is traceable for about 1 mile on an E. and W. strike. From a leader about 9 inches wide, in the middle of the lode, Mr. Litchfield made several assays, which averaged 11 per cent. of copper, 32 per cent. of lead, and 24 oz. of silver, and 4 dwt. of gold per ton. Within a radius of about 2 miles from this reef several outcrops showing copper ores occur. The country is rugged and little prospected.

Cooma District.—Inspector Milne reported (P.B. $\frac{2.2.1.2}{6.6}$) copper lode in slate in M.L 33, parish Abercrombie, county Beresford.

Strike N. and S., dip E. channel 2 feet to 4 feet wide, well-defined, carrying in bottom of 54 feet shaft, several small veins of yellow ore from 2 inches to 6 inches thick. Assay value, 16 per cent. copper, and 6 dwt. of gold per ton.

Aided to sink to 154 feet.

Cootralanta, M.C.Ps., parish Gegedzerick, county Wallace, about 6 miles from Berridale, and half a mile from the Cooma–Middling Flat Road.

Quartz vein in granite. Strike, N.W. vertical; width at N.W. end of 100 feet level, 3 ft. 6 in. wide; 2 ft. 2 in. at south-east.

Well-defined joint with clay dig on north-east side. Lodestuff-quartz with yellow sulphide; and subsulphide from enrichment; not solid, occurs in patches, strings, and disseminated particles in channel filling. Firsts probably equal 12 to 20 per cent.; seconds 5 per cent. copper.

Walls appear true, with dig; quartz filling channel mostly, though crushed granite makes in it in places.

Outcrop, ferruginous gossany quartz with carbonates—not traceable for any distance beyond immediate provings.

Lode has been stoped up about 10-feet above the 100-feet level between the main and travelling-way shafts.

The two shafts on the lode 106 feet and 118 feet deep, were cleaned out in 1906, and two parcels of ore despatched, 1 ton from surface yielding 6 per cent.; 9 tons from level 7¾ per cent.

The total output from October, 1906 to 19th September, 1907, during the latest operations, amounted to 76 tons 19 cwt. 3 qrs., averaging 11·39 per cent. of copper at Customs Smelting Works.

Kiandra Division.

Coronation Mine, Lobb's Hole, Yarrangobilly River, M.L. 18, 40 acres, parishes Pinbeyan and Selwyn, county Buccleuch.

Strike N.W. vertical, in Silurian sedimentaries, on north-western continuation of Lobb's Hole Central lode. Channel well defined. Opened by short tunnel and shaft. In shaft 3 in. to 4 in. of rich yellow copper ore showing at 20 feet level, in a channel about 3 ft. 6 in. wide. A former Kiandra syndicate extracted and despatched about 7 tons of ore in 1903. This parcel was taken from a shoot exposed in the river bed. The present shaft is on the river bank; the tunnel starts in a bluff face about 10 feet from the shaft.

Delegate Division.

Corrowong Copper Mine, situated on Corrowong Station, at the east end of Black Jack Range, parish Currowong, county Wellesley.—This mine was discovered about 1880, and subsequently opened by H. T. Allen, of Delegate, to a depth of 30 feet. The ore-vein was reported to have had a thickness of 1 foot at surface. At 30 feet it consisted chiefly of clay, with grains of native copper. Two tons of ore despatched at the time to Sydney are reported to have yielded 10 per cent. of copper and a little gold. During 1898 the Writer visited the locality; operations for reopening had just begun on behalf of Victorian investors. Traces of copper occur over some little distance in granite; but no evidence of a defined ore-body was revealed in the shallow openings so far excavated.

Reopened and prospected by J. Jackson in 1907.

Queanbeyan Division.

Cowley Copper Lode (see *Congwarra*).—Copper ores occur in this locality near the junction of limestone and granite. The limestone has an apparent north-east and south-west strike. The deposit on portion 20 has been prospected to a small extent by open cuts and a tunnel. The outcrop shows abundance of iron oxide and stainings of copper carbonates.

Mr. J. B. Jaquet describes the iron ore as essentially magnetite, with varying amounts of hornblende, and the greater portion of it as of excellent quality. The estimated quantity in sight being at least 1,000,000 tons.[1]

[1] Memoirs Geol. Surv. N. S. Wales, No. 2, 1901, p. 60.

copper carbonate. At bottom the joint is filled with black stains probs of subsulphide of copper. Native copper grains are obtained by washing latter.

The average sulphide ore at grass probably runs about 5 to 6 per cent copper. A picked sample assayed :—

No. 07-3090—Copper	.....	13·95 per cent.
Gold	.....	7 dwt. 15 grs. per ton.
Silver	.....	11 dwt. 23 grs. ,,

Gundagai, Adelong, and Tumut Divisions.

Gundagai-Tumut District.—In the vicinity of Gundagai, Adelong, Tumut copper ores occur in numerous places, but in one only—Snow Mine—in sufficient quantity to work. The following localities have b noted :—

Snowball.

Red Hill, 7 and 12 miles from Gundagai, ores assaying 6 to 11 per cen

Mount Parnassus, Gundagai, assaying up to 11·61 per cent.

Parish Wagara, assaying 6·42 per cent.

Darbalara, in serpentine on the south side of Mount Lightning, indicati cut out at a shallow depth.

Wyangle, in serpentine on Geary's property, assaying 26·60 per cent.

Brungle.

Adjungbilly Creek, in Tea-tree Gully, ¾ of a mile south of Adjungl Creek.

Mingary Mount, about 3 miles S.E. of Snowball Copper Mine.

Gundagai Mine, 7 miles from Gundagai, portion 205, parish Kimo, cou Wynyard.

Queanbeyan Division.

Hall, parish Gininderra, county Murray, 24 miles south-east of Yas Warden Maitland stated that 10 tons of ore from this locality, treate Sydney, yielded 14 per cent. of copper and 8 dwt. of gold per ton.

Cooma Division.

Jindabyne Copper Mine, portion 94, parish Jinderboine, county Wall about 4 miles from Jindabyne, and about 1 mile from the Cooma-road.

Mr. Andrew Sturgeon, of Jindabyne, stated that the principal work at mine began about 1884, and that operations ceased about 1889, when m mines in the Colony were closed owing to the great fall in the valu copper. The shaft had reached a depth of about 80 feet.

Under a provisional agreement with the owner, Messrs. Skidmore Molesworth obtained from 3 to 22 per cent. of copper and 16 dwt. of per ton by assay from the accessible portions of the lode (the shaft ha caved in), and from a large outcrop about ¼ mile to the south.

Examined by the Writer in 1907.

Quartz vein in granite. Strike, N. 80″ E.; dip, S. 10″ E. Traceable a considerable distance westerly. Proved by several shafts and sha openings for a length of about 175 feet; and in one shaft to a dept 80 feet. Copper stains are again visible about 9 chains west of 80 feet sl where a little gossanous quartz occurs.

TUMUT AND ADELONG MINING DISTRICT—*continued.*

In the 80 feet and other shafts, copper carbonates occur as films on joint faces of quartz. At 80 feet slight traces of sulphides are visible.

No ore dispatched. Appearances unfavourable for solid or permanent makes of ore.

Tumut Division.

Kangaroo Mount.—Copper ore was discovered by J. A. Harrison, about 1 mile from Mr. Owen's homestead, near the Mount. The apparent width of lode was reported as 6 feet at surface, in serpentine, carrying carbonates and sulphide, but only shallow prospecting by open-cut was attempted.

Kiandra Division.

Kiandra District (see Lobb's Hole Mines).—At the 15-Mile, Tumut River, Geological-Surveyor Young, in 1880, p. 258, recorded the occurrence of small veins of copper pyrites in the slates of this neighbourhood, similar to those at Lobb's Hole, but smaller.

Cooma Division.

Kyloe Copper Mine, M.Ps. 1 and 2, and P.M.Ls. 1 and 2, parish Seymour, county Wallace, 2 miles from Adaminaby, on F. Reynolds' land, 30 miles from Cooma Railway Station.

Discovered by the owner of the land in 1860; taken up as an M.C.P.; opened to 75 feet; no ore sent away.

Held by Messrs Litchfield and Hassall for a few months in 1901. 30 tons extracted from the 50-foot level are reported to have yielded 16 to 24 per cent. of copper.

Schaefer Brothers obtained possession in 1904, and up to the Kyloe Company's option in the beginning of 1907, despatched about 500 tons of dressed ore to Waratah, for a return of 11 to 25·5 per cent. of copper, and stacked about 500 tons of seconds, worth about 5 per cent.

Aided in 1906 from the Prospecting Vote (P.B. $\frac{1}{0}\frac{a}{a}\frac{o}{1}$) to sink from 75 feet to 175 feet.

The lode strikes N.W. and dips S.E. about 1 in 16 in upper levels, but becomes vertical at 130 feet; occurs at or near junction of granite and slate.

Proved by shafts and levels for a length of about 550 feet, and for depths ranging from 65 to 130 feet (to April, 1907).

The lode occurs in quartz-felsite (which passes into highly quartzose aplitic, and biotitic granite away from the channel); very close to junction with slate; in fact, at the 130-foot level, south-east end, slate forms one wall.

The lode varies in thickness from 2 ft. 6 in. to 5 or 6 feet where bunches occur. In the early workings only the better grades were mined, leaving a skin on walls. In the centre of the ore channel a later fissure occurs, particularly noticeable from 70 feet downwards. Where solid chalcopyrite forms its walls they have been slickensided and burnished. The ore impregnates the quartz-felsite of the channel on both sides of the central fissure, the purest usually occurring in close proximity to the crack. The greatest width of high grade ore so far encountered being about 3 feet.

The ores consist of quartz with carbonates, cuprite, and bornite in the oxidized zone. A little powdery chalcocite occurs with chalcopyrite in zone of enrichment about the 40-foot level. Below this, yellow sulphide occurs, and when free from gangue is of very pure quality.

In places the ore is mixed in small veins and strings through the quartz and crushed brecciated felsitic channel filling.

Sales of ore to March, 1907, amounted to 269½ tons, yielding from 9 to 2[illegible] per cent.

Progress of Development.—A concentrating mill, erected in July, 190[illegible] consisting of a Krupp Ball Mill, and a four compartment May Brothers jig.

The Kyloe Copper Mines (No Liability) supplied the latest particulars to date, May 29th, 1908, viz., greatest depth of proving, 200 feet; length 350 feet (at 100-foot level).

Concentrates despatched, 266¼ tons; matte produced at mine, 64 tons—50 per cent. grade.

Capacity of concentrating mill, 30 tons per day; capacity of furnace, 10 tons per day.

Kiandra Division.

Lobb's Hole Copper Mine.—On Yarrangobilly River, about 4 miles above its junction with the Tumut River, and about 12 miles from Kiandra. The Rev. W. B. Clarke, in his "Southern Gold-fields," page 108, states that on the "western flanks of the Munniong [Snowy.—J.E.C.] Range, and in the mountainous regions of Jagungal or Big Bogong and Kiandra, ores of copper abound, sulphurets and carbonates of that metal promising a profitable field of labour and enterprise. Such have been long known to exist in the great breaks of the Tumut, near Lobb's Hole."

Mining probably began at Lobb's Hole about 1874, for in that year the following parcels of ore from the deposit were treated at Waratah:—

5	tons	16	cwt.	; yield,	26¼	per cent. of copper.
8	,,	10	,,	,,	26½	,, ,,
2	,,	10	,,	,,	26½	,, ,,

In 1892, aid was granted to Weselman and party to continue sinking on this lode to 160 feet, but they abandoned it after the 80-feet level was reached. Afterwards, the pumping plant was removed to Storey's Reef, Paddy's River, near Tumbarumba. Later, some members of the party re-pegged the ground, and, subsequently, it was examined by E. C. Whittell, who reported the lode to be 3 inches, with occasional bunches 12 inches thick, as proved by several shafts for about 1,130 feet horizontal and 30 to 40 feet in depth.

In 1901, Geological Surveyor Andrews reported the Lobb's Hole lode as occurring "in the bed and alongside the Yarrangobilly River, the latter lying in a gorge exceeding 3,000 feet in depth; the country consisting of quartzite breccias, and silicious argillaceous strata, overlain by conglomerates, sandstone, quartzite, limestones, and slates of the same age. Folding by great granite intrusions is very pronounced; the strata at the mines being forced into a dome-shaped mass, possessing an almost horizontal dip, but inclined in all directions from this spot as a centre."

The Lobb's Hole lode had then been traced for a considerable distance along the river bank. It varies from 4 to 18 inches in width, averaging about 7 inches of rich yellow ore. Rarely lenticular patches of ore occurred as much as 3 feet in width. In other parts, the walls closed almost to the exclusion of ore.

Pumping and haulage was by water power obtained by means of a race. Ore packed on horseback to an elevation of 2,400 feet above the river; thence by teams to Tumut.

E. C. A ndrews. **Yarrangobilly Valley. Lobb's Hole.**

E. C. Andrews. **Lobbs' Hole Copper Mine, Yarrangobilly River.**

The main shaft was deepened to 130 feet in 1902.

In 1906 the workings were flooded, necessitating more powerful pumping plant.

In May, 1907, the prospectus of the Lobb's Hole Copper Mining Company, N.L. was issued, and the company subsequently floated for the purpose of securing Messrs. Adolph R. Reeckmann and Julius Fostrom's interests in M.Ls. 1. 30, and 31, parishes of Pingany and Selwyn, county Buccleuch, which cover the Lobb's Hole lode.

At this period the ore-lens had been proved for a length of 540 feet out of 790 feet along its strike, N. 65° W.; and to a depth of 130 feet. The flow of water averaged between 4,000 and 5,000 gallons per hour.

In April, 1907, the Writer visited Lobb's Hole and measured the following section at the south-east end of level at 130 feet. In a crosscut south-westerly from the shaft at this level two other parallel veins of ore were cut—these are included in the section :—



In the south-eastern level, at 130 feet, a solid mass or ore 6 feet wide was encountered at 200 feet from the shaft, consisting of 2 feet of rich yellow ore, and 4 feet of mixed iron and copper pyrites. The clean ore was equal to 28 per cent. copper; the mixed sulphides gave the following excellent smelting mixture :—

No. 07-3085—	Copper	6·10 per cent.
	Iron	39·90 ,,
	Silica	13·28 ,,
	Gold	1 dwt. 2 grs. per ton.
	Silver	9 ,, 19 ,, ,,

The widest bunch of clean ore yet discovered in the lode, according to Mr. Reeckmann, was 4 feet, the average thickness being about 7 inches. The thicker bunches make where rolls occur, and the dip flattens. As the underlay steepens, the ore pinches.

In the ore-vein itself a later fissure occurs, through which water percolates so freely as to wear the chalcopyrite surfaces smooth like an ordinary water-worn surface.

This percolation is evidence of extensive fissuring, for the water rises under pressure from below, gas being evolved. This gas is slightly inflammable when allowed to accumulate in old workings. It causes considerable movement—like ebullition—when water is allowed to accumulate at the point of escape. An attempt was made to obtain a sample for analysis, but the bottles

leaked in transit. The mine water yielded the following results:—(05-
Total solids (dried at 220° F.) = 118·160 grains per gallon. The solids
sist of chloride of sodium, calcium carbonate, and a little magnesium
bonate. No sulphuretted hydrogen or sulphur detected.

The channel of the Lobb's Hole lode is very true and persistent, but c
partly occupied by copper ore, the balance being country more or less crus
Blanks occur, particularly on the north-western strike, where metal val
are practically or wholly absent.

On the south-eastern strike a long blank also occurs, but good ore re
again 300 to 400 feet from the shaft.

The ore usually makes solid and of unusual purity. The average valu
1,833 tons extracted prior to sale of the mine to the present company on
April, 1907, was a shade over 28 per cent. of copper. Rarely did the
signments vary 1 per cent.

During Messrs. Reeckmann and Fostrom's mining operations, pum
and haulage was by means of a race working a Pelton wheel under 50
pressure. The ore was hand-picked, and the solid selected ore broke
convenient gauge and bagged. The remainder was broken and jigge
hand, in two jigs of 4-holes to the square inch. The fines afterwards p
into an 8-hole jig.

The tailings from the 4-hole jigs were stacked. An average sample o
latter gave—

No. 05-3083—Copper	6·82 per cent.		
Gold	a trace	}	per ton.
Silver	6 dwt. 13 grs.		

The slimes or fines from the jigs yielded :—

No. 05-3084—Copper	11·55 per cent.		
Iron	14·70 ,,		
Silica	47·02 ,,		
Gold	a trace	}	per ton.
Silver	7 dwt. 4 grs.		

From the 4-hole jigs the most pyritic ore is picked out and dumped.
average sample gave—

No. 05-3082—Copper	8·25 per cent.		
Gold	2 dwt. 4 grs.	}	per ton.
Silver	8 ,, 17 ,,		

These all await treatment when the local smelting plant is erected,
paddocks in hand will average from 7 to 10 per cent of copper.

In the first half-yearly report of the company, 30th June, 1907, it is sta
that the 130 feet level had been continued south-easterly 57 feet, making
total length in that direction from the shaft 345 feet. Six inches of 28
cent. ore continued in the drive for the first 40 feet; but in the last sevent
pinched to 2 or 3 inches.

The advantage of the site is permanent and cheap motive power from
continuously flowing Yarrangobilly River, for all mining purposes, includ
milling, lighting, &c., which offsets the disadvantages of transport,
ticularly now the latter have been lessened by the completion of the new r
out of the gorge, which enables teams to reach the mine.

The previous costs of transport amounted to £2 15s. per ton by pack-ho
and teams to the Tumut railway station; thence 15s. 3d. per ton for rail
freight to smelting works. Total, £3 10s. 3d. per ton.

The purity of the copper ensured a smelting allowance of 50 shillings
ton of copper.

second half-yearly report for half-year ending 31st December, 1907, the following particulars of works in progress :—

ter-race 2 miles long completed, capable of carrying a flow of water wide by 1 foot deep.

stantial dam constructed across river at intake ; 30-horse-power turbine in position near shaft, and connection made with outlet of race by wrought-iron pipes, 33 inches in diameter ; heavy Cornish lift pump, 3-inch columns placed in position in new shaft.

pet heads erected. An attempt to deepen shaft with original pros- s' appliances failed ; unable to cope with water. The rapidly increasing f water in the shaft below the 130-foot level is attributed to a 6-inch f high grade ore cut at 147 feet. Another vein (5-inch) was intersected up when timbering.

everberatory furnace is being erected to smelt ore after clamp roasting ; nding firsts and seconds it is expected a 12 per cent. grade can be main- . Red bricks being made at mine.

b's Hole (additional sites).—R. Joyce took up a 20-acre lease in parish ngobilly, county Buccleuch, to north-east of Lobb's Hole, in 1903. 25 feet in a copper vein about 1 inch thick of pure yellow sulphide.

ty acres taken up by Fostrom and party in 1907, adjoining Lobb's Hole ietary on the south ; and south of this again an 80-acre block by Brown IcGregor. Copper stains are visible, but no prospecting had been done.

out 5 miles above Lobb's Hole, Smith and Thomas opened a copper vein bank of the river ; and sank 14 feet in a formation about 2 feet wide, ning about 1 foot of mixed quartz and copper ore.

b's Hole Central Mine (formerly Alpine, and later Sonoma), MLs. 19 2, parishes Pinbeyan and Selwyn, counties Buccleuch and Selwyn.— ining Lobb's Hole Proprietary Mine. Two parallel lines of lode occur mine, both traversing the river bed until it bends away from the

original prospecting shaft (Kerry and Forrester's) is on the south bank Yarrangobilly. In 1901 Geological Surveyor Andrews described this lode (the Alpine) as well pronounced, containing ore equal to the ietary, but narrower, from 3 to 4 inches thick, outcropping for the r part of its length in the river bed. Dip, south. Appears to junction he main vein about 7 chains east of Lobb's Hole Main River Shaft. A was sunk south of outcrop to cut reef at a depth and then to drive river. This shaft was carried down about 70 feet ; 10 tons of ore from it realised 32¼ per cent. of copper.

1904 the shaft was unwatered ; apparently little done.

1905 the workings were flooded ; but unwatered at end of year.

May, 1907, the leases were floated into the Lobb's Hole Central Com- At this time two shafts had been sunk on the north bank on a el vein to the Alpine, to depths of 28 and 38 feet, at a distance of 40 part, and but a few feet from the water's edge. Both north-west and west along the strike from the shaft the vein ran into the river bed, as etch plan.

lode channel exposed in the shafts is well defined between true walls 4 feet apart. The character of the filling is illustrated in the accom- ig section of the lower part of the 38-foot shaft. Here about 8 inches yellow sulphide is separated by 3 to 4 inches of slate ; the rest of the el is also filled with slate.

TUMUT AND ADELONG MINING DISTRICT—*continued.*

Pumping was performed by water-power, a small water-wheel being s in the river itself, and worked by the current.

Since the company took over the property a new (main) shaft has bee started well out of flood reach, and it is intended to cross-cut to the lode at depth so as to leave a solid cover, for the lode traverses the river bed for th greater part of its course.

During the previous operations, about 50 tons of high-grade ore have been despatched.

In subsequently cross-cutting from the main shaft to the lode, three veins were cut from 2½ inches to 10 inches thick of rich yellow sulphide.

Tumut Division.

McAlpine Copper Mine, portion 30, parish Wagra, county Buccleuch about 20 miles from Tumut, and 19 from Gundagai.—This lode wa originally opened to a depth of 90 feet at junction of granite and serpentine Reopened by J. J. Kelly about 1898, who sank another 20 feet, and too out 38 tons of ore; 9 tons 17 cwt. of which yielded 10 per cent. of coppe at Dapto. A sample recently taken by J. M. Dodds from a 6 feet lode, cu in east drive, from 104 feet level, yielded:—Copper, 13·74; zinc, 18·73 iron, 18·62; sulphur, 22·48; silica, 8·15 per cent.; gold, a trace; and silve 3 dwt. 6 grs. per ton.

About one mile north, Inspector J. James reported (P.B. $\frac{2}{0}\frac{2}{2}\frac{2}{2}$) a copp vein, about 3 inches thick, in granite and slate; strike N. and S. Aided t sink 60 feet. Cut out at 30 feet. Three tons of ore raised returned 6 p cent. No improvement at 40 feet.

Cooma Division.

Macanally Gold and Copper Mine, portion 3, parish Rose Valley, count Beresford.—Worked for many years for gold. Copper discovered by J. Ireland in 1906. Strike about N. and S., dip. E. Ore shoot pitches nortl Depth of proving, 70 feet. Thickness of vein, from a few inches to 1 foo Length of proving, about 200 feet. Outcrop, about 500 feet.

The following particulars of output were supplied by Mr. J. Murray:—

4 tons yielded £84 15s. 3d. for gold and copper.

	Gold per to
22nd October, 1907, 21 tons 11 cwt. yielded 9·18 per cent of copper	2·158 o
8th February, 1908, 10 tons 12 cwt. yielded 12·07 per cent. of copper ...	1·59 o
8th April, 1908, 8 tons 10 cwt. assayed 2·49 per cent. of copper...	3 oz. 8 dwt. 9 gr
8 tons 12 cwt. yielded 3·84 per cent. copper, 3·127 oz. gold.	

Depreciation in copper value in the later parcels being doubtless due t passing below the zone of enrichment.

Gundagai Division.

Mingary Copper Lode.—Under Mingary Mount, about 14 miles south Gundagai, and 3 miles north of Snowball Mine. Lode reported, 6 inches t 6 feet wide. Limestone in close proximity of the latter.

Cooma Division.

Monaro Copper Mine, late Dyball's, portion 92, parish Arable, count Wallace; about 11 miles from Berridale.—Opened about 1898 by H. Dybal Later a syndicate sank to about 39 feet and extracted 3 tons of ore.

The present Montreal Syndicate entered into possession, under authority to enter, in February, 1907. Cleaned out old shaft and started a new one at south-west end of workings, making four shafts in a distance of 40 feet in direction N. 65° E. The new shaft, by March, 1908, had been sunk to 100 feet, where a little iron pyrites was exposed. Aided to drive from the bottom under the old surface workings to test persistence of lens in depth.

In the old shaft, cleaned out by the Montreal Syndicate, a considerable chamber had been excavated, and a short drive put in to the north.

The country is soft, slippy-headed slate, with sandstone bands, in which copper carbonate stains are visible for a width of 20 feet or more, without defined walls or definite channel. Small concretionary nodules of rich grey ore, and carbonates as veins and impregnations occur at intervals, and search for these has caused the "rooting" visible in close holes. If no defined ore body be encountered in the drive at 100-foot level, the prospects of further developments will be hopeless.

A sample of the concretionary grey ore yielded 34·30 per cent. of copper on assay ($\frac{a}{o}\frac{o}{7}\frac{s}{2}$), a trace of gold, and 2 oz. 7 dwt. 22 grs. of silver per ton. About 25 chains north-west, in same lease, a 6-inch vein of quartz, containing a little galena and yellow ore, occurs in granite. From an opening in it about 8 feet deep, a picked sample gave 15·35 per cent. of copper, and 20 oz. of silver per ton. The average, however, would be very low. Too small to merit attention.

Monmouth Copper Mine, Gulgandra Creek, Monaro.—In the catalogue of the Sydney Exhibition of 1870, copper ores from this mine are mentioned. Work was at that time being carried on by a party of Victorians, who were sinking a shaft.

Queanbeyan Division.

Mount Bullen.—About one mile S.E. of Coyle's Mine. Mr. Danvers Power, stated, in 1898, that a recent discovery of copper ore was made at Mount Bullen in an amphibolite dyke in felsite and syenite country. The dyke has a width of about 1 chain and can be traced over Mount Bullen to the Cotter River, where copper stains are visible. The outcrop consists generally of magnetic iron with stains of copper carbonates. The only proving is to a depth of about 10 feet by a length of 10 feet in copper-stained lodestuff.

Mr. Power contributed the following notes of position in March, 1900:—"Tunnel, 98 feet; winze, 36 feet from mouth; down 34 feet on underlay. Bottom of winze below level of Paddy's River, about 25 feet below the tunnel level.

"Copper ore occurs in spots and small cracks with magnetite in an amphibolite dyke. No sign of defined lode. Nothing payable disclosed." (Probably refers to Congwarra and Cowley sites.)

Gundagai Division.

Mount Mingary Copper Lodes, Mount Horeb Estate, portion 249, parish Calafat, county Wynyard.—About 2½ miles east from Mount Horeb Railway Station, and 1½ from Calafat.

The principal lode was opened about 1905 for gold. It strikes about N. 5° W., and dips west at about 58°. It has been dissected by a creek to a depth of between 300 and 400 feet. At the creek level a shaft was sunk 40 feet, exposing about 2 feet of quartz veinstone, with a little yellow sulphide of copper and pyrites. It has also been exposed in an open trench

alongside. A quantity of this stone was stacked for crushing, but a trial parcel of 6 tons only was treated for a reported yield of 7 per cent. copper, and about ½ oz. of gold per ton.

Assays made in the departmental laboratory returned 5 to 7 dwt. of gold per ton.

Copper stains are reported to occur in the outcrop on ridge north of creek.

The lode occurs at junction of slate and intrusive quartz-felsite, and varies from 10 inches to 2 feet in thickness.

Rich specimens of cuprite were found about 100 feet above the shaft on the southern strike. Higher up this ridge sulphides were showing in a 25 feet shaft.

Though not workable as a copper proposition, if gold-bearing to the extent mentioned—5 to 7 dwt.—it would form a useful flux in matte roasting, especially if the adjacent Snowball Mine again became the site of smelting operations.

On the opposite side of the southern ridge traversed by the lode, Fuller's 3-acre block divides the Mingary north and south areas. Fuller's two shallow shafts are on western parallel quartz vein. About 5 tons of stone from it are reported to have yielded as high as 19 dwt. of gold per ton.

On the Mingary South the continuation of this vein has been found, and a shaft had just been started at date of inspection in 1907. Quartz, solid and gossany, is here stained with copper carbonates; the enclosing walls to a slight extent also.

On the east of this lode, some chains distant, the old Hawthorn lode was opened when Snowball Copper Mine was working, a shaft being sunk to 75 feet on a north and south vein, having a thickness from 9 to 24 inches, much resembling the West Mingary lode, but of slightly better grade. A few tons of ore lately raised from it would, perhaps, yield, when dressed, about 7 per cent. of copper.

Within a few chains of the Mingary West lode is an outcrop of limestone, which was burned for lime many years ago to supply requirements of Adelong and Gundagai. This would be useful for Snowball smelting—being only about 2½ miles distant. Its composition is shown in the following analysis:—

	Per ton.
07-3088—Carbonate of calcium	96·89
Ferric oxide and alumina	0·70
Gangue	1·80
Magnesium carbonate and undetermined	0·63
	100·00

Delegate Division.

Mount Trooper.—A little copper ore occurs in granite in the Snowy River Valley, on a low spur opposite Mount Trooper, on the east bank of Sandy Creek, about 2 miles from the Victorian border. Copper ore in minute quantities was also detected by the Writer on the border about half a mile east of the Snowy River. At Sandy Creek a little prospecting was done, but the indications were not favourable for the existence of ore in quantity. A picked sample of the best grade yielded 7·03 per cent. of copper, and silver at the rate of 17 dwt. 9 grs. per ton.

Cooma Division.

Nithholm Copper Mine.—Situated in W. Jardine's Nithholm Estate, 4½ miles easterly from Cooma, and adjoining the Dartmoor Cooper Mine property, parish Montague, county Beresford.

The following particulars of bulk tests of ores from this mine were supplied by Mr. J. R. Maccue, Cooma:—

No. 1 sample—7 cwt. 2 qrs., Wallaroo Smelting Works; copper, 29 per cent.; silver, 16 oz. per ton.
No. 2 sample—1 ton 7 cwt. 1 qr., Wallaroo Smelting Works; copper, 8 per cent.; silver, 18 oz. per ton.
No. 3 sample—1 ton 1 cwt. 2 qrs., The Smelting Company of Australia's Works, Dapto; copper, 14·02 per cent.; silver, 7 oz. per ton.
No. 4 sample—1 ton 12 cwt., The Smelting Company of Australia's Works, Dapto; copper, 10·22 per cent.; silver, 21 oz. per ton.
No. 5 sample—2 tons 2 cwt., The Smelting Company of Australia's Works, Dapto; copper, 2·43 per cent.; silver, 5 oz. per ton.

Peak, 9 miles from Cooma.—Mr. J. F. Carey noted a well-defined quartz outcrop traceable for some distance (unprospected), copper carbonates and sulphides showing at two points.

Tumut Division.

Pether's Lode, Jounama Creek, Talbingo.—Strike N. 5° to 10° W. Outcropping in four places—three on north and one on south side of the creek. Best developments at junction of limestone, where garnet has been developed by contact of igneous rock. Copper carbonates and sulphides present. The creek has dissected lode to a depth of about 400 feet below southern outcrop, and 500 below northern. Further north, at a higher elevation, galena is developed to a small extent in limestone. Still further north, about three-quarters of a mile, a massive outcrop of magnetic iron occurs about 1,800 feet above. In the Jounama Creek the outcrop is silicious, with traces only of copper ore. On the first point north of creek, very kindly looking gossan is exposed on west side of limestone, showing traces of copper. Particles of rich yellow sulphide occur in calcite walls of lode—highly altered slate.

North from this point the lode outcrops strong, but very silicious. Specular iron is developed to a small extent at contact in connection with garnet rock.

On the south side the limestone dips east at 32°. Copper stains occur here in small outcrops for about 60 feet, but apparently cannot be traced southerly though not prospected for.

Massive garnet outcrops occur a little higher up Jounama Creek, striking a little west of north.

Queanbeyan Division.

Queanbeyan District.—Copper indications occur in and near the town of Queanbeyan, but nothing payable or permanent has yet been discovered. Copper ores are also reported from near Rose Valley, assaying ($\frac{1}{10}\frac{3}{8}$) 9·02 per cent.; from 6 miles from Queanbeyan, assaying ($\frac{4}{5}\frac{1}{7}\frac{0}{2}$) 13·08 per cent. of copper. From McDonald's Mine, Uriara, 16 miles from Queanbeyan, copper ore, yielding ($\frac{2}{5}\frac{1}{6}$) 6·54 per cent. has been forwarded.

Copper ore is also reported at London Bridge, near Queanbeyan.

In 1906, W. A. Trewenack prospected a deposit in parish Carwoola, 10 tons of ore raised being valued at £90. (Ann. Rept., 1906, p. 48.)

Tumut Division.

Red Hill Copper Mine, portion 30, parish Wagra, county Buccleuch, near Red Hill Homestead.—Inspector E. C. Whittell reported (P. B. $\frac{2}{3}\frac{2}{2}\frac{1}{1}$) copper and zinc bearing lode at junction of serpentine and granite.

Shaft 90 feet. Worked some years before. Payable oxidised ore removed. P. Kiley sold ore to the value of £120. Zinc blende in excess of copper sulphide at bottom of shaft. Bunch of these ores from 1 foot to 6 feet wide.

Aided to sink from 78 feet to 178 feet.

Progress: At 118 feet lode about 4 feet wide, rock hard; a little water making. At 125 feet no copper ore apparent.

Cooma Division.

Rosebank Mine (Hayes, Jennings, and Party's), portion 12, parish of Umeralla, county Beresford.—Held as a 10-acre lease on the Rosebrook Estate. Shaft 40 feet, in slate country. From this mine the following parcels of ore were treated at the Smelting Company of Australia's works, Dapto:—

2 tons, yielding 14 per cent. copper, 11 dwt. of gold, and 2 oz. silver per ton.
2 ,, 10 ,, ,, 9 dwt. 4 grs. of gold, and 2 oz. silver per ton.
1 ton 5 cwt., yielding 16 per cent. lead, 11 dwt. of gold, and 13 oz. of silver per ton.

Gundagai Division.

Snowball Copper Mine, about 9 miles from Gundagai, towards Adelong, Portion 168, parish Willie Ploma, county Wynyard.—Situated on Snowball Hill, at the head of Snowball Creek, a tributary of the Murrumbidgee River.

This lode was discovered by James Clayton, in 1873, close to the marked-tree line on the mountain track between Adelong and Gundagai, and taken up by him as a lease in conjunction with his two brothers. Later, other leases were acquired, and the property passed into the possession of a company.

The earliest official record is that by Chief Inspector Slee, in 1876, to the effect that thirty men were then employed and a furnace was being erected. Gossan outcrop, traceable for about 1,000 feet, but lode only opened for about 100 feet in length. Assays of yellow sulphide reported to yield from 7 to 22 per cent. of copper.

In 1877 a syndicate to properly work the mine was proposed by Mr. S. L. Bensusan. At this time it was reported that the lode in the deepest shaft—100 feet—was 10 feet wide, and consisted of yellow sulphides, averaging about 10 per cent. Other shafts, 45 and 70 feet deep, had the lode from 5 to 9 feet wide, 3 feet of which was reported to be good carbonate ore. Four other shafts had been started on tribute. A tunnel was being driven at right-angles to intersect the lode in the main shaft at the 136-feet level.

In the same year, Mr. Slee reported the deepest shaft as 130 feet, lode 10 feet wide, slaty, with solid bunches of sulphide ore. Two furnaces were in full work, and a third in course of erection. Population, about 150.

In 1878–9 the Warden reported considerable activity at Snowball, and anticipated fair prospects of success when the railway-line to Gundagai was completed.

In 1880 the Mining Registrar reported the abandonment of smelting operations.

In 1881 the property was purchased by Messrs. Benson and Samper, but apparently no work was done, the mineral conditional purchase into which the lease was being converted being cancelled for non-payment of balance due. Later it was taken up as a conditional purchase.

In 1895 and 1896 Mr. Benson partly unwatered the mine and extracted 12 tons of ore from the 175-feet level, and 6 tons from the 100-feet. The two parcels are stated to have averaged 7 per cent. of copper at Lloyd's Smelting Works, Eskbank.

THE SNOWBALL COPPER MINE

Parish of Willie Ploma. County of Wynyard.

Plan of Workings *(After F. Danvers-Power, Esq.)*

Scale 0 40 80 Feet

Longitudinal Section

West S 60° E ⟶ **East**



Cross Section

North **South**



Plan



Plan showing locality

Scale 0 2 3 Chains



PHOTO LITHOGRAPHED BY W. A. GULLICK, GOVERNMENT PRINTER SYDNEY N.S.W.

In 1898 the mine was visited by the Writer. The country consists of slate and igneous rock—partly epidotic—the lode apparently occurring as a junction deposit. The outcrop is a strong one, and extends from some little distance. The workings, however, were confined to about 300 feet in length. The strike is nearly east and west. The old workings were unsafe, and water prevented inspection below 120 feet; but, judging from the old stopes, the ore channel is a wide and strong one, though the ore has evidently been bunchy in places. On one wall slickensides are well developed, which indicates considerable movement, and therefore permanency. At the west end of the workings a joint or cross-course divides the lode; but as ore is seen in the country beyond, there is no apparent faulting. A silicious, gossany outcrop a short distance to the west-north-west is regarded by some as the faulted continuation of the lode; but sufficient work has not been done to test this question. A sample of the gossan ($\frac{A}{9}\frac{A}{9}$) yielded 0·01 per cent. of copper only, which is no guide, as copper is likely to be detected in the country for some distance in this cupriferous locality.

A sample of the rejected ore from the 175 feet level, extracted by Mr. Benson, was assayed ($\frac{A}{9}\frac{A}{9}$) with the following results:—

Copper	1·87 per cent.
Iron	18·49 ,,
Silica	39·00 ,,

Neither gold nor silver.

It is evident that the lower levels of the lode constitute a concentration problem, though bunches may be found of direct smelting ore, as at higher levels.

It has not been possible to ascertain the quantity of copper produced during the smelting operations; but, judging from the slag dump, which roughly measures from 2,000 to 3,000 tons, it must have been fairly considerable, as some of the ores were of high grade.

Mine reopened in November, 1906, by J. M. Dodd; subsequently floated into the Snowball Copper-mining Company, which started operations 18th March, 1907. Unwatered to 150 feet level by June, 1907. Old stopes 4 to 20 feet wide between No. 1 and 2 shafts, 50 feet apart. Ore left on footwall at 80 feet assayed 3 to 4 per cent.

Bottom of No. 1 shaft reached, 6th July, at 192 feet, underhand stope going west of shaft about 35 feet. About 12 feet of ore showing.

Twenty-six tons from west end of lode at 176 feet yielded 6½ per cent. at Blayney Smelting Works.

Samples from this level tried during prospecting operations gave the following returns:—

Assay No.	Description.	Copper, per cent.	Gold, per ton.	Silver, per ton.
			dwt. grs.	dwt. grs.
07-3256	From footwall	3·95	1 2	5 10
07-3257	,, ,,	2·67	trace.	5 10
07-6686	From west drive at 210-foot level	5·27	,,	6 13
07-6687	From old shaft on ridge	8·35	,,	4 8

Revisited by Writer, January, 1908, when the mine was unwatered.

TUMUT AND ADELONG MINING DISTRICT—*continued.*

Strike of lode, N. 80° W. Dips at first N. 10° E., then nearly vertical, afterwards S. 10° W.; dips at 76° at 100-foot level. Greatest length of proving in old workings about 310 feet. Further westward carbonates have been cut in a recent prospecting shaft—not promising at this point. Channel of old workings up to 20 feet wide, evidencing a strong body of ore extracted to surface from 176 feet. As there are practically no tips the whole must have been smelted as mined, and apparently proved self-fluxing. About 8 chains on eastern strike an old shaft on ridge shows carbonates. The lode becomes irregular at western end of stopes. Indications exist of parallel veins at Snowball. Cross-cutting would be advisable.

The following samples were secured during examination which reveal the character of the ores. Subsequent samples show the nature of the lode in the winze below the 176-foot level, recently unwatered and cleaned out. The latter proved the lode to a total depth of 259 feet from surface. Though narrow (about 2 to 4 feet), the ore in the winze proved of excellent quality :—

Assay No.	Description.	Copper, per cent.	Iron, per cent.	Sulphur per cent.	Silica, per cent.	Gold, per ton.	Silver, per ton.
							dwt. grs.
08-437	Sulphide, S.E. drive 176-foot level from heap at grass.	9·50	22·40	11·64	32·02	A trace	8 17
08-438	Sulphide, west end of lens (bagged ore).	10·57	24·22	13·03	25·80	,,	3 6
08-1036	Sulphide bottom of winze 259-foot level.	16·82	31·78	16·33	13·24	,,	7 15

The prospects obtained in the winze should encourage further test at lower levels, by sinking and driving. It is very probable that lenses of good ore will be found.

The original smelting plant at Snowball consisted of four reducing, and one refining, furnaces. A fairly representative sample of the slag dump yielded the following composition :—

No. 08-606—Silica (SiO_2)	36·70	per cent.
*Alumina (Al_2O_3)	11·96	,,
Ferrous oxide (FeO)	38·97	,,
Titanic oxide (TiO)	absent.	
Manganous oxide (MnO)	·83	per cent.
Zinc oxide (ZnO)	·17	,,
Lead oxide (PbO)	trace	,,
†Copper sulphide (Cu_2S)	·98	,,
Lime (CaO)	1·18	,,
Magnesia (MgO)	8·43	,,
Alkalies and undetermined	1·28	,,
	100·90	

* Including phosphoric acid (P_2O_5) present. † Equal to 0·78 per cent. of copper; silver, 1 dwt. 2 grains portion; gold, a few grains.

Cooma Division.

Snowy River.—Copper carbonates reported to occur about 1 mile below junction of Moonbar and Snowy River, in granite; about 300 or 400 yards back from the Snowy.

Tumut and Adelong Mining District—*continued.*

Gundagai Division.

South Gundagai.—Copper-stained slate occurs in portion 292, parish South Gundagai. Opened by two shallow shafts, but no channels or joints so far disclosed, in which concentration would be likely; copper carbonates staining cleavage of slates.

Tumut Division.

Tumut District.—The occurrence of copper ores at Mingary Mount and in D. Ford's property on the west side of Mingary Range, in parish Califat, and in J. Dean's land on east side of Gilmore Creek, proved the extension of a cupriferous belt between the latter point and the Snowball Copper Mine in parish Willie Ploma, county Wynyard. This narrow belt trends in a N. 37° W. direction for a distance of 9 miles between the points mentioned.

Ford's property is situated at the foot of Mingary Range. The copper belt here consists of crushed porphyry, schist, and serpentine in close conjunction. A thin vein of copper carbonate was opened in the schist and crushed porphyry, but cut out at 23 feet in a shaft sunk in 1899. Judging from appearance, prospects are not good for extensive deposits, though a few tons of good ore are obtainable by careful spalling and picking. A sample of picked ore yielded :—

No. 00-1459—Copper	.....	27·05 per cent.
Silver	.....	1 oz. 3 dwt. 18 grs. per ton.
No gold.		

A short distance S.E. from the shaft, traces of copper carbonates are visible in the porphyry, but are unimportant.

The quartzite outcrops near the porphyry contact are highly silicified, and charged with specular iron ore; simulating lodes in appearance.

The copper indications on J. Dean's property, near junction of Adelong and Upper Gilmore roads, consist of a large untried gossany outcrop, showing slight traces of copper carbonate. It occurs in slates and schists. The iron oxide has evidently resulted from alteration of pyrites. A sample taken from the outcrops showing copper stains yielded :—

No. 00-1458—Silver	.....	5 oz. 8 dwt. 21 grs. per ton.
Gold	.....	nil, per ton.
Copper	.....	a trace.

Three miles from Tumut, on Micalong-road, Inspector E. C. Whittell reported (P.B. $\frac{21}{0}\frac{9}{2}\frac{1}{1}$), a copper-bearing vein in eruptive rock at this site, containing blue and green carbonates, with limonite; thickness, 6 inches; quality good. Aided to sink 50 feet. Ore reported to have pinched out at 10 feet, made again at 18 feet, 9 inches wide; dipping west.

Mingary Mount, parish Calafat, county Wynyard, in Crane's C.P.—Lode 8 to 9 inches thick. Sample from surface assayed (07-345)—Copper, 11·17 per cent.; gold, a trace; silver, 17 dwt. 10 grs. per ton.

From half a mile further north, from a vein 18 inches wide at surface, samples of quartz and slate with copper carbonates yielded :—

No. 07-349—Copper	.....	2·55 per cent.
Gold	.....	2 dwt. 4 grs. per ton.
Silver	.....	13 dwt. 1 gr. ,,

Other samples from this property yielded from 4·10 to 22·39 per cent. of copper.

Tumut and Adelong Mining District—*continued.*

Kiandra Division.

Tumut River.—About 1 mile below the Gaslight Mine, McMillan Bros. sank 30 feet and drove 30 feet in a 5 feet channel, containing mostly iron pyrites, with rare splashes of copper. Formation lying very flat.

About half a mile above O'Heher's Bridge, over Tumut River, copper occurs; only slightly prospected.

Cooma Division.

Wambrook Station.—About 18 miles westerly from Cooma. On this station, about 5 miles north-west of the Gegedzerick Copper Mine, a copper lode was opened about 1878. Mr. G. F. Litchfield stated that it consists of quartz, with malachite and chalcopyrite, striking east and west in granite. The outcrop was not regarded as payable, but some rich specimens were obtained from the lode, which averaged about 3 feet in thickness.

Tumut Division.

Wyangle, parish Wyangle, county Buccleuch.—In Geary's private land copper ores in serpentine have been exposed in an open cut. Assay ($\frac{2}{4}\frac{2}{8}\frac{0}{0}$) yielded 13·64 per cent., and ($\frac{1}{0}\frac{6}{7}\frac{2}{2}$) 20·4 per cent. of copper, and 5 oz. 8 dwt. 21 grs. of silver per ton. A sample from Kiley's 50 feet shaft assayed ($\frac{2}{0}\frac{1}{7}\frac{4}{2}$) 12·30 per cent.

Kiandra Division.

Yarrangobilly, parish Yarrangobilly, county Buccleuch.—One of the well-known Yarrangobilly Limestone Caves bears the name of Copper Mine Cave, because of the proximity of a quartz-reef carrying a little copper ore; in fact, from Yarrangobilly village to the Caves, a distance of about 7 miles, copper ores occur, and numerous small prospecting holes have been sunk, but nothing of importance was proved.

Lower down Yarrangobilly Creek, about 4 miles above its junction with the Tumut River, Lobb's Hole Copper-mine is situated.

Inspector J. R. Godfrey reported a large body of porous ironstone 1¼ miles east of 39-mile peg, in village of Yarrangobilly, on Waugh's private land. Strike N. and S. About 300 yards distant shafts had been sunk in limestone on an old lead and copper show. Aided (P.B. $\frac{1}{0}\frac{6}{0}\frac{1}{2}$). Apparently resultless.

Three miles south-west of Yarrangobilly Caves House, Inspector H. Hooke reported (P.B. $\frac{2}{0}\frac{6}{7}\frac{8}{2}$) a well-defined copper-bearing lode apparently in a true fissure, traceable for over a mile. Ore rather poor, but amenable to concentration.

On west side of river, on continuation of Castle Cave lode, copper ore showing at surface, carbonates and possibly grey sulphide.

Batty's shafts, alongside main road, 1½ mile south of Yarrangobilly village. Limestone country. A few tons of carbonate ore sent for trial after concentration by sluice washing. Shafts sunk and abandoned some years ago.

Mount Fiery copper lode, M.L. 4, parish Yarrangobilly, county Buccleuch.—A large bluff of quartz in limestone ending against quartz-felsite. Quartz slightly cavernous and stained with copper carbonates. The quartz occurs irregularly in the limestone.

Further westward, on the same portion, a wide mass of shattered limestone with crystal-lined vugs of quartz, has been superficially tested to about 10 feet deep.

In the joints of the limestone stains of copper carbonate occur as a result of oxidation of chalcopyrite, which is discernible in the mass very leanly distributed.

The sinking has been carried out in detrital filling in a cavity in the limestone. Might be advisable to sink about 50 feet and crosscut to ascertain whether copper sulphides make more solid. Aid from Prospecting Vote subsequently granted on Inspector H. Hooke's report, for 100 feet of sinking and 100 feet of cross-cutting.

In mode of occurrence as regards quartz vugs and associated copper sulphides it resembles the Mount Felstead deposit near Cootamundra.

A sample chipped from the exposed faces yielded :—

No. 06-1109—Copper	.....	0·6 per cent.
Gold	.....	a trace
Silver	.....	4 dwt. 8 grs. per ton.

A few chains west a shaft was sunk about 1899, on a 2-inch vein of rich copper ore; in an outcrop 12 inches to 15 inches thick, striking N. 65° E. in limestone, and dipping N. 25 W. A few bags of rich ore were raised but not despatched; a sample from them yielded :—

No. 06-1110—Copper	.....	22·03 per cent.
Gold	.....	2 dwt. 4 grs. per ton
Silver	.....	13 ,, 21 ,, ,,

The outcrop is traceable between the abovementioned sites by the quartz in the limestone.

About 20 chains west of the west boundary of M.L. 4, between it and Yarrangobilly River, an old shaft and small trenches expose a quartz reef stained with copper carbonates on joint faces and cracks, and containing small cellular spaces after decomposed sulphides.

About 11 chains north of the latter is the deepest shaft on the reserve; sunk in a pipe-like mass of gossan in limestone to a reported depth of 60 feet. Traces of copper carbonate are visible in the gossan, which gives place below to massive cubical iron pyrites with a little copper sulphide. An average sample yielded :—

No. 06-1111—Copper	.....	4·62 per cent.
Gold	.....	10 dwt. 21 grs. per ton.
Silver	.....	5 ,, 10 ,, ,,

In M.P. 5, an ironstone outcrop in limestone was opened for silver about 1888, by two shafts. The ironstone has resulted from oxidation of cubical pyrites. Prills of native copper occur sparingly in it; might be useful as a flux if ever smelting is established in the vicinity. This applies also to a large bluff of gossan on the opposite side of gully about 15 chains distant N. 10 W., where old prospecting holes occur.

A sample of the cupriferous iron from the shafts yielded :—

No. 06-1114—Copper	.....	0·55 per cent.
Gold	.....	a trace.
Silver	.....	,,

Copper Mine Cave Old Shaft near S.E. corner of M.L. 8.—Two old shafts and an open cut in a quartz vein in limestone. The quartz is partly crystallised and slightly stained with copper carbonates. Thickness, about 5 feet.

Yarrangobilly Caves Reserve.

Castle Copper Lode., M.P. 1, parish Yarrangobilly, county Buccleuch Massive quartz lode; striko, N. 79 E, nearly vertical; thickness about 6 fe slightly stained with copper carbonates; copper pyrites also sparsely tributed. No work done beyond shallow trenches; not favourable for cop lode. Outcrop traceable towards river, obscured in other direction.

A sample broken from outcrop yielded:—

No. 06-1108—	Copper	0·8 per cent.
	Gold	a trace
	Silver	3 dwt. 6 grs. per ton

Another vein appears to junction with the above on the north side.

Local Refractory Materials used in the Manufacture of Firebrick.

From consideration of the composition of local refractory materials utilised at various centres (revealed in the following analyses), it would appear that almost any silicious grit or sand with just sufficient clay to bind it, will withstand the melting temperature of copper (2,000° F., or 1,093 Cent. according to Dr. Peters) long enough to serve a useful purpose in smelting furnaces far removed from supplies of the ordinary market firebrick. The composition of some western bricks brings them into a class with pure silica bricks, as the cementing clay is largely silica. In some cases the materials are crushed; in others, they are used in the extemporised pug-mill just as obtained; fragments and pebbles of quartz—as at Girilambone—are frequently as large or even larger, than marbles; none the less, the resulting bricks answer all their requirements sufficiently well to enable the imported article being dispensed with, and thus ensuring a considerable saving in carriage. Cost of transit was a most serious item in the early days of the Cobar copper-field. The first firebricks transported from Sydney to Cobar are reported to have cost £50 per thousand. Later they were manufactured locally from a clay brought from Tindarey—about 36 miles northerly from the mine—by the copper teams returning from Bourke for loading. Subsequently a reward was offered for the discovery of suitable clay at a more convenient distance, and a site was selected about 6 miles north-westerly from the mine. This clay, of which an analysis is given, was used in equal parts with crushed quartz and fine-grained sandstone obtained near by. From this mixture firebricks were manufactured, until the use of refractory material ceased on the advent of water-jacketed furnaces in 1893–4.

Fireclays.—Local clays are usually turned to account for manufacture of firebrick, ordinary brick, and mortar or fettling, not because they are the most suitable or satisfactory, but on what Peters terms "the sound business principle of always employing the cheapest material which will fill the requirements of the case." ("Principles of Copper-smelting," 1907, page 502.) A principle which naturally applies strongest where long carriage enhances cost of the better article.

It has, moreover, been found that some of the local substitutes withstand best alternating expansion and contraction, consequent on frequent cessation of smelting.

Analyses of local substitutes are given wherever used, as a guide to the uses of theoretically inferior material.

It has been found in practice that the silica required for slagging the ferrous oxide of the converter charge, is best supplied in the form of lining, ores of a silicious character being used for this purpose. Auriferous and argentiferous linings repay cost of wastage. Barren linings add to cost and, as Professor Douglas points out, "The extra cost of the material, plus the cost of replacing it, involved in the treatment of lower, instead of high grade matte by some other method, or by changing the furnace mixture. If on the other hand, the lining consists of gold or silver or copper ore, then rapid consumption as lining may prove the cheapest way of smelting them." [1]

[1] Trans. Inst. Mining and Metallurgy, viii, 1899–1900, page 22.

Analysis of clay from 6 miles north-westerly from Cobar, formerly used with crush and sandstone in the manufacture of firebricks for the reverberatory copper fu

Chemical Composition.

No. $\frac{2091}{68}$	Moisture at 100° C	1·75
	Combined water	4·54
	Silica (SiO_2)	65·82
	Alumina (Al_2O_3)	20·74
	Ferric oxide (Fe_2O_3)	1·45
	Manganous oxide (MnO)	trace
	Lime (CaO)	·10
	Magnesia (MgO)	·97
	Potash (K_2O)	4·58
	Soda (Na_2O)	·07
	Phosphoric acid (P_2O_5)	minute trace
	Sulphur trioxide (SO_3)	·19
		100·21

Both Waratah and Lithgow firebricks were used at the commence smelting at Girilambone, but a locally-manufactured article sup both. The life of the latter was satisfactory, lasting about eight in the hottest parts of the furnaces. It consists essentially of about cent. silica in the form of coarse quartz, gravel and sand, with just clay to bind it tolerably well. It undergoes no preparation prior to pu The following analysis was made of the clay separated by washing f quartz gravel and sand :—

Chemical Composition.

No. $\frac{2221}{68}$	Water	15·02
	Silica (SiO_2)	50·50
	Alumina (Al_2O_3)	22·15
	Ferric oxide (Fe_2O_3)	6·21
	Ferrous oxide (FeO)	2·46
	Manganous oxide (MnO)	absent
	Lime (CaO)	0·30
	Magnesia (MgO)	1·04
	Potash (K_2O)	2·32
	Soda (Na_2O)	·27
	Phosphoric acid (P_2O_5)	·17
		100·44

Mount Hope firebricks are made wholly from a sandy clay obtain depth of about 60 feet, at a distance of 7 miles from Mount Ho discovered in sinking a well for water. Most refractory firebrick from it direct after crushing. The clay is of Tertiary age, and conta angular quartz pebbles. The material was panned off, and the per of quartz determined, viz., quartz and sand, 68·8 per cent. Followir analysis of the fine-clay settlings from the pannings :—

Chemical Composition.

No. $\frac{2232}{68}$	Moisture at 100° C.	·61
	Combined water	7·33
	Silica (SiO_2)	63·00
	Alumina (Al_2O_3)	25·75
	Ferric oxide (Fe_2O_3)	1·24
	Manganous oxide (MnO)	trace
	Lime (CaO)	·40
	Magnesia (MgO)	trace
	Potash (K_2O)	1·69
	Soda (Na_2O)	·14
	Phosphoric acid (P_2O_5)	trace
	Sulphur trioxide (SO_3)	·10
		100·26

For analysis of the unwashed Mt. Hope clay see page 215.

The Waratah (near Newcastle) firebricks are so well and favourably known in local smelting works that this section would be incomplete without an analysis of the shale principally used in their manufacture. It belongs to the Permo-Carboniferous Coal Measures of the Newcastle Coal-field :—

Chemical Composition.

No. $\frac{1041}{98}$—Moisture at 100° C.	2·88
Combined water	·86
Silica (SiO_2)	65·40
Alumina (Al_2O_3)	19·01
Ferric oxide (Fe_2O_3)	5·36
Ferrous oxide (FeO)	absent
Manganous oxide (MnO)	minute trace
Lime (CaO)	·05
Magnesia (MgO)	·07
Soda (Na_2O)	·29
Potash (K_2O)	·35
Phosphoric acid (P_2O_5)	absent
Sulphur trioxide (SO_3)	·13
	100·40

Fireclay used at the Burraga Smelting Works—obtained about 2 miles distant.

Chemical Composition.

No. $\frac{1304}{98}$—Moisture at 100° C.	·25
Combined water	1·57
Silica (SiO_2)	90·52
Alumina (Al_2O_3)	4·71
Ferric oxide (Fe_2O_3)	1·91
Manganous oxide (MnO)	trace
Lime (CaO)	·34
Magnesia (MgO)	·30
Potash (K_2O)	·63
Soda (Na_2O)	.10
Phosphoric acid (P_2O_5)	·02
Sulphur trioxide (SO_3)	trace
Organic matter	,,
	100·05

Locality—Eskbank—Mixed clays used in the manufacture of firebrick at Farrant's Brick Works, Eskbank. Formerly used at the Great Cobar Syndicate's Copper Refinery

Chemical Composition.

No. $\frac{605}{98}$—Moisture at 100° C.	·40
Combined water	3·12
Silica (SiO_2)	88·80
Alumina (Al_2O_3)	5·74
Ferric oxide (Fe_2O_3)	1·12
Manganous oxide (MnO)	trace
Lime (CaO)	·20
Magnesia (MgO)	trace
Potash (K_2O)	·50
Soda (Na_2O)	·14
Phosphoric acid (P_2O_5)	·09
Sulphur trioxide (SO_3)	trace
	100·11

As a guide to the localities of refractory materials suitable for the m facture of firebrick, the following analyses are extracted from the An Reports of the Department of Mines, with the remarks by the Departm Analyst, Mr. J. C. H. Mingaye :—

Locality—County Cumberland. (?)—(Ann. Rept., 1889, p. 46.)

Moisture at 100° C	1·45
Combined moisture	3·44
Silica	80·79
Alumina	13·20
Oxide of iron	·86
Oxide of manganese	nil
Lime	·15
Magnesia	traces
Alkalies, loss, &c.	·11
	100·00

"Remarks.—This is an excellent description of fireclay, and can be cla as equal, if not superior, in quality to the English imported article. should prove useful for the manufacture of firebricks, tiles, &c., and per might be utilised for the manufacture of crucibles. The percentage of s is higher than that usually present in the English fireclays."

Locality—Narrabeen, near Manly.—(Ann. Rept., 1191, p. 60.)

Silica	89·45
Alumina	10·40
Oxide of iron	trace
Lime	,,
Magnesia	,,
Potash	·32
Soda	·36
Titanic acid	trace
	100·53

"Remarks.—The clay was finely ground, damped with water, and fashi into two small bricks with sharp edges, which were, after drying, submi to a severe heat in an assay furnace. The bricks were solid and burnt w the sharp edges being retained. I am of opinion that this clay is suitable the manufacture of a good description of firebrick."

Shale with Plant Impressions from Parramatta [Wianamatta Series.—J. E. C.].—(An Rept., 1891, p. 61.)

Moister at 100° C.	1·05
Combined water	2·35
Ferric oxide (Fe_2O_3)	·79
Ferrous oxide (FeO)	nil
Manganous oxide (MnO)	trace
Alumina (Al_2O_3)	8·81
Silica (SiO_2)	85·35
Lime (CaO)	nil
Magnesia (MgO)	·43
Potash (K_2O)	1·48
Soda (Na_2O)	trace
Phosphoric acid (P_2O_5)	,,
Sulphuric acid (SO_3)	nil
Titanic acid (TiO_2)	trace
	100·26

"Remarks.—Experiments were conducted as to the fire-resisting proper of this clay. Bricks were made of it and burnt, also with the additio

20·35 per cent. of silica. From the results obtained, and on comparing analysis made with those of British fireclays, I am of opinion that this is suitable for the manufacture of firebrick."

Locality—Towrang. White Felspathic Sandstone Rock.—(Ann. Rept., 1891, p. 61.)

Moisture at 100° C. / Combined water	4·78
Silica	80·68
Alumina	13·86
Oxide of iron	·51
Oxide of manganese	nil
Lime	·15
Magnesia	trace
Titanic acid	,,
Potash	,,
Soda	,,
	100·18

"Remarks.—This is an excellent description of fireclay, and from the large percentage of silica present, should prove very refractory."

Locality—Forster (?), Cape Hawke, North Coast.—(Ann. Rept., 1892, p. 57.)

Moisture at 100° C.	2·88
Combined water	5·95
Silica (SiO_2)	70·57
Alumina (Al_2O_3)	16·27
Ferric oxide (Fe_2O_3)	1·07
Ferrous oxide (FeO)	nil
Manganous oxide (MnO)	,,
Lime (CaO)	·13
Magnesia (MgO)	·38
Potash (K_2O)	2·20
Soda (Na_2O)	·27
Phosphoric anhydride (P_2O_5)	nil
Sulphuric anhydride (SO_3)	·41
Titanic acid (TiO_2)	nil
Organic matter	,,
	100·13

"Remarks.—Bricks made from this clay and submitted to a high heat in the coke assay furnace showed no fusion, the sharp edges being retained. The bricks appear to be of excellent quality."

Locality—Aberdare Coal-mine, Swan Bay, Richmond River. Light, grey-coloured clay, 6 feet thick.—(Ann. Rept., 1892, p. 59.)

Moisture at 100° C.	2·37
Combined water	6·07
Silica	65·17
Alumina	21·89
Ferric oxide	·19
Manganous oxide	nil
Lime	·50
Magnesia	1·03
Potash	2·02
Soda	1·16
Phosphoric acid	trace
Sulphuric acid	nil
Titanic acid	,,
Organic matter	,,
	100·40

"Remarks.—Several small bricks, with and without the addition of Sili were made of this clay and carefully dried, then submitted to a high heat the coke assay furnace, with the result that no fusion took place, the sh edges being retained. The bricks had the appearance of being excelle firebrick." [Several other analyses of this shale were made with approxim results.—J.E.C.]

Locality—Heathcote, Southern Line.—(Ann. Rept., 1893, p. 52.)

	(749)	(750)	(751)
Moisture at 100° C.	.....	1·04	1·76
Combined water	4·57	3·33	5·56
Silica	74·48	78·31	72·41
Alumina	18·93	15·29	16·70
Ferric oxide	·39	·74	·28
Manganous oxide	trace	trace	1·00 (ferrous oxide.)
Lime	,,	,,	·45
Magnesia	·72	,,	·36
Potash	1·58	.....	1·45
Soda	nil	1·29	
Phosphoric anhydride	trace	trace	trace
Sulphuric acid	,,	nil	,,
Titanic acid	,,	,,	,,
	100·59	100·00	100·00

Locality—Port Stephens. Gritty White Clay.—(Ann. Rept., 1893, p. 53.)

Moisture at 100° C.	1·84
Combined water	4·36
Silica	74·57
Alumina	16·47
Lime	·17
Magnesia	trace
Ferric oxide	1·18
Manganous oxide	trace
Potash	1·03
Soda	nil
Phosphoric acid	nil
Sulphuric acid	trace
Titanic acid	nil
	99·62

Locality—Pyrmont, Sydney. Sandstone used as freestone. Hawkesbury (Triassic) Series (Ann. Rept., 1894, p. 65.)

Moisture at 190° C.	·45
Combined water	1·40
Silica	87·60
Alumina	8·53
Ferric oxide	·03
Ferrous oxide	·10
Manganous oxide	nil
Lime	·60
Magnesia	·29
Potash	·28
Soda	·45
Phosphoric acid	trace
Sulphuric acid	·11
Chloride of sodium	trace
Soluble silica	·40
	100·24

For additional analyses, see Cadia and Gulf Creek Mines, pages 132 and 3

Limestone.

nestone Flux, Cobar District.—Limestone is not now used at the · Copper Mine. When formerly required it was obtained from the ·kilns about 26 miles distant towards Nymagee. A geological ination has not yet been made of the locality, but from a few specimens ·sils from the limestone it appears to be of Upper Silurian age.

ıall concretionary segregated nodules of magnesian limestone occur ıionally in the slates and sandstones in the immediate vicinity of Cobar, n too limited quantity to be of any value.

ıe composition of the latter has been determined in the following ysis :—

Chemical Composition.

o. $\frac{1}{1}\frac{9}{9}\frac{2}{2}$.—Moisture at 100 C	·31		
Combined water	1·10		
Silica (SiO_2)	19·08	Insoluble in acids. = 27·33%	
Alumina (Al_2O_3)	6·61		
Magnesia (MgO)	·62		
Potash (K_2O)	1·02		
Soda (Na_2O)	trace		
Calcium carbonate ($CaCO_3$)	39·42	Soluble in acids. = 71·08%	
Magnesium carbonate ($MgCO_3$)	30·17		
Ferric oxide (Fe_2O_3)	1·49		
Alumina (Al_2O_3)	trace		
Phosphoric acid (P_2O_5)	minute trace		
Sulphur trioxide (SO_3)	absent		
	99·82		

considerable outcrop of encrinital limestone occurs about 10 miles from ıgee Copper Mine, on the Bobadah-road. It is probably of Upper ian age, though no identifiable fossils have yet been obtained. It is of lent quality as will be seen by the following partial analysis :—

. 3460.—Gangue (sand)	1·76	
Calcium Carbonate $CaCO_3$)	97·39	CaO 54·54%
Alumina and ferric oxide	·41	
Magnesia	·20	
	99·76	

mall quantity of iron pyrites present.

ıe to the Anaconda, Big Ben, and Melrose Copper Mines, near ıse, a thin superficial deposit of pulverulent carbonate of lime occurs, ıg on the slates of the locality over a small area. It appears to have ted from local deposition. Its chemical composition has been determined llows :—

No. $\frac{2}{3}\frac{3}{3}\frac{1}{1}$.—Moisture at 100° C	·45
Organic matter	·73
Calcium carbonate ($CaCO_3$)	92·67
Magnesium carbonate ($MgCO_3$)	1·05
Silica (SiO_2)	3·34
Ferric oxide (Fe_2O_3) / Alumina (Al_2O_3)	1·50
Sulphur trioxide(SO_3)	nil
Phosphoric acid (P_2O_5)	trace
	99·74

Limestone used as flux at Captain's Flat (Lake George Mines) obtai about 3 miles distant, on the road towards Bungendore—Mine assay.

Lime carbonate ($CaCO_3$)	99·08	per cent.
Ferrous oxide (FeO)	·06	,,
Silica (SiO_2)	·86	,,
	99·92	

The general average of the flux is from 96 to 98 per cent.

For additional analyses of limestone flux used at Cadia, Mount Bul Queen Bee, Gulf Creek, see pages 131, 158, 260, and 325. For ot localities—Cangai, Attunga, Warialda, Bredbo, Mingary, see pages 182, 2 315, 332, 376, and 390.

APPENDIX I.

Local Customs Smelting Companies.

Great Cobar, Limited.

The Refinery Works,
Lithgow, N.S.W., 1st January, 1907.

All Communications to be addressed: "The General Manager."

Tariff for Purchase of Ores.

All previous tariff notices are hereby cancelled.

1. **Smelting Charge.**—20s. per ton of 2,240 lb. dry weight for parcels weighing not less than 5 tons. Under 5 tons the smelting charge will be 25s. All parcels weighing less than 1 ton will be charged as 1 ton, and deductions will be made as if the parcel weighed 1 ton. No weighing, sampling, or assaying charges will be made on any parcel, except as per clause 25.

Deductions per ton of 2,240 lb. dry weight and payment for metals as follows:—

2. **From Gold.**—Deduct first pennyweight, and pay at the rate of £3 15s. per oz. for the balance.

3. **From Silver.**—First 3 oz. deducted 1s. 9d. per oz. paid for the balance.

4. **From Copper.**—Deduct one unit on wet assay from containing up to and including 10 per cent. copper, one and a quarter unit from 10 per cent. and including 20 per cent., one and a half unit from 20 per cent. and including 30 per cent., and two units from ores containing over 30 per cent. copper. Copper to be paid for at the company's latest quotation for standard copper, less 2s. 6d. per unit, such quotation being the one received during the week in which the sampling is finished.

5. **All ore to be delivered at the works free, but it can be arranged that freight may be charged to the works and afterwards be deducted from account sales.**

6. Before receiving any ore for treatment, we require to be supplied with a fair representative sample of the ore (weighing not less than 50 lb.) which it is proposed to despatch to us. If analysis shows that the sample contains arsenic, bismuth, antimony, lead, or zinc, we are not prepared to buy such ore; and we also wish to make it clear that ore despatched to us must be according to sample in regard to being free from the metals named above, or we will refuse to take delivery of it, or if delivery has been taken and any of the above objectionable metals are found in the ore on sampling we will not accept the ore as per clause 25.

7. **Railage and all charges on preliminary samples must be prepaid, otherwise we will not accept delivery of same.**

Method of Sampling Ore.

8. **The company does not guarantee to keep parcels separate from others after weighing and sampling, and parcels once mixed cannot be claimed by seller. The portion that is drawn for sampling as described in clause 11 is always retained until assays are agreed, and when occasion requires this portion can be re-sampled on condition named hereafter (clause 13). When the company's assay is taken without checking (clause 17) the portion referred to is kept for one week after account sales have been posted, and is then sent to the furnaces.**

9. **Tare of bags and actual weight of moisture to be deducted from weight of parcel.**

10. **Moisture sample to be taken at the commencement of the weighing and sampling operation.**

11. **The sample is made by taking each fifth or tenth bag, or if the ore is in bulk from each fifth or tenth shovelful.**

12. **To gain accuracy of results, the portion so drawn is first divided into two equal parts, which are called "first" and "second" samples, each of these parts is considered as a separate sample, are separately crushed finer if necessary, and each sample is divided into three parts, to be disposed of as follows:—**

A.—**One of each is to be retained by the company for assay.**

B.—One of each is to be placed at the disposal of the seller.

C.—One of each is to be sealed with company's seal, and if representative is prese with his seal also. These are to be considered as umpire samples, which remain in t care of the company until it is sent to the agreed on umpire.

13. In the event of the assay results of the "first" and "second" samples n comparing closely, either party has the option, subject to clause 8, of calling for a r sample at his own expense, but such call must be made *prior to exchange of assays*, an the difference in the assay result upon which the demand is based must be declared b the party calling for the re-sample.

14. Should a re-sample take place the results of all previous samplings will becom null and void.

15. The actual cost from any variation from the above methods of sampling or assayin made at the seller's request is to be borne by the seller.

16. The determination of gold and silver to be by fire method, and for copper, b either the iodide method or electrolytic copper essay. Results obtained by cyanide wil not be accepted. Seller's attention is drawn to this point, and in the case of an umpir assay, the assayer making the assay is required to certify as to the above methods being followed in determining the gold, silver, and copper in the sample.

17. The seller is given the option of accepting the company's assay results as final without checking, or of settling on the mean of his and the company's assay, subject to the limit of difference named below.

18. The seller must declare before or at the sampling if he wishes a seller's sample, otherwise the company's assay alone is to be taken as the basis of settlement.

19. If the seller takes the seller's sample he must produce the assay results of both "first" and "second" samples, when settlement will be made on the mean of the company's assay of "first" and "second" samples and the mean of the seller's assay of "first" and "second" samples, subject to limits of difference and arrangements for umpiring.

20. If the seller does not wish to assay his samples they must be returned to the company with the seals unbroken before the company declares its results.

21. If the respective mean results of "first" and "second" samples agree within 1 dwt. gold, 2 oz. of silver, or one quarter of 1 per cent. of copper, the mean of buyer's and seller's assays are taken for settlement.

22. When greater differences occur they may be divided by mutual agreement, but either party may demand the umpire's samples be submitted for assay to an umpire mutually chosen. Then the average of the two nearest assays of the three is to be accepted as final by both sides.

Example :—

	First.	Second.	Mean.
D—Seller's assays, copper	10·0%	11·0%	10·5%
Buyer's assays, copper	10·5%	10·7%	10·6%
Mean assay for basis of settlement			10·55%
	First.	Second.	Mean.
E—Seller's assays, copper	10·0%	11·0%	10·5%
Buyer's assays, copper	10·7%	11·1%	10·9%
Umpire's assays, copper	10·3%	10·9%	10·6%
Mean of umpire's assay and nearest to umpire for settlement			10·55%

23. The cost of the umpire's assay is to be borne by the party whose assay is further from that of the umpire.

24. The preliminary samples are not kept by the company, they being samples t determine in the first instance if the ore is suitable.

25. Ore found on sampling to contain lead, arsenic, antimony, bismuth, or zinc, in an proportion, the company will not accept, and the sender will be required to pay for a actual expense incurred in unloading, sampling, and assaying such ore.

26. The seller or his representative may be present at the unloading, weighing, an sampling of his ore, provided written notice of his intention to do so is received previou to arrival of ore, but if any extra expenses are incurred by reason of delay so caused they must be borne by the seller.

27. When despatching ore in bulk or in bags, the company must be notified of truc numbers, and the sender must state the number of bags if the ore is sent bagged.

28. Address all correspondence to "The General Manager," to save the delay whic may arise through letters being addressed by name.

English and Australian Copper Smelting Works, Waratah, near Newcastle.

29. Consignors are reminded that they must load the railway trucks to within 5 per cent. of their marked capacity to get the lowest freight charges from the Railway Department, and to declare the value of the ore. Consignments of ore should be addressed and ticketed "Great Cobar, Limited, Eskbank." If the value is not known, consign as "crude ore under £20 per ton"; but the seller must pay any additional freight if the ore comes under the higher railway rates for ore.

30. The weight delivered over the company's scales is to be accepted as final, whether seller or his representative is present or not.

G. H. BLAKEMORE, General Manager.

English and Australian Copper Company, Limited. Established 1851.

Branch Works: Waratah and Newcastle, New South Wales. Chief Office in Australia Port Adelaide, South Australia. London Office: 17, Gracechurch-street, E.C.

This company purchases copper ores and mattes in any quantities, paying for the copper contained, as shown by assay, at 1s. per unit less than the latest telegraphed price of standard copper in London, "spot" or "three months" at the company's option.

When the ore does not contain impurities (such as arsenic, bismuth, &c.), and the company considers the copper of sufficiently good quality to bear its "P.C.C." brand, a special allowance of 6d. per unit (£2 10s. per ton of copper) will be made.

The charge for smelting varies, according to the nature of the ore and other circumstances, but does not exceed 45s. per ton of 21 cwt., except in the case of especially refractory ores.

No charge will be made for weighing, sampling, or assaying when the parcel weighs 12 cwt. or over.

All purchases of ore (and matte) are made subject to the following conditions, unless other arrangements are agreed upon previous to arrival of the ore at the works:—

1. Ores are purchased delivered at the company's works, Waratah, N.S.W., but sellers can arrange for railway carriage or freight to be paid by the company, and deducted in account sales.
2. Three samples will in all cases be taken; one to be retained by the seller, one by the company, and the third to be sealed and kept as a reference sample.
3. The seller or his representative may be present at the weighing and sampling, provided notice of his intention to attend is received before the ore has been sampled.
4. When the seller's assay differs from that of the company, the difference will be divided, provided it does not amount to more than 1 per cent. of copper; if greater, the reference sample will be submitted to an independent assayer (to be selected by agreement), and payment made on the middle assay of the three.
5. Ores, &c., are weighed 21 cwt. to ton, as customary in the copper smelting business.
6. The company pays for the whole of the copper contained in the ore; as shown by fire assay. When seller's assays are made by wet method the following deductions will be made from the results so obtained:—

Ores assaying	12 per cent. or under		deduct	1	per cent.
,,	,, over 12 and under 20	per cent.,	,,	1¼	,,
,,	,, 20 ,,	,, 35 ,,	,,	1½	,,

7. In the case of parcels less than 21 cwt., a charge of 20s. will be made for sampling and assaying, and a similar charge of 10s. in the case of parcels of 21 cwt. and less than 42 cwt.
8. The date upon which the sample is taken will be considered to be the date of purchase of the ore.
9. Payment by cheque immediately assays are agreed.
10. Other conditions as usual in the copper smelting business.

The company reserves the right to make special terms and arrangements for large parcels or regular consignments and to refuse ores containing an extraordinary quantity of bismuth or other metal which affects the quality of ore.

Any further information required will be supplied on application to this office; to the Manager, Port Adelaide, S.A.; or to the company's agent in West Australia.

All previous tariffs are cancelled.

THOMAS JOHNSON, Manager, New South Wales Branch.

Waratah, N.S.W., July 13, 1908.

The Melbourne and Great Northern Smelting Company, Limited.

Works: Waratah, near Tighe's Hill, Newcastle, New South Wales.

Tariff for Copper Ores and Mattes.

The company will purchase copper ores and mattes in any quantities, and act as Customs smelters, on the following terms:—

Delivery at works, Tighe's Hill, Newcastle, New South Wales. Consignors can arrange to have railage or sea freight paid by works and deducted from returns.

Weights.—The net dry weight as shown by the company's tested scales, at the rate of 21 cwt. to ton, will be taken as basis for payment.

Moisture samples will be taken at time of weighing and the moisture ascertained in usual way.

Tare of bags.—When ore is in bags, these will be weighed on same bridge, in order to ascertain the tare of bags to deduct.

Assay samples according to the ore.—Sampling will be done by quartering down the whole or a fraction of each parcel, by taking a specified number of bags from the lot, and quartering these. This may be done automatically or by hand. The final sample will be divided into three equal and similar proportions—one for buyer, one for seller, and one will be sealed up for umpire.

Agreement of assays.—For copper differences of 1 per cent., for gold differences of 1 dwt., and for silver differences of 1 oz., will be split. When differences exceed these limits, the assay will be referred to umpire. The agreed assay shall be the mean of umpire's result, and that nearest his result. The party whose result is furthest from umpire will pay cost of umpire assays.

Deduction from wet assay of copper.—When copper is determined by wet methods, the following deductions will be made:—

Ores assaying under 10 per cent.	.....	1 unit.
,, ,, over 10 and under 20 per cent.	.....	1½ units.
,, ,, over 20 and under 35 per cent.	.....	1½ units.

Gold and silver assays, when necessary, will be charged 5s. each, and made by fire and scorification methods.

Bags.—Used bags will be returned to customers free of railage.

Payment for gold and silver will be made when either of both are present in sufficient quantities to pay for cost of extraction.

If the ore, which is consigned to this company, contains no impurities such as arsenic, bismuth, tin, lead, or antimony, &c., and can be refined into a first-class copper, an additional allowance of 6d. per unit will be made to the consignor.

Impurities.—Ores found to contain deleterious impurities in sufficient quantities to impair the value of the resulting metal, will be penalised in proportion to quantities contained.

Representation.—All weighing and sampling can be witnessed by seller's representative.

The ore will be weighed and sampled as soon as possible after arrival at the works. Should the consignors or representatives wish to be present at the weighing and sampling notice must be given, and then an appointment will be arranged.

The date on which the ore is weighed and sampled will be considered the date of purchase.

Returning charge will be £2 5s. per ton of dry ores, weighed as specified higher up (Clause 3). Lower terms may be arranged for specially suitable ores in large quantities.

Price basis for copper.—The latest cabled price before, or on sampling day, will be taken as basis price of copper. Unless otherwise arranged, the price of forward standard copper will be taken, less a deduction of 1s. 3d. (one shilling and threepence), per unit.

Discharging and sampling will be charged for at 1s. 6d. per ton.

Assaying.—No charge will be made for assaying for copper.

Draftage.—No draftage deduction will be made.

Payments will be made by cheque as soon as weights and assays are agreed upon.

The company reserve themselves the right to refuse ores of unsuitable nature, or to vary this tariff for specially good or bad smelting ores. In such case due notice will be given seller, in order to avoid expense to him.

The company will receive and examine parcels of ore of about 10 lb. weight from intending customers, and will advise them free of charge as to the returning charges for similar ores in larger lots.

All communications to be addressed to the Manager, Melbourne and Great Northern Smelting Company (Limited), Tighe's Hill, Newcastle, New South Wales.

Blayney Copper Mines and Smelting Company, N.L.

Mines and Works, Blayney, New South Wales,
2 September, 1907.

Head Office : 375 Collins-street, Melbourne ; Sydney Office : Australasia Chambers, Martin-place.

All previous tariff notices are hereby cancelled.

Smelting charge.—Twenty-five shillings per ton. Parcels weighing less than 1 ton will be charged, and deductions made as if the parcel weighed 1 ton.

Weighing and sampling.—A uniform charge of £1 will be made on all parcels irrespective of weight. Metal deductions and prices at per ton of 2,240 lb. net dry weight.

Copper.—From ore assaying by wet method :—

Up to 10 per cent.								Deduct	1¼ units.
Over 10 per cent. up to and including 15 per cent....								,,	1½ ,,
,,	15	,,	,,	,,	20	,,	...	,,	2 ,,
,,	20	,,	.....					,,	2½ ,,

Price.—Net copper contents as determined above to be paid for at the latest London quotation for standard copper, "spot" or "three months" at the company's option, less £5 6d. per unit, such quotation being the average for the week in which sampling is finished.

Gold.—Deduct 2 dwt. Balance paid for at 80s. per ounce.

Silver.—First 3 ounce deducted, balance said for at 1s. 6d. per ounce.

Penalties :—

Arsenic and, or antimony, 2s. 6d. per unit.

Zinc, up to 5 per cent., nil ; over 5 per cent., 1s. per unit.

Lead, up to 5 per. cent., 1s. per unit. Ores containing more than 5 cent. lead will not be purchased.

Bismuth.—Ores containing bismuth will not be purchased.

Payment.—Cash on agreement of assays.

Special notice.—Before sending parcels to the works, producers should forward a representative sample (about 50 lb.), and it must be clearly understood that the parcel will be up to sample as regards freedom from bismuth and lead (above 5 per cent.). Should the parcel prove to contain bismuth, and (or more than) 5 per cent. lead, the company will refuse to accept delivery.

Conditions of purchase.

1. **Ores** will be purchased, freight paid, at the company's works, Annandale Siding, near Blayney, New South Wales. By previous arrangement, rail freight will be advanced by the company, and amount deducted on account sales.

2. **Weighing and sampling** at the company's works.—The seller, or his representative, may be present, provided that written notice of his intention to do so is received previous to arrival of ore. The company, however, guarantees correct weighing and sampling in all cases.

3. **All ores** weighed at 20 cwt. to the ton of 2,240 lb. ; weights, as delivered over the company's scales, to be final.

4. **Three samples** will be taken : one for the buyer, and one for the seller, and the third to be sealed and kept as a reference sample. Differences of more than one quarter of 1 per cent. copper, 1 dwt. gold, or 2 oz. silver, require that the reference sample shall be assayed. Average of reference assay and one nearest to it will be taken as basis for settlement. The party whose assay is farthest from the reference to pay the cost of the latter.

5. **Either party** has the option of calling for a re-sample prior to exchange of assays. Should a re-sample take place, the results of all previous samplings will become null and void.

6. **The determination** of gold and silver to be by fire method, and for copper by either the iodide method or electrolytic copper assay. Results obtained by cyanide will not be accepted. Seller's attention is drawn to this point ; in the case of an umpire assay, the assayer is required to certify as to the above methods being followed in determining the gold, silver, and copper in the sample.

7. **If no word** is received from the seller previous to assaying, the company's assay results are to be final.

8. If the seller does not wish to assay his samples they must be returned to the compa with the seals unbroken before the company declares its result.

9. The company does not guarantee to keep parcels separate after weighing a sampling, and parcels once mixed cannot be claimed by seller.

10. All other conditions as usual.

Consign to Annandale Siding.

Advise Company of truck Nos., number of bags, and distinguishing marks (if any).

F. L. PIDDINGTON, General Manager.

The Electrolytic Refining and Smelting Company of Australia (Limited).

Works in Process of Construction.

Port Kembla, N.S.W.,
21 April, 1908.

The plant will consist of a tank-house, a furnace refinery, silver and gold refinery, smelter and converter plant, and all other buildings necessary for a plant of th description. The electrolytic plant will consist of 360 tanks, approximately 10 ft. 3 ft. 6 in. x 3 ft. 6 in., and will be capable of treating between 35 and 40 tons of blist copper per day.

The furnace refinery will consist of two 100-ton reverberatory copper-refini furnaces, equipped with mechanical casting wheels, capable of casting 25 or 30 tons copper per hour.

The smelter will consist of reverberatory smelting plant capable of treating 150 to of ore per day, and the converter plant will consist of two 10 ft. 6 in. x 7 ft. 6 in electrically operated converters. This plant will be capable of converting 60 tons of per cent. copper matte per day.

The power-house will consist of two 550 k.w. electrolytic generators at 150 volts, tw 150 k.w. power generators at 250 volts; one turbo-blower for converters, running 8,500 revolutions, and capable of compressing 3,500 cubic feet of air against 15 l pressure. This power-plant will also contain air-compressors compressing to 30 lb. air-pressure, and to 80 lb.; the latter for operating air lifts to be used throughout th plant.

All transportation between buildings will be conducted by means of electr locomotives.

The feeding of the reverberatory furnace will be automatic. The boiler-house wi consist of five large Babcock and Wilcox boilers, complete with all modern appliance This plant will be absolutely free of all labour, as the coal received on a high line discharged into a bin, which directly feeds into the hoppers of the automatic stokers.

The load factor of our power plant will be about 98 per cent., and it is expected th our power will be generated at ½d. per k.w. hour.

The plant will give employment to about 250 men, and we expect to begin operation in the smelting department by December of this year.

Provision is also made for the installation of a blast furnace, which will be built if th Government will make wharfage rates which will enable us to carry into this port lo grade copper ores from the Australian States, and from foreign ports.

The plant will use not less than 14,000,000 gallons of water per year, and the succes of the plant is in a large manner dependent on an ample water supply. At the price w pay the Government for water the Government will derive 1s. 6d. on the sale of wat for every ton of material treated in this plant.

APPENDIX II.

SOUTHERN MINING DISTRICT—*Nowra Division.*

Ettrema Lodes (*see* page 345).

The highest deposit in Ettrema Creek bed, though not the highest of the series, consists of a bed of quartzite impregnated with mispickel—chiefly zinc-blende, galena, and chalcopyrite. The actual thickness is not exposed, but several feet are revealed. A representative sample chipped from the exposed faces and broken material yielded :—

No. 08–2589—	Arsenic	17·37 per cent.
	Zinc	10·55 ,,
	Lead	6·20 ,,
	Copper	1·42 ,,
	Gold	a few grains per ton.
	Silver	8 oz. 13 dwt. 3 gr. per ton

A lower deposit further down the creek forms the apex of an anticlinal fold, with a pitch N. 20° W. The exposed thickness is about 25 feet, but the base is not visible. Zinc blende predominates in this deposit. A representative sample from the face and from broken material from a small opening yielded :—

No. 08–2590—	Zinc	28·12 per cent.
	Lead	8·90 ,,
	Arsenic	3·77 ,,
	Copper	1·60 ,,
	Gold	a few grains per ton.
	Silver	9 oz. 14 dwt. 22 gr. per ton.

From a still lower deposit, apparently cutting across the bedding, a representative sample yielded :—

No. 08–2591—	Zinc	22·79 per cent.
	Copper	0·15 ,,
	Lead	none detected.
	Gold	a few grains per ton.
	Silver	18 dwt. 12 gr. per ton.

It is apparent that, as is usually the case, the silver is associated with the lead ore.

It is further evident that the principal value of the deposits is in zinc. Doubtless a considerable proportion of zinc-blende could be roughly classified to commercial grade, but the great bulk would require both concentration and separation.

Possibly a double process may be devised by which both zinc and arsenic may be successively sublimed as commercial products, leaving a cupriferous residue, freed from these highly injurious associates.

The silver-lead ore could also be roughly classified into a smeltable product, leaving a residue so small as to be negligible in the other processes.

The composition of the best limestone is shown in the following partial analysis :—

No. 08–2588—	Carbonate of calcium	86·07
	Carbonate of magnesium	1·13
	Ferric oxide and alumina	2·16
	Insoluble	10·44
	Moisture at 100° C.	·23
		100·03

Talwong Mine (*see* page 367). Examined 27 July, 1908.

The Talwong lode varies from a few inches to over 8 feet in thickness, and dips apparently S. 65° W. at 30°. Where it traverses rigid quartzite strata it makes strongest, the pinches naturally occurring in the more yielding slates.

It outcrops on both sides of a precipitous gorge which has dissected it roughly in the direction of the dip.

By three tunnels, from 27 to 57 feet in length, and numerous shallow cuts, the lode has been exposed for a length of 2,283 feet. The highest opening above the Shoalhaven River is 770 feet, the lowest about 200 feet.

The principal lode material, where it makes solid, appears to be mispickel (arsenide of iron), but the unexpected presence of tin sulphide (stannine) in the 37 feet tunnel at No. 6 opening renders further examination throughout necessary for determination of

that mineral in other portions of the lode. The copper had previously been determined in the ore from this opening, but not the tin, until the Writer submitted an average sample to the departmental laboratory, when its presence was detected and the amount determined.

The presence of tin ore in sedimentary rocks at Talwong at some distance from granite is of interest. It is probable that felsitic contemporaneous rocks may be included in the former which have not yet been carefully examined.

Fluor-spar, in rich emerald-green masses, also occurs at intervals.

Galena and zinc-blende are present in parts of the lode, but the aggregate proportion is small, especially the zinc-blende.

An average sample of the best copper ore from all openings, including the stannine, yielded :—

No. 08-2592—	Copper	10·23 per cent.
	Tin	2·10 ,,
	Arsenic	8·78 ,,
	Gold	a few grains per ton.
	Silver	2 oz. 15 dwt. 13 grs. per ton.

This sample consisted chiefly of ore showing chalcopyrite.

An average sample selected from all openings yielded :—

No. 08-2593—	Copper	6·12 per cent.
	Tin	2·30 ,,
	Arsenic	15·80 ,,
	Gold	a trace.
	Silver	2 oz. 9 dwt. 0 gr. per ton.

A sample carefully averaged from a considerable quantity broken from a 7 feet face in the 37 feet tunnel at No. 6 opening, and from the stack of mineral raised in driving it, yielded :—

No. 08-2594—	Metallic copper	14·13 per cent.
	,, tin	10·26 ,,
	,, arsenic	0·96 ,,
	Gold	a few grains per ton.
	Silver	1 oz. 8 dwt. 7 grs. per ton.

Talwong mining is only in the initial stage of preliminary development with a view of determining method of treatment, &c. Hitherto arsenic has been regarded as the primary product to be recovered in form of commercial oxide in preliminary roasting, and doubtless, from this strong and permanent lode, it can be obtained in quantity. The presence of both copper and tin as residual products after expulsion of the highly deleterious associate, arsenic, gives a higher value to the ore, though its metallurgy will be complex and difficult.

Careful preliminary classification may result in the copper-tin ore being kept fairly free from arsenic.

It is desirable that further prospecting, and careful assay tests, be carried out for the purpose of locating the stannine makes in the lode, and ascertaining their prospective proportions.

APPENDIX III.

Prepared by W. R. COLLIS.

Methods of acquiring Titles to Prospect or Mine for Copper on Crown Lands. (Mining Act, 1906.)

The Mining Act, 1906, provides that the term "Crown Lands" shall include lands vested in His Majesty, lands held under lease from the Crown, except conditional leases, conditional purchase leases in terms of the Crown Lands Acts, or leases granted under the Mining Act, 1906; also lands reserved, dedicated, appropriated, or resumed for public purposes, whether vested in His Majesty or in any person as constructing authority or trustee; lands under navigable waters, or under any harbour, estuary, bay, river, or creek vested in His Majesty, whether navigable or not, and any lands which the Governor may declare by proclamation to be Crown lands.

Crown lands.—Certain classes of Crown lands are, however, exempt from occupation as mineral prospecting areas or claims under miners' rights, viz., lands reserved, dedicated, or appropriated or resumed for public purposes (excepting lands reserved for a temporary common, or for mining or mining purposes) whether vested in His Majesty or in any person as constructing authority or trustee for public purposes, residential leases, settlement leases, or special leases for purposes other than pastoral or grazing purposes; lands held under lease for water supply, in virtue of any special Act or otherwise; lands granted or vested in trust by the Crown for the purpose of a racecourse, cricket ground, recreation reserve, park, permanent common, or for any other public purpose, and lands the subject of a pending application for lease under the Mining Act, 1906.

Prospecting area.—The holder of a miners' right may mark off Crown lands, not exempt from occupation as above, to the extent of 40 acres, for the purpose of prospecting for copper. One man at least must be continuously employed, and the discovery of payable mineral must be reported to the local Mining Registrar within seven days, and within twenty-eight days from the date of the report the prospector must mark off a "reward" claim within his prospecting area, not exceeding 10 acres, or apply for a mineral lease. Any other miner may mark off an ordinary mineral claim not exceeding 4 acres, within the balance of the area.

The term "payable mineral" means sufficient mineral to pay current wages to the men employed on or in connection with the claim. The onus of proof that the mineral obtained is not payable, rests with the prospector.

One person may hold more than one prospecting area, but an additional miners' right must be held for each additional area, and each area must be represented by the proper amount of labour.

Authority to prospect.—Application may be made to the Minister by the holder of a miners' right, for authority to prospect on Crown lands, whether ordinary Crown lands or lands exempted from occupation under a miners' right, as above. Such authorities are granted on the recommendation of the Prospecting Board for a limited term, and subject to payment of such rent and the performance of such labour conditions as may be fixed by the Minister. On discovery of the copper or other minerals sought, the fact must be reported to the Warden within fourteen days; the authority-holder may then be required by the Minister to apply for a lease to cover the area, or such part as the Minister may determine, or to continue prospecting operations.

Lease.—Leases may be applied for over ordinary Crown lands, or over Crown lands which are exempt from the operation of miners' rights, excepting lands held under lease or application for lease in terms of the Mining Act, 1906.

The maximum area that may be held under one lease is fixed at 80 acres. The area must, where practicable, be measured in the form of a parallelogram, the length of which must not exceed three times the breadth. The rental is fixed at 5s. per acre per annum, and the labour conditions at not less than one man to 20 acres, or fraction of 20 acres, for the first twelve months of the term, and thereafter not less than one man to 10 acres, or fraction of 10 acres.

Leases may be granted for a period of twenty years, renewable for a like period.

Where such leases are granted over lands held from the Crown as settlement leases, residential leases, and such like tenures under the Crown Lands Acts, the holders thereof are entitled to compensation for any damage that may be done to the land by reason of the mining operations, such compensation to be assessed by the Warden and paid by such lessee.

Methods of acquiring Titles to Prospect or Mine for Copper on Private Lands.

In cases where the Crown grants contain, or, if not yet issued, would, when issued, contain a reservation to the Crown, of all minerals in the land, the right to prospect for copper, may be obtained by applying to the local Warden for an authority to enter, with a view to applying for a lease, or an agreement to mine may, with the concurrence of the Minister, be made with the owner of the land (*see* Section 69).

Authority to enter.—An authority to enter may be granted for a period of twelve months, subject to payment of rent and compensation, to be fixed by the Warden, and to the employment of labour in the proportion of one man to 20 acres, or fraction of 20 acres. An authority may be extended by the Warden from time to time, but so as not to exceed, with the original term of the authority, a period of twenty-four months, on such terms as he may deem fit, if he is satisfied that further time is required to enable the holder to complete his prospecting operations. Applications must be lodged with the Warden's Clerk of the Division in which the land required is situated.

Lease.—During the currency of the authority the holder may apply for a lease of the area or such part thereof as he may desire. Leases may be granted for a period not exceeding twenty years, renewable for a like period, subject to the payment of rent at the rate of £1 per acre per annum, half-yearly in advance, but such rental is payable only in respect of the area of the surface leased. A royalty at the rate of 1 per centum of the mineral won, must be paid to the Crown, after deduction of the rent paid to the owner.

The labour conditions are fixed at not less than one man to 20 acres, or fraction of 20 acres, for the first twelve months of the term, and thereafter not less than one man to 10 acres, or fraction thereof.

Agreements.

The owner of land in which the minerals are reserved to the Crown, may enter into an agreement with the holder of a miners' right, allowing such holder to mine for copper or other minerals, upon such conditions as to rent and period as may be mutually agreed upon. The area must not exceed 80 acres; the agreement is subject to the concurrence of the Minister, and must not contain any provision or stipulation for payment to the owner of any sum by way of royalty on the mineral raised. A royalty of 1 per centum is payable to the Crown after deduction of the rental payable to the owner. Labour conditions, as in ordinary leases, must be complied with (Section 69).

Where the minerals are not reserved to the Crown, the owner may enter into an agreement with any person, whether the holder of a miners' right or not, allowing the latter to mine upon such land. If registered, such agreement will protect the land from application for authority to enter and prospect for gold (Section 70).

INDEX.

PAGE.

ne ... 389
yle Copper Leases ... 304
... 100
Dam ... 94
ine ... 285
naby ... 383
e Mine ... 304, 310
gbilly Creek ... 374, 382
District ... 90
Waterholes ... 289, 291, 292
ndra Mine ... 90
Copper Mine ... 90, 387
o Mine ... 279
nda Mine ... 48, 84, 269
ses—
s and firebricks ... 325, 399-406
nga ore ... 315
limestone ... 315
f Creek clay ... 325
, Snowball ... 394
ain's Flat, ore ... 26, 356
, Cadia ... 132
Cobar ... 400
ar ores ... 234
sulphides ... 235
E. L. C. copper ... 244
ndale Mine ... 14, 106, 111
ney ... 44
y ... 155, 159
C. Mine ... 106, 108, 155
a C. Mines ... 45
l ... 110
lale ... 311
lale Division—
ndarra Mine ... 318
trong C. Mine ... 269
nagong ... 269
ic ... 43
... 84
e-Blayney C. Mine ... 109
ga C. Mine ... 313
,, ,, ... 328
ata Mine ... 91
n Mine ... 48
te ... 18
ammon Mine ... 194, 376
lor's Reef ... 335
Creek ... 270
's C. Mine ... 285
lava I. and C. Mine ... 90
nnel G. Mine ... 374
Nob Mine ... 305
ral C. Mine ... 109
Bang ... 148
g ... 143, 148
ba ... 317, 322
ba Division—
raba District ... 317
ir-Mile Lode ... 322
f Creek C. Mine ... 322
ubark Lode ... 326
rchison Lode ... 328
ing Creek C. Mine ... 329
pina C. Lode ... 333
ods Reef ... 333
er S. and C. Mine ... 91
Queen C. Mine ... 91
Ranges ... 91
' Lode ... 305
irst Division—
ley C. Mine ... 106
neralda C. Mine ... 142
en Swamp C. Mine ... 144
ers' Mine ... 148
kaley ... 150

PAGE.

Bathurst Division—*continued.*
Mount Morris Lode ... 159
Mountain Maid Lode ... 154
Red Hill Mine ... 166
Belara C. Mine ... 286
,, ... 299
Bell River ... 270
Bell View Mine ... 351
Belmore C. Mine ... 109, 270, 374
Belubula ... 175, 274, 275
,, C. Mine ... 110
Berridale ... 375, 388
Beshi ... 85
Black Jack Range ... 379
Black Lead ... 92
Black Mount Mine ... 110
Blakemore, G. H. ... 36, 241
Blayney ... 106, 109, 111, 114, 166, 170
,, C. Mine ... 14, 20, 111
,, ... 113
Blayney Division—
Annandale S. and C. Mine ... 106
Athole Blayney C. Mine ... 109
Blayney C. Mine ... 111
Blayney District ... 114
Diamond Hill ... 141
Guyong ... 141
Newbridge ... 160
Quigley's Hill C. Mine ... 166
Rise and Shine Mine ... 167
Sugarloaf C. Mine ... 170
Blue Bell Mine ... 270
Blue Creek ... 375
Big Ben C. Mine ... 270, 277
Big Wertago Mine ... 92
Binalong ... 270
Binalong Division—
Murrumbidgee C. Mine ... 365
Spion Kop Lode ... 367
Bingara ... 317, 329
,, Upper ... 326, 331
Bingara Division—
Bobby Whitlow ... 317
Borah Creek C. Mine ... 318
Harrison's Mine ... 326
Hilda May C. Lode ... 326
Mandourie Paddock ... 327
Mona C. Lode ... 327
Mount Lauff C. Lode ... 327
Prince of Wales C. Mine ... 329
Spring Creek ... 329
Sweet Nell C. Lode ... 331
Warialda ... 332
Birdite Mine ... 93
Birrama ... 365
Bismuth ... 42
Boambola ... 366
Bobadah ... 194, 217
Bobadah Division—
Emerald ... 217
Long Panel Lode ... 248
Recovery C. Mine ... 261
Walker's Hill ... 262
Yellow Mount ... 262
Bobby Whitlow Mine ... 317, 329
Bobs Mount ... 114
Bodangora ... 291
Bogan R. C. Mine ... 288
Bogong C. Mine ... 376
Bolairo ... 101
Bolderogery ... 372, 373
Bombah ... 174
Bonnie Dundee Mine ... 194
Boomerang Hill ... 95
Boone West ... 269

INDEX—*continued.*

PAGE.

Boori C. Mine 271
Boppy Mount 194
Borah Creek C. Mine 318, 320
Border Chief Mine 305
Boree Nyrang 273, 281
Bornite 18
Boro C. Mine 335
Bourke Division—
  Dorndilla C. Lode 216
Bowan Park 271
Bowenbang Creek 289
Bowling Alley Pt. 318
Brady's 93
Braidwood 335, 336, 361, 363, 364
Braidwood Division—
  Boro C. Mine 335
  Mount Fisher C. Lode 363
  Mulloon C. Mine 364
Brendalbane 339
Bredbo 376, 377
Britannia Mine 115
Broken Hill 93–96
  ,, Proprietary Mine 93
Broken Hill Division—
  Alexandra Mine 90
  Alpine C. Mine 90
  Balaclava I. and C. Mine 90
  Barrier Range 91
  Barrier S. and C. Syndicate 91
  Birdite Mine 93
  Black Lead 92
  Broken Hill Proprietary S. Mine 93
  Copper Blow Mine 97
  Copper King Mine 97
  Diamond Jubilee Mine 98
  Fairy Hill 99
  Federal C. Mine 99
  Florence Mine 99
  Glencoe Mine 99
  Hampton C. Mine 100
  Hornsby Range 100
  Invincible C. Mine 100
  Lady Hampden Mine 101
  Mootwingee C. Mine 101
  Nadbuck C. Mine 101
  Orient Mine 102
  Paragon Lode 102
  Pinnacles 103
  Ponto Mine 103
  Purnamoota 103
  Red Flag C. Mine 103
  Rockwell Paddock 103
  Ruby C. Mine 103
  Silverton 104
Broula 271, 276
Brown's Creek 115, 167
Brungle 377, 378
Buckenbah 370
Buckley's Crossing 378
Budgery C. Mine 13, 194
Budgerygar Mine 195
Bullio 336
Bull's Creek 116
Bumbaldry 271, 274
Bumbery C. Mine 271
Bundara Mine 318
Bundundah 337
Bungiebomar 289
Bungendore 363
Bungonia 337
Bunker's Hill Mine 96
Buppe C. Lode 196
Burra Burra 14, 65
Burraga 30, 117–126, 142, 401
Burraga Division—
  ,, C. Mine 117
  ,, (Lloyd) C. Mine 117
  Mount Burraga 169
  Sprague's Mine 169
Burril Ranges 290
Burly Jacky C. Mine 116
Burnt Yards 151
Burrowa 272, 335, 354, 360

PAGE.

Burrowa Division—
  Bhalong 270
  Bachelor's Reef 359
  Lang's Creek Mine 360
  Mayfield C. Mine 362
  Wallah Wallah C. Mines 358
Busy Bee C. Mine 280
Butte C. Mines 25, 32, 93
Byrag 126, 134, 140, 147, 162, 169
C.I.A. Mine 19
Cadia 153
  ,, C. Mine 137–138
  ,, Extended C. Mine 138
Calafat 360
Camel Back Mountain 187
Canbelego 194–199
  ,, C. Mine 200
Canbelego Division—
  Baal Gammon Mine 194
  Bounie Dundee Mine 198
  Boppy, Mount 194
  Budgery C. Mine 194
  Buppe C. Lode 196
  Canbelego C. Mine 196
  Shango Mine 197
  Canbelego North 201
  ,, Peak 197
  ,, Queen 197
  Hermidale 201
  Mount Boppy C. Mine 198
  North Shango 197
  South Budgery 201
  ,, Mount Boppy 201
Cangal C. Mine 180–181
Canning and Gibson's Mine 337
Canoblas C. Mine 131
Canowindra Division—
  Belubula C. Mine 159
  Copper Mine Creek 278
  Eurow C. Mine 278
  Fitzroy Mine 279
  Sugarloaf 279
  Vychan C. Mine 282
Capertee 360
Captain's Flat 337, 346, 354, 408
Captain's Flat Division—
  Canning and Gibson's Mine 337
  Federal Mine 346
  Grogan and Singleton's Mine 351
  Lake George Mine 354
Carangara C. Mine 194
Carcoar 125, 137, 170
Carcoar Division—
  Coombing Park C. Mine 137
  Infirtaris C. Mine 147
  Kemp field 149
  Summer's C. Mine 170
Cargo 273
Caroline C. Mine 360
Carwoola 361
Cash Essington Mine 126
Casino Division—
  Jones' Lode 188
  Just in Time Lode 188
  Minnie C. Lode 191
  Nil Desperandum Lode 192
  Nogrigar Lode 191
  Wallaroo Lode 193
Castle Hill C. Mine 305, 307
  ,, C. Lode 308
  ,, Rag 309
Chandler River 330
Cheeseman's Creek 273
Cheshire C. Mine 309
Chillagoe 46
Chisholm's C Mine 328
Chris. Watson Mine 280
Christmas Gift Mine 280
Clarence River 187
Cliefden 170
Cobar 218
  ,, Chesney G. and C. Mine 198
  ,, C. Ltd. 199
  ,, Gold Mines 211

INDEX—*continued.*

PAGE.

ir—Lyell Mine 212
Tharsis 210
r Division—
ar Chesney 198
Tharsis 210
Gold Mines 211
Cobar Mine 216
ntose Mine 226
& Cobar Mine 228
,, N. Mine 228
n Tank 210
ental S. Mine 256
Bee C. Mine 259
en Bee Mine 261
y 210
Division—
rang C. Mine 341
ly's Mine 344
wealth Mine 303
C. Mine 319
ation 44
n 270, 282
C. and G. Mine 273
n Division—
la Mine 269
C. Mine 270
ll Mine 270
blin C. and S. Mine 273
C. and G. Mine 277
annah C. Lode 279
Mine 281
n Lion Lode 282
ft Mine 282
C. and L. Mine 283
Lode 283
a 377, 379
reek 338
Mine 351
r 210
annite Mine 320
..... 377, 378, 380
Mine 377
vision—
le 375
C. Mine 376
District 377
C. Mine 377
anta 378
or C. Mine 380
C. Mine 388
rick 381
reek G. and C. Mine 381
ne C. Mine 382
Mine 383
ly G. and C. Mine 388
C. Mine 388
th C. Mine 389
n C. Mine 390
k 392
River 378, 394
ok 396
Park C. Mine 137
ripa C. Mine 320
ra 278, 278
G. and S. Mine 279
ra Division—
ead C. and S. Mine 278
O 101
..... 378, 381
Division 319
C. Mine 319
ek 320
..... 327
irst 180
irst Division—
e Lode 180
C. Mine 180
ck Mountain 187
our Mine 187
C. Lode 188
ne 189
an C Mine 189
een Lode 190
Mine 192

PAGE.

Copmanhurst Division—*continued.*
Potato Creek 93
Walker's Pinch Lode 193
Wiley's Lode 193
Yulgilbar 193
Copper Blow Mine 97
,, Gully 326
,, Hill 6, 7, 129, 276
,, ,, Mine 138, 289
,, King Mine 97
,, Mine Cave 396
,, ,, Creek 274
,, Well Mine 97
Coramba Division 191
Mount Browne C. and S. Mine 191
Corbould, W. H. 30, 58
Cordillera Hill 140
Cornish Settlement 134
Coronation Mine 379
Corrowong C. Mine 379
Cow Flat 109, 148, 141
,, C. Mine 140
Cowfell Mine 274
Cowley C. 377, 379
Cowra 141, 147, 280
,, Mine 176
Cowra Division—
Bronla 271
Burley Jacky C. Mine 116
Holmwood C. 147
King of England Mine 276
Wangoola Creek C. Mine 175
West Hill C. Mine 175
Coyle's Mine 389
Crowl Creek 211
,, ,, C. Mine 215
Cu Copper Mine 188
Cudal Division—
Bowan Park 271
Bumbery C. Mine 271
Cheeseman's Creek 273
Mount Keenan Mine 279
Nangar Range 280
United Empire Mine 283
Cudgegong 269
Cullen's Creek 306
Cullerin C. Mine 389
Cumnock 281
Cupriferous Shales 62
Curra Creek 341
Currowan Creek 326
Currowong 15
,, C. Mine 341
Currumbla 280
Customs Smelting Coy's. 406-412
Cyclops C. Mine 389
Dadauman 274
Dairy Hill 273
Dalmorton Division 192
Newton Boyd S. and C. Lode 192
Dandaloo Division—
Ace Mine 285
Bogan River C. Mine 288
Chris. Watson Mine 290
Honeybugle 291
Iron Duke Lode 291
Lady Elwyn Mine 292
Monarch Mine 292
Mount Keenan 292
Mount Pleasant C. Mine 254, 294
Mount Royal C. Mine 294
Orange Plains C. Mine 299
Sydney Wallaroo C. Mine 300
Dandaloo 285, 288, 289, 291, 294, 300
Darbalara 330, 332
Dartmoor C. Mine 380
Dawson's Mine 288
Day Bros.' Mine 226
Deepwater 305, 306
Deepwater Division—
Castle Hill C. Mine 305
Pye's Creek 311
Delaney's Dyke 274

INDEX—*continued*

PAGE.

Delegate Division—
Belmore C. Mine 374
Currowong C. Mine 379
Mount Trooper 390
Quidong 374
Democrat Mine 272
Denison Town 290
Diamond Hill 141
,, Jubilee Mine 98
Dingo Mine 143
Dinoga 331, 332
Doctor's Creek Lode 337
Dolcoath Lode 370
,, Mine 141
Dolconda 193
Donnybrook Lode 216
Doradilla C. Lode 216
Douglas Furnace 45
Drake 304, 311
Drake Division—
Adeline Mine 304
Bates' Lode 305
Border Chief Mine 305
Cullen's Creek 306
Drake District 307
Lady Mary Mine 309
Mount Carrington Mine 309
Pioneer Mine 310
Poor Man's Friend Mine 311
Rainbow Mine 311
Dripstone 290, 303
Dungowan 321, 328
Dyball's C. Mine 388
East Burraga Mine 142
,, Cobar Mine 216
,, ,, Freehold Mine 216
Eclipse C. Mine 98
Eldorado C. Mine 142
Elletson 226
Elrington 363
Emerald 217
Emmaville 305, 306, 308, 312
Emmaville Division—
Bald Nob Mine 305
Willows Mine 312
Emu Swamp 114
Endrick R. 336
Eskbank 401
Esmeralda C. Mine 142
Essington 136, 141, 143, 166
Ettrema Mine 345, 418
Eugowra 274
Eureka Mine 363
Euroa Mine 91
Eurow C. Mine 274
Europambella 321
Ewingar 187, 191, 192
Eyrie South Mine 177
Fairfield 305, 307
Fairy Hill 96, 99
Federal C. Mine 99, 345, 346
Fiery Creek 381
Fifield Division—
Mahgalore Lode 277
Mordialloc C. Mine 278
Fine Flour Mine 187
Firebricks 399–406
Fisher's C. Mine 321
Fittes Mine 302
Fitzroy Mine 143, 275
Flintoff's C. Lode 188
Florence Mine 99
Flux 260, 263, 298, 332
Foran's C. Mine 139
Forbes 274
Forest Reefs 169
Four-mile Lode 322
Fraser's Creek 328
Frogmore 345, 346, 351, 365–6
,, C. Mine 346
Frogmore Division—
,, C. Mine 346
Yundoo Lode 3

Frogmore Division—*continued.*
Pride of Frogmore Mine .....
Sapling Gully .....
Frog's Hollow .....
Fullback Mine .....
Galwadgery .....
Gaslight C. Mine .....
Gegedzerick .....
Gem Mine .....
George's Plains .....
Geuric .....
Gilgunnia .....
Gilgunnia Division—
Northumberland P.H. .....
May Day Mine .....
Gilmore Creek .....
,, Range .....
Gininderra .....
Girilambone 45
Gladstone Mine .....
Glen Creek .....
Glencoe Mine .....
Glamorgan C. Mine .....
Gobandry .....
Godfrey's Creek .....
Goobang .....
Good Hope C. Mine .....
Goodna Creek .....
Goodrich C. Mine .....
Goolma .....
Goondah .....
Goonumble Hill .....
Gordon .....
Gordon Brook .....
Goulburn .....
Goulburn Division—
Bungonia .....
Chisholm's, Merrilla .....
Cullerin C. Mine .....
Curra Creek Mine .....
Jasper's Gully .....
Lucky Hit Mine .....
Merrilla .....
Mummell C. Mine .....
Sassafras .....
Talwong Mine .....
Grafton C. Mine .....
Grasmere Mine .....
Great Burril Mine .....
,, Central C. Mine .....
,, Cobar Mine 23–25, 36, 41–
,, Eastern Mine .....
,, Peak Mine .....
,, Southern S. Mine .....
,, Western Mine .....
,, Wheal Burril Consols .....
Green Swamp Mine .....
,, Creek .....
Grenfell Division—
Arramagong .....
Boori C. Mine .....
Bumbaldry .....
Cowfell Mine .....
Grogan and Singleton's Mine .....
Growenbang .....
Gulf Creek 2
Gulgandra .....
Gulgong .....
Gulgong Division—
Belara C. Mine .....
Invicta G. and C. Mine .....
Gully Swamp .....
Gumble .....
Gundagai .....
Gundagai Division—
Back Creek .....
Darbalara C. Lode .....
Gundagai .....
,, Mine .....
,, South .....
Jones' Creek .....
Mingary C. Lode .....
Reno .....
Snowball C. Mine .....

INDEX—*continued.*

PAGE.

l 275, 280
..... 309
..... 141
..... 382
..... 330
Mine 100
idge 239
ne 326
..... 258
ef 263
Lode 146
..... 62
ek 353
..... 247
..... 309
. Lode 326
..... 330
vision—
..... 311
stake 311
Claim 311
S. and C. Mine 330
. Mine 147
..... 291
e 147
ge 100
..... 326
..... 27
ini 248
Mines 263
..... 143, 147, 158
..... 276
Mine 147
R. 60
ine 148
ision—
C. Lode 328
al C. Mine 291
. Mine 100
..... 43
ode 326
ne 273
dine 127, 291
dine 299
addock 290
e 148
dine 337
. Mine 187
..... 57, 84
lly 354
t 264
..... 116
. Mine 382
e 148
dine 148
l 75
ek 276
s 189
e 148
reek 391
sion—
G. and C. Mine 283
f 283
ne Lode 190
..... 193
e 291
Mountain 383
..... 191
..... 272, 354
..... 63
..... 149
..... 149, 174
Division—
ad 263
ill C. Mine 265
..... 350
..... 375, 383
Division—
ak Reefs 375
ion Mine 379
C. Mine 381
Hole C. Mine 384
obilly 396

PAGE.

Kiandra Division—*continued.*
Castle Copper Lode 398
Copper Mine Cave 398
Kimo 270, 275
Kindie 263
King of England Mine 276
Kookabookra 304
Kookabookra Division—
Aberfoyle C. Lodes 304
Guy Fawkes R. 309
Kooningbery Mountains 100
Koree 263, 265
Kosaka 85
Kupferschiefer 61, 74
Kyloe C. Mine 383
Lady Belmore Mine 149
,, Dorothy Mine 91, 99
,, Elwyn Mine 292
,, Hampton Mine 101
,, Lizzie Mine 372
,, Mary Mine 309, 327
Lake George Mines 26, 341, 354–360
,, Superior Mines 58, 79
Lal Lal 339, 340
Langford's Lease 280
Lang's Creek Mine 360
Larry's Hill C. Mine 163
Lead 44
Leadville 290
Leadville Division—
Bowenbang Creek 289
Denison Town 290
Mount Laut 292
,, ,, South 293
,, ,, Dawson's 294
Mount Scott 296
Mount Stewart 296
Lewis Ponds 115, 149, 150, 159
Limestone 405
Lindberg's Mine 302
Little Mount Currumbia 280
,, Bell Mount 149
,, Copper Hill Mine 276
,, Gem Mine 150
Lloyd's C. Mine 80, 117
Lobb's Hole C. Mines 379, 384–387, 396
,, ,, Central 387
Locksley 150
London Bridge 391
Long Flat 263
Long Panel Lode 248
Low grade ore 24
Lowther 150, 179
Lucknow 175
Lucky Hit Mine 150, 175
Macanally G. and C. Mine 388
Mahgalore Lode 277
Major's Creek 361, 363, 368
Major's Creek Division—
Mount Hope Mine 363
United Miners 368
Malachite 18
Mallee Tank 210
Malongulli 110, 274
Mandourie Paddock 337
Mandurama 151
Mandurama Division—
Mount Hope C. Mine 270
Manildra 145
Mann R. 192
Mannering's C. Mine 101
Mansfield 61, 74
Mary Bell Mine 96
May Day Mine 248
Mayfield C. Mine 362
May Queen Lode 190
M'Alpine C. Mine 388
M'Auley's Mine 307
M'Grath's C. Mine 96
M'Kinley's Claim 311
Melaconite 17
Melrose 269, 270, 277, 279, 283, 405
,, C. and S. Mine 277

INDEX—*continued.*

PAGE.

Merrilla 338, 361, 362
,, C. Mine 362-3
Meryula 247
Mickety Mulga 300
Middle Flat 377
Milburn Creek 20, 142
,, C. Mine 151, 155
Milparinka Division—
Kooningberry Mount 100
Milthorpe 161
Mines 19
,, abandoned 19
,, Water 15
Mingary C. Lode 388
,, Mount 305
,, South 390
Minnie C. Lode 191
Molong 138, 261, 274, 276, 278
Molong Division—
Armstrong C. Mine 269
Bell R. 270
Copper Hill C. Mine 138
Delaney's Dyke 274
Gumble 145
Little Copper Hill Mine 276
Molong Creek 278
Peabody C. Mine 281
Pine Hill C. Lode 281
Reedy Creek 282
Mona C. Lode 327
Monarch Elizabeth C. Mine 292
Monaro 374
,, C. Mine 388
Monmouth C. Mine 389
Montana 79
,, Ore Producing Co. 83
,, S. and C. Mine 155
Moondyke C. Mine 245
Moonta 14, 63, 64
Mootwingee C. Mine 101
Mookaie 94
Mount Bannaby C. Mine 363
,, Boppy C. Mine 246
,, Brown C. and G. Mine 191
,, Bulga C. Mine 157
,, Bullen 389
,, Burrara 169
,, Carrington 307
,, ,, Mine 309
,, Costigan 158
,, Currumbia 280
,, Everest C. Mine 327
,, Felstead C. and S. Mine 278
,, Fiery C. Lode 396
,, Fisher C. Lode 363
,, Fraser C. Mine 158
,, Hope 236, 292, 400
,, ,, C. Mine 250, 363
Mount Hope Division—
Great Central Cobar Mine 226
Mount Hope C. Mine 250
Mount Hornsby 96
,, Jasper C. Mine 284
,, ,, Peak Lode 285
,, Keenan 279, 292
,, Kenyu 351
,, Lauff C. Mine 327
,, Laut 292
,, ,, South 293
,, Lindsay C. Mine 158, 191
,, Lyell 15, 27, 70
,, McDonald 159
Mount McDonald Division—
Cowra District 141
Eldorado C. Mine 142
John Bull Mine 148
Milburn Creek C. Mine 151
Silver City Lode 159
Mount Mingary C. Lode 389
,, Morgan 14, 66
,, Morris 148
,, ,, C. Mine 159
,, Nobby 278
, Nome 159
Mount Parnassus .....
,, Pleasant C. Mine .....
,, Ragan .....
,, Rose .....
,, Royal C. Mine .....
,, Scott .....
,, Shorter .....
,, Stewart Mine .....
,, Susannah C. Lode .....
,, Trooper .....
,, View .....
,, Warning .....
Mountain Maid Lode .....
,, Run Mine .....
Mordialloc C. Mine .....
Moruya S. Mine .....
Mudgee Division—
Wilbetree .....
Mugin Wybra Creek .....
Mulga Springs .....
Mulloon C. Mine .....
Mullumbimby .....
Mundowie C. Lode .....
Mummell C. Mine .....
Murchison Lode .....
Murga .....
Murrumbidgee C. Lode .....
Nadbuck C. Mine .....
Namoi C. Mine .....
Nangar Range .....
Nangeribone .....
Narraba Creek .....
Narrabeen .....
Narradin .....
Narri .....
Native Bee Mine .....
Neila Creek .....
Nerriga .....
Nevada S. and C. Mine .....
New Babinda .....
Newbridge .....
New Burra Burra C. Mine .....
Newton Boyd S. and C. Lode ..
Nickel .....
Nil Desperandum Lode .....
Nine-Mile Claim .....
Nithholm .....
Nobby's Mine .....
Nogrigar C. Lode .....
North Buckinbar .....
,, Essington Mine .....
,, Nymagee C. Mine .....
,, Shango .....
Northumble .....
Nowendoc .....
Nowra Division—
Bundundah .....
Ettrema Lode .....
Touga C. Mine .....
Nundle Division—
Bowling Alley Pt. .....
Dungowan .....
Fisher's C. Mine .....
Mount Pleasant Mine .....
Nuntherungie C. Mine .....
Nymagee 45,
Nymagee Division—
Cobar Lyell Mine .....
Crowl Creek Mine .....
,, ,, S. C. Mine .....
Day Bros.' Mine .....
Donnybrook Lode .....
Girilambone C. Mine .....
Great Western Mine .....
Hunter's Claim .....
Moondyke C. Mine .....
Nangeribone .....
North Nymagee C. Mine .....
Nymagee C. Mine .....
Star of the West Mine .....
Wirlong .....
Nyngan Division—
Wi'garbone .....

INDEX—*continued.*

PAGE.

..... 139
..... 116
..... 130
..... 150
..... 174
..... 174
..... 179
..... 258
..... 161
..... 161
..... 114, 157, 158

..... 114
..... 115
..... 126
..... 127
ne 132
..... 133
..... 134
..... 146
..... 147
..... 149
..... 149
..... 158
..... 158
..... 159
..... 161
..... 161
..... 166
..... 166
..... 169
..... 175
..... 175
..... 292
..... 290
..... 17
..... 102
..... 194, 261
..... 100
..... 265
..... 102
..... 275, 280

e..... 275
..... 83
..... 271
..... 274
..... 281
..... 391
..... 66
..... 299
..... 161
..... 106
..... 70, 81
..... 391
..... 163, 281, 341
..... 44

..... 336
..... 281
..... 290
..... 310
..... 310
..... 192
..... 265
..... 103
..... 311
..... 265
i—
..... 263
..... 263
..... 264
ole 265
..... 265
..... 265
..... 58
..... 193
..... 365
..... 166
..... 329
..... 91
..... 86, 87

PAGE.

Production—World 88
Prosper Mine 166
Pucka 180, 190, 194
Pulganbar 182, 189, 192
Purnamoota 91, 93, 103
Pye's Creek 311
Pyritic Smelting 26–28
Queanbeyan Division—
  Balconnel G. Mine 374
  Congwarra C. Lode 377
  Cowley C. Lode 379
  Hall 382
  Mount Bullen 389
  Queanbeyan 391
Queen Bee 259
Queen of England Claim 276
  ,, the Stream Mine 309
Queensland 66
Quidong 9, 374
Quigley's Hill C. Mine 166
Rainbow Mine 307, 311
Ramping Lion Lode 282
Ranger's Mine 168
Rat's Castle Lode 166
Recovery C. Mine 261
Red Flag C. Mine 103
Red Hill 382, 391
Red Hill Mine 166, 366
Reedy Creek 271, 282
Refining 36
Refractory ores 41
Reno 282
Rifle Butt Claim 282
Rigby's Reef 261
Right Hand Creek 351
Rio Tinto 15, 20, 75
Rise and Shine Mine 167
Rivertree 306
Rockdale G. and C. Mine 283
Rockley 6, 115, 147, 150, 167, 168
Rockley Division—
  Balmoral C. Mine 109
  Belmore C. Mine 109
  Black Mountain Mine 110
  Brown's Creek 115
  Cash-Essington Mine 136
  Cow Flat C. Mine 140
  ,, District 141
  Dolcoath Mine 141
  Essington 143
  Fitzroy Mine 143
  Fullback Mine 143
  Integrity Mine 148
  Jackass Mine 148
  Jocelyn Mine 148
  Lucky Hit Mine 150
  Mountain Run 155
  Sugarloaf Mine 156
  Mount Bulga C. Mine 157
  North Essington Mine 160
  Phœnix C. Mine 163
  Larry's Hill C. Mine 163
  Prosper Mine 166
  Rockley District 167
  Ranger's Mine 168
  Shepherd's Mine 168
  South Wiseman's Creek C. Mine 169
  Summer Hill C. Mine 171
  Wiseman's Creek C. Mine 177
Rockwall Paddock 90, 103
Rosebank Mine 392
Rosedale 158, 166
Rose Hill C. Mine 265, 300
Rose Valley 381, 391
Royal George Mine 329
  ,, Sweep Mine 288
Ruby C. Mine 103
Running Stream 300
Rye Park 362
Rylstone 300
Sandy Creek 326
Sapling Gully 366
  ,, Point Creek 366
Sassafras 366

INDEX—*continued.*

PAGE.

Sawpit Gully ... 308
Shango Mine ... 197
Shepherd's ... 168, 281
Shoalhaven River ... 337, 366-7
Shuttleton C. Mine ... 211
Silica ... 44
Silver City Lode ... 169
Silverton ... 90, 91, 102, 104
Singleton Division ... 265
Slattery's Creek ... 169
Smelting ... 27
Snob's Mine ... 363
Snowball C. Mine ... 390, 392
,, Hill ... 392
Snowy River ... 394
Sofala ... 373
Sonoma ... 387
South Australia ... 63
,, Budgery ... 261
,, Mount Boppy ... 261
,, Queen Bee ... 261
,, Wiseman's Creek C. Mine ... 169
Spain ... 58, 75
Spion Kop ... 367
Sprague's Mine ... 169
Spring Creek ... 278, 329
,, C. Mine ... 329
Star of the West ... 261
Stuart Town Division—
Al Mine ... 369
Cheshire C. Mine ... 369
Cyclops C. Mine ... 369
Dolcoath Lode ... 370
Goodrich C. Mine ... 370
Lady Lizzie Mine ... 372
Mount Rose ... 372
N. Buckinbar ... 373
Tinby Hill ... 373
Viles' Lode ... 373
Yeoval ... 373
Styx River ... 311
Sugarloaf ... 170, 285
,, C. Mine ... 155, 170
Sultan C. and L. Mine ... 283
Summer's C. Mine ... 170
Summerhill ... 6, 7, 8
,, C. Mine ... 171
Sunny Corner ... 43, 155, 160, 172
Sunny Corner Division—
Nevada S. and C. Mine ... 160
Sunnyside C. and S. Mine ... 330
Sweet Nell Lode ... 331
Sydney-Wallaroo C. Mine ... 300
Talbragar ... 296
Tabratong ... 291, 292
Tabulam ... 187
Talbingo ... 391
Talwong Mine ... 367, 413
Tamworth ... 331
Tamworth Division—
Attunga C. Mine ... 313
Namoi C. Mine ... 328
Trough Gully N. Mine ... 331
Tara ... 93
Tarago ... 341
Taralga ... 363
Taralga Division—
Mount Bannaby C. Mine ... 363
Tarana ... 174, 179
Tarella Consols Mine ... 101
Tasmania ... 70
Tin ... 43
Tinby ... 369
Tinby Hill ... 373
Tindary ... 210
Tingha ... 329
Tingha Division—
Conrad Stannite Mines ... 329
Cope's Creek ... 330
Hoy's Reef ... 326
Lady Mary Mine ... 327
Royal George Mine ... 329
Thackaringa ... 97
Thames Gully ... 335
Tharsis C. Co. ...
Thompson's Creek ...
Top Bingara ...
Top Tank ...
Touga C. Mine ...
Trinidad C. Mine ...
Trough Gully N. Mine ...
Trundle ...
Trunkey ...
Tuena ...
Tuena Division—
Cordillera Hill ...
Mount Costigan ...
Peelwood C. Mine ...
Tuglow ...
Tumut ... 376, 381, 38
Tumut Division—
Adjungbilly Creek ...
Bogong C. Mine ...
Brungle ...
Kangaroo Mountain ...
McAlpine C. Mine ...
Mingary ...
Pether's Lode ...
Talbingo ...
Red Hill C. Mine ...
Wyangle ...
T. W. Copper Lode ...
Ulladulla Division—
Conjola Creek ...
Umberumberka ...
Umeralla ...
United Empire Mine ...
United Miners ...
United States ...
Upper Bingera ...
Uriara ...
Victory Lode ...
Viles' ...
Vychan C. Mine ...
Wadsworth, M. E. ...
Wagara ...
Walcha ...
Walcha Division—
Cooperacurripa C. Mine ...
Europambella Lode ...
Walker's Hill ...
,, Pinch Lode ...
Wallah Wallah ...
Wallaby Rocks ...
Wallaroo ...
,, Lode ...
Wambrook ...
Waratah ...
Ward's Mistake ...
Ware ...
Warialda ...
Washoe ...
Wauchope ...
Waugoola Creek C. Mine ...
Waukeroo ...
Weandre Creek ...
Weed, W. H. ...
Welcome Reef ...
Wellington ...
,, Champion Hill Lode ...
Wellington Division—
Backe's C. Mine ...
Bungiebomar ...
Dripstone ...
Great Wheal Burril C. Mine ...
Kaiser Mine ...
Rose Hill C. Mine ...
Wellington District ...
Yarragol C. Mine ...
Wellwood ...
Wertago ... 92, 93,
,, C. Mine ...
West Bogan ...
West Hill Lode ...
Wet Creek ...
White Cliffs Division—
Big Wertago Mine ...
Brady's Proprietary Mine ...

INDEX—*continued.*

PAGE.

White Cliffs Division—*continued.*
Broken Hill Mine 96
Copperwell Mine 97
Eclipse C. Mine 98
Grassmere Mine 100
Nuntherungie C. Mine 101
Wertago C. Mine 104
Wilbetree 303
Wiley's Lode 198
Wilgarbone 226, 247, 263
Willi Willi 265
Willie Ploma 302
Willow's Mine 312
Wilmatha Tank 277
Wilpina C. Lode 333
Wirlong 261
Wiseman's Creek 139, 148, 169, 177
" C. Mine 177–179
Wollondilly Valley 336
Wonaminta 100
Wood's Reef 326, 329, 333, 334
Woodstock 116, 175–76, 270
Woolgarlo Mine 368
Wrigntville 226
Wyangle 382, 396
Yarragol 303
Yarrakalkiarra 187
Yarrangobilly 379, 396, 398
Yass 8, 353, 366, 368
Yass Division—
Good Hope C. Mine 352
Kangiara Mine 354
Red Hill Mine 366
Sapling Point Creek 366
Woolgarlo Mine 368
Yates' Tarana Mine 179
Yellow Mount 248, 263
Yeoval 369–373
Yetholme 144, 269
Yorkey's Creek 179
Yulgilbar 198
Yundoo Lode 352
Zinc 41

Sydney: William Applegate Gullick, Government Printer.—1906.

P




Draught chimney to draw cold air past Conker plate
2'-6" high
Roof of culvert is arched
Roof of flue of brick slabs
5'-0"
6'-6"





ION OF THE

Scale o

MINING I

NUMERICA

olga	69	Mud
ey	70	Scon
Hill	71	Sing
nia	72	Mait
	73	Dun
ago	74	Cope
a	75	Bull
able	76	Wen
arabran	77	Hay
iah	78	Hill
rth	79	Mt.
	80	Eual
Oak	81	Carg
a Brook	82	Yalg
	83	Conc
acquarie	84	Wya
	85	Wya
nia	86	Grea
ee	87	Fort
h	88	Parl
	89	Mol
oo	90	Cud
rn	91	Can
ill	92	Car
	93	Cow
Town	94	Max
rton	95	Car
Denison	96	Bla
le) Town	97	Ora
g	98	Bat
ves	99	Roc
er	100	Tru
d	101	Obe
e	102	Wa

Photo-



INDEX—*continued.*

PAGE.

e Cliffs Division—*continued.*
)ken Hill Mine 96
ppenwell Mine..... 97
ipse C. Mine 98
ssmere Mine 100
ntherungie C. Mine..... 101
rtago C. Mine 104
etree 303
y's Lode 198
rbone..... 226, 247, 263
Willi 265
e Floma 302
w's Mine 312
natha Tank 277
ina C. Lode..... 333
ong..... 261
nan's Creek 139, 148, 169, 177
,, C. Mine 177-179
londilly Valley..... 336
nminta 100
d's Reef 326, 329, 333, 334
dstock 116, 175-76, 270

PAGE

Woolgarlo Mine 363
Wrightville 225
Wyangle 332, 336
Yarragol 306
Yarrakalkiarra 187
Yarrangobilly 272, 296, 306
Yass 8, 332, 333, 336
Yass Division—
Good Hope C. Mine 332
Kangiara Mine 334
Red Hill Mine..... 336
Sapling Point Creek 333
Woolgarlo Mine 336
Yates' Tarana Mine 179
Yellow Mount..... 248, 263
Yeoval 336-373
Yetholme 144, 339
Yorkey's Creek 179
Yulgilbar 198
Yundoo Lode 366
Zinc 41

Sydney: William Applegate Gullick, Government Printer.—1906.


Draught chimney to draw cold air past Conker plate
1' 6" high
Roof of culvert is arched
Roof of flue of brick slabs
6'6"

559
N53.
no.
ed.
190
BE

559.44 .N532mi [redacted] C.1
Stanford University Libraries
3 6105 033 006 797

DATE DUE			

Stanford University Libraries
Stanford, Ca.
94305